



(86) Date de dépôt PCT/PCT Filing Date: 2015/01/16

(87) Date publication PCT/PCT Publication Date: 2015/07/30

(45) Date de délivrance/Issue Date: 2022/06/07

(85) Entrée phase nationale/National Entry: 2016/06/14

(86) N° demande PCT/PCT Application No.: US 2015/011815

(87) N° publication PCT/PCT Publication No.: 2015/112450

(30) Priorité/Priority: 2014/01/21 (US61/929,673)

(51) Cl.Int./Int.Cl. *C22C 21/00* (2006.01),
C22C 21/14 (2006.01), *C22C 21/16* (2006.01)

(72) Inventeurs/Inventors:
HOSCH, TIMOTHY A., US;
LONG, RUSSELL S., US

(73) Propriétaire/Owner:
ARCONIC TECHNOLOGIES LLC, US

(74) Agent: BERESKIN & PARR LLP/S.E.N.C.R.L.,S.R.L.

(54) Titre : ALLIAGES D'ALUMINIUM 6XXX

(54) Title: 6XXX ALUMINUM ALLOYS

(57) **Abrégé/Abstract:**

New 6xxx aluminum alloys having an improved combination of properties are disclosed. The new 6xxx aluminum alloy generally include from 0.30 to 0.53 wt. % Si, from 0.50 to 0.65 wt. % Mg wherein the ratio of wt. % Mg to wt. % Si is at least 1.0:1 (Mg:Si), from 0.05 to 0.24 wt. % Cu, from 0.05 to 0.14 wt. % Mn, from 0.05 to 0.25 wt. % Fe, up to 0.15 wt. % Ti, up to 0.15 wt. % Zn, up to 0.15 wt. % Zr, not greater than 0.04 wt. % V, and not greater than 0.04 wt. % Cr, the balance being aluminum and other elements.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau

(43) International Publication Date

30 July 2015 (30.07.2015)



(10) International Publication Number

WO 2015/112450 A1

(51) International Patent Classification:

C22C 21/00 (2006.01) *C22C 21/16* (2006.01)*C22C 21/14* (2006.01)

(21) International Application Number:

PCT/US2015/011815

(22) International Filing Date:

16 January 2015 (16.01.2015)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/929,673 21 January 2014 (21.01.2014) US

(71) **Applicant:** **ALCOA INC.** [US/US]; 201 Isabella Street, Alcoa Corporate Center, Pittsburgh, Pennsylvania 15212-5858 (US).

(72) **Inventors:** **HOSCH, Timothy A.**; 165 Chavelle Court, Plum, Pennsylvania 15239 (US). **LONG, Russell S.**; 5059 Impala Drive, Murrysburg, Pennsylvania 15668 (US).

(74) **Agents:** **BRIGGS, Heath J.** et al.; GREENBERG TRAURIG, LLP, c/o Alcoa Inc., 100 Technical Drive, Alcoa Center, Pennsylvania 15069 (US).

(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,

BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

— with international search report (Art. 21(3))

(54) **Title:** 6XXX ALUMINUM ALLOYS

(57) **Abstract:** New 6xxx aluminum alloys having an improved combination of properties are disclosed. The new 6xxx aluminum alloy generally include from 0.30 to 0.53 wt. % Si, from 0.50 to 0.65 wt. % Mg wherein the ratio of wt. % Mg to wt. % Si is at least 1.0:1 (Mg:Si), from 0.05 to 0.24 wt. % Cu, from 0.05 to 0.14 wt. % Mn, from 0.05 to 0.25 wt. % Fe, up to 0.15 wt. % Ti, up to 0.15 wt. % Zn, up to 0.15 wt. % Zr, not greater than 0.04 wt. % V, and not greater than 0.04 wt. % Cr, the balance being aluminum and other elements.

**WO 2015/112450 A1**

6XXX ALUMINUM ALLOYS

CROSS-REFERENCE TO RELATED APPLICATION

[001] This patent application claims benefit of priority of United States Provisional Patent Application No. 61/929,673, filed January 21, 2014, entitled "6XXX Aluminum Alloys".

BACKGROUND

[002] Aluminum alloys are useful in a variety of applications. However, improving one property of an aluminum alloy without degrading another property often proves elusive. For example, it is difficult to increase the strength of an alloy without decreasing its corrosion resistance. Other properties of interest for aluminum alloys include formability and critical fracture strain, to name two.

SUMMARY OF THE DISCLOSURE

[003] Broadly, the present disclosure relates to new 6xxx aluminum alloys having an improved combination of properties, such as an improved combination of strength, critical fracture strain, formability, and/or corrosion resistance, among others.

[004] Generally, the new 6xxx aluminum alloys have from 0.30 to 0.53 wt. % Si, from 0.50 to 0.65 wt. % Mg wherein the ratio of wt. % Mg to wt. % Si is at least 1.0:1 (Mg:Si), from 0.05 to 0.24 wt. % Cu, from 0.05 to 0.14 wt. % Mn, from 0.05 to 0.25 wt. % Fe, up to 0.15 wt. % Ti, up to 0.15 wt. % Zn, up to 0.15 wt. % Zr, not greater than 0.04 wt. % V, and not greater than 0.04 wt. % Cr, the balance being aluminum and other elements.

[005] The amount of silicon (Si) and magnesium (Mg) in the new 6xxx aluminum alloys may relate to the improved combination of properties (e.g., strength, crush properties). Generally, the new 6xxx aluminum alloy includes from 0.30 to 0.53 wt. % Si. In one embodiment, a new 6xxx aluminum alloy includes at least 0.35 wt. % Si. In another embodiment, a new 6xxx aluminum alloy includes at least 0.375 wt. % Si. In yet another embodiment, a new 6xxx aluminum alloy includes at least 0.40 wt. % Si. In another embodiment, a new 6xxx aluminum alloy includes at least 0.425 wt. % Si. In one embodiment, a new 6xxx aluminum alloy includes not greater than 0.50 wt. % Si. In another embodiment, a new 6xxx aluminum alloy includes not greater than 0.475 wt. % Si. In one embodiment, a target amount of silicon in a new 6xxx aluminum alloy is 0.45 wt. % Si.

[006] Generally, the new 6xxx aluminum alloy includes from 0.50 to 0.65 wt. % Mg. In one embodiment, a new 6xxx aluminum alloy includes at least 0.525 wt. % Mg. In another

embodiment, a new 6xxx aluminum alloy includes at least 0.55 wt. % Mg. In yet another embodiment, a new 6xxx aluminum alloy includes at least 0.575 wt. % Mg. In one embodiment, a new 6xxx aluminum alloy includes not greater than 0.625 wt. % Mg. In one embodiment, a target amount of magnesium in a new 6xxx aluminum alloy is 0.60 wt. % Mg.

[007] Generally, the new 6xxx aluminum alloy includes silicon and magnesium such that the wt. % of Mg is equal to or greater than the wt. % of Si, i.e., the ratio of wt. % Mg to wt. % Si is at least 1.0:1 (Mg:Si). In one embodiment, the ratio of wt. % Mg to wt. % Si is at least 1.05:1(Mg:Si). In another embodiment, the ratio of wt. % Mg to wt. % Si is at least 1.10:1(Mg:Si). In yet another embodiment, the ratio of wt. % Mg to wt. % Si is at least 1.20:1(Mg:Si). In another embodiment, the ratio of wt. % Mg to wt. % Si is at least 1.30:1(Mg:Si). In one embodiment, the ratio of wt. % Mg to wt. % Si is not greater than 1.75:1(Mg:Si). In another embodiment, the ratio of wt. % Mg to wt. % Si is not greater than 1.65:1(Mg:Si). In yet another embodiment, the ratio of wt. % Mg to wt. % Si is not greater than 1.55:1(Mg:Si). In another embodiment, the ratio of wt. % Mg to wt. % Si is not greater than 1.45:1(Mg:Si). In one embodiment, a target ratio of wt. % Mg to wt. % Si in a new 6xxx aluminum alloy is 1.33:1 (Mg:Si).

[008] The amount of copper (Cu) in the new 6xxx aluminum alloys may relate to the improved combination of properties (e.g., corrosion resistance, strength). Generally, the new 6xxx aluminum alloy includes from 0.05 to 0.24 wt. % Cu. In one embodiment, a new 6xxx aluminum alloy includes not greater than 0.22 wt. % Cu. In another embodiment, a new 6xxx aluminum alloy includes not greater than 0.20 wt. % Cu. In yet another embodiment, a new 6xxx aluminum alloy includes not greater than 0.19 wt. % Cu. In another embodiment, a new 6xxx aluminum alloy includes not greater than 0.17 wt. % Cu. In one embodiment, a new 6xxx aluminum alloy includes at least 0.07 wt. % Cu. In another embodiment, a new 6xxx aluminum alloy includes at least 0.09 wt. % Cu. In yet another embodiment, a new 6xxx aluminum alloy includes at least 0.11 wt. % Cu. In another embodiment, a new 6xxx aluminum alloy includes at least 0.13 wt. % Cu. In one embodiment, a target amount of copper in a new 6xxx aluminum alloy is 0.15 wt. % Cu.

[009] The amount of manganese (Mn) in the new 6xxx aluminum alloys may relate to the improved combination of properties (e.g., formability, by controlling grain structure). Generally, the new 6xxx aluminum alloy includes from 0.05 to 0.14 wt. % Mn. In one embodiment, a new 6xxx aluminum alloy includes at least 0.06 wt. % Mn. In another embodiment, a new 6xxx aluminum alloy includes at least 0.07 wt. % Mn. In yet another

embodiment, a new 6xxx aluminum alloy includes at least 0.08 wt. % Mn. In one embodiment, a new 6xxx aluminum alloy includes not greater than 0.13 wt. % Mn. In another embodiment, a new 6xxx aluminum alloy includes not greater than 0.12 wt. % Mn. In one embodiment, a target amount of manganese in a new 6xxx aluminum alloy is 0.10 wt. % Mn.

[0010] Iron (Fe) is generally included in the new 6xxx aluminum alloy as an impurity, and in the range of from 0.05 to 0.25 wt. % Fe. In one embodiment, a new 6xxx aluminum alloy includes at least 0.10 wt. % Fe. In another one embodiment, a new 6xxx aluminum alloy includes at least 0.15 wt. % Fe. In one embodiment, a new 6xxx aluminum alloy includes not greater than 0.225 wt. % Fe. In yet another embodiment, a new 6xxx aluminum alloy includes not greater than 0.20 wt. % Fe.

[0011] Titanium (Ti) may optionally be present in the new 6xxx aluminum alloy, such as for grain refining purposes. In one embodiment, a new 6xxx aluminum alloy includes at least 0.005 wt. % Ti. In another embodiment, a new 6xxx aluminum alloy includes at least 0.010 wt. % Ti. In yet another embodiment, a new 6xxx aluminum alloy includes at least 0.0125 wt. % Ti. In one embodiment, a new 6xxx aluminum alloy includes not greater than 0.10 wt. % Ti. In another embodiment, a new 6xxx aluminum alloy includes not greater than 0.08 wt. % Ti. In yet another embodiment, a new 6xxx aluminum alloy includes not greater than 0.05 wt. % Ti. In one embodiment, a target amount of titanium in a new 6xxx aluminum alloy is 0.03 wt. % Ti.

[0012] Zinc (Zn) may optionally be included in the new alloy, and in an amount up to 0.15 wt. % Zn. Zinc may be present in scrap, and its removal may be costly. In one embodiment, a new alloy includes not greater than 0.10 wt. % Zn. In another embodiment, a new alloy includes not greater than 0.05 wt. % Zn.

[0013] Zirconium (Zr) may optionally be included in the new alloy, and in an amount up to 0.15 wt. % Zr. When present, zirconium may inhibit recrystallization. In one approach, a new 6xxx aluminum alloy includes 0.05 - 0.15 wt. % Zr. In another approach, zirconium is not purposefully used. In one embodiment, a new 6xxx aluminum alloy includes not greater than 0.10 wt. % Zr. In another embodiment, a new 6xxx aluminum alloy includes not greater than 0.05 wt. % Zr.

[0014] Both vanadium (V) and chromium (Cr) are preferentially avoided in the new 6xxx aluminum alloy. Such elements are costly and/or can form detrimental intermetallic particles in the new 6xxx aluminum alloy. Thus, the new 6xxx aluminum alloy generally includes not

greater than 0.04 wt. % V and not greater than 0.04 wt. % Cr. In one embodiment, a new 6xxx aluminum alloy includes not greater than 0.03 wt. % V. In another embodiment, a new 6xxx aluminum alloy includes not greater than 0.02 wt. % V. In one embodiment, a new 6xxx aluminum alloy includes not greater than 0.03 wt. % Cr. In another embodiment, a new 6xxx aluminum alloy includes not greater than 0.02 wt. % Cr.

[0015] As noted above, the balance of the new aluminum alloy is aluminum and other elements. As used herein, "other elements" includes any elements of the periodic table other than the above-identified elements, i.e., any elements other than aluminum (Al), Si, Mg, Cu, Mn, Fe, Ti, Zn, Zr, V, and Cr. The new aluminum alloy may include not more than 0.10 wt. % each of any other element, with the total combined amount of these other elements not exceeding 0.30 wt. % in the new aluminum alloy. In one embodiment, each one of these other elements, individually, does not exceed 0.05 wt. % in the aluminum alloy, and the total combined amount of these other elements does not exceed 0.15 wt. % in the aluminum alloy. In another embodiment, each one of these other elements, individually, does not exceed 0.03 wt. % in the aluminum alloy, and the total combined amount of these other elements does not exceed 0.10 wt. % in the aluminum alloy.

[0016] Except where stated otherwise, the expression "up to" when referring to the amount of an element means that that elemental composition is optional and includes a zero amount of that particular compositional component. Unless stated otherwise, all compositional percentages are in weight percent (wt. %).

[0017] The new 6xxx aluminum alloy may be used in all wrought product forms. In one embodiment, a new 6xxx aluminum alloy is a rolled product. For example, the new 6xxx aluminum alloys may be produced in sheet form. In one embodiment, a sheet made from the new 6xxx aluminum alloy has a thickness of from 1.5 mm to 4.0 mm.

[0018] In one embodiment, the new 6xxx aluminum alloys are produced using ingot casting and hot rolling. In one embodiment, a method includes the steps of casting an ingot of the new 6xxx aluminum alloy, homogenizing the ingot, rolling the ingot into a rolled product having a final gauge (via hot rolling and/or cold rolling), solution heat treating the rolled product, wherein the solution heat treating comprises heating the rolled product to a temperature and for a time such that substantially all of Mg_2Si of the rolled product is dissolved into solid solution, and after the solution heat treating, quenching the rolled product (e.g., cold water quenching). After the quenching, the rolled product may be artificially aged. In some embodiments, one or more anneal steps may be completed during the rolling (e.g.,

hot rolling to a first gauge, annealing, cold rolling to the final gauge). The artificially aged product can be painted (e.g., for an automobile part), and may thus be subjected to a paint-bake cycle. In one embodiment, the rolled aluminum alloy products produced from the new alloy may be incorporated in an automobile.

[0019] In another embodiment, the new 6xxx aluminum alloys products are cast via continuous casting. Downstream of the continuous casting, the product can be (a) rolled (hot and/or cold), (b) optionally annealed (e.g., between hot rolling and any cold rolling steps), (c) solution heat treated and quenched, (d) optionally cold worked (post-solution heat treatment), and (e) artificially aged, and all steps (a) - (e) may occur in-line or off-line relative to the continuous casting step. Some methods for producing the new 6xxx aluminum alloys products using continuous casting and associated downstream steps are described in, for example, U.S. Patent No. 7,182,825, U.S. Patent Application Publication No. 2014/0000768, and U.S. Patent Application Publication No. 2014/036998. The artificially aged product can be painted (e.g., for an automobile part), and may thus be subjected to a paint-bake cycle.

DETAILED DESCRIPTION

Example 1 - Industrial Scale Testing

[0020] Two industrial scale ingots were cast (one invention and one comparison), then scalped, and then homogenized. The compositions of the ingots are provided in Table 1, below. The ingots were then hot rolled to an intermediate gauge, then annealed at 800°F for 1 hour, and then cold rolled to final gauge (2.0 mm). The rolled products were then solution heat treated at a temperature and for a time such that substantially all of Mg_2Si of the rolled product was dissolved into solid solution. The rolled products were then immediately cold water quenched, and then naturally aged and artificially aged for various periods, as described below. Mechanical properties were then tested, including tensile yield strength (TYS), ultimate tensile strength (UTS), tensile elongation (T. Elong.), ultimate elongation (U. Elong.), and critical fracture strain (CFS), the results of which are shown in Tables 2-3. Mechanical properties including TYS, UTS, T. Elong. and U. Elong. were either tested in accordance with ASTM E8 and B557, or using a tapered version of the ASTM B557 specimen. Critical fracture strain (CFS) was derived from an engineering stress v. strain curve generated from the above described tests. Using the stress v. strain curve, the engineering strain at maximum load (ϵ_m), the engineering stress at maximum load (δ_m) and

the engineering stress at the fracture load (δ_f) were determined and then entered into the following equation to provide the critical fracture strain (CFS):

$$CFS = -\ln\left(\frac{\delta_f/\delta_m}{(1 + \varepsilon_m)^{1/2}}\right)$$

The CFS may be multiplied by 100 to convert from units of strain to units of percent (%). Corrosion resistance per ASTM G110 was also measured, the results of which are shown in Table 4, below.

Table 1 - Composition of Alloys of Example 1

Ingot	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	V	Mg:Si
1 (Inv.)	0.43	0.19	0.14	0.096	0.61	0.032	0.013	0.019	0.009	1.40
2 (Comp.)	0.81	0.19	0.14	0.143	0.71	0.032	0.013	0.019	0.009	0.88

Table 2 - Mechanical Properties of Alloy 1 (Invention) of Example 1

Natural Age Interval	Artificial Age Temp (°F)	Artificial Age Time (hours)	Dir.	TYS ksi (MPa)	UTS ksi (MPa)	U. Elong. (%)	T. Elong. (%)	CFS (%)
1 month	None	None	L	15.7 (108)	25.92 (179)	20.8	26.6	28.1
			LT	15.1 (104)	25.035 (173)	19.5	24.6	29.4
			45	15.5 (107)	25.785 (178)	23.0	29.9	26.2
3 months	300	8	L	27.3 (188)	37.1 (256)	14.6	21.0	31.2
			LT	25.7 (177)	35.7 (246)	15.7	21.0	23.7
			45	26.0 (180)	36.0 (248)	16.4	21.4	22.9
3 months	315	8	L	31.0 (214)	39.2 (270)	13.0	18.6	23.9
			LT	29.5 (204)	37.8 (261)	13.5	19.8	27.7
			45	29.8 (205)	38.1 (262)	14.1	20.0	21.1
35 days	356	8	LT	34.6 (239)	38.5 (266)	7.9	9.9	30.8

Table 3 - Mechanical Properties of Alloy 2 (Comparison) of Example 1

Natural Age Interval	Artificial Age Temp (°F)	Artificial Age Time (hours)	Direction	TYS ksi	UTS ksi	U. Elong. (%)	T. Elong. (%)	CFS (%)
30 days	None	None	L	22.9	37.2	20.8	26.2	23.1
			LT	21.6	35.8	20.9	26.5	19.1
			45	21.9	36.3	23.3	28.4	21.4
182 days	356	2	LT	38.4	46.2	13.2	18.2	13.2

Table 4 - Corrosion Resistance of Example 1 Alloys

Alloy	Condition	24 hours - ASTM G110 Max depth of attack (µm)					
		1	2	3	4	5	Ave.
1 (Inv.)	As Fabricated	0	30	0	0	0	6
1 (Inv.)	45 mins. @ 195°C	0	39	43	0	0	16
2 (Comp.)	As Fabricated	0	15	0	0	0	3
2 (Comp.)	45 mins. @ 195°C	36	15	32	20	29	26

[0021] As shown, the invention alloy (alloy 1) achieved improved properties over the comparison alloy (alloy 2). Specifically, with reference to tables 2 and 3, invention alloy 1 achieved improved critical fracture strain (CFS) over comparison alloy 2. For example, comparison alloy 2 after 30 days of natural aging and no artificial aging realized a CFS value of about 19% in the LT direction. In contrast, invention alloy 1 achieved improved critical fracture strain, realizing a CFS value of about 29% in the LT direction after 1 month of natural aging and no artificial aging. As another example, comparison alloy 2 after 182 days of natural aging and 2 hours of artificial aging at 356°F realized a CFS value of about 13% in the LT direction. In contrast, invention alloy 1 again achieved improved critical fracture strain, realizing a CFS value of about 28% in the LT direction after 3 months of natural aging and 8 hours of artificial aging at 315°F. Thus, the invention alloy achieved improved critical fracture strain (CFS) in the aged condition.

[0022] Higher critical fracture strain (CFS) values may correlate with improved crush properties. For example, a material (e.g., an aluminum alloy) which realizes a higher CFS value may also generally realize improved resistance to cracking in the tight folds of the material that may occur as a result of a crushing force. In one embodiment, alloys realizing a CFS value of at least 20% may be resistant to cracking (e.g., no cracking) in the tight folds produced by a crushing force.

[0023] As shown in table 4, invention alloy 1 achieved improved corrosion resistance over comparison alloy 2 after both alloys were artificially aged. For example, comparison alloy 2 after artificial aging for 45 minutes at 195°C realized an average depth of attack of 26 μm . In contrast, invention alloy 1 achieved improved corrosion resistance, realizing an average depth of attack of 16 μm after artificial aging for 45 minutes at 195°C, and with corrosion resistance occurring at only 2 sites (sites 2 and 3). Thus, the invention alloy achieved an improved combination of, for instance, critical fracture strain and corrosion resistance.

[0024] **Example 2 - Additional Industrial Scale Testing**

An additional invention alloy ingot (alloy 3) was cast as an ingot, the composition of which is shown in Table 5, below.

Table 5 - Composition of Example 2 Alloy

Ingot	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Ni	Mg:Si
3 (Inv.)	0.44	0.18	0.14	0.10	0.60	0.02	0.02	0.02	--	1.36

[0025] After casting, the alloy 3 ingot was scalped, and then homogenized. The ingot was then hot rolled to an intermediate gauge, then annealed at 800°F for 1 hour, and then cold rolled to two different final gauges of 2.0 mm (0.0787 inch) and 3.0 mm (0.118 inch). The rolled products were then solution heat treated at a temperature and for a time such that substantially all of Mg_2Si of the rolled product was dissolved into solid solution. The rolled products were then immediately cold water quenched, and then naturally aged for about two months. The rolled products were then artificially aged at various temperatures for about 27 hours. Some of the rolled products were then stretched about 2% while others of the rolled products were not stretched. Various ones of the products (both stretched and un-stretched) were then subjected to a simulated paint bake for 20 minutes at either 180°C (356°F) at 185°C (365°F). The mechanical properties of the rolled products were then tested. The processing

conditions for the various alloys are provided in Table 6, below. The mechanical properties are provided in Table 7, below.

Table 6 - Post-Rolling Processing Conditions for Example 2 Alloys

Alloy	Final Gauge (mm)	Artificially Aging Temp. °C / (°F) for ~ 27 hours	Stretch	Simulated Paint Bake
3A-1	2.0	146.1 / (295)	None	None
3A-2	2.0	137.8 / (280)	None	None
3A-3	3.0	146.1 / (295)	None	None
3A-4	3.0	137.8 / (280)	None	None
3B-1	2.0	146.1 / (295)	None	20 mins. at 180°C
3B-2	2.0	137.8 / (280)	None	20 mins. at 180°C
3B-3	3.0	146.1 / (295)	None	20 mins. at 180°C
3B-4	3.0	137.8 / (280)	None	20 mins. at 180°C
3C-1	2.0	146.1 / (295)	2%	20 mins. at 180°C
3C-2	2.0	137.8 / (280)	2%	20 mins. at 180°C
3C-3	3.0	146.1 / (295)	2%	20 mins. at 180°C
3C-4	3.0	137.8 / (280)	2%	20 mins. at 180°C
3D-1	2.0	146.1 / (295)	2%	20 mins. at 185°C
3D-2	2.0	137.8 / (280)	2%	20 mins. at 185°C
3D-3	3.0	146.1 / (295)	2%	20 mins. at 185°C
3D-4	3.0	137.8 / (280)	2%	20 mins. at 185°C

Table 7 - Mechanical Properties of Example 2 Alloys

Alloy	Final Gauge (mm)	Direction	TYS (MPa)	UTS (MPa)	U. Elong. (%)	T. Elong. (%)	CFS (%)
3A-1	2.0	L	227	285	13.3	18.8	22.5
3A-1	2.0	LT	219	275	13.8	19.3	26.8
3A-1	2.0	45	220	276	14.2	20.3	20.8
3A-2	2.0	L	205	272	14.9	22.0	29.5

Alloy	Final Gauge (mm)	Direction	TYS (MPa)	UTS (MPa)	U. Elong. (%)	T. Elong. (%)	CFS (%)
3A-2	2.0	LT	197	263	15.6	21.5	27.2
3A-2	2.0	45	198	263	16.4	21.6	22.6
3A-3	3.0	L	228	283	13.4	19.8	27.1
3A-3	3.0	LT	222	276	13.6	20.4	27.8
3A-3	3.0	45	223	276	14.0	21.0	21.2
3A-4	3.0	L	208	272	14.6	20.7	27.5
3A-4	3.0	LT	202	264	15.0	21.7	28.8
3A-4	3.0	45	203	266	16.0	22.4	22.7
3B-1	2.0	LT	218	271	13.3	18.9	24.8
3B-2	2.0	LT	200	260	14.0	19.7	24.1
3B-3	3.0	LT	221	272	12.8	19.8	26.5
3B-4	3.0	LT	206	263	13.5	20.3	27.2
3C-1	2.0	LT	245	279	11.4	16.7	25.4
3C-2	2.0	LT	234	274	12.4	18.2	32.2
3C-3	3.0	LT	248	280	11.2	17.7	29.7
3C-4	3.0	LT	238	275	11.6	19.3	28.8
3D-1	2.0	LT	247	278	10.8	16.8	30.9
3D-2	2.0	LT	236	273	11.6	17.4	27.2
3D-3	3.0	LT	249	280	10.6	18.2	29.2
3D-4	3.0	LT	240	276	11.4	18.2	28.0

[0026] As shown, the invention alloy realized an unexpectedly improved combination of strength, ductility and crush resistance. As shown, the invention alloy realized high CFS values (e.g., above 20%) for both the 2.0 mm and the 3.0 mm products. Further the CFS values were not negatively impacted by the application of the simulated paint bake (with or without 2% stretch), and thus would still be expected to show good cracking resistance upon application of a crushing force.

[0027] While various embodiments of the present disclosure have been described in detail, it is apparent that modifications and adaptations of those embodiments will occur to those skilled in the art. However, it is to be expressly understood that such modifications and adaptations are within the spirit and scope of the present disclosure.

CLAIMS

What is claimed is:

1. A recrystallized 6xxx aluminum alloy product consisting of:
 - 0.35 - 0.53 wt. % Si;
 - 0.50 - 0.65 wt. % Mg;
 - wherein a ratio of wt. % Mg to wt. % Si is at least 1.05:1 (Mg:Si);
 - 0.05 - 0.24 wt. % Cu;
 - 0.05 - 0.14 wt. % Mn;
 - 0.05 - 0.25 wt. % Fe;
 - up to 0.15 wt. % Ti;
 - up to 0.15 wt. % Zn;
 - up to 0.15 wt. % Zr;
 - not greater than 0.04 wt. % V;
 - not greater than 0.04 wt. % Cr;
 - the balance being aluminum and other elements, wherein each of the other elements does not exceed 0.10 wt. % in the recrystallized 6xxx aluminum alloy, and wherein a total of the other elements is not more than 0.30 wt. % in the recrystallized 6xxx aluminum alloy;
 - wherein the recrystallized 6xxx aluminum alloy product is a sheet product; and
 - wherein the recrystallized 6xxx aluminum alloy product realizes a typical long-transverse (LT) tensile yield strength of at least 200 MPa and a critical fracture strain (CFS) of at least 25% in an artificially aged condition.
2. The recrystallized 6xxx aluminum alloy product of claim 1 having 0.40 - 0.50 wt. % Si.
3. The recrystallized 6xxx aluminum alloy product of claim 1 having 0.55 - 0.65 wt. % Mg.
4. The recrystallized 6xxx aluminum alloy product of any one of claims 1-3, wherein the ratio of wt. % Mg to wt. % Si is at least 1.10:1.
5. The recrystallized 6xxx aluminum alloy product of any one of claims 1-3, wherein the ratio of wt. % Mg to wt. % Si is at least 1.20:1.
6. The recrystallized 6xxx aluminum alloy product of any one of claims 1-3, wherein the ratio of wt. % Mg to wt. % Si is at least 1.30:1.
7. The recrystallized 6xxx aluminum alloy product of any one of claims 1-3, wherein the ratio of wt. % Mg to wt. % Si is not greater than 1.75:1.
8. The recrystallized 6xxx aluminum alloy product of any one of claims 1-7 having not greater than 0.22 wt. % Cu.
9. The recrystallized 6xxx aluminum alloy product of any one of claims 1-8 having not greater than 0.20 wt. % Cu.

10. The recrystallized 6xxx aluminum alloy product of any one of claims 1-8 having not greater than 0.19 wt. % Cu.
11. The recrystallized 6xxx aluminum alloy product of any one of claims 1-10 having at least 0.07 wt. % Cu.
12. The recrystallized 6xxx aluminum alloy product of any one of claims 1-10 having at least 0.09 wt. % Cu.
13. The recrystallized 6xxx aluminum alloy product of any one of claims 1-10 having at least 0.11 wt. % Cu.
14. The recrystallized 6xxx aluminum alloy product of any one of claims 1-13 having 0.06 - 0.13 wt. % Mn.
15. The recrystallized 6xxx aluminum alloy product of any one of claims 1-13 having 0.07 - 0.12 wt. % Mn.
16. The recrystallized 6xxx aluminum alloy product of any one of claims 1-15 having not greater than 0.03 wt. % each of V and Cr.
17. The recrystallized 6xxx aluminum alloy product of any one of claims 1-16 having not greater than 0.02 wt. % V.
18. The recrystallized 6xxx aluminum alloy product of any one of claims 1-17 having not greater than 0.02 wt. % Cr.
19. A method comprising:
 - (a) casting an aluminum alloy product, wherein the aluminum alloy product comprises:
 - 0.35 - 0.53 wt. % Si;
 - 0.50 - 0.65 wt. % Mg;
 - wherein a ratio of wt. % Mg to wt. % Si is at least 1.05:1 (Mg:Si);
 - 0.05 - 0.24 wt. % Cu;
 - 0.05 - 0.14 wt. % Mn;
 - 0.05 - 0.25 wt. % Fe;
 - up to 0.15 wt. % Ti;
 - up to 0.15 wt. % Zn;
 - up to 0.15 wt. % Zr;
 - not greater than 0.04 wt. % V;
 - not greater than 0.04 wt. % Cr;
 - the balance being aluminum and other elements, wherein each of the other elements does not exceed 0.10 wt. % in the 6xxx aluminum alloy, and wherein a total of the other elements is not more than 0.30 wt. % in the 6xxx aluminum alloy;

- (b) homogenizing the aluminum alloy product;
 - (c) rolling the aluminum alloy product into a rolled product having a final gauge of from 1.5 to 4.0 mm, wherein the rolled product is recrystallized;
 - (d) solution heat treating the rolled product, wherein the solution heat treating comprises heating the rolled product to a temperature and for a time such that substantially all of Mg_2Si of the rolled product is dissolved into solid solution; and
 - (e) after the solution heat treating, quenching the rolled product.
20. The method of claim 19, comprising: artificially aging the rolled product.
21. The method of any one of claims 19-20, wherein the quenching comprises cold water quenching.
22. A method comprising:
- (a) continuously casting an aluminum alloy product, wherein the aluminum alloy product comprises:
 - 0.35 - 0.53 wt. % Si;
 - 0.50 - 0.65 wt. % Mg;
 - wherein a ratio of wt. % Mg to wt. % Si is at least 1.05:1 (Mg:Si);
 - 0.05 - 0.24 wt. % Cu;
 - 0.05 - 0.14 wt. % Mn;
 - 0.05 - 0.25 wt. % Fe;
 - up to 0.15 wt. % Ti;
 - up to 0.15 wt. % Zn;
 - up to 0.15 wt. % Zr;
 - not greater than 0.04 wt. % V;
 - not greater than 0.04 wt. % Cr;
 - the balance being aluminum and other elements, wherein each of the other elements does not exceed 0.10 wt. % in the 6xxx aluminum alloy, and wherein a total of the other elements is not more than 0.30 wt. % in the 6xxx aluminum alloy;
 - (b) rolling the aluminum alloy product into a rolled product having a final gauge of from 1.5 to 4.0 mm, wherein the rolled product is recrystallized;
 - (c) solution heat treating the rolled product, wherein the solution heat treating comprises heating the rolled product to a temperature and for a time such that substantially all of Mg_2Si of the rolled product is dissolved into solid solution; and
 - (d) after the solution heat treating, quenching the rolled product.