



US 20170029727A1

(19) **United States**

(12) **Patent Application Publication**  
**DREES et al.**

(10) **Pub. No.: US 2017/0029727 A1**

(43) **Pub. Date: Feb. 2, 2017**

(54) **BONDED LAYER METHOD FOR  
PRECIPITATING SOLIDS, FOR TREATING A  
LIQUID CONTAINING CONTAMINANTS,  
FOR TREATING A SURFACE RESIDING IN A  
LIQUID CONTAINING CONTAMINANTS**

(60) Provisional application No. 61/770,963, filed on Feb. 28, 2013.

**Publication Classification**

(71) Applicant: **ELECTROLAB, INC.**, BOERNE, TX (US)

(51) **Int. Cl.**  
**C10G 75/04** (2006.01)  
**C10G 75/02** (2006.01)

(72) Inventors: **SEAN ERIC DREES**, BOERNE, TX (US); **ANDREW TIMOTHY MARZEC**, SAN ANTONIO, TX (US); **BRIAN KEITH BRASHEAR**, SAN ANTONIO, TX (US)

(52) **U.S. Cl.**  
CPC ..... **C10G 75/04** (2013.01); **C10G 75/02** (2013.01)

(73) Assignee: **ELECTROLAB, INC.**, BOERNE, TX (US)

(57) **ABSTRACT**


(21) Appl. No.: **15/164,859**

Methods for precipitating solids comprising asphaltenes and/or paraffins that may include precipitating the solid and contacting the solid with a surface comprising a bonded layer coating or alternatively may include precipitating the solid in the presence of such a surface, wherein the bonded layer is a molecularly bonded layer or a covalently bonded layer. The method for treating a liquid containing contaminants comprising asphaltenes and/or paraffins may include inserting into the liquid, a surface as described above, or further coating surfaces within the liquid with a bonded layer coating.

(22) Filed: **May 25, 2016**

**Related U.S. Application Data**

(63) Continuation of application No. 14/099,497, filed on Dec. 6, 2013, now Pat. No. 9,476,754.






FIG. 1




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG 4C.




FIG. 4D




FIG. 4E




FIG. 4F

**BONDED LAYER METHOD FOR  
PRECIPITATING SOLIDS, FOR TREATING A  
LIQUID CONTAINING CONTAMINANTS,  
FOR TREATING A SURFACE RESIDING IN A  
LIQUID CONTAINING CONTAMINANTS**

CROSS-REFERENCE TO RELATED  
APPLICATION DATA

[0001] This utility application is a continuation of U.S. patent application Ser. No. 14/099,497, filed Dec. 6, 2013, which claims priority to U.S. Provisional Patent Application Ser. No. 61/770,963 filed Feb. 28, 2013, both of which are incorporated herein by reference for all purposes.

FIELD OF THE INVENTION

[0002] The present invention relates to paraffin and asphaltene deposition on components used in crude oil service operations. In another aspect, the present invention relates to coatings for reduction of paraffin and asphaltene deposition on stainless steel and nickel alloy components utilized in crude oil service. In yet another aspect, the present invention relates to anti-paraffin coatings to address paraffin/asphaltene deposition on stainless steel and nickel alloy sensor components. In still another aspect, the present invention relates to unique application of commercially available nano-coatings for the reduction of paraffin and asphaltene deposition on stainless steel and nickel alloy components utilized in crude oil service. In yet another aspect, the present invention relates to a method and kit for surface treatment of cooperating, controller or sensor components used in crude oil service operations to reduce paraffin/asphaltene deposition.

BACKGROUND OF THE INVENTION

[0003] Paraffins, more commonly referred to as alkanes, are the chemical family of saturated hydrocarbons that result from combining  $\text{CH}_2$  groups in succession. Additional  $\text{CH}_2$  groups are added to form straight-chain paraffins.

[0004] The term “wax” simply refers to saturated hydrocarbons that contain more than 16 carbon atoms in the paraffin series ( $\text{C}_{16}\text{-C}_{40}$ ) and are in a solid state at room temperature. The majority of waxes present in crude oil are considered synthetic paraffin waxes with non-oxidized saturated alkanes.

[0005] Paraffins may exist in crude oil in all three states. At standard room temperature,  $\text{C}_{16}\text{+n}$ -paraffins generally exists in a solid form and solidify to form deposits. Wax is the product of paraffin deposition, so in the industrial context, “wax” and “paraffin” are often used interchangeably.

[0006] Therefore, “paraffin wax deposition” refers to the solid form of paraffins that solidify to cause deposition.

[0007] Because asphaltene is typically talked about in the same context as paraffin, it is important to understand what asphaltene is and why it is problematic to the crude oil service operations. Asphaltene is the material present in petroleum that is insoluble in n-paraffins but soluble in aromatic solvents. Asphaltenes cause catalyst deactivation and sediment formation.

[0008] Tars or asphaltenes occur in many crudes as colloidally suspended solid particles. Precipitation takes place when the crude loses its ability to keep those particles

dispersed. Many of the same factors affecting paraffin deposition (discussed below) also affect asphaltene deposition.

[0009] Paraffins precipitate out of waxy crudes when there is a slight change in equilibrium conditions, causing a loss of solubility of the wax in the crude. A lowering in temperature is the most common cause of paraffin precipitation.

[0010] Thus, hydrocarbon liquids, including both crude oils and condensates, form a paraffin or asphaltene solid phase when process temperatures fall below the cloud point (or Wax Appearance Temperature) of the liquid. While this normally occurs in colder temperature services, it may also occur in any process where the combination of complex composition factors, such as API gravity, pressure/temperature variables and other factors favor deposition.

[0011] The presence of asphaltenes increases the difficulties for paraffin wax treatments because these structures are almost always found in association with waxes when they are retrieved from wells, storage tanks, or pipelines (Becker J. R. 1997, *Crude oil waxes, emulsions, and asphaltenes*. Tulsa, Okla.; PennWell Publishing Company). While paraffin wax deposition may be reduced by increasing the flow velocity of crude, increasing fluid velocities increases the likelihood of asphaltene deposition.

[0012] Further, studies show that the amount of asphaltene precipitation decreases as the number of carbons forming straight-chain paraffins increases. In other words, treatment of paraffin wax could escalate the precipitation of heavier, problematic asphaltene compounds. Therefore, treatment of paraffin and asphaltene deposition must both be considered in the balance.

[0013] Once formed, these paraffin/asphaltene solids will typically deposit on tank-mounted level sensors and instrumentation. This deposition presents a potential safety hazard when critical operational and/or safety sensors are affected. This may cause a loss of billions of dollars per year worldwide through the enormous cost of remediation, reduced or deferred production, well shut-ins, equipment replacements and/or abandonments, equipment failures, extra horsepower requirements, and increased manpower needs.

[0014] The modern petroleum industry has developed new technologies for controlling the deposition of petroleum paraffin and asphaltenes, particularly in wells, storage tanks, and pipelines. However, these technologies have been less effective on sensitive tank level sensors, flow sensors, and other instrumentation. Traditional methods of management and remediation have been established for many years and include the following:

[0015] a. Chemical Treatments and Additives: While chemical treatments help to manage solids deposition in connected lines, instrument tubing and storage tank internal components, some chemicals do not suspend the paraffin indefinitely and may be damaging to the environment.

[0016] b. Hot Oiling: Hot oiling is one method often employed for removing deposition in storage tanks. Paraffin and asphaltene buildup is handled by periodically pumping very hot oil, augmented by cleansing additives, into the vessels in order to melt the accumulations from tank walls, sensors and internal equipment.

[0017] c. Manual Cleaning: During normal maintenance operations, internally mounted equipment may be periodically subject to manual cleaning. This typically involves removal of sensors, instruments, etc.



from out-of-service tanks and process equipment for cleaning. Alternately, personnel may physically enter out-of-service tanks to perform the cleaning with sensors and equipment in place. These methods typically involve considerable expense in time and labor for taking equipment out of service, the cleaning process itself, and management of safety associated with hazardous conditions, including hydrogen sulfide (H<sub>2</sub>S) exposure.

**[0018]** However, these procedures are labor and cost intensive and are not very effective with sensitive sensors and instrumentations. The solution is to avoid wax and asphaltene depositions in the first place.

#### SUMMARY OF THE INVENTION

**[0019]** The AP (Anti-Paraffin) Coating composition of the present invention provides a unique and cost-effective way for petroleum facility owner/operators to address common paraffin/asphaltene deposition on cooperating stainless steel and nickel alloy sensor components and instrumentation. It is anticipated that the present method may be utilized with a wide range of metals as well as non-metallic components.

**[0020]** The present invention is a new application of a modified, existing, chemical technology representing a significant potential for reduction in typical labor and costs of paraffin/asphaltene remediation in critical process instrumentation and the elimination of associated hazards. Using available nano-coating materials applied to cooperating surfaces of subject components produces permanent changes in the molecular characteristics of subject component metal, wetted parts and/or entire sensor assemblies, making them highly resistant to solids deposition in the extreme process environments normally encountered in petroleum production facilities. The present invention provides improved reliability of sensors and devices, as well as providing improved operational and maintenance personnel safety. Again, the key strategy is to avoid the initial affixation of the paraffin and asphaltene deposits on the surface subject components.

#### BRIEF DESCRIPTION OF THE FIGURES

**[0021]** FIG. 1 illustrates a diagram of the present invention method showing the process steps.

**[0022]** FIG. 2 is the perspective view of a foil packet of the present inventive kit.

**[0023]** FIG. 3 is a basic illustration of some components of a digital level sensor described in this application.

**[0024]** FIGS. 4A-4F are illustrations of capacitance sensors which have been treated along exposed surfaces with the anti-paraffin coating composition of the present invention.

**[0025]** FIGS. 4A-4C illustrate capacitance sensors having cylindrical outer housings.

**[0026]** FIGS. 4D-4E show an alternative embodiment of a capacitance sensor having a generally rectangular outer housing.

**[0027]** FIG. 4F is a perspective view of the embodiment of FIGS. 4D and 4E.

#### DETAILED DESCRIPTION OF A PREFERRED EMBODIMENT

**[0028]** The present invention to create resistance to and/or reduce paraffin/asphaltene deposition on stainless steel and

nickel alloy components utilizes a composition known as a Self-Assembled Monolayer of Phosphonate (SAMP). SAMP is commercially available from a wide range of suppliers. Typically, SAMP is utilized with an alcohol-based carrier which allows for rapid drying. It is anticipated that the SAMP may be combined with a glycol carrier for use in the treatment of components used in crude oil service operation.

**[0029]** A monolayer is a nanoscale coating that is one molecule thick or 1-4 nanometers in thickness (1 nm=1×10<sup>-9</sup> meters). A phosphonate is a phosphorous acid connected with a carbon-based group through a highly stable phosphorus carbon bond.

**[0030]** The phosphonic acid reacts with the component surface through stable metal phosphorus bonds, and the carbons are chosen for their non-stick chemical functionality. The SAMP is covalently bound to the substrate, forming a durable, low-surface tension, non-stick surface. This permanent chemical bond is highly stable under ambient conditions. Currently, an alcohol-based carrier is combined with the SAMP in some applications, but using a glycol-based carrier is unique in crude oil environments.

**[0031]** Through standard Dyne pen testing, surface energy is shown to be significantly and permanently reduced through application of a nano-coating to the tested component. Field trials with components treated via the present inventive process indicate a significant reduction of paraffin/asphaltene deposition on stainless steel sensor components installed in crude oil storage tanks operated in low acidity/low turbulence applications at normal temperatures.

**[0032]** The present inventive process may be utilized in the manufacture of sensors and instrumentation for a crude oil service operation. As a non-limiting embodiment, a typical application method during manufacture involves a simple two-part process in which a cleaner/primer wipe is manually applied to prepare the surface of the stainless steel or nickel alloy components and rinsed with di-ionized water to remove dirt, grease, etc. After the initial cleaning/preparation step and drying, a nano-coating wipe is manually applied directly to the component to be protected. The method is simple: clean, dry, apply, insert, and monitor process, as illustrated in FIG. 1.

**[0033]** As an example, the manufacture of a vertical crude oil storage tank level sensor includes a continuous 316L, square, stainless steel outer tubing that cooperates with the float carrier and all electronic sensor components and switches that are activated by the movement of float carrier to measure the level of the liquid in the storage tank. FIG. 3 shows the square tubing 50 of a digital level sensor (DLS), a float carrier 52 with floats members 54 attached to the carrier 52. During operation, the outer surface 56 of tubing comes into contact with the inner surface 58 of the carrier 52. This sliding contact between the tubing 50 and the inner surface 58 of the float carrier 52 is adversely affected if paraffin or asphaltene deposits build up on these surfaces. When deposits build up on the surfaces of the components, the float carrier 52 does not freely move up and down the tubing 50, thereby causing false level readings in the digital level sensor. The outer tubing extends the entire length of the sensor from top tank connection to the bottom of the sensor. After assembly and testing, the sensor is disassembled and the nano-treatment is completed in the following steps:

**[0034]** a. The sensor assembly including the stainless steel tubes 50, float carrier 52, and floats 54 are placed

on horizontal support racks. The entire sensor assembly is thoroughly cleaned on all sides with an alcohol or phosphate-based detergent laden sponge or wipe **60** to remove any mill oil, dirt, grease, etc. and liberally flushed with clean water. This process step is repeated until all visual indications of surface contaminants are removed.

**[0035]** b. The assembly is thoroughly dried using clean, lint-free cloth or absorbent paper towels.

**[0036]** c. Immediately after drying, the nano-treatment chemical composition of the present invention (SAMP) is directly applied to the clean outer tube surfaces **56** and the inner carrier surfaces **58** of the assembly parts with a soft cloth or wipe **62** impregnated with the SAMP composition and gently rubbed into the outer surface **56** and inner surface **58** in order to assure complete chemical coverage. After approximately 1 minute of contact time, excess SAMP composition residue is removed and the complete assembly is thoroughly dried and reassembled.

**[0037]** According to the present inventive method, capacitance sensors **70A**, **70B**, **70C** and **70D** as shown in FIGS. **4A-4F** may be treated as described above. The nano-treatment chemical composition (SAMP) is directly applied to the clean outer surfaces **72A**, **72B**, **72C**, **72D**; the inner surfaces **74A-74D**; and core elements **78A-78D** as described above. It may be further understood that openings **76A**, **76B**, and **76C** in FIGS. **4A-4C** allow crude oil to flow through the sensors, **70A-70C** and become exposed to the sensor core **78A-78C**. In FIGS. **4D-4F**, capacitance sensor **70D** has a different, unique design wherein rather than utilizing a generally, cylindrical tube **80A-80C**, as shown in FIGS. **4A-4C**, two spaced-apart stainless steel plates **90** are held in a generally parallel relationship by two, perforated plastic sidewalls **92**. A shrink wrapped printed circuit board sensor **94**, with an explosion-proof head **91** attached to one end of the sensor, is disposed within the generally rectangular enclosure or housing formed by the two steel plates **90** and the perforated plastic side walls **92**.

**[0038]** The nano-treatment chemical composition (SAMP) is applied to the inner surfaces **96** and outer surfaces **98** of the spaced-apart stainless steel plates **90**. Crude oil flows through the perforation **93** in the sidewall **92** to be read by the sensor printed circuit board **94**.

**[0039]** Excess SAMP composition residue is removed from the treated surfaces. With the sensors **70A**, **70B**, **70C** and **70D**, it is the utilization of the anti-paraffin composition along the surfaces exposed to the crude oil which reduces the paraffin build-up which may affect the sensitivity of the sensor.

**[0040]** In future applications involving larger scale factory coating processes, the manual system described above can easily be replaced with more automated processes, non-limiting examples of which include spray-type applicators and/or a tank dip system. A commercial embodiment of the present invention may comprise bulk supply and large scale application of primer/cleaner, coating chemical, and rinse/flush agents. The coatings of the present invention may be designed for coating a wider range of metal as well as non-metal surfaces (including glass, polymers, etc.).

**[0041]** In another non-limiting embodiment, a kit may be employed wherein individual wipes **60** and **62** (FIG. **2**) are separately sealed and robustly packaged to withstand long-term storage and handling. Wipe **60** is a cleaning wipe

having an alcohol or phosphate-based detergent. Wipe **62** is impregnated with a SAMP composition appropriate for the application. The chemical components are non-toxic, REACH compliant (having approximately the same environmental characteristics as common isopropyl alcohol), and have no known adverse environmental impacts. No specialized training or Personal Protective Equipment (PPE) is required for use.

**[0042]** A proper application of the nano-coating composition produces a permanent molecular bond that is highly stable under normal ambient conditions. However, components subjected to turbulent flow profiles in which basic sediment index is high (abrasive service), or those subject to high acidity/temperature may require a re-application of the protective coating due to surface abrasion of the metal component.

**[0043]** It should be understood that the AP coating is monitored to evaluate the effectiveness of the SAMP composition coating. Recoating of components may be accomplished by cleaning, drying, and applying, as described above.

**[0044]** It should be understood that the SAMP composition of the present invention may be enhanced by the addition of tracer additives which impart a "tint" or color to treated components. Such "tinting" will result in an observable indication of the sufficiency of the component coating. As the "tint" intensity decreases, the operator will be able to determine if additional coating coverage is required. Further, enhancements may include additives to produce a wider range of component surface characterizations including, but not limited to, corrosion inhibitors, anti-static properties, and the like. As described above, utilization of a glycol-based carrier component to the SAMP composition may enhance crude oil process/service applications.

**[0045]** The present invention is useful for surfaces that come into contact with hydrocarbon liquids, including both crude oils and condensates, in which paraffins and/or asphaltenes are present or may become present.

**[0046]** Non-limiting examples of commercial applicability of the present invention include petroleum production, petroleum pipelines, petroleum equipment (storage tanks and specialty vessels, etc.), and petroleum sensor and instrument manufacturing.

**[0047]** The foregoing is considered as illustrative only of the principles of the invention. Further, since numerous modifications and changes will readily occur to those skilled in the art, it is not desired to limit the invention to the exact construction and operation shown and described.

**[0048]** Those skilled in the art will recognize other embodiments of the invention which may be drawn from the illustrations and the teachings herein. To the extent that such alternative embodiments are so drawn, it is intended that they shall fall within the ambit of protection of the claims appended hereto.

**[0049]** Having disclosed the invention in the foregoing specification and accompanying drawings in such a clear and concise manner, those skilled in the art will readily understand and easily practice the invention.

What is claimed is:

1. A method for handling precipitating solids comprising at least one selected from the group consisting of paraffin and asphaltene, comprising the steps of:

- precipitating the solid; and,  
contacting a surface with the solid, wherein the surface comprises a bonded layer,  
wherein the bonded layer is a molecularly bonded layer or a covalently bonded layer.
2. The method of claim 1, wherein the solids reside in crude oil, and the contacting occurs in the presence of crude oil.
3. The method of claim 1, wherein the surface further comprises at least one of a tracer additive, corrosion inhibitor, or anti-static additive.
4. A method for handling solids comprising at least one selected from the group consisting of paraffin and asphaltene, comprising the step of:  
contacting a surface with the solid, wherein the surface comprises a bonded layer,  
wherein the bonded layer is a molecularly bonded layer or a covalently bonded layer.
5. The method of claim 4, wherein the solids reside in crude oil, and the contacting occurs in the presence of crude oil.
6. The method of claim 4, wherein the surface further comprises at least one of a tracer additive, corrosion inhibitor, or anti-static additive.
7. A method for precipitating solids comprising at least one selected from the group consisting of paraffin and asphaltene, the method comprising the step of:  
precipitating the solids in the presence of a surface comprising a bonded layer,  
wherein the bonded layer is a molecularly bonded layer or a covalently bonded layer.
8. The method of claim 7, wherein the precipitating occurs in the presence of crude oil.
9. The method of claim 7, wherein the surface further comprises at least one of a tracer additive, corrosion inhibitor, or anti-static additive.
10. A method for handling a liquid containing contaminants, wherein the contaminants comprise at least one selected from the group consisting of asphaltenes and paraffins, and wherein the contaminants may comprise a solid phase in the liquid, be solubilized in the liquid, or both, the method comprising the step of:  
inserting into the liquid, a surface comprising a bonded layer, wherein the bonded layer is a molecularly bonded layer or a covalently bonded layer.
11. The method of claim 10, wherein the liquid comprises a hydrocarbon liquid.
12. The method of claim 10, wherein the liquid comprises a crude oil.
13. The method of claim 10, wherein the surface further comprises at least one of a tracer additive, corrosion inhibitor, or anti-static additive.
14. A method for handling a liquid containing contaminants, wherein the contaminants comprise at least one selected from the group consisting of asphaltenes and paraffins, and wherein the contaminants may comprise a solid phase in the liquid, be solubilized in the liquid, or both, the method comprising the step of:  
flowing the liquid past a surface comprising a bonded layer, wherein the bonded layer is a molecularly bonded layer or a covalently bonded layer.
15. The method of claim 14, wherein the liquid comprises a hydrocarbon liquid.
16. The method of claim 14, wherein the liquid comprises a crude oil.
17. The method of claim 14, wherein the surface further comprises at least one of a tracer additive, corrosion inhibitor, or anti-static additive.
18. A method for treating a surface residing in a liquid containing contaminants, wherein the contaminants comprise at least one selected from the group consisting of asphaltenes and paraffins, and wherein the contaminants may be in the solid phase, solubilized in the liquid, or both, the method comprising the step of:  
applying a bonded layer composition to the surface, wherein the bonded layer is a molecularly bonded layer or a covalently bonded layer.
19. The method of claim 18, wherein the liquid comprises a hydrocarbon liquid.
20. The method of claim 18, wherein the liquid comprises a crude oil.
21. The method of claim 18, wherein the surface further comprises at least one of a tracer additive, corrosion inhibitor, or anti-static additive.
- \* \* \* \* \*