

[54] 2,2,2-TRIS(HYDROXYMETHYL)ETHYL-PHOSPHONIC ACID AND METHOD FOR ITS PREPARATION

3,933,427 1/1976 Bohnsack et al. 21/2.7 A
3,963,636 6/1976 Harris et al. 252/181
3,966,630 6/1976 Quinlan 252/180
3,978,166 8/1976 Hechenbleikier 260/969

[75] Inventor: Lawrence J. Carr, Elk Grove Village, Ill.

FOREIGN PATENT DOCUMENTS

[73] Assignee: Borg-Warner Corporation, Chicago, Ill.

1,369,429 10/1974 United Kingdom.
245,098 10/1969 U.S.S.R. 260/502.4 R

[21] Appl. No.: 750,101

OTHER PUBLICATIONS

[22] Filed: Dec. 13, 1976

"A Report to Water Treatment Service Companies" (Monsanto).

[51] Int. Cl.² C07F 9/38

Primary Examiner—Joseph E. Evans
Attorney, Agent, or Firm—Joseph Shekleton

[52] U.S. Cl. 260/502.4 R; 210/58; 252/180

[58] Field of Search 260/502.4 R

[56] References Cited

[57] ABSTRACT

U.S. PATENT DOCUMENTS


2,573,568 10/1951 Harman et al. 260/961
3,270,091 8/1966 Spivack 260/502.4 R
3,271,306 9/1966 Capriati et al. 260/502.4 R
3,483,279 12/1969 Davis et al. 260/969
3,493,639 2/1970 Tavs 260/502.4 R
3,925,455 12/1975 Maier 260/502.4 P
3,926,801 12/1975 Quinlan 210/58

This invention relates to a novel phosphonic acid, 2,2,2-tris (hydroxymethyl) ethylphosphonic acid, and to a process for its preparation. It also relates to the use of such phosphonic acid as an inhibitor of corrosion of metal surfaces and as an inhibitor of the development of scale in cooling water.


1 Claim, No Drawings

2,2,2-TRIS(HYDROXYMETHYL)ETHYLPHOSPHONIC ACID AND METHOD FOR ITS PREPARATION

It has been discovered in accordance with the present invention that the phosphonic acid of the structure




known as tris(hydroxymethyl)ethylphosphonic acid, or more precisely, as 3-hydroxy-2,2-bis(hydroxymethyl)propylphosphonic acid, is obtained by hydrolysis of a polyphosphonic acid having



as its repeating unit. The hydrolysis reaction is accomplished quite simply, merely by heating with water, no catalyst or unusual conditions being required.

The polyphosphonic acid is available from the polymerization of pentaerythritol phosphite which is characterized by the structure



This polymerization is disclosed in U.S. Pat. No. 3,978,166; it is carried out by heating pentaerythritol phosphite at a relatively high temperature, i.e., from about 160° to about 250° C, until the polymerization is complete; usually, this requires at least about four hours, depending upon the particular temperature used.

The tris(hydroxymethyl)ethylphosphonic acid is an effective water treatment additive. That is, in the case of cooling water, it can be used to prevent the development of scale. Its efficacy in this respect is shown by data obtained from a scale inhibition test carried out as follows: Test solutions (A through F) of calcium chloride, sodium bicarbonate, sodium carbonate, tris(hydroxymethyl)ethylphosphonic acid and sodium hydroxide are prepared so as to give a solution containing 800 ppm of dissolved calcium carbonate, 12.5 (or 25.0) ppm of the phosphonate, and a pH of 9.0. The resulting mixture is maintained at room temperature for a period of time. At this point the calcium ion concentration, expressed as calcium carbonate, is determined and compared with the calcium ion concentration of the same solution, also kept at room temperature for the same period, but without the phosphonate present. The formation of scale involves the precipitation of calcium carbonate, so that a relatively high calcium ion concentration indicates effective scale inhibition.

The present scale inhibition (PSI) is calculated according to the formula

$$PSI = \frac{V_1 - V_0}{V_2 - V_0} \times 100$$

where

V_1 = Calcium concentration with phosphonate inhibitor;

V_0 = Calcium concentration without phosphonate inhibitor; and

V_2 = Calcium concentration (800 ppm) at start of test.

The results are shown in Table I. Test solution E is as described above; test solutions B, C, D and F are the same except that the phosphonic acid content is neutralized by the addition of zinc dust; test solution A is similar to E except that it also contains 12.5 ppm of ZnCl_2 . In each case, i.e., test solutions A through F, the test solution is compared with a solution which is similar except that it contains no phosphonate.

Table I

Test Solutions	Phosphonate (ppm)	% Scale Inhibition			
		48 Hrs.	72 Hrs.	120 Hrs.	168 Hrs.
A	12.5	41			32
B	12.5	43			36
C	25.0		28		
D	12.5			55*	
E	12.5	17			3
F	12.5	27			30

*70° C for 24 hours then room temperature for 96 hours.

Another test which is effective to demonstrate the scale inhibiting properties of the phosphonic acid herein depends on the amount of scale which adheres to the wall surface of a container. The percent scale inhibition in such instances is calculated according to the formula

$$PSI = \frac{W_c - W_i}{W_c} \times 100$$

where

W_c = weight of scale adhering to the wall surface when phosphonate is present, and

W_i = weight of scale adhering to the wall surface when no phosphonate is present.

Test solutions similar to B, D and F (in Table I) are permitted to stand in a glass beaker and a copper beaker for 240 hours and 196 hours, respectively. The percent scale inhibition in each case is shown in Table II.

Table II

Test Solutions	Wall Surface	196 Hrs.	240 Hrs.
		G	
H	glass copper	65	

Effective scale-inhibiting concentrations of the phosphonic acid herein in water range from about 5 ppm to about 25 ppm.

The tris(hydroxymethyl)ethylphosphonic acid herein is effective also as an aqueous corrosion inhibitor. This is shown by the data in Table III. The data reflects results obtained from tests carried out in a synthetic hard water at room temperature. The "hard water" contains the following ingredients:

1.267 g. Na_2CO_3
4.987 g. NaHCO_3
8.039 g. CaCl_2
4.334 g. MgSO_4

per 18 liters of water. Its pH is 8.2. A 1008 mild steel coupon (1 × 1 × 3/16 inch) is suspended in the water for three days and the loss in weight noted. The water is agitated at room temperature all the while. The de-

