# United States Patent [19]

Johnson et al.

[11] **3,769,107**[45] **Oct. 30, 1973** 

[54]		CHNIC COMPOSITION FOR FING LEAD BASED SMOKE	[56]		eferences Cited  STATES PATENTS
[75]	Inventors:	Duane M. Johnson, Bicknell; Donald R. Hazelton, Winslow, both of Ind.	2,995,526 3,046,168 3,140,207	8/1961 7/1962 7/1964	De Ment
[73]	Assignee:	The United States of America as represented by the Secretary of the Navy, Washington, D.C.		Donaldson et al 149/19	
[22]	Filed:	Oct. 28, 1968			ver and R. Miller
[21]	Appl. No.	773,694	[57]		ABSTRACT
[52]	U.S. Cl	U.S. Cl149/19.6, 149/20, 149/22, 149/117  A pyrotechnic composition comprising lead alkali iodate, boron, and epoxy resin which up		and epoxy resin which upon com-	
[51]	Int. Cl	C06d 5/06	used for artificial weather modification.		
[58]	Field of Se	earch 149/19, 22, 44, 83–85			

# PYROTECHNIC COMPOSITION FOR GENERATING LEAD BASED SMOKE

#### **GOVERNMENT INTEREST**

The invention herein described may be manufactured and used by or for The Government of the United States of America for governmental purposes without the payment of any royalties thereon or therefor.

#### **BACKGROUND OF THE INVENTION**

Various types of pyrotechnic compositions capable of providing clouds of smoke upon combustion are well known as are pyrotechnic compositions containing silver iodate which upon combustion produce silver iodide nuclei which if properly introduced into the ap- 15 propriate cloud may increase rainfall, make hail formation more difficult, or disperse supercooled fog. The technique of seeding undercooled clouds is known. Two widely used artificial ice nuclei are dry ice (solid carbon dioxide) used successfully for cloud modifica- 20 tion by Schaefer in 1946, and silver iodide whose excellent activity was discovered by Vonnegut in 1947. The use of silver iodide as a seeding material is based on its property of acting as freezing nuclei at relatively high temperatures, namely between -4° C. and -5° C. and 25 of turning undercooled clouds into ice particles. Heretofore only very few substances have become known which have nucleus properties similar to silver iodide, such as lead iodide. The generation of silver iodide remains comparatively expensive. However, the genera- 30 tion of lead based nuclei by pyrotechnic means has never been too successful and therefore has not produced results comparable to silver iodide smokes. The present invention provides a pyrotechnic composition which not only produces lead-based freezing nuclei 35 which show excellent ice forming activity, but the material is fairly inexpensive.

## SUMMARY OF THE INVENTION

The invention relates to improved pyrotechnic compositions. More particularly, to a pyrotechnic which upon combustion yields a lead-based active nuclei which has application in artificially influencing the

The general purpose of this invention is to provide a pyrotechnic composition which is comparable to or better than other pyrotechnic compositions which upon combustion yield by-products which show improved freezing nuclei activity. Another object is to provide a pyrotechnic which is economical to prepare and safe to handle.

## DESCRIPTION OF THE INVENTION

The present invention is for a composition comprising at least two oxidizers, one an alkali iodate and the other lead iodate, a nonmetallic fuel, and a binder which contains no halogens other than iodine.

The alkali iodate used includes potassium, cesium, sodium and rubidium iodate. The preferred fuel is boron which is safe and does not tend to form more energetic bonds with iodine than with oxygen. Other metals which may be used are aluminum or magnesium; also, others which do not tend to form more energetic bonds with iodine than with oxygen. The preferred binder is epoxy resin. It is necessary to aid in the consolidation of the composition if pelletizing is desired. It is important to this composition that the binder used

contain no halogens other than iodine. Other halogens may reduce the efficiency of this composition. The preferred formulation is accomplished by maintaining an alkali metal to lead mole ratio between 1:1 and 20:1.

5 Sufficient fuel is added to react with the oxygen present in the composition but is not necessarily required as the composition will function with less. It is not necessary that a stoichiometric quantity of fuel be used, but it is recommended that no more than twice this amount be 10 used. The quantity of binder is that needed to mix the materials needed to compact into a solid grain.

Upon combustion the present improved pyrotechnic compositions yield lead iodide-alkali metal iodide complexes. It is postulated that by forming the alkali iodide the lead iodide formed is chemically and physically protected by chemically bonding the metallic iodides as double base salts or by physically forming a protective layer around the lead iodide in the flame and/or upon cooling to the solid state, i.e., smoke particles. This protection is believed to prevent the oxidation of the lead iodide formed in the flame and/or when contact with atmospheric oxygen occurs.

The following examples better illustrate this invention but should not be considered as limiting.

#### **EXAMPLE I**

Ingredients	Percent by weight
Lead iodate	48.9
Potassium iodate	37.6
Borón	7.5
D Epoxy resin binder	6.0
The inverse burn rate =4.3 sec/inch.	

The nucleation efficiency (nuclei per gram of composition) is as follows:

### **EXAMPLE II**

Ingredients	Percent by weight
Lead iodate	26.2
Potassium iodate	59.6
Boron	8.2
Epoxy resin binder	6.0
The inverse burn rate =4.3 sec/inch.	

The nucleation efficiency (nuclei per gram of composition) is as follows:

 $-6.5^{\circ}$  C.,  $2.2 \times 10^{11}$ 

 $-7.5^{\circ}$  C.,  $3.2 \times 10^{11}$ 

 $-10.5^{\circ}$  C.,  $1.2 \times 10^{12}$ 

#### **EXAMPLE III**

Ingredients		Percent by weight
Lead iodate		87.2
Boron		6.8
Epoxy resin	oinder	6.0
The inverse l	urn rate = 5.2 sec/inch	

The nucleation efficiency (nuclei per gram of composition) is as follows:

 $-9^{\circ}$  C.,  $3.4 \times 10^{11}$ 

# **EXAMPLE IV**

Ingredients	Percent by weight
Lead iodate	26.2
Potassium iodate	59.6
_ Boron	4.7
5 Gilsonite	3.5
Epoxy binder	6.0
The inverse burn rate =12 sec/inch	

### **EXAMPLE V**

Percent by weight
41.0
31.5
21.5
6.0

## **EXAMPLE VI**

Ingredients Lead iodate Potassium iodate Boron	Percent by weight 40.0 46.2 7.8
Epoxy binder	6.0

## **EXAMPLE VII**

(2)
62.6 24.1
7.3 6.0

The nucleation activity of Examples VI and VII were about the same as those for Example I above.

All of the Examples (I – VII) were prepared by dissolving the epoxy resin and curing agent which is used with the epoxy in acetone. The other ingredients are added while agitating until a homogeneous mixture was obtained. The acetone was then removed by vacuum and the composition pressed into cylinders of predetermined size and cured. When burned, these compositions produce smokes ranging from white to pink in color. The compositions show good nuclei activity at temperatures ranging from  $-1^{\circ}$  to  $-10^{\circ}$  C.

The preferred epoxy resin system is DER 321, which may be obtained from Dow Chemical Company. It is a liquid having an epoxide equivalent of 187 - 193; average molecular weight 350 - 400 and viscosity at 25° C. of 11,000 - 16,000 centipoises. It is a reaction 35

product of Bisphenol A and epichlorohydrin to which is added about 10 weight percent butyl glycidyl ether as a reactive diluent. It is cured with about 11 parts by weight to 100 parts of the resin/diluent combination of a conventional curing agent, such as diethylene triamine. Epoxy resins were found to be the best binders because they give a longer, more stable shelf life to the composition.

Use of this lead based composition in pyrotechnic generators for cloud seeding experiments has shown that the ice forming efficiency is equal to or better than that of silver and much less expensive. These pyrotechnic devices are either fired from the ground or from airplanes as they fly into the preselected clouds. Because the crystal of lead complex formed, like the silver iodide used in the prior art, is similar to that of ice, it acts as a seed for the growth of ice crystals in a supercooled cloud.

The boron and other nonmetals such as silicon offer greater safety in manufacturing as well as much better storage properties and resistance to moisture degradation.

What is claimed is:

5 1. A pyrotechnic composition comprising the following:

Ingredients	Percent by weight
Lead iodate	25 - 65
Potassium iodate	25 - 60
Boron	4 - 8
Epoxy resin	6 - 8.

2. The composition of claim 1 to which gilsonite is added in a percent by weight ranging from 3 - 4, as needed for desired burning rate.

40

45

50

55

60