



(11) **EP 4 105 974 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
21.12.2022 Bulletin 2022/51

(51) International Patent Classification (IPC):
H01L 21/768^(2006.01) H01L 29/78^(2006.01)

(21) Application number: **22173279.5**

(52) Cooperative Patent Classification (CPC):
H01L 21/76897; H01L 29/785; H01L 21/76898

(22) Date of filing: **13.05.2022**

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME
Designated Validation States:
KH MA MD TN

- **WALLACE, Charles H.**
Portland, 97212 (US)
- **PULS, Conor P.**
Portland, 97229 (US)
- **HAFEZ, Walid M.**
Portland, 97229 (US)
- **SUBRAMANIAN, Sairam**
Portland, 97229 (US)
- **SANDFORD, Justin S.**
Tigard, 97224 (US)
- **MORARKA, Saurabh**
Portland, 97229 (US)
- **PURSEL, Sean**
Tigard, 97224 (US)
- **HASAN, Mohammad**
Aloha, 97006 (US)

(30) Priority: **14.06.2021 US 202117347034**

(71) Applicant: **INTEL Corporation**
Santa Clara, CA 95054 (US)

(72) Inventors:

- **GULER, Leonard P.**
Hillsboro, 97124 (US)
- **GHANI, Tahir**
Portland, 97229 (US)

(74) Representative: **2SPL Patentanwälte PartG mbB**
Landaubogen 3
81373 München (DE)

(54) **CONDUCTIVE VIA BAR SELF-ALIGNED TO GATE END**

(57) Conductive via bars self-aligned to gate ends are described. In an example, an integrated circuit structure includes a plurality of gate structures. The integrated circuit structure also includes a plurality of dielectric spacers, a corresponding one of the plurality of dielectric spacers laterally surrounding a corresponding one of the plurality of gate structures. A plurality of conductive trench

contact structures is alternating with the plurality of gate structures. A conductive via bar is along ends of the plurality of gate structures and ends of the plurality of conductive trench contact structures, wherein the plurality of dielectric spacers is between the ends of the plurality of gate structures and the conductive via bar.




FIG. 6

EP 4 105 974 A1

Description**TECHNICAL FIELD**

[0001] Embodiments of the disclosure are in the field of advanced integrated circuit structure fabrication and, in particular, conductive via bars self-aligned to gate ends.

BACKGROUND

[0002] For the past several decades, the scaling of features in integrated circuits has been a driving force behind an ever-growing semiconductor industry. Scaling to smaller and smaller features enables increased densities of functional units on the limited real estate of semiconductor chips. For example, shrinking transistor size allows for the incorporation of an increased number of memory or logic devices on a chip, lending to the fabrication of products with increased capacity. The drive for ever-more capacity, however, is not without issue. The necessity to optimize the performance of each device becomes increasingly significant.

[0003] Variability in conventional and currently known fabrication processes may limit the possibility to further extend them into the 10 nanometer node or sub-10 nanometer node range. Consequently, fabrication of the functional components needed for future technology nodes may require the introduction of new methodologies or the integration of new technologies in current fabrication processes or in place of current fabrication processes.

[0004] In the manufacture of integrated circuit devices, multi-gate transistors, such as tri-gate transistors, have become more prevalent as device dimensions continue to scale down. Tri-gate transistors are generally fabricated on either bulk silicon substrates or silicon-on-insulator substrates. In some instances, bulk silicon substrates are preferred due to their lower cost and compatibility with the existing high-yielding bulk silicon substrate infrastructure.

[0005] Scaling multi-gate transistors has not been without consequence, however. As the dimensions of these fundamental building blocks of microelectronic circuitry are reduced and as the sheer number of fundamental building blocks fabricated in a given region is increased, the constraints on the semiconductor processes used to fabricate these building blocks have become overwhelming.

BRIEF DESCRIPTION OF THE DRAWINGS**[0006]**

Figures 1A and 1B illustrate tilted and angled cross-sectional views representing various operations in a method of fabricating an integrated circuit structure having cut metal gates, in accordance with an em-

bodiment of the present disclosure.

Figures 2A and 2B illustrate tilted and angled cross-sectional views illustrating various operations in a method of fabricating an integrated circuit structure having conductive via bars self-aligned to gate ends, in accordance with an embodiment of the present disclosure.

Figure 3 illustrates a tilted and angled cross-sectional view illustrating an integrated circuit structure having conductive via bars aligned to gate ends, in accordance with an embodiment of the present disclosure.

Figure 4 illustrates a plan view illustrating an integrated circuit structure having conductive via bars aligned to gate ends, in accordance with an embodiment of the present disclosure.

Figures 5 and 6 illustrate tilted and angled cross-sectional views illustrating various operations in a method of fabricating an integrated circuit structure having conductive via bars self-aligned to gate ends, in accordance with another embodiment of the present disclosure.

Figures 7A-7J illustrates cross-sectional views of various operations in a method of fabricating a gate-all-around integrated circuit structure, in accordance with an embodiment of the present disclosure.

Figure 8 illustrates a cross-sectional view of a non-planar integrated circuit structure as taken along a gate line, in accordance with an embodiment of the present disclosure.

Figure 9 illustrates cross-sectional views taken through nanowires and fins for a non-endcap architecture (left-hand side (a)) versus a self-aligned gate endcap (SAGE) architecture (right-hand side (b)), in accordance with an embodiment of the present disclosure.

Figure 10 illustrates cross-sectional views representing various operations in a method of fabricating a self-aligned gate endcap (SAGE) structure with gate-all-around devices, in accordance with an embodiment of the present disclosure.

Figure 11A illustrates a three-dimensional cross-sectional view of a nanowire-based integrated circuit structure, in accordance with an embodiment of the present disclosure.

Figure 11B illustrates a cross-sectional source or drain view of the nanowire-based integrated circuit structure of Figure 11A, as taken along the a-a' axis, in accordance with an embodiment of the present disclosure.

Figure 11C illustrates a cross-sectional channel view of the nanowire-based integrated circuit structure of Figure 11A, as taken along the b-b' axis, in accordance with an embodiment of the present disclosure.

Figure 12 illustrates a computing device in accordance with one implementation of an embodiment of the disclosure.

Figure 13 illustrates an interposer that includes one

or more embodiments of the disclosure.

DESCRIPTION OF THE EMBODIMENTS

[0007] Conductive via bars self-aligned to gate ends, and methods of fabricating conductive via bars self-aligned to gate ends, are described. In the following description, numerous specific details are set forth, such as specific integration and material regimes, in order to provide a thorough understanding of embodiments of the present disclosure. It will be apparent to one skilled in the art that embodiments of the present disclosure may be practiced without these specific details. In other instances, well-known features, such as integrated circuit design layouts, are not described in detail in order to not unnecessarily obscure embodiments of the present disclosure. Furthermore, it is to be appreciated that the various embodiments shown in the Figures are illustrative representations and are not necessarily drawn to scale.

[0008] The following detailed description is merely illustrative in nature and is not intended to limit the embodiments of the subject matter or the application and uses of such embodiments. As used herein, the word "exemplary" means "serving as an example, instance, or illustration." Any implementation described herein as exemplary is not necessarily to be construed as preferred or advantageous over other implementations. Furthermore, there is no intention to be bound by any expressed or implied theory presented in the preceding technical field, background, brief summary or the following detailed description.

[0009] This specification includes references to "one embodiment" or "an embodiment." The appearances of the phrases "in one embodiment" or "in an embodiment" do not necessarily refer to the same embodiment. Particular features, structures, or characteristics may be combined in any suitable manner consistent with this disclosure.

[0010] Terminology. The following paragraphs provide definitions or context for terms found in this disclosure (including the appended claims):

[0011] "Comprising." This term is open-ended. As used in the appended claims, this term does not foreclose additional structure or operations.

[0012] "Configured To." Various units or components may be described or claimed as "configured to" perform a task or tasks. In such contexts, "configured to" is used to connote structure by indicating that the units or components include structure that performs those task or tasks during operation. As such, the unit or component can be said to be configured to perform the task even when the specified unit or component is not currently operational (e.g., is not on or active). Reciting that a unit or circuit or component is "configured to" perform one or more tasks is expressly intended not to invoke 35 U.S.C. §112, sixth paragraph, for that unit or component.

[0013] "First," "Second," etc. As used herein, these terms are used as labels for nouns that they precede,

and do not imply any type of ordering (e.g., spatial, temporal, logical, etc.).

[0014] "Coupled" - The following description refers to elements or nodes or features being "coupled" together. As used herein, unless expressly stated otherwise, "coupled" means that one element or node or feature is directly or indirectly joined to (or directly or indirectly communicates with) another element or node or feature, and not necessarily mechanically.

[0015] In addition, certain terminology may also be used in the following description for the purpose of reference only, and thus are not intended to be limiting. For example, terms such as "upper", "lower", "above", and "below" refer to directions in the drawings to which reference is made. Terms such as "front", "back", "rear", "side", "outboard", and "inboard" describe the orientation or location or both of portions of the component within a consistent but arbitrary frame of reference which is made clear by reference to the text and the associated drawings describing the component under discussion. Such terminology may include the words specifically mentioned above, derivatives thereof, and words of similar import.

[0016] "Inhibit" - As used herein, inhibit is used to describe a reducing or minimizing effect. When a component or feature is described as inhibiting an action, motion, or condition it may completely prevent the result or outcome or future state completely. Additionally, "inhibit" can also refer to a reduction or lessening of the outcome, performance, or effect which might otherwise occur. Accordingly, when a component, element, or feature is referred to as inhibiting a result or state, it need not completely prevent or eliminate the result or state.

[0017] Embodiments described herein may be directed to front-end-of-line (FEOL) semiconductor processing and structures. FEOL is the first portion of integrated circuit (IC) fabrication where the individual devices (e.g., transistors, capacitors, resistors, etc.) are patterned in the semiconductor substrate or layer. FEOL generally covers everything up to (but not including) the deposition of metal interconnect layers. Following the last FEOL operation, the result is typically a wafer with isolated transistors (e.g., without any wires).

[0018] Embodiments described herein may be directed to back-end-of-line (BEOL) semiconductor processing and structures. BEOL is the second portion of IC fabrication where the individual devices (e.g., transistors, capacitors, resistors, etc.) get interconnected with wiring on the wafer, e.g., the metallization layer or layers. BEOL includes contacts, insulating layers (dielectrics), metal levels, and bonding sites for chip-to-package connections. In the BEOL part of the fabrication stage contacts (pads), interconnect wires, vias and dielectric structures are formed. For modern IC processes, more than 10 metal layers may be added in the BEOL.

[0019] Embodiments described below may be applicable to FEOL processing and structures, BEOL processing and structures, or both FEOL and BEOL processing and structures. In particular, although an exemplary process-

ing scheme may be illustrated using a FEOL processing scenario, such approaches may also be applicable to BEOL processing. Likewise, although an exemplary processing scheme may be illustrated using a BEOL processing scenario, such approaches may also be applicable to FEOL processing.

[0020] In accordance with an embodiment of the present disclosure, conductive deep via bars are described. One or more embodiments described herein are directed to gate all around devices and associated deep via bars. It is to be appreciated that, unless indicated otherwise, reference to nanowires herein can indicate nanowires or nanoribbons. One or more embodiments described herein are directed to FinFET structures and associated deep via bars.

[0021] To provide context, gate end and source or drain epitaxial (epi) shorting to a deep via bar can become an issue as scaling continues. In an embodiment, a gate cut is used with spacerized gate ends, and a DVB etch is deflected away from an end cap. Epi structures can be protected from the DVB by a dielectric barrier. In accordance with one or more embodiments of the present disclosure, non-selective metal gate and/or pre-spacer cut processes can be combined with a gate end self-aligned DVB process. Embodiments described herein can be implemented to simplify fabrication of a deep via bar.

[0022] As an exemplary processing scheme to provide a gate cut process that can ultimately be combined with a self-aligned conductive via bar process, Figures 1A and 1B illustrate tilted and angled cross-sectional views representing various operations in a method of fabricating an integrated circuit structure having cut metal gates, in accordance with an embodiment of the present disclosure. Figures 2A and 2B illustrate tilted and angled cross-sectional views illustrating various operations in a method of fabricating an integrated circuit structure having conductive via bars self-aligned to gate ends, in accordance with an embodiment of the present disclosure. Figure 3 illustrates a tilted and angled cross-sectional view illustrating an integrated circuit structure having conductive via bars aligned to gate ends, in accordance with an embodiment of the present disclosure. Figure 4 illustrates a plan view illustrating an integrated circuit structure having conductive via bars aligned to gate ends, in accordance with an embodiment of the present disclosure.

[0023] Referring to Figure 1A, a starting structure 100 includes a plurality of subfins 104, such as silicon subfins, extending from a substrate 102, such as a silicon substrate, and through shallow trench isolation (STI) structures 103. A plurality of horizontally stacked nanowires 106 is over a corresponding one of the subfins 104. A dielectric cap 109 may be over a corresponding one of the horizontally stacked nanowires 106, as is depicted. A gate dielectric structure 108 is around each of the nanowires 106 and over the subfins 104. In one embodiment, the gate dielectric structure 108 includes a high-k gate dielectric layer and may further include an oxidized

portion of the nanowires 106 and the subfins 104. A gate layer 110, such as a workfunction metal gate layer, is on the gate dielectric structure 108. A gate fill 112, such as a metal gate fill, is on the gate layer 110. An insulating gate cap layer 114 is on the gate fill 112. Reference to a gate stack may refer to a structure including gate dielectric structure 108, gate layer 110 and gate fill 112. Dielectric spacers 116 are along sides of the gate stacks. Epitaxial source or drain structures 118 are between the dielectric spacers 116 of neighboring gate stacks. An insulating source or drain cap material 120 is over the epitaxial source or drain structures 118.

[0024] Referring to Figure 1B, a gate cut 150 cuts select ones of the gate stacks to form patterned gate dielectric structure 108A, patterned gate layer 110A, patterned gate fill 112A, and patterned insulating gate cap layer 114A. In one embodiment, the gate cut is non-selective in that patterned dielectric spacers 116A, patterned epitaxial source or drain structures 118A and patterned insulating source or drain cap material 120A is also formed. That is, in one embodiment, the gate cut 150 is not confined between the dielectric spacers 116.

[0025] Referring to Figure 2A, an exemplary implementation of the structure of Figure 1B is depicted, using structure 200 as a starting structure. Structure 200 includes a plurality of subfins 204 extending from a substrate 202 and into shallow trench isolation (STI) structures and a dielectric trench contact template 206. Gate structures are covered by the dielectric trench contact template 206. Dielectric spacers 212 separate the gate structures and openings for trench contacts and trench via bars, the openings formed over epitaxial source or drain structures 216. In one embodiment, remnants of a protective insulator layer 215 can be retained in locations where contact between an ultimately formed the conductive via bar and the epitaxial source or drain structures 216 is to be blocked. A conductive material 220 or stack of conductive materials is formed in the openings for trench contacts and trench via bars, as is depicted in Figure 2B.

[0026] Referring to Figure 3, the structure of Figure 2B can planarized to provide a structure 300, as shown through a trench contact cut. Structure 300 includes a plurality of subfins 304 extending from a substrate 302 and through shallow trench isolation (STI) structures 306. Gate structures are depicted as including a gate electrode 308 and gate dielectric 310. Trench contacts 314 are depicted over epitaxial source or drain structures 316. Dielectric spacers 312 separate the gate structures and the trench contacts 314. As exemplary non-limiting structures, trench contact plugs 318 (e.g., as remnants of a dielectric template), a gate block region 309, and a conductive via bar 314A are also depicted. Also, in one embodiment, remnants of a protective insulator layer 315 can be retained in locations where contact between the conductive via bar 314A and the epitaxial source or drain structures 316 is to be blocked.

[0027] Referring to Figure 4, a plan view of an exem-

plarity implementation of the structure of Figure 3 is depicted. An integrated circuit structure 400 includes a plurality of gate structures (shown as gate electrodes 408 and gate dielectrics 410). The integrated circuit structure 400 also includes a plurality of dielectric spacers 412, a corresponding one of the plurality of dielectric spacers 412 laterally surrounding a corresponding one of the plurality of gate structures 408/410. A plurality of conductive trench contact structures 414 is alternating with the plurality of gate structures 408/410. A conductive via bar 414A is along ends of the plurality of gate structures 408/410 and ends of the plurality of conductive trench contact structures 414. The plurality of dielectric spacers 412 is between the ends of the plurality of gate structures 408/410 and the conductive via bar 414A.

[0028] It is to be appreciated that the conductive via bars illustrated in association with the Figures described above are depicted as having a bottommost surface above a top surface of sub-fins of the structure. In other embodiments, the conductive via bars can have a bottommost surface below a top surface of sub-fins of the structure. As an exemplary process and resulting structure, Figures 5 and 6 illustrate tilted and angled cross-sectional views illustrating various operations in a method of fabricating an integrated circuit structure having conductive via bars self-aligned to gate ends, in accordance with another embodiment of the present disclosure.

[0029] Referring to Figure 5, a starting structure 500 includes a plurality of subfins 504 extending from a substrate 502 and into shallow trench isolation (STI) structures and a dielectric trench contact template 506. Gate structures (shown as gate electrodes 508 and gate dielectrics 510, and an optional gate block region 509) are covered by the dielectric trench contact template 506. Dielectric spacers 512 separate the gate structures and openings for trench contacts and trench via bars, the openings formed over epitaxial source or drain structures 516. In one embodiment, remnants of a protective insulator layer 515 can be retained in locations where contact between an ultimately formed the conductive via bar and the epitaxial source or drain structures 516 is to be blocked.

[0030] Referring to Figure 6, a conductive material or stack of conductive materials can then be formed in the openings of structure 500. The conductive material or stack of conductive materials can be planarized to form trench contacts 514 and conductive via bar 514A.

[0031] With reference again to Figures 3, 4 and 6, in accordance with an embodiment of the present disclosure, an integrated circuit structure includes a plurality of gate structures. The integrated circuit structure also includes a plurality of dielectric spacers, a corresponding one of the plurality of dielectric spacers laterally surrounding a corresponding one of the plurality of gate structures. A plurality of conductive trench contact structures is alternating with the plurality of gate structures. A conductive via bar is along ends of the plurality of gate structures and ends of the plurality of conductive trench

contact structures, wherein the plurality of dielectric spacers is between the ends of the plurality of gate structures and the conductive via bar.

[0032] In one embodiment, the plurality of dielectric spacers has an uppermost surface co-planar with an uppermost surface of the plurality of gate structures and co-planar with an uppermost surface of the plurality of conductive trench contact structures and co-planar with an uppermost surface of the conductive via bar. In one embodiment, one or more of the plurality of conductive trench contact structures is separated from the conductive via bar by a corresponding dielectric plug.

[0033] In one embodiment, the plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface above a top surface of the one or more sub-fins. In another embodiment, the plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface below a top surface of the one or more sub-fins.

[0034] In one embodiment, the plurality of gate structures is over one or more stacks of semiconductor nanowires. In one embodiment, the plurality of gate structures is over one or more stacks of semiconductor nanoribbons. In one embodiment, the plurality of gate structures is over one or more semiconductor fins.

[0035] In an embodiment, a semiconductor structure or device described herein is a non-planar device such as, but not limited to, a fin-FET or a tri-gate device. In such an embodiment, a corresponding semiconducting channel region is composed of or is formed in a three-dimensional body. In one such embodiment, corresponding gate electrode stacks surround at least a top surface and a pair of sidewalls of the three-dimensional body. In another embodiment, at least the channel region is made to be a discrete three-dimensional body, such as in a gate-all-around device. In one such embodiment, corresponding gate electrode stacks completely surrounds the channel region.

[0036] As an exemplary fabrication scheme, a starting structure includes one or more gate stack structures disposed above a substrate. The gate stack structures may include a gate dielectric layer and a gate electrode. Trench contacts, e.g., contacts to diffusion regions of the substrate or to epitaxial region formed within the substrate are spaced apart from gate stack structures by dielectric spacers. In an embodiment, the contact pattern is essentially perfectly aligned to an existing gate pattern while eliminating the use of a lithographic operation with exceedingly tight registration budget. In one such embodiment, this approach enables the use of intrinsically highly selective wet etching (or anisotropic dry etch processes some of which are non-plasma, gas phase isotropic etches (e.g., versus classic dry or plasma etching) to generate contact openings. In an embodiment, a contact pattern is formed by utilizing an existing gate pattern in combination with a contact plug lithography operation. In one such embodiment, the approach enables elimination of the need for an otherwise critical lithography operation

to generate a contact pattern, as used in other approaches. This also allows for perfect or near-perfect self-alignment with a larger edge placement error margin. In an embodiment, a trench contact grid is not separately patterned, but is rather formed between poly (gate) lines. For example, in one such embodiment, a trench contact grid is formed subsequent to gate grating patterning but prior to gate grating cuts.

[0037] Furthermore, the gate stack structures may be fabricated by a replacement gate process. In such a scheme, dummy gate material such as polysilicon or silicon nitride pillar material, may be removed and replaced with permanent gate electrode material. In one such embodiment, a permanent gate dielectric layer is also formed in this process, as opposed to being carried through from earlier processing. In an embodiment, dummy gates are removed by a dry etch or wet etch process. In one embodiment, dummy gates are composed of polycrystalline silicon or amorphous silicon and are removed with a dry etch process including SF_6 . In another embodiment, dummy gates are composed of polycrystalline silicon or amorphous silicon and are removed with a wet etch process including aqueous NH_4OH or tetramethylammonium hydroxide. In one embodiment, dummy gates are composed of silicon nitride and are removed with a wet etch including aqueous phosphoric acid.

[0038] In an embodiment, one or more approaches described herein contemplate essentially a dummy and replacement gate process in combination with a dummy and replacement contact process. In one such embodiment, the replacement contact process is performed after the replacement gate process to allow high temperature anneal of at least a portion of the permanent gate stack. For example, in a specific such embodiment, an anneal of at least a portion of the permanent gate structures, e.g., after a gate dielectric layer is formed, is performed at a temperature greater than approximately 600 degrees Celsius. The anneal is performed prior to formation of the permanent contacts.

[0039] It is to be appreciated that, in a particular embodiment, nanowires or nanoribbons or fins, or sacrificial intervening layers, may be composed of silicon. As used throughout, a silicon layer may be used to describe a silicon material composed of a very substantial amount of, if not all, silicon. However, it is to be appreciated that, practically, 100% pure Si may be difficult to form and, hence, could include a tiny percentage of carbon, germanium or tin. Such impurities may be included as an unavoidable impurity or component during deposition of Si or may "contaminate" the Si upon diffusion during post deposition processing. As such, embodiments described herein directed to a silicon layer may include a silicon layer that contains a relatively small amount, e.g., "impurity" level, non-Si atoms or species, such as Ge, C or Sn. It is to be appreciated that a silicon layer as described herein may be undoped or may be doped with dopant atoms such as boron, phosphorous or arsenic.

[0040] It is to be appreciated that, in a particular em-

bodiment, nanowires or nanoribbons or fins, or sacrificial intervening layers, may be composed of silicon germanium. As used throughout, a silicon germanium layer may be used to describe a silicon germanium material composed of substantial portions of both silicon and germanium, such as at least 5% of both. In some embodiments, the amount of germanium is greater than the amount of silicon. In particular embodiments, a silicon germanium layer includes approximately 60% germanium and approximately 40% silicon ($\text{Si}_{40}\text{Ge}_{60}$). In other embodiments, the amount of silicon is greater than the amount of germanium. In particular embodiments, a silicon germanium layer includes approximately 30% germanium and approximately 70% silicon ($\text{Si}_{70}\text{Ge}_{30}$). It is to be appreciated that, practically, 100% pure silicon germanium (referred to generally as SiGe) may be difficult to form and, hence, could include a tiny percentage of carbon or tin. Such impurities may be included as an unavoidable impurity or component during deposition of SiGe or may "contaminate" the SiGe upon diffusion during post deposition processing. As such, embodiments described herein directed to a silicon germanium layer may include a silicon germanium layer that contains a relatively small amount, e.g., "impurity" level, non-Ge and non-Si atoms or species, such as carbon or tin. It is to be appreciated that a silicon germanium layer as described herein may be undoped or may be doped with dopant atoms such as boron, phosphorous or arsenic.

[0041] It is to be appreciated that the embodiments described herein can also include other implementations such as nanowires and/or nanoribbons with various widths, thicknesses and/or materials including but not limited to Si and SiGe. For example, group III-V materials may be used.

[0042] Described below are various devices and processing schemes that may be used to fabricate a device that can be integrated with conductive via bars. It is to be appreciated that the exemplary embodiments need not necessarily require all features described, or may include more features than are described. For example, nanowire release processing may be performed through a replacement gate trench. Examples of such release processes are described below. Additionally, in yet another aspect, backend (BE) interconnect scaling can result in lower performance and higher manufacturing cost due to patterning complexity. Embodiments described herein may be implemented to enable front-side and back-side interconnect integration for nanowire transistors.

[0043] One or more embodiments described herein are directed dual epitaxial (EPI) connections for nanowire or nanoribbon transistors using partial source or drain (SD) and asymmetric trench contact (TCN) depth. In an embodiment, an integrated circuit structure is fabricated by forming source-drain openings of nanowire/nanoribbon transistors which are partially filled with SD epitaxy. A remainder of the opening is filled with a conductive material. Deep trench formation on one of the source or

drain side enables direct contact to a back-side interconnect level.

[0044] As an exemplary process flow for fabricating a gate-all-around device of a gate-all-around integrated circuit structure, Figures 7A-7J illustrates cross-sectional views of various operations in a method of fabricating a gate-all-around integrated circuit structure, in accordance with an embodiment of the present disclosure.

[0045] Referring to Figure 7A, a method of fabricating an integrated circuit structure includes forming a starting stack which includes alternating sacrificial layers 704 and nanowires 706 above a fin 702, such as a silicon fin. The nanowires 706 may be referred to as a vertical arrangement of nanowires. A protective cap 708 may be formed above the alternating sacrificial layers 704 and nanowires 706, as is depicted. A relaxed buffer layer 752 and a defect modification layer 750 may be formed beneath the alternating sacrificial layers 704 and nanowires 706, as is also depicted.

[0046] Referring to Figure 7B, a gate stack 710 is formed over the vertical arrangement of horizontal nanowires 706. Portions of the vertical arrangement of horizontal nanowires 706 are then released by removing portions of the sacrificial layers 704 to provide recessed sacrificial layers 704' and cavities 712, as is depicted in Figure 7C.

[0047] It is to be appreciated that the structure of Figure 7C may be fabricated to completion without first performing the deep etch and asymmetric contact processing described below. In either case (e.g., with or without asymmetric contact processing), in an embodiment, a fabrication process involves use of a process scheme that provides a gate-all-around integrated circuit structure having epitaxial nubs, which may be vertically discrete source or drain structures.

[0048] Referring to Figure 7D, upper gate spacers 714 are formed at sidewalls of the gate structure 710. Cavity spacers 716 are formed in the cavities 712 beneath the upper gate spacers 714. A deep trench contact etch is then optionally performed to form trenches 718 and to form recessed nanowires 706'. A patterned relaxed buffer layer 752' and a patterned defect modification layer 750' may also be present, as is depicted.

[0049] A sacrificial material 720 is then formed in the trenches 718, as is depicted in Figure 7E. In other process schemes, an isolated trench bottom or silicon trench bottom may be used.

[0050] Referring to Figure 7F, a first epitaxial source or drain structure (e.g., left-hand features 722) is formed at a first end of the vertical arrangement of horizontal nanowires 706'. A second epitaxial source or drain structure (e.g., right-hand features 722) is formed at a second end of the vertical arrangement of horizontal nanowires 706'. In an embodiment, as depicted, the epitaxial source or drain structures 722 are vertically discrete source or drain structures and may be referred to as epitaxial nubs.

[0051] An inter-layer dielectric (ILD) material 724 is then formed at the sides of the gate electrode 710 and

adjacent the source or drain structures 722, as is depicted in Figure 7G. Referring to Figure 7H, a replacement gate process is used to form a permanent gate dielectric 728 and a permanent gate electrode 726. The ILD material 724 is then removed, as is depicted in Figure 7I. The sacrificial material 720 is then removed from one of the source drain locations (e.g., right-hand side) to form trench 732, but is not removed from the other of the source drain locations to form trench 730.

[0052] Referring to Figure 7J, a first conductive contact structure 734 is formed coupled to the first epitaxial source or drain structure (e.g., left-hand features 722). A second conductive contact structure 736 is formed coupled to the second epitaxial source or drain structure (e.g., right-hand features 722). The second conductive contact structure 736 is formed deeper along the fin 702 than the first conductive contact structure 734. In an embodiment, although not depicted in Figure 7J, the method further includes forming an exposed surface of the second conductive contact structure 736 at a bottom of the fin 702. Conductive contacts may include a contact resistance reducing layer and a primary contact electrode layer, where examples can include Ti, Ni, Co (for the former and W, Ru, Co for the latter.)

[0053] In an embodiment, the second conductive contact structure 736 is deeper along the fin 702 than the first conductive contact structure 734, as is depicted. In one such embodiment, the first conductive contact structure 734 is not along the fin 702, as is depicted. In another such embodiment, not depicted, the first conductive contact structure 734 is partially along the fin 702.

[0054] In an embodiment, the second conductive contact structure 736 is along an entirety of the fin 702. In an embodiment, although not depicted, in the case that the bottom of the fin 702 is exposed by a back-side substrate removal process, the second conductive contact structure 736 has an exposed surface at a bottom of the fin 702.

[0055] In an embodiment, the structure of Figure 7J, or related structures of Figures 7A-7J, can be formed to include a conductive via bars self-aligned to one or more gate end, such as described above in association with Figures 3, 4 and/or 6.

[0056] In another aspect, in order to enable access to both conductive contact structures of a pair of asymmetric source and drain contact structures, integrated circuit structures described herein may be fabricated using a back-side reveal of front-side structures fabrication approach. In some exemplary embodiments, reveal of the back-side of a transistor or other device structure entails wafer-level back-side processing. In contrast to a conventional TSV-type technology, a reveal of the back-side of a transistor as described herein may be performed at the density of the device cells, and even within sub-regions of a device. Furthermore, such a reveal of the back-side of a transistor may be performed to remove substantially all of a donor substrate upon which a device layer was disposed during front-side device processing.

As such, a microns-deep TSV becomes unnecessary with the thickness of semiconductor in the device cells following a reveal of the back-side of a transistor potentially being only tens or hundreds of nanometers.

[0057] Reveal techniques described herein may enable a paradigm shift from "bottom-up" device fabrication to "center-out" fabrication, where the "center" is any layer that is employed in front-side fabrication, revealed from the back-side, and again employed in back-side fabrication. Processing of both a front-side and revealed back-side of a device structure may address many of the challenges associated with fabricating 3D ICs when primarily relying on front-side processing.

[0058] A reveal of the back-side of a transistor approach may be employed for example to remove at least a portion of a carrier layer and intervening layer of a donor-host substrate assembly. The process flow begins with an input of a donor-host substrate assembly. A thickness of a carrier layer in the donor-host substrate is polished (e.g., CMP) and/or etched with a wet or dry (e.g., plasma) etch process. Any grind, polish, and/or wet/dry etch process known to be suitable for the composition of the carrier layer may be employed. For example, where the carrier layer is a group IV semiconductor (e.g., silicon) a CMP slurry known to be suitable for thinning the semiconductor may be employed. Likewise, any wet etchant or plasma etch process known to be suitable for thinning the group IV semiconductor may also be employed.

[0059] In some embodiments, the above is preceded by cleaving the carrier layer along a fracture plane substantially parallel to the intervening layer. The cleaving or fracture process may be utilized to remove a substantial portion of the carrier layer as a bulk mass, reducing the polish or etch time needed to remove the carrier layer. For example, where a carrier layer is 400-900 μm in thickness, 100-700 μm may be cleaved off by practicing any blanket implant known to promote a wafer-level fracture. In some exemplary embodiments, a light element (e.g., H, He, or Li) is implanted to a uniform target depth within the carrier layer where the fracture plane is desired. Following such a cleaving process, the thickness of the carrier layer remaining in the donor-host substrate assembly may then be polished or etched to complete removal. Alternatively, where the carrier layer is not fractured, the grind, polish and/or etch operation may be employed to remove a greater thickness of the carrier layer.

[0060] Next, exposure of an intervening layer is detected. Detection is used to identify a point when the back-side surface of the donor substrate has advanced to nearly the device layer. Any endpoint detection technique known to be suitable for detecting a transition between the materials employed for the carrier layer and the intervening layer may be practiced. In some embodiments, one or more endpoint criteria are based on detecting a change in optical absorbance or emission of the back-side surface of the donor substrate during the polishing or etching performance. In some other embodiments, the endpoint criteria are associated with a change in optical

absorbance or emission of byproducts during the polishing or etching of the donor substrate back-side surface. For example, absorbance or emission wavelengths associated with the carrier layer etch byproducts may change as a function of the different compositions of the carrier layer and intervening layer. In other embodiments, the endpoint criteria are associated with a change in mass of species in byproducts of polishing or etching the back-side surface of the donor substrate. For example, the byproducts of processing may be sampled through a quadrupole mass analyzer and a change in the species mass may be correlated to the different compositions of the carrier layer and intervening layer. In another exemplary embodiment, the endpoint criteria is associated with a change in friction between a back-side surface of the donor substrate and a polishing surface in contact with the back-side surface of the donor substrate.

[0061] Detection of the intervening layer may be enhanced where the removal process is selective to the carrier layer relative to the intervening layer as non-uniformity in the carrier removal process may be mitigated by an etch rate delta between the carrier layer and intervening layer. Detection may even be skipped if the grind, polish and/or etch operation removes the intervening layer at a rate sufficiently below the rate at which the carrier layer is removed. If an endpoint criteria is not employed, a grind, polish and/or etch operation of a predetermined fixed duration may stop on the intervening layer material if the thickness of the intervening layer is sufficient for the selectivity of the etch. In some examples, the carrier etch rate: intervening layer etch rate is 3:1-10:1, or more.

[0062] Upon exposing the intervening layer, at least a portion of the intervening layer may be removed. For example, one or more component layers of the intervening layer may be removed. A thickness of the intervening layer may be removed uniformly by a polish, for example. Alternatively, a thickness of the intervening layer may be removed with a masked or blanket etch process. The process may employ the same polish or etch process as that employed to thin the carrier, or may be a distinct process with distinct process parameters. For example, where the intervening layer provides an etch stop for the carrier removal process, the latter operation may employ a different polish or etch process that favors removal of the intervening layer over removal of the device layer. Where less than a few hundred nanometers of intervening layer thickness is to be removed, the removal process may be relatively slow, optimized for across-wafer uniformity, and more precisely controlled than that employed for removal of the carrier layer. A CMP process employed may, for example employ a slurry that offers very high selectivity (e.g., 100:1-300:1, or more) between semiconductor (e.g., silicon) and dielectric material (e.g., SiO) surrounding the device layer and embedded within the intervening layer, for example, as electrical isolation between adjacent device regions.

[0063] For embodiments where the device layer is revealed through complete removal of the intervening layer

er, back-side processing may commence on an exposed back-side of the device layer or specific device regions there in. In some embodiments, the back-side device layer processing includes a further polish or wet/dry etch through a thickness of the device layer disposed between the intervening layer and a device region previously fabricated in the device layer, such as a source or drain region.

[0064] In some embodiments where the carrier layer, intervening layer, or device layer back-side is recessed with a wet and/or plasma etch, such an etch may be a patterned etch or a materially selective etch that imparts significant non-planarity or topography into the device layer back-side surface. As described further below, the patterning may be within a device cell (i.e., "intra-cell" patterning) or may be across device cells (i.e., "inter-cell" patterning). In some patterned etch embodiments, at least a partial thickness of the intervening layer is employed as a hard mask for back-side device layer patterning. Hence, a masked etch process may preface a correspondingly masked device layer etch.

[0065] The above described processing scheme may result in a donor-host substrate assembly that includes IC devices that have a back-side of an intervening layer, a back-side of the device layer, and/or back-side of one or more semiconductor regions within the device layer, and/or front-side metallization revealed. Additional back-side processing of any of these revealed regions may then be performed during downstream processing.

[0066] It is to be appreciated that the structures resulting from the above exemplary processing schemes may be used in a same or similar form for subsequent processing operations to complete device fabrication, such as PMOS and/or NMOS device fabrication. As an example of a completed device, Figure 8 illustrates a cross-sectional view of a non-planar integrated circuit structure as taken along a gate line, in accordance with an embodiment of the present disclosure.

[0067] Referring to Figure 8, a semiconductor structure or device 800 includes a non-planar active region (e.g., a fin structure including protruding fin portion 804 and sub-fin region 805) within a trench isolation region 806. In an embodiment, instead of a solid fin, the non-planar active region is separated into nanowires (such as nanowires 804A and 804B) above sub-fin region 805, as is represented by the dashed lines. In either case, for ease of description for non-planar integrated circuit structure 800, a non-planar active region 804 is referenced below as a protruding fin portion. In an embodiment, the sub-fin region 805 also includes a relaxed buffer layer 842 and a defect modification layer 840, as is depicted.

[0068] A gate line 808 is disposed over the protruding portions 804 of the non-planar active region (including, if applicable, surrounding nanowires 804A and 804B), as well as over a portion of the trench isolation region 806. As shown, gate line 808 includes a gate electrode 850 and a gate dielectric layer 852. In one embodiment, gate line 808 may also include a dielectric cap layer 854. A

gate contact 814, and overlying gate contact via 816 are also seen from this perspective, along with an overlying metal interconnect 860, all of which are disposed in inter-layer dielectric stacks or layers 870. Also seen from the perspective of Figure 8, the gate contact 814 is, in one embodiment, disposed over trench isolation region 806, but not over the non-planar active regions. In another embodiment, the gate contact 814 is over the non-planar active regions.

[0069] In an embodiment, the semiconductor structure or device 800 is a non-planar device such as, but not limited to, a fin-FET device, a tri-gate device, a nanoribbon device, or a nanowire device. In such an embodiment, a corresponding semiconducting channel region is composed of or is formed in a three-dimensional body. In one such embodiment, the gate electrode stacks of gate lines 808 surround at least a top surface and a pair of sidewalls of the three-dimensional body.

[0070] As is also depicted in Figure 8, in an embodiment, an interface 880 exists between a protruding fin portion 804 and sub-fin region 805. The interface 880 can be a transition region between a doped sub-fin region 805 and a lightly or undoped upper fin portion 804. In one such embodiment, each fin is approximately 10 nanometers wide or less, and sub-fin dopants are optionally supplied from an adjacent solid state doping layer at the sub-fin location. In a particular such embodiment, each fin is less than 10 nanometers wide.

[0071] Although not depicted in Figure 8, it is to be appreciated that source or drain regions of or adjacent to the protruding fin portions 804 are on either side of the gate line 808, i.e., into and out of the page. In one embodiment, the material of the protruding fin portions 804 in the source or drain locations is removed and replaced with another semiconductor material, e.g., by epitaxial deposition to form epitaxial source or drain structures. The source or drain regions may extend below the height of dielectric layer of trench isolation region 806, i.e., into the sub-fin region 805. In accordance with an embodiment of the present disclosure, the more heavily doped sub-fin regions, i.e., the doped portions of the fins below interface 880, inhibits source to drain leakage through this portion of the bulk semiconductor fins. In an embodiment, the source and drain regions have associated asymmetric source and drain contact structures, as described above in association with Figure 7J.

[0072] With reference again to Figure 8, in an embodiment, fins 804/805 (and, possibly nanowires 804A and 804B) are composed of a crystalline silicon germanium layer which may be doped with a charge carrier, such as but not limited to phosphorus, arsenic, boron, gallium or a combination thereof.

[0073] In an embodiment, trench isolation region 806, and trench isolation regions (trench isolation structures or trench isolation layers) described throughout, may be composed of a material suitable to ultimately electrically isolate, or contribute to the isolation of, portions of a permanent gate structure from an underlying bulk substrate

or isolate active regions formed within an underlying bulk substrate, such as isolating fin active regions. For example, in one embodiment, trench isolation region 806 is composed of a dielectric material such as, but not limited to, silicon dioxide, silicon oxy-nitride, silicon nitride, or carbon-doped silicon nitride.

[0074] Gate line 808 may be composed of a gate electrode stack which includes a gate dielectric layer 852 and a gate electrode layer 850. In an embodiment, the gate electrode of the gate electrode stack is composed of a metal gate and the gate dielectric layer is composed of a high-k material. For example, in one embodiment, the gate dielectric layer 852 is composed of a material such as, but not limited to, hafnium oxide, hafnium oxy-nitride, hafnium silicate, lanthanum oxide, zirconium oxide, zirconium silicate, tantalum oxide, barium strontium titanate, barium titanate, strontium titanate, yttrium oxide, aluminum oxide, lead scandium tantalum oxide, lead zinc niobate, or a combination thereof. Furthermore, a portion of gate dielectric layer 852 may include a layer of native oxide formed from the top few layers of the substrate fin 804. In an embodiment, the gate dielectric layer 852 is composed of a top high-k portion and a lower portion composed of an oxide of a semiconductor material. In one embodiment, the gate dielectric layer 852 is composed of a top portion of hafnium oxide and a bottom portion of silicon dioxide or silicon oxy-nitride. In some implementations, a portion of the gate dielectric is a "U"-shaped structure that includes a bottom portion substantially parallel to the surface of the substrate and two sidewall portions that are substantially perpendicular to the top surface of the substrate.

[0075] In one embodiment, the gate electrode layer 850 is composed of a metal layer such as, but not limited to, metal nitrides, metal carbides, metal silicides, metal aluminides, hafnium, zirconium, titanium, tantalum, aluminum, ruthenium, palladium, platinum, cobalt, nickel or conductive metal oxides. In a specific embodiment, the gate electrode layer 850 is composed of a non-workfunction-setting fill material formed above a metal workfunction-setting layer. The gate electrode layer 850 may consist of a P-type workfunction metal or an N-type workfunction metal, depending on whether the transistor is to be a PMOS or an NMOS transistor. In some implementations, the gate electrode layer 850 may consist of a stack of two or more metal layers, where one or more metal layers are workfunction metal layers and at least one metal layer is a conductive fill layer. For a PMOS transistor, metals that may be used for the gate electrode include, but are not limited to, ruthenium, palladium, platinum, cobalt, nickel, tungsten and conductive metal oxides, e.g., ruthenium oxide. A P-type metal layer will enable the formation of a PMOS gate electrode with a workfunction that is between about 4.9 eV and about 5.2 eV. For an NMOS transistor, metals that may be used for the gate electrode include, but are not limited to, hafnium, zirconium, titanium, tantalum, aluminum, alloys of these metals, and carbides of these metals such as hafnium

carbide, zirconium carbide, titanium carbide, tantalum carbide, and aluminum carbide. An N-type metal layer will enable the formation of an NMOS gate electrode with a workfunction that is between about 3.9 eV and about 4.2 eV. In some implementations, the gate electrode may consist of a "U"-shaped structure that includes a bottom portion substantially parallel to the surface of the substrate and two sidewall portions that are substantially perpendicular to the top surface of the substrate. In another implementation, at least one of the metal layers that form the gate electrode may simply be a planar layer that is substantially parallel to the top surface of the substrate and does not include sidewall portions substantially perpendicular to the top surface of the substrate. In further implementations of the disclosure, the gate electrode may consist of a combination of U-shaped structures and planar, non-U-shaped structures. For example, the gate electrode may consist of one or more U-shaped metal layers formed atop one or more planar, non-U-shaped layers.

[0076] Spacers associated with the gate electrode stacks may be composed of a material suitable to ultimately electrically isolate, or contribute to the isolation of, a permanent gate structure from adjacent conductive contacts, such as self-aligned contacts. For example, in one embodiment, the spacers are composed of a dielectric material such as, but not limited to, silicon dioxide, silicon oxy-nitride, silicon nitride, or carbon-doped silicon nitride.

[0077] Gate contact 814 and overlying gate contact via 816 may be composed of a conductive material. In an embodiment, one or more of the contacts or vias are composed of a metal species. The metal species may be a pure metal, such as tungsten, nickel, or cobalt, or may be an alloy such as a metal-metal alloy or a metal-semiconductor alloy (e.g., such as a silicide material).

[0078] In an embodiment (although not shown), a contact pattern which is essentially perfectly aligned to an existing gate pattern 808 is formed while eliminating the use of a lithographic step with exceedingly tight registration budget. In an embodiment, the contact pattern is a vertically symmetric contact pattern, or an asymmetric contact pattern such as described in association with Figure 7J. In other embodiments, all contacts are front-side connected and are not asymmetric. In one such embodiment, the self-aligned approach enables the use of intrinsically highly selective wet etching (e.g., versus conventionally implemented dry or plasma etching) to generate contact openings. In an embodiment, a contact pattern is formed by utilizing an existing gate pattern in combination with a contact plug lithography operation. In one such embodiment, the approach enables elimination of the need for an otherwise critical lithography operation to generate a contact pattern, as used in conventional approaches. In an embodiment, a trench contact grid is not separately patterned, but is rather formed between poly (gate) lines. For example, in one such embodiment, a trench contact grid is formed subsequent to gate grating

patterning but prior to gate grating cuts.

[0079] In an embodiment, providing structure 800 involves fabrication of the gate stack structure 808 by a replacement gate process. In such a scheme, dummy gate material such as polysilicon or silicon nitride pillar material, may be removed and replaced with permanent gate electrode material. In one such embodiment, a permanent gate dielectric layer is also formed in this process, as opposed to being carried through from earlier processing. In an embodiment, dummy gates are removed by a dry etch or wet etch process. In one embodiment, dummy gates are composed of polycrystalline silicon or amorphous silicon and are removed with a dry etch process including use of SF₆. In another embodiment, dummy gates are composed of polycrystalline silicon or amorphous silicon and are removed with a wet etch process including use of aqueous NH₄OH or tetramethylammonium hydroxide. In one embodiment, dummy gates are composed of silicon nitride and are removed with a wet etch including aqueous phosphoric acid.

[0080] Referring again to Figure 8, the arrangement of semiconductor structure or device 800 places the gate contact over isolation regions. Such an arrangement may be viewed as inefficient use of layout space. In another embodiment, however, a semiconductor device has contact structures that contact portions of a gate electrode formed over an active region, e.g., over a fin 805, and in a same layer as a trench contact via.

[0081] In an embodiment, the structure of Figure 8 can be formed to include a conductive via bars self-aligned to one or more gate end, such as described above in association with Figures 3, 4 and/or 6.

[0082] It is to be appreciated that not all aspects of the processes described above need be practiced to fall within the spirit and scope of embodiments of the present disclosure. Also, the processes described herein may be used to fabricate one or a plurality of semiconductor devices. The semiconductor devices may be transistors or like devices. For example, in an embodiment, the semiconductor devices are a metal-oxide semiconductor (MOS) transistors for logic or memory, or are bipolar transistors. Also, in an embodiment, the semiconductor devices have a three-dimensional architecture, such as a nanowire device, a nanoribbon device, a tri-gate device, an independently accessed double gate device, or a FIN-FET. One or more embodiments may be particularly useful for fabricating semiconductor devices at a sub-10 nanometer (10 nm) technology node.

[0083] In an embodiment, as used throughout the present description, interlayer dielectric (ILD) material is composed of or includes a layer of a dielectric or insulating material. Examples of suitable dielectric materials include, but are not limited to, oxides of silicon (e.g., silicon dioxide (SiO₂)), doped oxides of silicon, fluorinated oxides of silicon, carbon doped oxides of silicon, various low-k dielectric materials known in the arts, and combinations thereof. The interlayer dielectric material may be formed by conventional techniques, such as, for exam-

ple, chemical vapor deposition (CVD), physical vapor deposition (PVD), or by other deposition methods.

[0084] In an embodiment, as is also used throughout the present description, metal lines or interconnect line material (and via material) is composed of one or more metal or other conductive structures. A common example is the use of copper lines and structures that may or may not include barrier layers between the copper and surrounding ILD material. As used herein, the term metal includes alloys, stacks, and other combinations of multiple metals. For example, the metal interconnect lines may include barrier layers (e.g., layers including one or more of Ta, TaN, Ti or TiN), stacks of different metals or alloys, etc. Thus, the interconnect lines may be a single material layer, or may be formed from several layers, including conductive liner layers and fill layers. Any suitable deposition process, such as electroplating, chemical vapor deposition or physical vapor deposition, may be used to form interconnect lines. In an embodiment, the interconnect lines are composed of a conductive material such as, but not limited to, Cu, Al, Ti, Zr, Hf, V, Ru, Co, Ni, Pd, Pt, W, Ag, Au or alloys thereof. The interconnect lines are also sometimes referred to in the art as traces, wires, lines, metal, or simply interconnect.

[0085] In an embodiment, as is also used throughout the present description, hardmask materials, capping layers, or plugs are composed of dielectric materials different from the interlayer dielectric material. In one embodiment, different hardmask, capping or plug materials may be used in different regions so as to provide different growth or etch selectivity to each other and to the underlying dielectric and metal layers. In some embodiments, a hardmask layer, capping or plug layer includes a layer of a nitride of silicon (e.g., silicon nitride) or a layer of an oxide of silicon, or both, or a combination thereof. Other suitable materials may include carbon-based materials. Other hardmask, capping or plug layers known in the arts may be used depending upon the particular implementation. The hardmask, capping or plug layers maybe formed by CVD, PVD, or by other deposition methods.

[0086] In an embodiment, as is also used throughout the present description, lithographic operations are performed using 193nm immersion lithography (i193), EUV and/or EBDW lithography, or the like. A positive tone or a negative tone resist may be used. In one embodiment, a lithographic mask is a trilayer mask composed of a topographic masking portion, an anti-reflective coating (ARC) layer, and a photoresist layer. In a particular such embodiment, the topographic masking portion is a carbon hardmask (CHM) layer and the anti-reflective coating layer is a silicon ARC layer.

[0087] In another aspect, one or more embodiments are directed to neighboring semiconductor structures or devices separated by self-aligned gate endcap (SAGE) structures. Particular embodiments may be directed to integration of multiple width (multi-Wsi) nanowires and nanoribbons in a SAGE architecture and separated by a SAGE wall. In an embodiment, nanowires/nanoribbons

are integrated with multiple Wsi in a SAGE architecture portion of a front-end process flow. Such a process flow may involve integration of nanowires and nanoribbons of different Wsi to provide robust functionality of next generation transistors with low power and high performance. Associated epitaxial source or drain regions may be embedded (e.g., portions of nanowires removed and then source or drain (S/D) growth is performed).

[0088] To provide further context, advantages of a self-aligned gate endcap (SAGE) architecture may include the enabling of higher layout density and, in particular, scaling of diffusion to diffusion spacing. To provide illustrative comparison, Figure 9 illustrates cross-sectional views taken through nanowires and fins for a non-endcap architecture (left-hand side (a)) versus a self-aligned gate endcap (SAGE) architecture (right-hand side (b)), in accordance with an embodiment of the present disclosure.

[0089] Referring to the left-hand side (a) of Figure 9, an integrated circuit structure 900 includes a substrate 902 having fins 904 protruding therefrom by an amount 906 above an isolation structure 908 laterally surrounding lower portions of the fins 904. Upper portions of the fins may include a relaxed buffer layer 922 and a defect modification layer 920, as is depicted. Corresponding nanowires 905 are over the fins 904. A gate structure may be formed over the integrated circuit structure 900 to fabricate a device. However, breaks in such a gate structure may be accommodated for by increasing the spacing between fin 904/nanowire 905 pairs.

[0090] By contrast, referring to the right-hand side (b) of Figure 9, an integrated circuit structure 950 includes a substrate 952 having fins 954 protruding therefrom by an amount 956 above an isolation structure 958 laterally surrounding lower portions of the fins 954. Upper portions of the fins may include a relaxed buffer layer 972 and a defect modification layer 970, as is depicted. Corresponding nanowires 955 are over the fins 954. Isolating SAGE walls 960 (which may include a hardmask thereon, as depicted) are included within the isolation structure 952 and between adjacent fin 954/nanowire 955 pairs. The distance between an isolating SAGE wall 960 and a nearest fin 954/nanowire 955 pair defines the gate endcap spacing 962. A gate structure may be formed over the integrated circuit structure 900, between insulating SAGE walls to fabricate a device. Breaks in such a gate structure are imposed by the isolating SAGE walls. Since the isolating SAGE walls 960 are self-aligned, restrictions from conventional approaches can be minimized to enable more aggressive diffusion to diffusion spacing. Furthermore, since gate structures include breaks at all locations, individual gate structure portions may be layer connected by local interconnects formed over the insulating SAGE walls 960. In an embodiment, as depicted, the SAGE walls 960 each include a lower dielectric portion and a dielectric cap on the lower dielectric portion. In accordance with an embodiment of the present disclosure, a fabrication process for structures associated with Figure 9 involves use of a process scheme that provides

a gate-all-around integrated circuit structure having epitaxial source or drain structures.

[0091] In an embodiment, the structure of part (a) of Figure 9 can be formed to include a conductive via bars self-aligned to one or more gate end, such as described above in association with Figures 3, 4 and/or 6. In an embodiment, the structure of part (b) of Figure 9 can be formed to include a conductive via bars self-aligned to one or more gate end, such as described above in association with Figures 3, 4 and/or 6.

[0092] A self-aligned gate endcap (SAGE) processing scheme involves the formation of gate/trench contact endcaps self-aligned to fins without requiring an extra length to account for mask mis-registration. Thus, embodiments may be implemented to enable shrinking of transistor layout area. Embodiments described herein may involve the fabrication of gate endcap isolation structures, which may also be referred to as gate walls, isolation gate walls or self-aligned gate endcap (SAGE) walls.

[0093] In an exemplary processing scheme for structures having SAGE walls separating neighboring devices, Figure 10 illustrate cross-sectional views representing various operations in a method of fabricating a self-aligned gate endcap (SAGE) structure with gate-all-around devices, in accordance with an embodiment of the present disclosure.

[0094] Referring to part (a) of Figure 10, a starting structure includes a nanowire patterning stack 1004 above a substrate 1002. A lithographic patterning stack 1006 is formed above the nanowire patterning stack 1004. The nanowire patterning stack 1004 includes alternating sacrificial layers 1010 and nanowire layers 1012, which may be above a relaxed buffer layer 1082 and a defect modification layer 1080, as is depicted. A protective mask 1014 is between the nanowire patterning stack 1004 and the lithographic patterning stack 1006. In one embodiment, the lithographic patterning stack 1006 is trilayer mask composed of a topographic masking portion 1020, an anti-reflective coating (ARC) layer 1022, and a photoresist layer 1024. In a particular such embodiment, the topographic masking portion 1020 is a carbon hardmask (CHM) layer and the anti-reflective coating layer 1022 is a silicon ARC layer.

[0095] Referring to part (b) of Figure 10, the stack of part (a) is lithographically patterned and then etched to provide an etched structure including a patterned substrate 1002 and trenches 1030.

[0096] Referring to part (c) of Figure 10, the structure of part (b) has an isolation layer 1040 and a SAGE material 1042 formed in trenches 1030. The structure is then planarized to leave patterned topographic masking layer 1020' as an exposed upper layer.

[0097] Referring to part (d) of Figure 10, the isolation layer 1040 is recessed below an upper surface of the patterned substrate 1002, e.g., to define a protruding fin portion and to provide a trench isolation structure 1041 beneath SAGE walls 1042.

[0098] Referring to part (e) of Figure 10, the sacrificial layers 1010 are removed at least in the channel region to release nanowires 1012A and 1012B. Subsequent to the formation of the structure of part (e) of Figure 10, a gate stacks may be formed around nanowires 1012B or 1012A, over protruding fins of substrate 1002, and between SAGE walls 1042. In one embodiment, prior to formation of the gate stacks, the remaining portion of protective mask 1014 is removed. In another embodiment, the remaining portion of protective mask 1014 is retained as an insulating fin hat as an artifact of the processing scheme.

[0099] Referring again to part (e) of Figure 10, it is to be appreciated that a channel view is depicted, with source or drain regions being locating into and out of the page. In an embodiment, the channel region including nanowires 1012B has a width less than the channel region including nanowires 1012A. Thus, in an embodiment, an integrated circuit structure includes multiple width (multi-Wsi) nanowires. Although structures of 1012B and 1012A may be differentiated as nanowires and nanoribbons, respectively, both such structures are typically referred to herein as nanowires. It is also to be appreciated that reference to or depiction of a fin/nanowire pair throughout may refer to a structure including a fin and one or more overlying nanowires (e.g., two overlying nanowires are shown in Figure 10). In accordance with an embodiment of the present disclosure, a fabrication process for structures associated with Figure 10 involves use of a process scheme that provides a gate-all-around integrated circuit structure having epitaxial source or drain structures.

[0100] In an embodiment, the structure of part (e) Figure 10 can be formed to include a conductive via bars self-aligned to one or more gate end, such as described above in association with Figures 3, 4 and/or 6.

[0101] In an embodiment, as described throughout, self-aligned gate endcap (SAGE) isolation structures may be composed of a material or materials suitable to ultimately electrically isolate, or contribute to the isolation of, portions of permanent gate structures from one another. Exemplary materials or material combinations include a single material structure such as silicon dioxide, silicon oxy-nitride, silicon nitride, or carbon-doped silicon nitride. Other exemplary materials or material combinations include a multi-layer stack having lower portion silicon dioxide, silicon oxy-nitride, silicon nitride, or carbon-doped silicon nitride and an upper portion higher dielectric constant material such as hafnium oxide.

[0102] To highlight an exemplary integrated circuit structure having three vertically arranged nanowires, Figure 11A illustrates a three-dimensional cross-sectional view of a nanowire-based integrated circuit structure, in accordance with an embodiment of the present disclosure. Figure 11B illustrates a cross-sectional source or drain view of the nanowire-based integrated circuit structure of Figure 11A, as taken along the a-a' axis. Figure 11C illustrates a cross-sectional channel view of the na-

nowire-based integrated circuit structure of Figure 11A, as taken along the b-b' axis.

[0103] Referring to Figure 11A, an integrated circuit structure 1100 includes one or more vertically stacked nanowires (1104 set) above a substrate 1102. In an embodiment, as depicted, a relaxed buffer layer 1102C, a defect modification layer 1102B, and a lower substrate portion 1102A are included in substrate 1102, as is depicted. An optional fin below the bottommost nanowire and formed from the substrate 1102 is not depicted for the sake of emphasizing the nanowire portion for illustrative purposes. Embodiments herein are targeted at both single wire devices and multiple wire devices. As an example, a three nanowire-based devices having nanowires 1104A, 1104B and 1104C is shown for illustrative purposes. For convenience of description, nanowire 1104A is used as an example where description is focused on one of the nanowires. It is to be appreciated that where attributes of one nanowire are described, embodiments based on a plurality of nanowires may have the same or essentially the same attributes for each of the nanowires.

[0104] Each of the nanowires 1104 includes a channel region 1106 in the nanowire. The channel region 1106 has a length (L). Referring to Figure 11C, the channel region also has a perimeter (Pc) orthogonal to the length (L). Referring to both Figures 11A and 11C, a gate electrode stack 1108 surrounds the entire perimeter (Pc) of each of the channel regions 1106. The gate electrode stack 1108 includes a gate electrode along with a gate dielectric layer between the channel region 1106 and the gate electrode (not shown). In an embodiment, the channel region is discrete in that it is completely surrounded by the gate electrode stack 1108 without any intervening material such as underlying substrate material or overlying channel fabrication materials. Accordingly, in embodiments having a plurality of nanowires 1104, the channel regions 1106 of the nanowires are also discrete relative to one another.

[0105] Referring to both Figures 11A and 11B, integrated circuit structure 1100 includes a pair of non-discrete source or drain regions 1110/1112. The pair of non-discrete source or drain regions 1110/1112 is on either side of the channel regions 1106 of the plurality of vertically stacked nanowires 1104. Furthermore, the pair of non-discrete source or drain regions 1110/1112 is adjoining for the channel regions 1106 of the plurality of vertically stacked nanowires 1104. In one such embodiment, not depicted, the pair of non-discrete source or drain regions 1110/1112 is directly vertically adjoining for the channel regions 1106 in that epitaxial growth is on and between nanowire portions extending beyond the channel regions 1106, where nanowire ends are shown within the source or drain structures. In another embodiment, as depicted in Figure 11A, the pair of non-discrete source or drain regions 1110/1112 is indirectly vertically adjoining for the channel regions 1106 in that they are formed at the ends of the nanowires and not between

the nanowires.

[0106] In an embodiment, as depicted, the source or drain regions 1110/1112 are non-discrete in that there are not individual and discrete source or drain regions for each channel region 1106 of a nanowire 1104. Accordingly, in embodiments having a plurality of nanowires 1104, the source or drain regions 1110/1112 of the nanowires are global or unified source or drain regions as opposed to discrete for each nanowire. That is, the non-discrete source or drain regions 1110/1112 are global in the sense that a single unified feature is used as a source or drain region for a plurality (in this case, 3) of nanowires 1104 and, more particularly, for more than one discrete channel region 1106. In one embodiment, from a cross-sectional perspective orthogonal to the length of the discrete channel regions 1106, each of the pair of non-discrete source or drain regions 1110/1112 is approximately rectangular in shape with a bottom tapered portion and a top vertex portion, as depicted in Figure 11B. In other embodiments, however, the source or drain regions 1110/1112 of the nanowires are relatively larger yet discrete non-vertically merged epitaxial structures such as nubs described in association with Figures 7A-7J.

[0107] In accordance with an embodiment of the present disclosure, and as depicted in Figures 11A and 11B, integrated circuit structure 1100 further includes a pair of contacts 1114, each contact 1114 on one of the pair of non-discrete source or drain regions 1110/1112. In one such embodiment, in a vertical sense, each contact 1114 completely surrounds the respective non-discrete source or drain region 1110/1112. In another aspect, the entire perimeter of the non-discrete source or drain regions 1110/1112 may not be accessible for contact with contacts 1114, and the contact 1114 thus only partially surrounds the non-discrete source or drain regions 1110/1112, as depicted in Figure 11B. In a contrasting embodiment, not depicted, the entire perimeter of the non-discrete source or drain regions 1110/1112, as taken along the a-a' axis, is surrounded by the contacts 1114.

[0108] Referring again to Figure 11A, in an embodiment, integrated circuit structure 1100 further includes a pair of spacers 1116. As is depicted, outer portions of the pair of spacers 1116 may overlap portions of the non-discrete source or drain regions 1110/1112, providing for "embedded" portions of the non-discrete source or drain regions 1110/1112 beneath the pair of spacers 1116. As is also depicted, the embedded portions of the non-discrete source or drain regions 1110/1112 may not extend beneath the entirety of the pair of spacers 1116.

[0109] Substrate 1102 may be composed of a material suitable for integrated circuit structure fabrication. In one embodiment, substrate 1102 includes a lower bulk substrate composed of a single crystal of a material which may include, but is not limited to, silicon, germanium, silicon-germanium, germanium-tin, silicon-germanium-tin, or a group III-V compound semiconductor material. An upper insulator layer composed of a material which

may include, but is not limited to, silicon dioxide, silicon nitride or silicon oxy-nitride is on the lower bulk substrate. Thus, the structure 1100 may be fabricated from a starting semiconductor-on-insulator substrate. Alternatively, the structure 1100 is formed directly from a bulk substrate and local oxidation is used to form electrically insulative portions in place of the above described upper insulator layer. In another alternative embodiment, the structure 1100 is formed directly from a bulk substrate and doping is used to form electrically isolated active regions, such as nanowires, thereon. In one such embodiment, the first nanowire (i.e., proximate the substrate) is in the form of an omega-FET type structure.

[0110] In an embodiment, the nanowires 1104 may be sized as wires or ribbons, as described below, and may have squared-off or rounder corners. In an embodiment, the nanowires 1104 are composed of a material such as, but not limited to, silicon, germanium, or a combination thereof. In one such embodiment, the nanowires are single-crystalline. For example, for a silicon nanowire 1104, a single-crystalline nanowire may be based from a (100) global orientation, e.g., with a <100> plane in the z-direction. As described below, other orientations may also be considered. In an embodiment, the dimensions of the nanowires 1104, from a cross-sectional perspective, are on the nano-scale. For example, in a specific embodiment, the smallest dimension of the nanowires 1104 is less than approximately 20 nanometers. In an embodiment, the nanowires 1104 are composed of a strained material, particularly in the channel regions 1106.

[0111] Referring to Figures 11C, in an embodiment, each of the channel regions 1106 has a width (Wc) and a height (Hc), the width (Wc) approximately the same as the height (Hc). That is, in both cases, the channel regions 1106 are square-like or, if corner-rounded, circle-like in cross-section profile. In another aspect, the width and height of the channel region need not be the same, such as the case for nanoribbons as described throughout.

[0112] In an embodiment, as described throughout, an integrated circuit structure includes non-planar devices such as, but not limited to, a finFET or a tri-gate device with corresponding one or more overlying nanowire structures. In such an embodiment, a corresponding semiconducting channel region is composed of or is formed in a three-dimensional body with one or more discrete nanowire channel portions overlying the three-dimensional body. In one such embodiment, the gate structures surround at least a top surface and a pair of sidewalls of the three-dimensional body, and further surrounds each of the one or more discrete nanowire channel portions.

[0113] In an embodiment, the structure of Figures 11A-11C can be formed to include a conductive via bars self-aligned to one or more gate end, such as described above in association with Figures 3, 4 and/or 6.

[0114] In an embodiment, as described throughout, an underlying substrate may be composed of a semicon-

ductor material that can withstand a manufacturing process and in which charge can migrate. In an embodiment, the substrate is a bulk substrate composed of a crystalline silicon, silicon/germanium or germanium layer doped with a charge carrier, such as but not limited to phosphorus, arsenic, boron, gallium or a combination thereof, to form an active region. In one embodiment, the concentration of silicon atoms in a bulk substrate is greater than 97%. In another embodiment, a bulk substrate is composed of an epitaxial layer grown atop a distinct crystalline substrate, e.g. a silicon epitaxial layer grown atop a boron-doped bulk silicon mono-crystalline substrate. A bulk substrate may alternatively be composed of a group III-V material. In an embodiment, a bulk substrate is composed of a group III-V material such as, but not limited to, gallium nitride, gallium phosphide, gallium arsenide, indium phosphide, indium antimonide, indium gallium arsenide, aluminum gallium arsenide, indium gallium phosphide, or a combination thereof. In one embodiment, a bulk substrate is composed of a group III-V material and the charge-carrier dopant impurity atoms are ones such as, but not limited to, carbon, silicon, germanium, oxygen, sulfur, selenium or tellurium.

[0115] Embodiments disclosed herein may be used to manufacture a wide variety of different types of integrated circuits and/or microelectronic devices. Examples of such integrated circuits include, but are not limited to, processors, chipset components, graphics processors, digital signal processors, micro-controllers, and the like. In other embodiments, semiconductor memory may be manufactured. Moreover, the integrated circuits or other microelectronic devices may be used in a wide variety of electronic devices known in the arts. For example, in computer systems (e.g., desktop, laptop, server), cellular phones, personal electronics, etc. The integrated circuits may be coupled with a bus and other components in the systems. For example, a processor may be coupled by one or more buses to a memory, a chipset, etc. Each of the processor, the memory, and the chipset, may potentially be manufactured using the approaches disclosed herein.

[0116] Figure 12 illustrates a computing device 1200 in accordance with one implementation of an embodiment of the present disclosure. The computing device 1200 houses a board 1202. The board 1202 may include a number of components, including but not limited to a processor 1204 and at least one communication chip 1206. The processor 1204 is physically and electrically coupled to the board 1202. In some implementations the at least one communication chip 1206 is also physically and electrically coupled to the board 1202. In further implementations, the communication chip 1206 is part of the processor 1204.

[0117] Depending on its applications, computing device 1200 may include other components that may or may not be physically and electrically coupled to the board 1202. These other components include, but are not limited to, volatile memory (e.g., DRAM), non-volatile

memory (e.g., ROM), flash memory, a graphics processor, a digital signal processor, a crypto processor, a chipset, an antenna, a display, a touchscreen display, a touchscreen controller, a battery, an audio codec, a video codec, a power amplifier, a global positioning system (GPS) device, a compass, an accelerometer, a gyroscope, a speaker, a camera, and a mass storage device (such as hard disk drive, compact disk (CD), digital versatile disk (DVD), and so forth).

[0118] The communication chip 1206 enables wireless communications for the transfer of data to and from the computing device 1200. The term "wireless" and its derivatives may be used to describe circuits, devices, systems, methods, techniques, communications channels, etc., that may communicate data through the use of modulated electromagnetic radiation through a non-solid medium. The term does not imply that the associated devices do not contain any wires, although in some embodiments they might not. The communication chip 1206 may implement any of a number of wireless standards or protocols, including but not limited to Wi-Fi (IEEE 802.11 family), WiMAX (IEEE 802.16 family), IEEE 802.20, long term evolution (LTE), Ev-DO, HSPA+, HSDPA+, HSUPA+, EDGE, GSM, GPRS, CDMA, TDMA, DECT, Bluetooth, derivatives thereof, as well as any other wireless protocols that are designated as 3G, 4G, 5G, and beyond. The computing device 1200 may include a plurality of communication chips 1206. For instance, a first communication chip 1206 may be dedicated to shorter range wireless communications such as Wi-Fi and Bluetooth and a second communication chip 1206 may be dedicated to longer range wireless communications such as GPS, EDGE, GPRS, CDMA, WiMAX, LTE, Ev-DO, and others.

[0119] The processor 1204 of the computing device 1200 includes an integrated circuit die packaged within the processor 1204. The integrated circuit die of the processor 1204 may include one or more structures, such as integrated circuit structures having conductive via bars self-aligned to gate ends, built in accordance with implementations of embodiments of the present disclosure. The term "processor" may refer to any device or portion of a device that processes electronic data from registers and/or memory to transform that electronic data into other electronic data that may be stored in registers and/or memory.

[0120] The communication chip 1206 also includes an integrated circuit die packaged within the communication chip 1206. The integrated circuit die of the communication chip 1206 may include one or more structures, such as integrated circuit structures having conductive via bars self-aligned to gate ends, built in accordance with implementations of embodiments of the present disclosure.

[0121] In further implementations, another component housed within the computing device 1200 may contain an integrated circuit die that includes one or structures, such as integrated circuit structures having conductive via bars self-aligned to gate ends, built in accordance

with implementations of embodiments of the present disclosure.

[0122] In various implementations, the computing device 1200 may be a laptop, a netbook, a notebook, an ultrabook, a smartphone, a tablet, a personal digital assistant (PDA), an ultra mobile PC, a mobile phone, a desktop computer, a server, a printer, a scanner, a monitor, a set-top box, an entertainment control unit, a digital camera, a portable music player, or a digital video recorder. In further implementations, the computing device 1200 may be any other electronic device that processes data.

[0123] Figure 13 illustrates an interposer 1300 that includes one or more embodiments of the present disclosure. The interposer 1300 is an intervening substrate used to bridge a first substrate 1302 to a second substrate 1304. The first substrate 1302 may be, for instance, an integrated circuit die. The second substrate 1304 may be, for instance, a memory module, a computer motherboard, or another integrated circuit die. Generally, the purpose of an interposer 1300 is to spread a connection to a wider pitch or to reroute a connection to a different connection. For example, an interposer 1300 may couple an integrated circuit die to a ball grid array (BGA) 1306 that can subsequently be coupled to the second substrate 1304. In some embodiments, the first and second substrates 1302/1304 are attached to opposing sides of the interposer 1300. In other embodiments, the first and second substrates 1302/1304 are attached to the same side of the interposer 1300. And in further embodiments, three or more substrates are interconnected by way of the interposer 1300.

[0124] The interposer 1300 may be formed of an epoxy resin, a fiberglass-reinforced epoxy resin, a ceramic material, or a polymer material such as polyimide. In further implementations, the interposer 1300 may be formed of alternate rigid or flexible materials that may include the same materials described above for use in a semiconductor substrate, such as silicon, germanium, and other group III-V and group IV materials.

[0125] The interposer 1300 may include metal interconnects 1308 and vias 1310, including but not limited to through-silicon vias (TSVs) 1312. The interposer 1300 may further include embedded devices 1314, including both passive and active devices. Such devices include, but are not limited to, capacitors, decoupling capacitors, resistors, inductors, fuses, diodes, transformers, sensors, and electrostatic discharge (ESD) devices. More complex devices such as radio-frequency (RF) devices, power amplifiers, power management devices, antennas, arrays, sensors, and MEMS devices may also be formed on the interposer 1300. In accordance with embodiments of the disclosure, apparatuses or processes disclosed herein may be used in the fabrication of interposer 1300 or in the fabrication of components included in the interposer 1300.

[0126] Thus, embodiments of the present disclosure include conductive via bars self-aligned to gate ends, and

methods of fabricating conductive via bars self-aligned to gate ends.

[0127] Although specific embodiments have been described above, these embodiments are not intended to limit the scope of the present disclosure, even where only a single embodiment is described with respect to a particular feature. Examples of features provided in the disclosure are intended to be illustrative rather than restrictive unless stated otherwise. The above description is intended to cover such alternatives, modifications, and equivalents as would be apparent to a person skilled in the art having the benefit of the present disclosure.

[0128] The scope of the present disclosure includes any feature or combination of features disclosed herein (either explicitly or implicitly), or any generalization thereof, whether or not it mitigates any or all of the problems addressed herein. Accordingly, new claims may be formulated during prosecution of the present application (or an application claiming priority thereto) to any such combination of features. In particular, with reference to the appended claims, features from dependent claims may be combined with those of the independent claims and features from respective independent claims may be combined in any appropriate manner and not merely in the specific combinations enumerated in the appended claims.

[0129] The following examples pertain to further embodiments. The various features of the different embodiments may be variously combined with some features included and others excluded to suit a variety of different applications.

[0130] Example embodiment 1: An integrated circuit structure includes a plurality of gate structures. The integrated circuit structure also includes a plurality of dielectric spacers, a corresponding one of the plurality of dielectric spacers laterally surrounding a corresponding one of the plurality of gate structures. A plurality of conductive trench contact structures is alternating with the plurality of gate structures. A conductive via bar is along ends of the plurality of gate structures and ends of the plurality of conductive trench contact structures, wherein the plurality of dielectric spacers is between the ends of the plurality of gate structures and the conductive via bar.

[0131] Example embodiment 2: The integrated circuit structure of example embodiment 1, wherein the plurality of dielectric spacers has an uppermost surface co-planar with an uppermost surface of the plurality of gate structures and co-planar with an uppermost surface of the plurality of conductive trench contact structures and co-planar with an uppermost surface of the conductive via bar.

[0132] Example embodiment 3: The integrated circuit structure of example embodiment 1 or 2, wherein one or more of the plurality of conductive trench contact structures is separated from the conductive via bar by a corresponding dielectric plug.

[0133] Example embodiment 4: The integrated circuit structure of example embodiment 1, 2 or 3, wherein the

plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface above a top surface of the one or more sub-fins.

[0134] Example embodiment 5: The integrated circuit structure of example embodiment 1, 2 or 3, wherein the plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface below a top surface of the one or more sub-fins.

[0135] Example embodiment 6: The integrated circuit structure of example embodiment 1, 2, 3, 4 or 5, wherein the plurality of gate structures is over one or more stacks of semiconductor nanowires.

[0136] Example embodiment 7: The integrated circuit structure of example embodiment 1, 2, 3, 4 or 5, wherein the plurality of gate structures is over one or more stacks of semiconductor nanoribbons.

[0137] Example embodiment 8: The integrated circuit structure of example embodiment 1, 2, 3, 4 or 5, wherein the plurality of gate structures is over one or more semiconductor fins.

[0138] Example embodiment 9: A computing device includes a board, and a component coupled to the board. The component includes an integrated circuit structure including a plurality of gate structures. The integrated circuit structure also includes a plurality of dielectric spacers, a corresponding one of the plurality of dielectric spacers laterally surrounding a corresponding one of the plurality of gate structures. A plurality of conductive trench contact structures is alternating with the plurality of gate structures. A conductive via bar is along ends of the plurality of gate structures and ends of the plurality of conductive trench contact structures, wherein the plurality of dielectric spacers is between the ends of the plurality of gate structures and the conductive via bar.

[0139] Example embodiment 10: The computing device of example embodiment 9, further including a memory coupled to the board.

[0140] Example embodiment 11: The computing device of example embodiment 9 or 10, further including a communication chip coupled to the board.

[0141] Example embodiment 12: The computing device of example embodiment 9, 10 or 11, further including a camera coupled to the board.

[0142] Example embodiment 13: The computing device of example embodiment 9, 10, 11 or 12, wherein the component is a packaged integrated circuit die.

[0143] Example embodiment 14: A method of fabricating an integrated circuit structure includes forming a plurality of gate structures. The method also includes forming a plurality of dielectric spacers, a corresponding one of the plurality of dielectric spacers laterally surrounding a corresponding one of the plurality of gate structures. A plurality of conductive trench contact structures is formed alternating with the plurality of gate structures. A conductive via bar is formed along ends of the plurality of gate structures and ends of the plurality of conductive trench contact structures, wherein the plurality of dielectric spacers is between the ends of the plurality of gate structures

and the conductive via bar.

[0144] Example embodiment 15: The method of example embodiment 14, wherein the plurality of dielectric spacers has an uppermost surface co-planar with an uppermost surface of the plurality of gate structures and co-planar with an uppermost surface of the plurality of conductive trench contact structures and co-planar with an uppermost surface of the conductive via bar.

[0145] Example embodiment 16: The method of example embodiment 14 or 15, wherein one or more of the plurality of conductive trench contact structures is separated from the conductive via bar by a corresponding dielectric plug.

[0146] Example embodiment 17: The method of example embodiment 14, 15 or 16, wherein the plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface above a top surface of the one or more sub-fins.

[0147] Example embodiment 18: The method of example embodiment 14, 15 or 16, wherein the plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface below a top surface of the one or more sub-fins.

[0148] Example embodiment 19: The method of example embodiment 14, 15, 16, 17 or 18, wherein the plurality of gate structures is over one or more stacks of semiconductor nanowires.

[0149] Example embodiment 20: The method of example embodiment 14, 15, 16, 17 or 18, wherein the plurality of gate structures is over one or more stacks of semiconductor nanoribbons.

[0150] Example embodiment 21: The method of example embodiment 14, 15, 16, 17 or 18, wherein the plurality of gate structures is over one or more semiconductor fins.

Claims

1. An integrated circuit structure, comprising:

a plurality of gate structures;
 a plurality of dielectric spacers, a corresponding one of the plurality of dielectric spacers laterally surrounding a corresponding one of the plurality of gate structures;
 a plurality of conductive trench contact structures alternating with the plurality of gate structures; and
 a conductive via bar along ends of the plurality of gate structures and ends of the plurality of conductive trench contact structures, wherein the plurality of dielectric spacers is between the ends of the plurality of gate structures and the conductive via bar.

2. The integrated circuit structure of claim 1, wherein the plurality of dielectric spacers has an uppermost surface co-planar with an uppermost surface of the

- plurality of gate structures and co-planar with an uppermost surface of the plurality of conductive trench contact structures and co-planar with an uppermost surface of the conductive via bar.
3. The integrated circuit structure of claim 1 or 2, wherein one or more of the plurality of conductive trench contact structures is separated from the conductive via bar by a corresponding dielectric plug. 5
4. The integrated circuit structure of claim 1, 2 or 3, wherein the plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface above a top surface of the one or more sub-fins. 10
5. The integrated circuit structure of claim 1, 2 or 3, wherein the plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface below a top surface of the one or more sub-fins. 15
6. The integrated circuit structure of claim 1, 2, 3, 4 or 5, wherein the plurality of gate structures is over one or more stacks of semiconductor nanowires. 20
7. The integrated circuit structure of claim 1, 2, 3, 4 or 5, wherein the plurality of gate structures is over one or more stacks of semiconductor nanoribbons. 25
8. The integrated circuit structure of claim 1, 2, 3, 4 or 5, wherein the plurality of gate structures is over one or more semiconductor fins. 30
9. A method of fabricating an integrated circuit structure, the method comprising: 35
- forming a plurality of gate structures;
 - forming a plurality of dielectric spacers, a corresponding one of the plurality of dielectric spacers laterally surrounding a corresponding one of the plurality of gate structures; 40
 - forming a plurality of conductive trench contact structures alternating with the plurality of gate structures; and 45
 - forming a conductive via bar along ends of the plurality of gate structures and ends of the plurality of conductive trench contact structures, wherein the plurality of dielectric spacers is between the ends of the plurality of gate structures and the conductive via bar. 50
10. The method of claim 9, wherein the plurality of dielectric spacers has an uppermost surface co-planar with an uppermost surface of the plurality of gate structures and co-planar with an uppermost surface of the plurality of conductive trench contact structures and co-planar with an uppermost surface of 55
- the conductive via bar.
11. The method of claim 9 or 10 wherein one or more of the plurality of conductive trench contact structures is separated from the conductive via bar by a corresponding dielectric plug.
12. The method of claim 9, 10 or 11, wherein the plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface above a top surface of the one or more sub-fins.
13. The method of claim 9, 10 or 11, wherein the plurality of gate structures is over one or more sub-fins, and the conductive via bar has a bottommost surface below a top surface of the one or more sub-fins.
14. The method of claim 9, 10, 11, 12 or 13, wherein the plurality of gate structures is over one or more stacks of semiconductor nanowires.
15. The method of claim 9, 10, 11, 12 or 13, wherein the plurality of gate structures is over one or more stacks of semiconductor nanoribbons.




FIG. 1A




FIG. 1B




FIG. 2A




FIG. 2B




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7D




FIG. 7C




FIG. 7G

FIG. 7F

FIG. 7E




FIG. 7H




FIG. 7I




FIG. 7J




FIG. 8




FIG. 9




FIG. 10




FIG. 11A




FIG. 11B




FIG. 11C




FIG. 12




FIG. 13



EUROPEAN SEARCH REPORT

Application Number
EP 22 17 3279

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X	WO 2018/063302 A1 (INTEL CORP [US]) 5 April 2018 (2018-04-05) * page 29, line 24 - page 32, line 28; figures 7A-7H *	1-15	INV. H01L21/768 H01L29/78
X	US 2018/040511 A1 (KAMINENI HIMANI SUHAG [US] ET AL) 8 February 2018 (2018-02-08) * paragraphs [0026] - [0036]; figures 2A-2I *	1, 6-9, 14, 15	
X	US 2020/013678 A1 (GU SIPENG [US] ET AL) 9 January 2020 (2020-01-09) * paragraph [0056]; figure 8 *	1, 6-9, 14, 15	
			TECHNICAL FIELDS SEARCHED (IPC)
			H01L
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 4 November 2022	Examiner Franche, Vincent
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

1
EPO FORM 1503 03:82 (P04C01)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 22 17 3279

5 This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

04-11-2022

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2018063302 A1	05-04-2018	CN 109690785 A	26-04-2019
		DE 112016007299 T5	19-06-2019
		TW 201814841 A	16-04-2018
		TW 202209579 A	01-03-2022
		US 2019221649 A1	18-07-2019
		US 2021074823 A1	11-03-2021
		WO 2018063302 A1	05-04-2018

US 2018040511 A1	08-02-2018	CN 107689342 A	13-02-2018
		TW 201806005 A	16-02-2018
		US 2018040511 A1	08-02-2018
		US 2018158733 A1	07-06-2018

US 2020013678 A1	09-01-2020	NONE	
