



US 20210242317A1

(19) **United States**

(12) **Patent Application Publication**
GU et al.

(10) **Pub. No.: US 2021/0242317 A1**

(43) **Pub. Date: Aug. 5, 2021**

(54) **SELF-ALIGNED CONTACT**

(52) **U.S. Cl.**

(71) Applicant: **GLOBALFOUNDRIES U.S. INC.**,
Santa Clara, CA (US)

CPC .. **H01L 29/4175** (2013.01); **H01L 29/41791**
(2013.01); **H01L 29/7851** (2013.01)

(72) Inventors: **Sipeng GU**, Clifton Park, NY (US);
Jiehui SHU, Dalian (CN); **Haiting WANG**,
Clifton Park, NY (US);
Yanping SHEN, Saratoga Springs, NY
(US)

(57) **ABSTRACT**

(21) Appl. No.: **16/777,531**

The present disclosure relates to semiconductor structures and, more particularly, to self-aligned contacts and methods of manufacture. The structure includes: adjacent diffusion regions located within a substrate material; sidewall structures located above an upper surface of the substrate material, aligned on sides of the adjacent diffusion regions; and a contact between the sidewall structures and extending to within the substrate material between and in electrical contact with the adjacent diffusion regions.


(22) Filed: **Jan. 30, 2020**



Publication Classification

(51) **Int. Cl.**

H01L 29/417 (2006.01)

H01L 29/78 (2006.01)








FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7

SELF-ALIGNED CONTACT

FIELD OF THE INVENTION

[0001] The present disclosure relates to semiconductor structures and, more particularly, to self-aligned contacts and methods of manufacture.

BACKGROUND

[0002] As semiconductor processes continue to scale downwards, e.g., shrink, the desired spacing between features (i.e., the pitch) also becomes smaller. To this end, in the smaller technology nodes it becomes ever more difficult to fabricate back end of line (BEOL) and middle of line (MOL) metallization features, e.g., interconnects and contacts, due to the critical dimension (CD) scaling and process capabilities, as well as materials that are used to fabricate such structures.

[0003] For example, to manufacture contact structures for source and drain contacts, it is necessary to remove dielectric material which is adjacent to the gate structures. The removal of the dielectric material is provided by an etching process, which also tends to erode the spacer material of the gate structure. That is, the low-k dielectric material used for the spacer or sidewalls of the gate structure can be eroded away in the downstream etching processes used to form the openings for the drain and source contacts. This loss of material will expose the metal material of the gate structure, resulting in a short between the metal material of the gate structure and the metal material used to form the contact, itself.

[0004] Also, due to the shrinking of the device, contact open issues result to the narrow source and drain silicide contacts, particularly as a result of lithographic limits. Accordingly, to solve this issue, larger sized silicide contacts for the source and drain are fabricated; however, this results in a size penalty.

SUMMARY

[0005] In an aspect of the disclosure, a structure comprises: adjacent diffusion regions located within a substrate material; sidewall structures above an upper surface of the substrate material, aligned on sides of the adjacent diffusion regions; and a contact between the sidewall structures and extending to within the substrate material between and in electrical contact with the adjacent diffusion regions.

[0006] In an aspect of the disclosure, a structure comprises: a source/drain region in a substrate; a pair of outer spacers above the source/drain region; and a contact to the source/drain region located between the pair of outer spacers and extending to below a surface of the substrate.

[0007] In an aspect of the disclosure, a structure comprising: a substrate; a first gate structure over the substrate; a second gate structure over the substrate and spaced apart from the first gate structure; a first source/drain region adjacent to the first gate structure and between the first gate structure and the second gate structure; a second source/drain region adjacent to the second gate structure and between the first gate structure and the second gate structure; and a contact extending into the substrate and making contact with the first source/drain region and the second source/drain region.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] The present disclosure is described in the detailed description which follows, in reference to the noted plurality of drawings by way of non-limiting examples of exemplary embodiments of the present disclosure.

[0009] FIG. 1A shows a plan view of a plurality of fin structures and dummy gate structures, amongst other features, and respective fabrication processes in accordance with aspects of the present disclosure.

[0010] FIG. 1B shows a cross-sectional view of FIG. 1A along line A-A.

[0011] FIG. 2 shows diffusion regions, amongst other features, and respective fabrication processes in accordance with aspects of the present disclosure.

[0012] FIG. 3 shows replacement and sacrificial gate structures, amongst other features, and respective fabrication processes in accordance with aspects of the present disclosure.

[0013] FIG. 4 shows a trench exposing the sacrificial gate structure, amongst other features, and respective fabrication processes in accordance with aspects of the present disclosure.

[0014] FIG. 5 shows a cavity in a fin structure between the diffusions, amongst other features, and respective fabrication processes in accordance with aspects of the present disclosure.

[0015] FIG. 6 shows silicide contacts, amongst other features, and respective fabrication processes in accordance with aspects of the present disclosure.

[0016] FIG. 7 shows self-aligned contacts, amongst other features, and respective fabrication processes in accordance with aspects of the present disclosure.

DETAILED DESCRIPTION

[0017] The present disclosure relates to semiconductor structures and, more particularly, to self-aligned contacts and methods of manufacture. More specifically, the present disclosure describes a self-aligned silicide contact for contacted gate (poly) pitch (CPP) devices. Advantageously, the present disclosure provides self-aligned contact formation on a wide gate pitch, for example, a 2×CPP (i.e., a gate pitch wider than 1×CPP) device or a 3×CPP device, in small technology nodes.

[0018] The self-aligned contacts of the present disclosure can be manufactured in a number of ways using a number of different tools. In general, though, the methodologies and tools are used to form structures with dimensions in the micrometer and nanometer scale. The methodologies, i.e., technologies, employed to manufacture the self-aligned contacts of the present disclosure have been adopted from integrated circuit (IC) technology. For example, the structures are built on wafers and are realized in films of material patterned by photolithographic processes on the top of a wafer. In particular, the fabrication of the self-aligned contacts uses three basic building blocks: (i) deposition of thin films of material on a substrate, (ii) applying a patterned mask on top of the films by photolithographic imaging, and (iii) etching the films selectively to the mask.

[0019] FIG. 1A shows a plan view of a plurality of fin structures and dummy gate structures, amongst other features, and related fabrication processes. FIG. 1B shows a cross-sectional view of FIG. 1A along line A-A. More specifically and referring to FIGS. 1A and 1B, the structure

10 includes a plurality of fin structures **12** formed from a substrate material, in both a 2×CPP and 1×CPP design scheme. It should be understood that the processes described herein for the 2×CPP design scheme can also be implemented in a 3×CPP design scheme, and that the use of a 2×CPP design scheme and 1×CPP design scheme are provided for ease of illustration.

[0020] In embodiments, the fin structures **12** are composed of substrate material which can be either bulk materials or semiconductor on insulator (SOI) technologies. For example, the plurality of fin structures **12** may be composed of any suitable material including, but not limited to, Si, SiGe, SiGeC, SiC, GaAs, InAs, InP, and other III/V or II/VI compound semiconductors. In the SOI technologies, an insulator layer is provided on top of a semiconductor wafer. The insulator layer comprises any suitable material including, e.g., silicon oxide, sapphire, or a buried oxide layer (BOX). A semiconductor material is formed on top of the insulator layer to form a semiconductor-on-insulator (SOI) substrate, which can be fabricated using wafer bonding, and/or other suitable methods. The semiconductor material can be composed of any of the materials described herein and is used in the fabrication of the plurality of fin structures **12**.

[0021] The fin structures **12** can be fabricated using conventional lithography and etching techniques including sidewall image transfer (SIT) or self-aligned double patterning (SADP). In the SIT technique, for example, a mandrel is formed on the substrate material using conventional CVD processes. A resist is formed on the mandrel material, and exposed to light to form a pattern (openings). A reactive ion etching (RIE) is performed through the openings to form the mandrels. Spacers are formed on the sidewalls of the mandrels which are preferably material that is different than the mandrels, and which are formed using conventional deposition processes known to those of skill in the art. The spacers can have a width which matches the dimensions of the fin structures **12**, for example. The mandrels are removed or stripped using a conventional etching process, selective to the mandrel material. An etching is then performed within the spacing of the spacers to form the sub-lithographic features. The sidewall spacers can then be stripped.

[0022] As further shown in FIGS. **1A** and **1B**, isolation material **14** is deposited between the fin structures **12**. The isolation material **14** is deposited using conventional deposition methods, e.g., a chemical vapor deposition (CVD) process. In embodiments, the isolation material **14** can be an oxide material. Following the deposition process, the isolation material **14** can be subjected to a planarization process, e.g., chemical mechanical processes (CMP).

[0023] Dummy gate structures **16**, **16a** are formed, and isolation material **14** is filled in between them using conventional deposition, lithography, and etching processes. It should be understood by those of skill in the art that the dummy gate structures **16**, **16a** preferably have the same gate width and the same gate to gate distance.

[0024] To form the dummy gate structures, for example, an optional gate dielectric material and polysilicon material can be deposited by any conventional deposition processes, e.g., CVD processes. Then, for example, a resist formed over the dummy gate material is exposed to energy (light) to form a pattern (opening). An etching process with a selective chemistry, e.g., RIE, will be used to form dummy gate structures **16**, **16a**. Following the resist removal by a con-

ventional oxygen ashing process or other known stripants, the insulator material **14** is deposited inside trenches between the dummy gate structures **16**, **16a**. Any residual material can be removed by conventional CMP processes. In embodiments, the gate dielectric material can be high-k gate dielectric material, e.g., HfO₂, Al₂O₃, Ta₂O₅, TiO₂, La₂O₃, SrTiO₃, LaAlO₃, ZrO₂, Y₂O₃, Gd₂O₃, and combinations including multilayers thereof. In embodiments, the dummy gate structures **16**, **16a** are formed over the fin structures **12**.

[0025] In FIG. **2**, diffusion regions **20** (e.g., source/drain regions) are provided in the substrate between the dummy gate structures **16**, **16a**. More specifically, the diffusion regions **20** (e.g., source/drain regions) are provided in the substrate between sidewalls (spacers) **18** of the gate structures **16**, **16a**. In this way, the sidewalls **18** of the gate structures **16**, **16a** are above the surface of the substrate and aligned with the diffusion regions **20**.

[0026] In embodiments, the diffusion regions **20** are formed in the substrate of the plurality of fin structures **12** using an ion implantation process or epitaxial growth process, for example. In preferred embodiments, the diffusion regions **20** are of the same size. As should be understood by those of skill in the art, ion implantation is a low-temperature process by which ions of a particular element are accelerated into the plurality of fin structures **12**, between the dummy gate structures **16**, **16a**. In more specific embodiments, the ion implantation processes or epitaxial growth process comprises a semiconductor doping with boron, phosphorus, or arsenic (depending on the type of device), followed by an anneal process (for ion implantation).

[0027] Prior to the ion implantation process, the insulator material **14** would be removed, followed by formation of sidewalls **18** on the dummy gate structures **16**, **16a**. The sidewalls **18** can be formed on the dummy gate structures **16**, **16a** by deposition of a low-k dielectric sidewall material, e.g., nitride, and anisotropic etching process as is known in the art. The anisotropic etching processes will remove the sidewall material from horizontal surfaces of the structure, e.g., an upper surface of the dummy gate structures **16**, **16a** and the plurality of fins **12**. In this way, the removal of the insulator material and the sidewall material (by anisotropic etching processes) will expose the plurality of fins **12** for the ion implantation process, as should be understood by those of ordinary skill in the art. Subsequent to the ion implantation process, insulator material **14a** will be redeposited within the spaces between the plurality of fins **12**, over the diffusion regions **20**. The insulator material **14a** can also undergo a planarization process, e.g., CMP.

[0028] In FIG. **3**, the dummy gate structures are replaced with metal gate structures **22**, **22a**. In this example, the metal gate structure **22a** is a sacrificial gate structure that will be removed at a later fabrication process to form a self-aligned source/drain contact. In embodiments, the material (e.g., poly) of the dummy gate structures **16**, **16a** is removed by conventional etching processes, and replaced with replacement metal gate material, e.g., workfunction materials, between the sidewalls **18**. In embodiments, examples of the workfunction materials for a p-channel FET include Ti, TiAlC, Al, TiAl, TaN, TaAlC, TiN, TiC or Co and combination thereof. In one embodiment, TiN is used for a p-channel FET. Examples of the workfunction materials for an n-channel FET include TiN, TaN, TaAlC, TiC, TiAl, TaC, Co, Al, TiAl, HfTi, TiSi, TaSi or TiAlC and combination thereof. In one embodiment, TaAlC, TiAl or Al is used for

an n-channel FET. The workfunction materials may be formed by chemical vapor deposition (CVD), physical vapor deposition (PVD) including sputtering, atomic layer deposition (ALD) or other suitable method. Following workfunction metal deposition, a conductive metal (e.g., W) will be used to fill in the rest of metal gate to increase gate conductivity. A CMP process follows the deposition of the workfunction materials.

[0029] Following the replacement gate processes, a capping material **25** is deposited over the replacement metal gate structures **22**, sacrificial gate structure **22a** and insulator material **14a**. In embodiments, the capping material **25** can be a nitride material, e.g., SiN, deposited by conventional CVD processes. An insulator material **24** is deposited over the capping material **25**, with a hardmask **26** deposited over the insulator material **24**. In embodiments, the insulator material **24** can be a blanket deposition of oxide material; whereas, the hardmask **26** can be representative of a stack of lithographic materials.

[0030] As shown in FIG. 4, trenches **28**, **30** are formed through the hardmask **26**, insulator material **24** and capping material **25**. In embodiments, the trench **28** is tapered (e.g., wider at the top than at the bottom) and will expose the sacrificial gate structure **22a**; whereas, the trenches **30** are also tapered and will extend to the capping material **25** and be aligned with the diffusion regions **20b**. The trenches **28**, **30** can be formed by conventional lithography and etching processes, with the hardmask **26** being part of the resist stack as an example.

[0031] In FIG. 5, the sacrificial gate structure **22a** is removed by an isotropic etching process performed through the trench **28**. In embodiments, the gate dielectric material, if any, could also be removed using a selective directional etching process. The selective directional etching process can be a dry or wet etching process, known to those of ordinary skill in the art. During the etching (removal) process, the hardmask **26** and sidewalls **18** will protect the insulator material **24**, **14a** (e.g., interlevel dielectric material composed of, e.g., oxide).

[0032] The removal of the sacrificial gate structure **22a** and, optionally, the gate dielectric material, will expose substrate material of the underlying fin structure **12** located between adjacent diffusion regions **20a**. Also, the sidewalls **18** will be aligned with the sides of the adjacent diffusion regions **20a**, protecting the oxide material, e.g., insulator material **14a**, from processing damage. The exposed substrate material of the fin structure **12** will then undergo a recess process, e.g., Si recess, to form a cavity **28a** extending under the sidewalls **18** and contacting adjacent diffusion regions **20a**. In embodiments, the cavity **28a** can be ball shaped, although other shapes are also contemplated herein.

[0033] The recess process is an isotropic Si etching process, which is highly selective to the sidewall material **18**, e.g., low-k spacer material, and insulator material, e.g., oxide. In more specific embodiments, the recess process is a wet etching process or dry etching process. For example, dry etchants can include plasma-based CF₄, plasma-based SF₆, or gas XeF₄ silicon etch, etc., and wet etching processes can include KOH and NH₄OH. In embodiments, the cavity structure **28a** is self-aligned with the adjacent diffusion regions **20a**.

[0034] FIG. 6 shows an additional etching process in which the trenches **30** are extended to expose the underlying diffusions **20b**. In embodiments, the etching process is an

isotropic oxide etching process, which is highly selective to the Si or other substrate material of the fin structure **12**; that is, the etching process will not attack the substrate material of the fin structure **12**. The hardmask material is then removed using a conventional stripant process.

[0035] Still referring to FIG. 6, a silicide process is performed to form silicide contacts **32a**, **32b** on the diffusion regions **20a**, **20b**. As shown, the silicide contacts **32a** are in contact with the diffusion regions **20a** below the upper surface of the substrate material of the plurality of the fin structures **12**; whereas, the silicide contacts **32b** are in contact with the diffusion regions **20b** above the surface of the substrate material of the plurality of the fin structures **12**. In this way, in the 2×CCP or 3×CPP design scheme, the silicide contacts **32a** and subsequently formed diffusion contacts will land on and make direct and proper contact (without shorting to an adjacent gate structure) with the diffusion regions **20a**, regardless of the scaling of the device.

[0036] As should be understood by those of skill in the art, the silicide process begins with deposition of a thin transition metal layer, e.g., nickel, cobalt, titanium, TiSi, or TiN over fully formed and patterned semiconductor devices (e.g., doped or ion implanted source and drain regions **20a**, **20b**). After deposition of the material, the structure is heated allowing the transition metal to react with exposed silicon (or other semiconductor material as described herein) in the active regions of the semiconductor device (e.g., source, drain, gate contact region) forming a low-resistance transition metal silicide. Following the reaction, any remaining transition metal is removed by chemical etching, leaving silicide contacts **32** in the active regions of the device.

[0037] Another option to form silicide contacts **32a** and **32b** is to selectively deposit TiSi on Si only by CVD, ALD or other methods. In this implementation, as is understood by one of skill in the art, the post anneal process could be skipped since TiSi has been formed as deposited.

[0038] In FIG. 7, an optional liner material **34** is deposited within the trenches **28**, **30** and within the cavity **28a**. The optional liner can be a diffusion barrier layer such as TiN, deposited by conventional deposition methods, e.g., CVD, atomic layer deposition (ALD) plasma enhanced CVD (PECVD), etc. A metal fill material is then deposited in the **28**, **30** and within the cavity **28a** to form self-aligned contacts **36a**, **36b**. In embodiments, the metal fill material can be tungsten (W) which provides an electrical conduction path from the diffusions **20a**. Any excessive metal fill material can be removed from the surface of the structure by a conventional CMP process.

[0039] The metal material in the cavity **28a** will form a ball shaped contact **36a** between the diffusion regions **20a**. In this way, the contact **36a** will have a wider dimension at its lower portion below the upper surface of the substrate material, compared to between the mid-portion between the outer sidewalls (spacers) **18** above the upper surface of the substrate material. It should be recognized that the mid-portion between the pair of sidewalls **18** (outer spacers) is at a level of the replacement second gate structures **22**. The upper portion of the contact **36a** can be tapered and is above the pair of sidewalls **18**.

[0040] The self-aligned contacts can be utilized in system on chip (SoC) technology. It should be understood by those of skill in the art that SoC is an integrated circuit (also known as a “chip”) that integrates all components of an electronic system on a single chip or substrate. As the

components are integrated on a single substrate, SoCs consume much less power and take up much less area than multi-chip designs with equivalent functionality. Because of this, SoCs are becoming the dominant force in the mobile computing (such as in Smartphones) and edge computing markets. SoC is also commonly used in embedded systems and the Internet of Things.

[0041] The method(s) as described above is used in the fabrication of integrated circuit chips. The resulting integrated circuit chips can be distributed by the fabricator in raw wafer form (that is, as a single wafer that has multiple unpackaged chips), as a bare die, or in a packaged form. In the latter case the chip is mounted in a single chip package (such as a plastic carrier, with leads that are affixed to a motherboard or other higher level carrier) or in a multichip package (such as a ceramic carrier that has either or both surface interconnections or buried interconnections). In any case the chip is then integrated with other chips, discrete circuit elements, and/or other signal processing devices as part of either (a) an intermediate product, such as a motherboard, or (b) an end product. The end product can be any product that includes integrated circuit chips, ranging from toys and other low-end applications to advanced computer products having a display, a keyboard or other input device, and a central processor.

[0042] The descriptions of the various embodiments of the present disclosure have been presented for purposes of illustration, but are not intended to be exhaustive or limited to the embodiments disclosed. Many modifications and variations will be apparent to those of ordinary skill in the art without departing from the scope and spirit of the described embodiments. The terminology used herein was chosen to best explain the principles of the embodiments, the practical application or technical improvement over technologies found in the marketplace, or to enable others of ordinary skill in the art to understand the embodiments disclosed herein.

What is claimed:

1. A structure comprising: adjacent diffusion regions located within a substrate material; sidewall structures above an upper surface of the substrate material, aligned on sides of the adjacent diffusion regions; and a contact between the sidewall structures and extending to within the substrate material between and in electrical contact with the adjacent diffusion regions.
2. The structure of claim 1, further comprising silicide contacts below the upper surface of the substrate material and in direct contact with the adjacent diffusion regions.
3. The structure of claim 2, wherein the silicide contacts are an intervening material between the contact and the adjacent diffusion regions.
4. The structure of claim 2, wherein the contact provides an electrical conduction path to both the adjacent diffusion regions.
5. The structure of claim 4, wherein the contact is a self-aligned contact.
6. The structure of claim 4, wherein a portion of the contact below the upper surface of the substrate material is ball shaped.

7. The structure of claim 4, wherein the portion of the contact below the upper surface of the substrate material is wider than a portion of the contact between the sidewall structures.

8. The structure of claim 1, further comprising a contact that extends to additional diffusion regions above the upper surface of the substrate material.

9. The structure of claim 1, wherein the diffusion regions are source and/or drain regions for adjacent gate structures.

10. The structure of claim 9, wherein the substrate material is a fin of a finFET device.

11. The structure of claim 10, wherein the adjacent gate structures include sidewalls which are of a same material as the sidewall structures.

12. A structure comprising:

- a source/drain region in a substrate;
- a pair of outer spacers above the source/drain region; and
- a contact to the source/drain region located between the pair of outer spacers and extending to below a surface of the substrate.

13. The structure of claim 12, wherein the source/drain region is adjacent source/drain regions comprising a first source/drain region and a second source/drain region for a first gate structure and a second gate structure, respectively, and the contact abuts both the first source/drain region and the second source/drain region below the surface of the substrate.

14. The structure of claim 13, wherein the contact has a lower portion which is below the first and second gate structures.

15. The structure of claim 13, wherein the contact has a mid-portion which is between the pair of outer spacers and is at a level of the first and second gate structures.

16. The structure of claim 13, wherein the contact has an upper portion which is above the pair of outer spacers.

17. A structure comprising:

- a substrate;
- a first gate structure over the substrate;
- a second gate structure over the substrate and spaced apart from the first gate structure;
- a first source/drain region adjacent to the first gate structure and between the first gate structure and the second gate structure;
- a second source/drain region adjacent to the second gate structure and between the first gate structure and the second gate structure; and
- a contact extending into the substrate and making contact with the first source/drain region and the second source/drain region.

18. The structure of claim 17, wherein the contact partially extends between opposing sidewalls above the substrate.

19. The structure of claim 18, wherein a lower portion of the contact is wider than a portion of the contact that partially extends between the opposing sidewalls above the substrate.

20. The structure of claim 17, further comprising silicide contacts below an upper surface of the substrate and in direct contact with the first source/drain region and the second source/drain region.

* * * * *