



US 20150380403A1

(19) **United States**

(12) **Patent Application Publication**

Kotsar et al.

(10) **Pub. No.: US 2015/0380403 A1**

(43) **Pub. Date: Dec. 31, 2015**

(54) **SEMICONDUCTOR DEVICE WITH THERMALLY GROWN OXIDE LAYER BETWEEN FIELD AND GATE ELECTRODE AND METHOD OF MANUFACTURING**

H01L 21/02 (2006.01)
H01L 21/311 (2006.01)
H01L 29/78 (2006.01)
H01L 29/423 (2006.01)

(71) Applicant: **Infineon Technologies AG**, Neubiberg (DE)

(52) **U.S. Cl.**
CPC *H01L 27/088* (2013.01); *H01L 29/78* (2013.01); *H01L 29/7813* (2013.01); *H01L 29/7811* (2013.01); *H01L 29/407* (2013.01); *H01L 29/66734* (2013.01); *H01L 29/4236* (2013.01); *H01L 21/823437* (2013.01); *H01L 21/823462* (2013.01); *H01L 21/26533* (2013.01); *H01L 21/02236* (2013.01); *H01L 21/31111* (2013.01); *H01L 21/266* (2013.01); *H01L 21/02164* (2013.01); *H01L 21/02255* (2013.01)

(72) Inventors: **Yulia Kotsar**, Villach (AT); **Sven Lanzerstorfer**, Feldkirchen (AT); **Robert Zink**, Riegersdorf (AT)

(21) Appl. No.: **14/745,908**

(22) Filed: **Jun. 22, 2015**

(30) **Foreign Application Priority Data**

Jun. 26, 2014 (DE) 102014108966.9

Publication Classification

(51) **Int. Cl.**
H01L 27/088 (2006.01)
H01L 29/40 (2006.01)
H01L 29/66 (2006.01)
H01L 21/266 (2006.01)
H01L 21/8234 (2006.01)
H01L 21/265 (2006.01)

(57) **ABSTRACT**

A first trench and a second trench, both extending from a main surface into a semiconductor layer, are filled with a first fill material. The first fill material is selectively recessed in the first trench. A mask is formed that covers the second trench and that exposes the first trench. An oxidation rate promoting material is implanted into an exposed first section of the recessed fill material in the first trench. The mask is removed. Then the first fill material is thermally oxidized, wherein on the first section an oxidation rate is at least twice as high as on non-implanted sections of the first fill material.




FIG 1A




FIG 1B




FIG 1C




FIG 2A




FIG 2B




FIG 2C




FIG 2D




FIG 2E




FIG 2F




FIG 3A




FIG 3B




FIG 3C




FIG 3D




FIG 3E




FIG 3F




FIG 4A




FIG 4B




FIG 6A





FIG 6B



**SEMICONDUCTOR DEVICE WITH
THERMALLY GROWN OXIDE LAYER
BETWEEN FIELD AND GATE ELECTRODE
AND METHOD OF MANUFACTURING**

[0001] This application claims priority to German Patent Application No. 10 2014 108 966.9 filed on 26 Jun. 2014, the content of said application incorporated herein by reference in its entirety.

BACKGROUND

[0002] In microcell power MOSFETs (metal oxide semiconductor field effect transistors) a vertical current flows through transistor cells between the source and drain electrodes placed at the front and back sides of a semiconductor body. In MOSFETs based on trench gate technology the transistor channel is formed along vertical sidewalls of trench gate structures extending from the front side into the semiconductor body. Below the gate structures, field electrodes, which may be electrically connected to the source electrode, decrease the gate to drain capacity and provide a counter charge with respect to a charge resulting from the doping in the drift zone. Smart power semiconductor devices may include signal processing circuits integrated with the transistor cells in the same semiconductor body.

[0003] It is desirable to improve reliability and to reduce manufacturing costs of power semiconductor devices.

SUMMARY

[0004] According to an embodiment, a method of manufacturing a semiconductor device includes filling a first trench and a second trench with a first fill material, wherein the first trench and the second trench extend from a main surface into a semiconductor substrate. The first fill material in the first trench is selectively recessed. A mask is formed that covers the second trench and that exposes the first trench. An oxidation rate promoting material is implanted into an exposed first section of the recessed fill material in the first trench. After removing the mask, the first fill material is thermally oxidized, wherein on the first section an oxidation rate is at least twice as high as on non-implanted sections of the first fill material.

[0005] According to another embodiment, a semiconductor device includes field electrode structures extending from a first surface into a semiconductor body. The field electrode structures include field electrodes. Gate structures extend from the first surface into the semiconductor body and include field electrodes and gate electrodes between the field electrodes and the first surface. A thin separation oxide of grown silicon oxide is on the field electrodes of the field electrode structures. A thick separation oxide of grown silicon oxide separates the gate and field electrodes of the gate structures. A vertical extension of the thick separation oxide is greater than a vertical extension of the thin separation oxide.

[0006] According to a further embodiment, an electronic circuit includes a semiconductor device including field electrode structures that extend from a first surface into a semiconductor body. The field electrode structures include field electrodes. Gate structures extend from the first surface into the semiconductor body and include field electrodes and gate electrodes between the field electrodes and the first surface. A thin separation oxide of grown silicon oxide is on the field electrodes of the field electrode structures. A thick separation oxide of grown silicon oxide separates the gate and field

electrodes of the gate structures. A vertical extension of the thick separation oxide is greater than a vertical extension of the thin separation oxide.

[0007] Those skilled in the art will recognize additional features and advantages upon reading the following detailed description and on viewing the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] The accompanying drawings are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification. The drawings illustrate the embodiments of the present invention and together with the description serve to explain principles of the invention. Other embodiments of the invention and intended advantages will be readily appreciated as they become better understood by reference to the following detailed description.

[0009] FIG. 1A is a schematic cross-sectional view of a portion of a semiconductor substrate for illustrating a method of manufacturing a semiconductor device according to an embodiment, after recessing a first fill material in a first trench.

[0010] FIG. 1B is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 1A after implanting an oxidation rate promoting material into a first section of the recessed fill material in the first trench.

[0011] FIG. 1C is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 1B after a thermal oxidation of exposed semiconductor material.

[0012] FIG. 2A is a schematic cross-sectional view of a portion of a semiconductor substrate for illustrating a method of manufacturing a semiconductor device according to another embodiment, after recessing the first fill material in the first trench.

[0013] FIG. 2B is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 2A after implanting an oxidation rate promoting material into the first fill material.

[0014] FIG. 2C is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 2B after forming a first mask.

[0015] FIG. 2D is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 2C after etching a field dielectric layer using the first mask.

[0016] FIG. 2E is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 2D after thermal oxidation of exposed semiconductor material.

[0017] FIG. 2F is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 2E after depositing and recessing a second fill material.

[0018] FIG. 3A is a schematic cross-sectional view of a portion of a semiconductor substrate for illustrating a method of manufacturing a semiconductor device according to an embodiment including an oxide damage implant, after recessing a first fill material in a first trench.

[0019] FIG. 3B is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 3A after the oxide damage implant.

[0020] FIG. 3C is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 3B after implanting an oxidation rate promoting material.

[0021] FIG. 3D is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 3C after a masked etch of a field dielectric layer.

[0022] FIG. 3E is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 3D after thermal oxidation of exposed semiconductor material.

[0023] FIG. 3F is a schematic cross-sectional view of the semiconductor substrate portion of FIG. 3E after depositing and recessing a second fill material.

[0024] FIG. 4A is a schematic illustration of masks used in the method of FIGS. 3A to 3F.

[0025] FIG. 4B is a schematic cross-sectional view of a portion of a semiconductor device manufactured in a process using the masks of FIG. 4A.

[0026] FIG. 5 is a schematic cross-sectional view of a portion of a semiconductor device in accordance with another embodiment.

[0027] FIG. 6A is a schematic circuit diagram of an electronic circuit including a smart FET (field effect transistor) according to an embodiment.

[0028] FIG. 6B is a schematic circuit diagram of an electronic circuit including a half-bridge circuit according to a further embodiment.

DETAILED DESCRIPTION

[0029] In the following detailed description, reference is made to the accompanying drawings, which form a part hereof and in which are shown by way of illustrations specific embodiments in which the invention may be practiced. It is to be understood that other embodiments may be utilized and structural or logical changes may be made without departing from the scope of the present invention. For example, features illustrated or described for one embodiment can be used on or in conjunction with other embodiments to yield yet a further embodiment. It is intended that the present invention includes such modifications and variations. The examples are described using specific language, which should not be construed as limiting the scope of the appending claims. The drawings are not scaled and are for illustrative purposes only. For clarity, the same elements have been designated by corresponding references in the different drawings if not stated otherwise.

[0030] The terms “having,” “containing,” “including,” “comprising” and the like are open, and the terms indicate the presence of stated structures, elements or features but do not preclude additional elements or features. The articles “a,” “an” and “the” are intended to include the plural as well as the singular, unless the context clearly indicates otherwise.

[0031] The term “electrically connected” describes a permanent low-ohmic connection between electrically connected elements, for example a direct contact between the concerned elements or a low-ohmic connection via a metal and/or highly doped semiconductor. The term “electrically coupled” includes that one or more intervening element(s) adapted for signal transmission may be provided between the electrically coupled elements, for example elements that are controllable to temporarily provide a low-ohmic connection in a first state and a high-ohmic electric decoupling in a second state.

[0032] The Figures illustrate relative doping concentrations by indicating “-” or “+” next to the doping type “n” or “p”. For example, “n-” means a doping concentration which is lower than the doping concentration of an “n”-doping region while an “n+”-doping region has a higher doping concentration than an “n”-doping region. Doping regions of the same relative doping concentration do not necessarily have the same absolute doping concentration. For example, two

different “n”-doping regions may have the same or different absolute doping concentrations.

[0033] FIG. 1A shows a semiconductor substrate **500a** consisting of or containing a semiconductor layer **100a** of a single-crystalline semiconductor material. The semiconductor substrate **500a** may be a semiconductor wafer from which a plurality of identical semiconductor dies is obtained. The single crystalline semiconductor material of the semiconductor layer **100a** may be silicon (Si), silicon carbide (SiC), germanium (Ge), a silicon germanium crystal (SiGe), gallium nitride (GaN), gallium arsenide (GaAs) or any other $A_{III}B_V$ semiconductor, by way of example.

[0034] A direction perpendicular to a main surface **101a** of the semiconductor layer **100a** defines a vertical direction and directions orthogonal to the vertical direction are horizontal directions.

[0035] From the main surface **101a**, first trenches **191** and second trenches **192** extend into the semiconductor layer **100a**. A vertical extension of the first and second trenches **191**, **192** may be in a range from 1 to 10 μm , for example from 3 to 5 μm . A horizontal width of the trenches **191**, **192** may be in a range from 0.2 to 2 μm , for example in a range from 0.8 to 1.0 μm . The first and second trenches **191**, **192** are stripe-shaped trenches or portions of stripe-shaped trenches extending in a horizontal direction orthogonal to the cross-sectional plan. The first and second trenches **191**, **192** may have the same cross-sectional area. According to other embodiments, the second trenches **192** may be wider and deeper than the first trenches **191**. For example, a width of the second trenches **192** exceeds a width of the first trenches **191** by 5%.

[0036] A conformal field dielectric layer **240** of uniform layer thickness lines the first and second trenches **191**, **192** and covers the main surface **101a**. The field dielectric layer **240** may consist of or include a thermally grown semiconductor oxide, for example a thermally grown silicon oxide in case the semiconductor layer **100a** is single crystalline silicon. According to another embodiment, the field dielectric layer **240** may be a deposited semiconductor oxide, for example deposited silicon oxide such as silicon oxide obtained by using TEOS (tetraethyl orthosilicate) as precursor material. According to other embodiments, the field dielectric layer **240** may include a silicon nitride layer, a silicon oxide layer or another dielectric material. A layer thickness of the field dielectric layer **240** may be in a range from 50 to 300 nm, for example in a range from 200 to 250 nm. A first fill material **165** fills the space between portions of the field dielectric layer **240** lining the first and second trenches **191**, **192**. The first fill material **165** consists of or contains heavily doped polycrystalline silicon.

[0037] A mask layer may be deposited and patterned by a photolithographic method to obtain an etch mask that covers the second trenches **192** and that exposes the first trenches **191**. Using the etch mask first fill portions **165a** of the first fill material **165** in the first trenches **191** are selectively recessed with respect to second fill portions **165b** of the first fill material **165** in the second trenches **192**.

[0038] According to an embodiment, the etch mask for recessing the first fill material **165** may be used as an implant mask **410** in the following. According to other embodiments, the implant mask **410** is another mask replacing the etch mask. According to a further embodiment, the implant mask **410** may be formed by modifying the etch mask. An oxidation rate promoting material **411** is implanted into portions of the field dielectric layer **240** and into portions of the recessed first

fill portions **165a** in the first trenches **191** exposed by the implant mask **410**. The oxidation rate promoting material **411** may be or may contain arsenic ions. The implant is performed at comparatively high dose and low energy.

[0039] FIG. 1B shows the implant mask **410** that exposes the first fill portions **165a** in the first trenches **191** and that covers the second fill portions **165b** in the second trenches **192** such that the oxidation rate promoting material **411** is selectively implanted into a first section **166** of the first fill portions **165a**, whereas no oxidation rate promoting material is implanted into the second fill portions **165b**.

[0040] Then the implant mask **410** or another mask replacing the implant mask **410** may be used as an etch mask for selectively removing an exposed portion of the field dielectric layer **240**, wherein sections of the semiconductor layer **100a** are exposed. After removal of the implant mask **410** the semiconductor substrate **500a** may be subjected to a heat treatment in an oxygen containing ambient, wherein a thermal semiconductor oxide is formed on exposed semiconducting surfaces. An oxidation growth rate is higher on the implanted first section **166** of the first fill material **165** than on semiconducting material without implanted oxidation rate promoting material **411**, e.g., on the semiconductor layer **100a** and on the second fill portions **165b**.

[0041] FIG. 10 shows a first portion **240a** of a resulting field dielectric completely lining the second trenches **192**. A second portion **240b** lines bottom portions of the first trenches **191**. A thin gate dielectric **242** is grown on the single crystalline surface in a portion of the semiconductor layer **100a**, where the field dielectric layer **240** has been removed. The thin gate dielectric **242** lines top portions of the first trenches **191**. A thick separation oxide **241** grows on the first fill portions **165a**, whereas only a thin separation oxide **241b** grows on the second fill portions **165b** in the second trenches **192**.

[0042] By masking the implant of the oxidation rate promoting material **411**, the implant mask **410** of FIG. 1B suppresses the formation of a thick oxide on the second fill portions **165b** in the second trenches **192**. The topology and above as well as the surface in a region containing the second trenches **192** remain flat. The flat surface simplifies subsequent processing. For example, when a second fill material is deposited and recessed to fill the upper portions of the first trenches **191**, no ancillary spacers are formed above the second trenches **192**.

[0043] FIGS. 2A to 2F illustrate a method according to a comparative example for discussing effects of the method illustrated in FIGS. 1A to 10.

[0044] A conformal field dielectric layer **240** is formed on a semiconductor layer **100a** of a semiconductor substrate **501a** including first trenches **191** and second trenches **192**. A first fill material **165** is deposited and selectively recessed in the first trenches **191**.

[0045] FIG. 2A shows the first and second trenches **191**, **192** extending from a main surface **101a** into the semiconductor layer **100a**. The field dielectric layer **240** covers the main surface **101a** and lines the first trenches **191** and the second trenches **192**. First fill portions **165a** of the first fill material **165** fill bottom portions of the first trenches **191**. Second fill portions **165b** of the first fill material completely fill the second trenches **192**.

[0046] An oxidation rate promoting material **411** is implanted into exposed portions of the field dielectric layer

240 and into exposed surfaces of the first fill material **165** in an implant process without implant mask.

[0047] FIG. 2B shows implant portions **240x** of the field dielectric layer **240**. The thickness of the implant portions **240x** may be in a range from about 5 to 50 nm. Implanted first sections **166** of the first fill material **165** contain the oxidation rate promoting material **411**.

[0048] A mask layer is deposited and patterned by photolithography to form an etch mask **405** for patterning the field dielectric layer **240**.

[0049] FIG. 2C shows the etch mask **405** covering a region of the main surface **101a** including the second trenches **192** and exposing a region of the main surface **101a** including the first trenches **191**.

[0050] Using the etch mask **405** an exposed portion of the field dielectric layer **240** is removed. After patterning the field dielectric layer **240** the first mask **405** is removed, wherein the implanted first sections **166** of the first fill material **165** are exposed.

[0051] FIG. 2D shows the patterned field dielectric **240a**, **240b** with a first portion **240a** covering a first region of the main surface **101a** and lining the second trenches **192**. A second portion **240b** lines bottom portions of the first trenches **191**. The oxidation rate promoting material **411** also damages the material of the field dielectric layer **240** such that the etch results in a smooth edge of the first portion **240a** of the field dielectric on the main surface **101a**. An HFB (buffered aqueous solution of hydrogen fluoride) etch that lasts for several minutes removes the implanted portions **240x** to avoid an undesired outdiffusion of the oxidation rate promoting material **411** at a later process stage.

[0052] The semiconductor substrate **500a** is subjected to a heat treatment in an oxygen-containing atmosphere, wherein the oxidation rate promoting material promotes the oxidation of the semiconductor material on the exposed surfaces of the first sections **166** of the first fill material **165**.

[0053] FIG. 2E shows separation oxides **241** grown at high oxidation rate on the first and second fill portions **165a**, **165b**. A thin gate dielectric **242** is grown on exposed portions of the semiconductor layer **100a**. The separation oxide **241** grown on the second fill portion **165b** protrudes from an exposed edge of the field dielectric **240a** by several nanometers, for example by about 150 nm.

[0054] A second fill material **155** is deposited and recessed such that the second fill material **155** is removed from portions outside the first trenches **191**. When the second fill material **155** is deposited, the vertical extension of the deposited second fill material is greater in areas around steps and protrusions in the underlying surface, e.g., around the protrusions formed by the separation oxide **241** above the second trenches **192**. The recess of the second fill material **155** is mainly anisotropic with a high removal rate along the vertical direction. As a result, ancillary spacers **155a** of the second fill material **155** may be formed along the vertical sidewalls of the separation oxides **241** above the second trenches **192**. Increasing the process time for reliably removing the ancillary spacers **155a** also further recesses the portions of the second fill material **155** forming the gate electrode, such that a distance between the main surface **101a** and the second fill material **155** in the first trenches **191** may become too large for shallow source implants.

[0055] FIGS. 3A to 3F refer to an embodiment including an oxide damage implant. The description of details described with reference to FIGS. 1A to 10 is omitted.

[0056] Using a first mask as an etch mask, first trenches 191 and second trenches 192 are formed that extend in a cell area 610 from a main surface 101a into a semiconductor layer 100a of a semiconductor substrate 500a. A conformal field dielectric layer 240 is formed, for example by growing a semiconductor oxide on the semiconductor layer 100a.

[0057] FIG. 3A shows the conformal field dielectric layer 240 formed on the main surface 101a in the cell area 610 and in a logic area 620. The logic area 620 may be devoid of any patterned structures such as gate electrodes at this stage. The conformal field dielectric layer 240 lines the first trenches 191 and the second trenches 192. A first fill material 165, for example heavily doped polycrystalline silicon, is deposited and locally recessed using a second mask as an etch mask. The second mask may be removed after the recess.

[0058] FIG. 3A shows locally recessed first fill portions 165a of the first fill material 165 in the first trenches 191 and unrecessed second fill portions 165b in the second trenches 192. The field dielectric layer 240 lines at uniform thickness the first and second trenches 191, 192 and covers the main surface 101a in both the cell area 610 and the logic area 620.

[0059] An oxide damage material 412, for example argon (Ar) atoms may be implanted at an implant energy of about 40 keV and an implant dose of about $4E+13 \text{ cm}^{-2}$.

[0060] FIG. 3B shows an implant portion 240y of the field dielectric layer 240. The implant portion 240y contains the oxide damage material 412, which does not or only to a very low degree affect an oxidation rate of the first fill material 165.

[0061] A third mask layer is deposited and patterned by photolithography to form a third mask 430. The material of the third mask 430, for example a photoresist, can be recessed or etched with high selectivity against the material of the field dielectric layer 240. An oxidation rate promoting material 411, for example arsenic (As) atoms, are implanted, wherein the third mask 430 is effective as an implant mask and shields a covered region against the implant of the oxidation rate promoting material 411.

[0062] FIG. 3C shows the third mask 430 covering a first region in the cell area 610 containing the second trenches 192 and exposing, in the cell area 610, a second region containing the first trenches 191. The third mask 430 may also cover further regions in the logic area 620. Implanted first sections 166 of the first fill portions 165a in the first trenches 191 contain the oxidation rate promoting material 411. No oxidation rate promoting material 411 is implanted into the second fill portions 165b in the second trenches 192, which are shielded against the implant by the second mask 420.

[0063] The field dielectric layer 240 may be patterned using the third mask 430 or another mask replacing the third mask 430 as an etch mask. The third mask 430 may be removed after patterning the field dielectric layer 240. An HFB etch for removing remnants including arsenic atoms may follow. Since the patterning of the field dielectric layer 240 removes all portions of the field dielectric layer 240 containing arsenic atoms, which are effective as undesired dopant in the semiconductor material of the semiconductor layer 100a, when they diffuse out from the field dielectric layer 240 into the semiconductor layer 100a during further processing, the HFB time may be shortened to not more than approximately one minute without adversely affecting the device characteristics.

[0064] FIG. 3D shows the patterned field dielectric with first portions 240a covering the main surface 101a and lining the second trenches 192 in a first region and with second portions 240b separating the first fill portions 165a from the

semiconductor layer 100a in a second region. The damage implant in the implant portion 240y containing the argon atoms results in smooth edges of the first portions 240a on the main surface 101a. For example, transitions TR at the edges of the first portions 240a may have a slope angle α with respect to the main surface 101a in a range from 30 degree to 40 degree.

[0065] According to the illustrated embodiment, the implant of the oxidation rate promoting material 411 and the etch of the field dielectric layer 240 use the same mask such that the oxidation rate promoting material is only formed where the field dielectric is removed. The oxide damaging implant is performed before the shared mask is applied. According to other embodiments, the oxidation rate promoting implant may share the same mask as the recess of the first fill material 165 such that the oxidation promoting material is only implanted where the first fill material 165 is recessed. The oxide damaging implant may be performed maskless, e.g., before the shared mask or the mask for etching the field dielectric layer 240 is applied.

[0066] A thermal oxidation process is performed, wherein an oxidation rate in semiconductor materials containing the oxidation rate promoting material 411 is higher, e.g., at least twice or at least four times as high as in semiconductor materials without oxidation rate promoting material.

[0067] As illustrated in FIG. 3E, thick separation oxides 241a are exclusively formed on the recessed first fill portions 165a, whereas only thin separation oxides 241b are formed on the second fill portions 165b. The oxidation process further forms a thin gate dielectric 242 on exposed portions of the semiconductor layer 100a. A second fill material 165 is deposited and recessed.

[0068] FIG. 3E shows the recessed second fill material 165 in the upper portions of the first trenches 191. Since no high and steep edges and transitions are formed on the front side, no ancillary spacers are formed as a side effect. Gate electrodes 158 of lateral transistors may be formed in the logic area 620. Further, heavily doped source zones 110 and source/drain zones 111 of a first conductivity type as well as body and termination zones 115, 116 of a second, complementary conductivity type may be formed in the semiconductor layer 100a, which may be of the n-conductive in the rest.

[0069] FIG. 3F refers to a device including DMOS power transistor cells with p-conductive body regions, n-conductive source zones 110 and an n-conductive drift region 121. Pn-junctions formed between the body regions 115 and the drift region 121 may be adjusted to the transition between the gate dielectric 242 and the second portions 240b of the field dielectric. Formation of the source zones 110 may be combined with the formation of source/drain zones 110 of lateral transistor cells in the logic area 620. Third portions 240c of the field dielectric in the logic area 620 may form field dielectrics of high-voltage transistors, by way of example.

[0070] The masked implant of the oxidation rate promoting material 411 avoids ancillary spacers above the second trenches 192 and reduces the residence time for the HFB etch significantly with respect to the comparative example illustrated in FIGS. 2A to 2F. The shorter HFB avoids the formation of steps at edges of the first portions 240b of the field dielectric and also the formation of further ancillary spacers, which may be formed during the recess of the second fill material 155 along such edges.

[0071] FIG. 4A shows masks used in the method as described in FIGS. 3A to 3F. A first mask 702 exposes regu-

larly spaced parallel stripes, portions of which form the first and second trenches **191**, **192**. A second mask **704** exposes a first region where the first fill material is recessed and covers a second region, where the first fill material is not recessed. Portions of the stripe-shaped trenches covered by the second mask **704** are second trenches **192** and portions of the stripe shaped trenches exposed by the third mask **706** are first trenches **191**. A third mask **706** covers the first portions of the field dielectric layer and exposes regions where a thin gate dielectric replaces the field dielectric layer. An overlap of the third mask **706** with respect to termination trenches at the edges of a field of parallel stripe-shaped trenches is at least 250 nm such that the field dielectric transitions or edges are reliably spaced from the trench edges. Either the second or the third mask **704**, **706** may be used as the implant mask for the oxidation rate promoting implant.

[0072] FIG. 4B shows a vertical cross-section along line A-B-C-D in FIG. 4A. As shown on the right hand side, in transition trenches **193** between first and second trenches **191**, **192**, which form portions of the same stripe-shaped trench, only thin separation oxides **241c** are formed where both thick field dielectrics **240a** are formed and the first fill portions **195a** are recessed. When the third mask **706** for etching the field dielectric layer also shields the transition trench **193** against the implant of the oxidation rate promoting material, only the thin separation oxides **241c** are formed between the first fill material **165** and the second fill material **155** in the transition trenches **193**. With respect to break-through reliability a possible negative impact of the thin separation oxides **241c** may be at least partly compensated by the contiguous thick field dielectric along the trench sidewalls.

[0073] FIG. 5 refers to a semiconductor device **500** including transistor cells TC and manufactured by the method as described with regard to the previous Figures. The semiconductor device **500** may be or may include an IGFET (insulated gate field effect transistor), for example a MOSFET (metal oxide semiconductor FET) in the usual meaning including FETs with metal gates as well as FETs with non-metal gates, by way of example. Another embodiment may refer to an IGBT (insulated gate bipolar transistor). The semiconductor device **500** may integrate further signal processing circuits, e.g., logic circuits, driver circuits, sensor circuits and control circuits in a logic area **620** separated from a cell area **610** that includes the transistor cells TC. The semiconductor device **500** may integrate transistors in DMOS (diffusion metal oxide semiconductor) technology and CMOS (complementary metal-oxide semiconductor) technology and may be a smart FET, e.g. a smart low-side or high-side switch or a smart power IC (integrated circuit), e.g. a multi-channel switch or a CAN (controller area network) transceiver.

[0074] The semiconductor device **500** is based on a semiconductor body **100** from a single-crystalline semiconductor material such as silicon (Si), silicon carbide (SiC), germanium (Ge), a silicon germanium crystal (SiGe), gallium nitride (GaN), gallium arsenide (GaAs) or any other $A_{III}B_V$ semiconductor.

[0075] The semiconductor body **100** has a first surface **101** which may be approximately planar or which may be defined by a plane spanned by coplanar surface sections as well as a mainly planar second surface **102** parallel to the first surface **101**. A distance between the first and second surfaces **101**, **102** is selected to achieve a specified voltage blocking capability of the transistor cells TC and may be at least 40 μm , by way of example. In a plane perpendicular to the cross-section

plane, the semiconductor body **100** may have a rectangular shape with an edge length in the range of several millimeters.

[0076] The semiconductor body **100** includes a drift region **121** of a first conductivity type as well as a drain layer **130** of the first conductivity type between the drift region **121** and the second surface **102**.

[0077] A dopant concentration in the drift region **121** may gradually or in steps increase or decrease with increasing distance to the first surface **101** at least in portions of its vertical extension. According to other embodiments, the dopant concentration in the drift region **121** may be approximately uniform. A mean dopant concentration in the drift region **121** may be between $5\text{E}12\text{ cm}^{-3}$ and $1\text{E}15\text{ cm}^{-3}$, for example in a range from $5\text{E}13\text{ cm}^{-3}$ to $5\text{E}14\text{ cm}^{-3}$. The drift region **121** may include further doped zones of the first and/or second conductivity type.

[0078] A dopant concentration in the drain layer **130** along the second surface **102** is sufficiently high to form an ohmic contact with a metal directly adjoining the second surface **102**. In case the semiconductor body **100** is based on silicon Si, along the second surface **102** a dopant concentration in an n-conductive drain layer **130** may be at least $1\text{E}18\text{ cm}^{-3}$, for example at least $5\text{E}19\text{ cm}^{-3}$ and in a p-conductive drain layer **130** at least $1\text{E}16\text{ cm}^{-3}$, for example at least $5\text{E}17\text{ cm}^{-3}$.

[0079] A field stop layer **128** of the first conductivity type may separate the drift region **121** from the drain layer **130**, wherein a mean dopant concentration in the field stop layer **128** may be at least five times as high as a mean impurity concentration in the drift region **121** and at most one-fifth of a maximum impurity concentration in the drain layer **130**.

[0080] Field electrode structures **160** and gate structures **150** extend from the first surface **101** into the semiconductor body **100** in the cell area **610**. The gate structures **150** include gate electrodes **155** in top portions oriented to the first surface **101** and field electrodes **165** in bottom portions oriented to the second surface **102**. The field electrode structures **160** include field electrodes **165** but do not contain gate electrodes **155**. Thick field dielectrics **240a**, **240b** separate the field electrodes **165** from the surrounding semiconductor material of the semiconductor body **100**. A thin gate dielectric **242** separates the gate electrodes **155** from the semiconductor material of the semiconductor body **100**.

[0081] A thick separation oxide **241a** separates the gate electrodes **155** from the field electrodes **165**. A thin separation oxide **241b** from the same material as the thick separation oxide **241a** may be formed on a surface of the field electrodes **165** in the field electrode structures **160**. The separation oxides **341a**, **241b** are silicon oxides thermally grown on a polycrystalline substrate. A vertical extension of the thick separation oxide **241a** exceeds at least twice the vertical extension of the thin separation oxide **241b**. According to an embodiment, the maximum vertical extension of the thick separation oxide **241a** is at least five times as large as the vertical extension of the thin separation oxide **241b**.

[0082] The field dielectrics **240a**, **240b** may be conformal layers of grown semiconductor oxide, for example grown silicon oxide in case the semiconductor body **100** is made from single crystalline silicon. According to other embodiments, the field dielectrics **240a**, **240b** may include a silicon nitride layer or a silicon oxide resulting from a deposition process.

[0083] The gate dielectric **242** is thermally grown semiconductor oxide, for example thermally grown silicon oxide. The

separation oxide **241** is a semiconductor oxide thermally grown on the material of the field electrodes **165**. Gate and field electrodes **155**, **165** consist of or contain heavily doped polycrystalline silicon.

[0084] In mesa portions of the semiconductor body **100** between the gate structures **150** and field electrode structures **160**, doped source zones **110** of the first conductivity type may directly adjoin the first surface **101**. Body zones **115** of the second conductivity type form first pn-junctions with the source zones **110** and second pn-junctions with the drift region **121**. The body zones **115** separate the source zones **110** from the drift region **121**. Outside the semiconductor body **100** an interlayer dielectric **245** separates the gate electrodes **155** from a first load electrode **310**. The interlayer dielectric **245** may include one or more dielectric layers from silicon oxide, silicon nitride, silicon oxynitride, doped or undoped silicon glass, for example BSG (boron silicate glass), PSG (phosphorus silicate glass) or BPSG (boron phosphorus silicate glass), by way of example.

[0085] The interlayer dielectric **245** is a homogeneous or layered conformal structure with uniform cross-section above the gate structures **150** and above the field electrode structures **160**.

[0086] The first load electrode **310** may form or may be electrically coupled or connected to a first load terminal, for example the source terminal S in case the transistor cells TC form an n-channel IGFET. Contact structures **315** extend through the interlayer dielectric **245** and electrically connect the first load electrode **310** with the body zones **115** and the source zones **110**.

[0087] A second load electrode **320**, which directly adjoins the second surface **102** and the drain layer **130**, may form or may be electrically connected to a second load terminal, which may be the drain terminal D in case the transistor cells TC form an n-channel IGFET.

[0088] Each of the first and second load electrodes **310**, **320** may consist of or contain, as main constituent(s), aluminum (Al), copper (Cu), or alloys of aluminum or copper, for example AlSi, AlCu or AlSiCu. According to other embodiments, at least one of the first and second load electrodes **310**, **320** may contain, as main constituent(s), nickel (Ni), titanium (Ti), tungsten (W), tantalum (Ta), vanadium (V), silver (Ag), gold (Au), platinum (Pt), and/or palladium (Pd). For example, at least one of the first and second load electrodes **310**, **320** may include two or more sub-layers, wherein each sub-layer contains one or more of Ni, Ti, V, Ag, Au, Pt, W, and Pd as main constituent(s), e.g., a silicide, a nitride and/or an alloy.

[0089] In the logic area **620** the semiconductor device **500** may include a signal processing circuit, for example a logic circuit, a sense circuit, a control circuit, or a driver circuit such as a gate driver circuit. The signal processing circuit may include lateral transistors TCL with planar gate electrodes **158** and shallow source/drain zones **111**, which may be formed contemporaneously with the source zones **110** in the cell area **610**, wherein the source zones **110** and the source/drain zones **111** may have the same vertical extension. The logic area **620** may further include high voltage transistors including further portions of the field dielectric used for decoupling low-doped lateral drain extensions.

[0090] Since no thick separation oxide is formed in the vertical projection of the field electrode structures **160**, no conductive spacer remnants that may result from the formation of the gate electrodes **155** and that may adversely affect device reliability appear in the interlayer dielectric **245**.

[0091] FIG. 6A refers to an electronic circuit **591** including a semiconductor device **500** as described in the previous figures. The semiconductor device **500** may be a smart FET usable as a low-side switch and including a power FET **505** and a signal processing circuit **506**. A drain terminal D is electrically connected to a drain electrode of the power FET **505** and may be connected to a load LD which may be a motor winding, a coil or a transformer winding, by way of example. The load LD is electrically arranged in series between the anode of a battery BAT and the drain terminal D. A source terminal S of the semiconductor device **500** is electrically connected to a source electrode of the power FET **505** and may be connected to a cathode of the battery BAT. Further power terminals Vdd, Gnd may provide the supply voltage for the internal signal processing circuit **506**. A gate control circuit **510** may be electrically connected to an input terminal IN and may supply a signal for controlling the switching cycle of the semiconductor device **500**.

[0092] The power FET **505** includes a microcell power transistor in a DMOS portion of the semiconductor device **500**. The signal processing circuit **506** includes transistors of another technology, e.g., CMOS transistors, low-voltage FETs, lateral high-voltage FETs and/or bipolar transistors in a further portion, e.g., a CMOS portion. The signal processing circuit **506** may provide overvoltage protection, ESD protection, current limitation, overload protection and/or short-circuit protection, by way of example. Other embodiments refer to smart high-side switches.

[0093] In the electronic circuit **592** of FIG. 6B the semiconductor device **500** is a monolithically integrated half-bridge circuit and includes two power FETs **505** and a signal processing circuit **506**. The source of the high-side switch is connected to a high-side output terminal OutH and the drain of the low-side switch is connected to a low-side output terminal OutL. A motor winding may be electrically arranged between the high-side output terminal OutH and the low-side output terminal OutL. The signal processing circuit **506** may provide pulse width modulation, gate driving, overvoltage protection, ESD protection, current limitation, overload protection and/or short-circuit protection, by way of example.

[0094] Although specific embodiments have been illustrated and described herein, it will be appreciated by those of ordinary skill in the art that a variety of alternate and/or equivalent implementations may be substituted for the specific embodiments shown and described without departing from the scope of the present invention. This application is intended to cover any adaptations or variations of the specific embodiments discussed herein. Therefore, it is intended that this invention be limited only by the claims and the equivalents thereof.

What is claimed is:

1. A method of manufacturing a semiconductor device, the method comprising:

filling a first trench and a second trench, which extend from a main surface into a semiconductor layer, with a first fill material and selectively recessing the first fill material in the first trench;

forming a mask covering the second trench and exposing the first trench;

implanting an oxidation rate promoting material into an exposed first section of the recessed fill material in the first trench; and

thermally oxidizing, after removing the mask, the first fill material, wherein on the first section an oxidation rate is at least twice as high as on non-implanted sections of the first fill material.

2. The method of claim **1**, further comprising: forming, by thermal oxidation and before forming the mask, a field dielectric layer lining the first and second trenches and covering the first surface.

3. The method of claim **2**, further comprising: removing a section of the field dielectric layer exposed by the mask.

4. The method of claim **3**, further comprising: a cleaning etch using a buffered aqueous solution of hydrogen fluoride, the cleaning etching being performed after removing a section of the field dielectric layer and before oxidizing the recessed first fill material.

5. The method of claim **2**, further comprising: implanting, before forming the mask, an oxide damaging material into the field dielectric layer, wherein the oxide damaging material does not affect oxide growth on the first fill material.

6. The method of claim **5**, wherein the oxide damaging material comprises argon atoms.

7. The method of claim **1**, wherein a gate dielectric is formed on exposed sidewall portions of the first trench during thermally oxidizing the recessed first fill material in the first trench.

8. The method of claim **1**, further comprising: depositing and recessing, after thermally oxidizing the recessed first fill material, a second fill material in the first trench.

9. The method of claim **8**, further comprising: forming, after recessing the second fill material, gate electrodes of signal processing circuits in a logic area outside a cell area that comprises the first and second trenches.

10. The method of claim **1**, wherein a plurality of the first and second trenches are formed, respectively.

11. The method of claim **10**, wherein the first trenches are central portions of stripe-shaped trenches and end portions of the stripe-shaped trenches are second trenches.

12. The method of claim **10**, further comprising: forming, in mesa sections of the semiconductor layer between neighboring first trenches, source zones adjoining the main surface and body zones forming first pn junctions with the source zones.

13. The method of claim **1**, wherein thermally oxidizing the first fill material forms a thin separation oxide of grown silicon oxide on the non-im-

planted sections of the first fill material in the second trenches and a thick separation oxide of grown silicon oxide on the implanted first section of the first fill material in the first trench, wherein a vertical extension of the thin separation oxide is smaller than a vertical extension of the thick separation oxide.

14. The method of claim **1**, further comprising: forming, after thermally oxidizing the first fill material an interlayer dielectric on the main surface, wherein the interlayer dielectric has a uniform homogenous or layered configuration in a cell area comprising the first and second trenches.

15. The method of claim **14**, wherein the interlayer dielectric is devoid of thermally grown silicon oxide.

16. A semiconductor device comprising: field electrode structures extending from a first surface into a semiconductor body and comprising field electrodes; gate structures extending from the first surface into the semiconductor body and comprising field electrodes and gate electrodes between the field electrodes and the first surface;

a thin separation oxide of grown silicon oxide on the field electrodes of the field electrode structures; and

a thick separation oxide of grown silicon oxide separating the gate and field electrodes of the gate structures, wherein a vertical extension of the thick separation oxide is greater than a vertical extension of the thin separation oxide.

17. The semiconductor device of claim **16**, wherein the thick separation oxide is at least twice as thick as the thin separation oxide.

18. The semiconductor device of claim **16**, further comprising: lateral transistors comprising planar gate electrodes.

19. An electronic circuit comprising a semiconductor device, the semiconductor device comprising:

field electrode structures extending from a first surface into a semiconductor body and comprising field electrodes; gate structures extending from the first surface into the semiconductor body and comprising field electrodes and gate electrodes between the field electrodes and the first surface;

a thin separation oxide of grown silicon oxide on the field electrodes of the field electrode structures; and

a thick separation oxide of grown silicon oxide separating the gate and field electrodes of the gate structures, wherein a vertical extension of the thick separation oxide is greater than a vertical extension of the thin separation oxide.

* * * * *