



(19) **United States**

(12) **Patent Application Publication**

**Gazda et al.**

(10) **Pub. No.: US 2021/0359289 A1**

(43) **Pub. Date: Nov. 18, 2021**

(54) **PROTECTIVE LAYER INCLUDING TIN FLUORIDE DISPOSED ON A LITHIUM ANODE IN A LITHIUM-SULFUR BATTERY**

103, filed on Nov. 30, 2019, provisional application No. 62/926,225, filed on Oct. 25, 2019, provisional application No. 63/179,106, filed on Apr. 23, 2021.

(71) Applicant: **Lyten, Inc.**, San Jose, CA (US)

(72) Inventors: **Jerzy Gazda**, Austin, TX (US); **Qianwen Huang**, San Jose, CA (US); **Elena Rogojina**, San Jose, CA (US); **You Li**, Sunnyvale, CA (US); **Jesse Baucom**, Sunnyvale, CA (US); **Jeffrey Bell**, Santa Clara, CA (US); **John Thorne**, Sunnyvale, CA (US); **Anurag Kumar**, Sunnyvale, CA (US); **Jingning Shan**, San Jose, CA (US)

(73) Assignee: **Lyten, Inc.**, San Jose, CA (US)

(21) Appl. No.: **17/383,793**

(22) Filed: **Jul. 23, 2021**

**Publication Classification**


(51) **Int. Cl.**  
*H01M 4/133* (2006.01)  
*H01M 10/0525* (2006.01)  
*H01M 4/62* (2006.01)  
*H01M 4/1393* (2006.01)  
*H01M 4/583* (2006.01)  
(52) **U.S. Cl.**  
CPC ..... *H01M 4/133* (2013.01); *H01M 10/0525* (2013.01); *H01M 4/583* (2013.01); *H01M 4/1393* (2013.01); *H01M 4/621* (2013.01)

**Related U.S. Application Data**

(63) Continuation-in-part of application No. 17/236,291, filed on Apr. 21, 2021, which is a continuation-in-part of application No. 17/209,038, filed on Mar. 22, 2021, which is a continuation-in-part of application No. 16/942,229, filed on Jul. 29, 2020, now Pat. No. 11,127,941, which is a continuation-in-part of application No. 16/785,020, filed on Feb. 7, 2020, which is a continuation-in-part of application No. 16/785,076, filed on Feb. 7, 2020.  
(60) Provisional application No. 63/018,930, filed on May 1, 2020, provisional application No. 63/019,145, filed on May 1, 2020, provisional application No. 62/942,

(57) **ABSTRACT**

A battery is disclosed that includes an anode, a graded interface layer disposed on the anode, a cathode positioned opposite to the anode, an electrolyte, and a separator. The anode may output lithium ions during cycling of the battery. A graded interface layer may be disposed on the anode and include a tin fluoride layer. A tin-lithium alloy region may form between the tin fluoride layer and the anode. The tin-lithium alloy region may produce a lithium fluoride uniformly dispersed between the anode and the tin fluoride layer during operational cycling of the battery. The electrolyte may disperse throughout the cathode and the anode. The separator may be positioned between the anode and cathode. In some aspects, the battery may also include lithium electrodeposited on one or more exposed surfaces of the anode.






Figure 1






Figure 3




Figure 4




Figure 5




Figure 6




Figure 7




Figure 8A




Figure 8B




Figure 8C

800D




Figure 8D




Figure 9B




Figure 9A

1050 ↗




Figure 10B

1000 ↗




Figure 10A




Figure 11




Figure 12




Figure 13





Figure 14

1500 ↘



1510 ↘




Figure 15




Figure 16




Figure 17

1800 ↗






Figure 18



1900 ↘



1910 ↘



*Figure 19*



*Figure 20*




Figure 21

**PROTECTIVE LAYER INCLUDING TIN  
FLUORIDE DISPOSED ON A LITHIUM  
ANODE IN A LITHIUM-SULFUR BATTERY**

**CROSS-REFERENCE TO RELATED  
APPLICATIONS**

**[0001]** This Patent Application is a continuation-in-part application and claims priority to U.S. patent application Ser. No. 17/236,291 entitled “TERNARY SOLVENT PACKAGE FOR LITHIUM-SULFUR BATTERIES” filed on Apr. 21, 2021, which claims priority to U.S. Provisional Patent Application No. 63/019,145, entitled “RUBBER VULCANIZATION ACCELERATORS AS ELECTROLYTE ADDITIVES” filed on May 1, 2020, and to U.S. Provisional Patent Application No. 63/018,930, entitled “PREVENTING POLYSULFIDE MIGRATION” filed on May 1, 2020, and is a continuation-in-part application and claims priority to U.S. patent application Ser. No. 17/209,038 entitled “CARBON COMPOSITE ANODE WITH EX-SITU ELECTRODEPOSITED LITHIUM” filed on Mar. 22, 2021, which is a continuation-in-part application of and claims priority to U.S. patent application Ser. No. 16/942,229 entitled “CARBON-BASED STRUCTURES FOR INCORPORATION INTO LITHIUM (LI) ION BATTERY ELECTRODES” filed on Jul. 29, 2020, which is a continuation-in-part application of and claims priority to U.S. patent application Ser. No. 16/785,020 entitled “3D SELF-ASSEMBLED MULTI-MODAL CARBON BASED PARTICLE” filed on Feb. 7, 2020 and to U.S. patent application Ser. No. 16/785,076 entitled “3D SELF-ASSEMBLED MULTI-MODAL CARBON BASED PARTICLES INTEGRATED INTO A CONTINUOUS FILM LAYER” filed on Feb. 7, 2020, both of which claim priority to U.S. Provisional Patent Application No. 62/942,103 entitled “3D HIERARCHICAL MESOPOROUS CARBON-BASED PARTICLES INTEGRATED INTO A CONTINUOUS ELECTRODE FILM LAYER” filed on Nov. 30, 2019 and to U.S. Provisional Patent Application No. 62/926,225 entitled “3D HIERARCHICAL MESOPOROUS CARBON-BASED PARTICLES INTEGRATED INTO A CONTINUOUS ELECTRODE FILM LAYER” filed on Oct. 25, 2019, all of which are assigned to the assignee hereof. This Patent Application also claims the benefit of priority to U.S. Provisional Patent Application No. 63/179,106, entitled “LI-S BATTERY LI-PROTECTIVE LAYER FOR LONG TERM STABLE ANODES” filed on Apr. 23, 2021, which is assigned to the assignee hereof. The disclosures of all prior Applications are considered part of and are incorporated by reference in this Patent Application in their respective entireties.

**TECHNICAL FIELD**

**[0002]** This disclosure relates generally to batteries, and, more particularly, to lithium-ion batteries that can compensate for operational cycle losses.

**DESCRIPTION OF RELATED ART**

**[0003]** Recent developments in batteries allow consumers to use electronic devices in many new applications. However, further improvements in battery technology are desirable.

**SUMMARY**

**[0004]** This Summary is provided to introduce in a simplified form a selection of concepts that are further described below in the Detailed Description. This Summary is not intended to identify key features or essential features of the claimed subject matter, nor is it intended to limit the scope of the claimed subject matter.

**[0005]** One innovative aspect of the subject matter described in this disclosure may be implemented as a battery include an anode, a cathode, a protective sheath disposed on the cathode, a separator, and an electrolyte. The anode may be arranged in a lattice configuration and include carbonaceous materials. The cathode may be positioned opposite to the anode. The separator may be disposed between the anode and cathode. The protective sheath disposed on the cathode may include a tri-functional epoxy compound and a diamine oligomer-based compound, both of which may chemically react with each other. In this way, the protective sheath may prevent polysulfide migration within the battery based on chemical binding between the protective sheath and one or more lithium-containing polysulfide intermediates. The electrolyte may disperse within the cathode and contact the anode.

**[0006]** In one implementation, a polymeric network may be deposited over one or more exposed surfaces of the anode. The polymeric network may have fluorinated polymer chains grafted with carbonaceous materials and be cross-linked with each another. In this way, the polymeric network may retain an alkali-metal containing fluoride, which in turn may suppress alkali metal dendrite formation associated with the anode.

**[0007]** In various implementations, cracks may extend into the cathode, where protective sheath may disperse throughout the one or more cracks. In this way, the protective sheath may be arranged to reduce a susceptibility of the cathode to rupturing. In one implementation, the protective sheath has a cross-linked, three-dimensional structure based on the tri-functional epoxy compound and the di-amine oligomer-based compound. In some examples, the tri-functional epoxy compound is one or more of trimethylolpropane triglycidyl ether (TMPTE), tris(4-hydroxyphenyl) methane triglycidyl ether, or tris(2,3-epoxypropyl) isocyanurate, and the di-amine oligomer-based compound is one or more of dihydrazide sulfoxide (DHSO) or JEFFAMINE® D-230 polyetheramine. In addition, or the alternative, the protective sheath may include trimethylolpropane tris [poly(propylene glycol) and amine terminated ether.

**[0008]** In some implementations, the carbonaceous materials may include flat graphene, wrinkled graphene, a plurality of carbon nano-tubes (CNTs), and/or a plurality of carbon nano-onions (CNOs). In one implementation, the cathode may include a host structure with one or more of flat graphene, wrinkled graphene, carbon nanotubes (CNTs), or carbon nano-onions (CNOs), where the anode includes a solid lithium metal layer.

**[0009]** In one implementation, a tin fluoride layer may be disposed on the anode, and a lithium fluoride layer may be formed between the tin fluoride layer and the anode. The lithium fluoride layer may be associated with chemical reactions between fluorine ions and lithium ions. In this way, the lithium fluoride layer may inhibit lithium-containing dendritic growth from the anode. In some aspects, a solid-electrolyte interphase may be disposed on the anode. The solid-electrolyte interphase may include tin, manganese,

molybdenum, fluorine compounds, tin fluoride, manganese fluoride, silicon nitride, lithium nitride, lithium nitrate, lithium phosphate, manganese oxide, and/or lithium lanthanum zirconium oxide (LLZO).

[0010] Details of one or more implementations of the subject matter described in this disclosure are set forth in the accompanying drawings and the description below. Other features, aspects, and advantages will become apparent from the description, the drawings, and the claims. Note that the relative dimensions of the following figures may not be drawn to scale.

#### BRIEF DESCRIPTION OF THE DRAWINGS

[0011] FIG. 1 shows a diagram depicting an example battery, according to some implementations.

[0012] FIG. 2 shows a diagram depicting another example battery, according to some implementations.

[0013] FIG. 3 shows a diagram of an example electrode of a battery, according to some implementations.

[0014] FIG. 4 shows a diagram a diagram of a portion of an example battery that includes a protective lattice, according to some implementations.

[0015] FIG. 5 shows a diagram of an anode structure including a tin fluoride ( $\text{SnF}_2$ ) layer, according to some implementations.

[0016] FIG. 6 shows a diagram of an enlarged portion of the anode structure of FIG. 5, according to some implementations.

[0017] FIG. 7 shows a diagram of a polymeric network of a battery, according to some implementations.

[0018] FIG. 8A shows a diagram of an example carbonaceous particle with graded porosity, according to some implementations.

[0019] FIG. 8B shows a diagram of an example of a tri-zone particle, according to some implementations.

[0020] FIG. 8C shows an example step function representative of the tri-zone particle of FIG. 8B, according to some implementations.

[0021] FIG. 8D shows a graph depicting an example distribution of pore volume versus pore width of an example carbonaceous particle, according to some implementations.

[0022] FIGS. 9A and 9B show electron micrographs of example carbonaceous particles, aggregates, and/or agglomerates depicted in FIG. 8A and/or FIG. 8B, according to some implementations.

[0023] FIGS. 10A and 10B show transmission electron microscope (TEM) images of carbonaceous particles treated with carbon dioxide ( $\text{CO}_2$ ), according to some implementations.

[0024] FIG. 11 shows a diagram depicting carbon porosity types prevalent in the anodes and/or the cathodes of the present disclosure, according to some implementations.

[0025] FIG. 12 shows a graph depicting cumulative pore volume versus pore width for micropores and mesopores dispersed throughout the anode or cathode of a battery, according to some implementations.

[0026] FIG. 13 shows graphs depicting battery performance per cycle number, according to some implementations.

[0027] FIG. 14 shows a bar chart depicting capacity per cycle number, according to some implementations.

[0028] FIG. 15 shows graphs depicting battery performance per cycle number, according to some implementations.

[0029] FIG. 16 shows a graph depicting battery discharge capacity per cycle number, according to some implementations.

[0030] FIG. 17 shows a graph depicting battery discharge capacity per cycle number, according to some implementations.

[0031] FIG. 18 shows a graph depicting battery specific discharge capacity for various TB T-containing electrolyte mixtures, according to some implementations.

[0032] FIG. 19 shows graphs depicting battery specific discharge capacity per cycle number for the battery of FIG. 1, according to some implementations.

[0033] FIG. 20 shows graphs depicting battery specific discharge capacity and discharge capacity retention per cycle number for the battery of FIG. 2, according to other implementations.

[0034] FIG. 21 shows graphs depicting battery specific discharge capacity and discharge capacity retention per cycle number for the battery of FIG. 2, according to some other implementations.

[0035] Like reference numbers and designations in the various drawings indicate like elements.

#### DETAILED DESCRIPTION

[0036] The following description is directed to some example implementations for the purposes of describing innovative aspects of this disclosure. However, a person having ordinary skill in the art will readily recognize that the teachings herein can be applied in a multitude of different ways. The described implementations can be implemented in any type of electrochemical cell, battery, or battery pack, and can be used to compensate for various performance related deficiencies. As such, the disclosed implementations are not to be limited by the examples provided herein, but rather encompass all implementations contemplated by the attached claims. Additionally, well-known elements of the disclosure will not be described in detail or will be omitted so as not to obscure the relevant details of the disclosure.

[0037] Batteries typically include several electrochemical cells that can be connected to each other to provide electric power to a wide variety of devices such as (but not limited to) mobile phones, laptops, electric vehicles (EVs), factories, and buildings. Certain types of batteries, such as lithium-ion or lithium-sulfur batteries, may be limited in performance by the type of electrolyte used or by uncontrolled battery side reactions. As a result, optimization of the electrolyte may improve the cyclability, the specific discharge capacity, the discharge capacity retention, the safety, and the lifespan of a respective battery. For example, in an unused or “fresh” battery, lithium ions are transported freely from the anode to the cathode upon activation and later during initial and subsequent discharge cycles. Then, during battery charge cycles, lithium ions may be forced to migrate back from their electrochemically favored positions in the cathode to the anode, where they are stored for subsequent use. This cyclical discharge-charge process associated with rechargeable batteries can result in the generation of undesirable chemical species that can interfere with the transport of lithium ions to and from the cathode during respective discharge and charge of the battery. Specifically, lithium-containing polysulfide intermediate species (referred to herein as “polysulfides”) are generated when lithium ions interact with elemental sulfur (or, in some configurations, lithium sulfide,  $\text{Li}_2\text{S}$ ) present in the cathode. These polysulf-

rides are soluble in the electrolyte and, as a result, diffuse throughout the battery during operational cycling, thereby resulting in loss of active material from cathode. Generation of excessive concentration levels of polysulfides can result in unwanted battery capacity decay and cell failure during operational cycling, potentially reducing the driving range for electric vehicles (EVs) and increasing the frequency with which such EVs need recharging.

**[0038]** In some cases, polysulfides participate in the formation of inorganic layers in a solid electrolyte interphase (SEI) provided in the battery. In one example, the anode may be protected by a stable inorganic layer formed in the electrolyte and containing 0.020 M  $\text{Li}_2\text{S}_5$  (0.10 M sulfur) and 5.0 wt %  $\text{LiNO}_3$ . The anode with a lithium fluoride and polysulfides ( $\text{LiF-Li}_2\text{S}_x$ ) may enrich the SEI and result in a stable Coulombic efficiency of 95% after 233 cycles for Li—Cu half cells, while preventing formation of lithium dendrites or other uncontrolled lithium growths that can extend from the anode to the cathode and result in a failed or ruptured cell. However, when polysulfides are generated at certain concentrations (such as greater than 0.50 M sulfur), formation of the SEI may be hindered. As a result, lithium metal from the anode may be undesirably etched, creating a rough and imperfect surface exposed to the electrolyte. This unwanted deterioration (etching) of the anode due to a relatively high concentration of polysulfides may indicate that polysulfide dissolution and diffusion may be limiting battery performance.

**[0039]** In some implementations, the porosity of a carbonaceous cathode may be adjusted to achieve a desired balance between maximizing energy density and inhibiting the migration of polysulfides into and/or throughout the battery's electrolyte. As used herein, carbonaceous may refer to materials containing or formed of one or more types or configuration of carbon. For example, cathode porosity may be higher in sulfur and carbon composite cathodes than in conventional lithium-ion battery electrodes. Denser electrodes with relatively low porosity may minimize electrolyte intake, parasitic weight, and cost. Sulfur utilization may be limited by the solubility of polysulfides and conversion from those polysulfides into lithium sulfide ( $\text{Li}_2\text{S}$ ). The conversion of polysulfides into lithium sulfide may be based on the accessible surface area of the cathode. Aspects of the present disclosure recognize that cathode porosity may be adjusted based on electrolyte constituent materials to maximize battery volumetric energy density. In addition, or in the alternative, one or more protective layers or regions can be added to surfaces of the cathode and/or the anode exposed to the electrolyte to adjust cathode porosity levels. In some aspects, these protective layers or regions can inhibit the undesirable migration of polysulfides throughout the battery.

**[0040]** Various aspects of the subject matter disclosed herein relate to a lithium-sulfur battery including a liquid-phase electrolyte, which may include a ternary solvent package and one or more additives. In some implementations, the lithium-sulfur battery may include a cathode, an anode positioned opposite to the cathode, and an electrolyte. The cathode may include several regions, where each region may be defined by two or more carbonaceous structures adjacent to and in contact with each other. In some instances, the electrolyte may be interspersed throughout the cathode and in contact with the anode. In some aspects, the electrolyte may include a ternary solvent package and 4,4'-thiobis-

benzenethiol (TBT). In other instances, the electrolyte may include the ternary solvent package and 2-mercaptobenzothiazole (MBT).

**[0041]** In various implementations, the ternary solvent package may include 1,2-Dimethoxyethane (DME), 1,3-Dioxolane (DOL), tetraethylene glycol dimethyl ether (TEGDME) and one or more additives, which may include a lithium nitrate ( $\text{LiNO}_3$ ), all which may be in a liquid-phase. In some implementations, the ternary solvent package may be prepared by mixing approximately 5,800 microliters ( $\mu\text{L}$ ) of DME, 2,900 microliters ( $\mu\text{L}$ ) of DOL, and 1,300 microliters ( $\mu\text{L}$ ) of TEGDME with one another to create a mixture. Approximately 0.01 mol of lithium bis(trifluoromethanesulfonyl)imide ( $\text{LiTFSI}$ ) may be dissolved into the ternary solvent package to produce an approximate dilution level of 1 M  $\text{LiTFSI}$  in DME:DOL:TEGDME at a volume ratio of 2:1:1 including approximately 2 weight percent (wt. %) lithium nitrate. In other implementations, the ternary solvent package may be prepared with 2,000 microliters ( $\mu\text{L}$ ) of DME, 8,000 microliters ( $\mu\text{L}$ ) of DOL, and 2,000 microliters ( $\mu\text{L}$ ) of TEGDME and include approximately 0.01 mol of dissolved lithium bis(trifluoromethanesulfonyl)imide ( $\text{LiTFSI}$ ). In some aspects, the ternary solvent package may be prepared at a first approximate dilution level of 1 molar (M)  $\text{LiTFSI}$  in a mixture of DME:DOL:TEGDME. In other instances, the ternary solvent package may be prepared at a second approximate dilution level of approximately 1 M  $\text{LiTFSI}$  in DME:DOL:TEGDME at an approximate volume ratio of 1:4:1 and include either an addition of 5M TBT solution or an addition of 5M MBT solution, or an addition of other additives and/or chemical substances.

**[0042]** In various implementations, each carbonaceous structure may include a relatively high-density outer shell region and a relatively low-density core region. In some aspects, the core region may be formed within an interior portion of the outer shell region. The outer shell region may have a carbon density between approximately 1.0 grams per cubic centimeter (g/cc) and 3.5 g/cc. The core region may have a carbon density of between approximately 0.0 g/cc and 1.0 g/cc or some other range lower than the first carbon density. In other implementations, each carbonaceous structure may include an outer shell region and core region having the same or similar densities, for example, such that the carbonaceous structure does not include a graded porosity.

**[0043]** Various regions of the cathode may include microporous channels, mesoporous channels, and macroporous channels interconnected to each other to form a porous network extending from the outer shell region to the core region. For example, in some aspects, the porous network may include pores that each have a principal dimension of approximately 1.5 nm.

**[0044]** In some implementations, one or more portions of the porous network may temporarily micro-confine electroactive materials such as (but not limited to) elemental sulfur within the cathode, which may increase battery specific capacity by complexing with lithium ions. In some aspects, the ternary solvent package may have a tunable polarity, a tunable solubility, and be capable of transporting lithium ions. In addition, the ternary solvent package may at least temporarily suspend polysulfides (PS) during charge-discharge cycles of the battery.

[0045] Particular implementations of the subject matter described in this disclosure can be implemented to realize one or more potential advantages. In some implementations, the porous network formed by the interconnection of microporous, mesoporous, and macroporous channels within the cathode may include a plurality of pores having a multitude of different pore sizes. In some implementations, the plurality of pores may include micropores having a pore size less than approximately 2 nm, may include mesopores having a pore size between approximately 5 and 50 nm, and may include macropores having a pore size greater than approximately 50 nm. The micropores, mesopores, and macropores may collectively mitigate the undesirable migration or diffusion of polysulfides throughout the electrolyte. Since the poly sulfide shuttle effect may result in the loss of active material from the cathode, the ability to mitigate or reduce the polysulfide shuttle effect can increase battery performance.

[0046] In one implementation, the micropores may have a pore size of approximately 1.5 nm selected to micro-confine elemental sulfur ( $S_8$ , or smaller chains/fragments of sulfur, for example in the form of  $S_2$ ,  $S_4$  or  $S_6$ ) pre-loaded into the cathode. The micro-confinement of elemental sulfur within the cathode may allow TBT or MBT complexes generated during battery cycling to inhibit the migration of long-chain poly sulfides within the mesopores of the cathode. Accumulation of these long-chain polysulfides within the mesopores of the cathode may cause the cathode to volumetrically expand to retain the polysulfides and thereby reduce the polysulfide shuttle effect. Accordingly, lithium ions may continue to transport freely between the anode and the cathode via the electrolyte without being blocked or impeded by the polysulfides. The free movement of lithium ions throughout the electrolyte without interference by polysulfides can increase battery performance.

[0047] In addition, or the alternative, one or more protective layers, sheaths, films, and/or regions (collectively referred to herein as “protective layers”) may be disposed on the anode and/or the cathode and/or the separator and in contact with the electrolyte. The protective layers may include materials capable of binding with polysulfides to impede polysulfide migration and prevent lithium dendrite formation. In some aspects, the protective layers may be arranged in different configurations and used with any of the electrolyte chemistries and/or compositions disclosed herein, which in turn may result in complete tunability of the battery.

[0048] In one implementation, carbonaceous materials may be grafted with fluorinated polymer chains and deposited on one or more exposed surfaces of the anode. The fluorinated polymer chains can be cross-linked into a polymeric network on contact with Lithium metal from the anode surface via the Wurtz reaction. The cross-linked polymeric network formation may, in turn, suppress Lithium metal dendrite formation associated with the anode, and may also generate Lithium fluoride. Fluorinated polymers within the polymeric network may participate in chemical reactions during battery operational cycling to yield Lithium fluoride. Formation of the lithium fluoride may involve the chemical binding of lithium ions from the electrolyte with fluorine ions.

[0049] In addition, or the alternative, the polymeric network may be combined with any of the electrolyte chemistries and/or compositions disclosed herein and/or a protec-

tive sheath disposed on the cathode. In one implementation, the protective sheath can be formed by combining compounds containing di-functional, or higher functionality Epoxy and Amine or Amide compounds. Their intermolecular cross-linking would result in formation of 3D network with high chemical resistance to dissolution in electrolyte. Composition, for example, may include a tri-functional epoxy compound and a di-amine oligomer-based compound, which may react with each other to produce a protective lattice that can bind to polysulfides generated in the cathode and prevent their migration or diffusion into the electrolyte. In addition, the protective lattice may diffuse through one or more cracks that may form in the cathode due to battery cycling. The protective lattice, when diffused throughout such cracks formed in the cathode, may increase the structural integrity of the cathode and reduce potential rupture of the cathode associated with volumetric expansion.

[0050] In various implementations, one or more of the disclosed battery components may be combined with a conformal coating disposed on edges or surfaces of the anode exposed to the electrolyte. In some implementations, the conformal coating may include a graded interface layer that may replace the polymeric network. In some aspects, the graded interface layer may include a tin fluoride layer and a tin-lithium alloy region formed between the tin fluoride layer and the anode. The tin-lithium alloy region may form a layer of lithium fluoride uniformly dispersed between the anode and the tin-fluoride layer in response to operational cycling of the battery.

[0051] In various implementations, a lithium-sulfur battery employing various aspects of the present disclosure may include an electroactive material extracted from an external source, e.g., a subterranean source and/or an extraterrestrial subterranean source. In such implementations, the cathode may be prepared as a sulfur-free cathode including functional pores that may microconfine the electroactive material within the cathode. In some aspects, the cathode may include aggregates including a multitude of carbonaceous particles joined together, and may include agglomerates including a multitude of the aggregates joined together. In one implementation, the carbonaceous materials used to form the cathode (and/or the anode) may be tuned to define unique pore sizes, size ranges, and volumes. In some implementations, the carbonaceous particles may include non-tri-zone particles with and without tri-zone particles. In other implementations, the carbonaceous particles may not include tri-zone particles. Each tri-zone particle may include micropores, mesopores, and macropores, and both the non-tri-zone and tri-zone particles may each have a principal dimension in an approximate range of 20 nm to 300 nm. Each of the carbonaceous particles may include carbonaceous fragments nested within each other and separated from immediate adjacent carbonaceous fragments by mesopores. In some aspects, each of the carbonaceous particles may have a deformable perimeter that changes in shape and coalesces with adjacent materials.

[0052] Some of the pores may be distributed throughout the plurality of carbonaceous fragments and/or the deformable perimeters of the carbonaceous particles. In various implementations, mesopores may be interspersed throughout the aggregates, and macropores may be interspersed throughout the plurality of agglomerates. In one implementation, each mesopore may have a principal dimension between 3.3 nanometers (nm) and 19.3 nm, each aggregate

may have a principal dimension in an approximate range between 10 nm and 10 micrometers ( $\mu\text{m}$ ), and each agglomerate may have a principal dimension in an approximate range between 0.1  $\mu\text{m}$  and 1,000  $\mu\text{m}$ . As further described below, specific combinations of pore sizes matched with unique electrolyte formulations and protective layers can be used to reduce or mitigate the harmful effects of unwanted polysulfide diffusion, which may further increase battery performance.

[0053] FIG. 1 shows an example battery 100, according to some implementations. The battery 100 may be a lithium-sulfur electrochemical cell, a lithium-ion battery, or a lithium-sulfur battery. The battery 100 may have a body 105 that includes a first substrate 101, a second substrate 102, a cathode 110, an anode 120 positioned opposite to the cathode 110, and an electrolyte 130. In some aspects, the first substrate 101 may function as a current collector for the anode 120, and the second substrate 102 may function as a current collector for the cathode 110. The cathode 110 may include a first thin film 111 deposited onto the second substrate 102, and may include a second thin film 112 deposited onto the first thin film 111. In some implementations, the electrolyte 130 may be a liquid-phase electrolyte including one or more additives such as lithium nitrate, tin fluoride, lithium iodide, lithium bis(oxalate)borate (LiBOB), cesium nitrate, cesium fluoride, ionic liquids, lithium fluoride, fluorinated ether, TBT, MBT, DPT and/or the like. Suitable solvent packages for these example additives may include various dilution ratios, including 1:1:1 of 1,3-dioxolane (DOL), 1,2-dimethoxyethane, (DME), tetraethylene glycol dimethyl ether (TEGDME), and/or the like.

[0054] Although not shown for simplicity, in one implementation, a lithium layer may be electrodeposited on one or more exposed carbon surfaces of the anode 120. In some instances, the lithium layer may include elemental lithium provided by the ex-situ electrodeposition of lithium onto exposed surfaces of the anode 120. In some aspects, the lithium layer may include lithium, calcium, potassium, magnesium, sodium, and/or cesium, where each metal may be ex-situ deposited onto exposed carbon surfaces of the anode 120. The lithium layer may provide lithium ions available for transport to-and-from the cathode 110 during operational cycling of the battery 100. As a result, the battery 100 may not need an additional lithium source for operation. Instead of using lithium sulfide, elemental sulfur ( $\text{S}_8$ ) may be pre-loaded in various pores or porous networks formed in the cathode 110. During operational cycling of the battery, the elemental sulfur may form lithium-sulfur complexes that can microconfine (at least temporarily) greater amounts of lithium than conventional cathode designs. As a result, the battery 100 may outperform batteries that rely on such conventional cathode designs.

[0055] In various implementations, the lithium layer may dissociate and/or separate into lithium ions 125 and electrons 174 during a discharge cycle of the battery 100. The lithium ions 125 may migrate from the anode 120 towards the cathode 110 through the electrolyte 130 to their electrochemically favored positions within the cathode 110, as depicted in the example of FIG. 1. As the lithium ions 125 move through the electrolyte 130, electrons 174 are released from lithium ions 125 and become available to carry charge, and therefore conduct an electric current, between the anode 120 and cathode 110. As a result, the electrons 174 may travel from the anode 120 to the cathode 110 through an

external circuit to power a load 172. The load 172 may be any suitable circuit, device, or system such as (but not limited to) a lightbulb, consumer electronics, or an electric vehicle (EV).

[0056] In some implementations, the battery 100 may include a solid-electrolyte interphase layer 140. The solid-electrolyte interphase layer 140 may, in some instances, be formed artificially on the anode 120 during operational cycling of the battery 100. In such instances, the solid-electrolyte interphase layer 140 may also be referred to as an artificial solid-electrolyte interphase, or A-SEI. The solid-electrolyte interphase layer 140, when formed as an A-SEI, may include tin, manganese, molybdenum, and/or fluorine compounds. Specifically, the molybdenum may provide cations, and the fluorine compounds may provide anions. The cations and anions may interact with each other to produce salts such as tin fluoride, manganese fluoride, silicon nitride, lithium nitride, lithium nitrate, lithium phosphate, manganese oxide, lithium lanthanum zirconium oxide (LLZO,  $\text{Li}_7\text{La}_3\text{Zr}_2\text{O}_{12}$ ), etc. In some instances, the A-SEI may be formed in response to exposure of lithium ions 125 to the electrolyte 130, which may include solvent-based solutions including tin and/or fluorine.

[0057] In various implementations, the solid-electrolyte interphase layer 140 may be artificially provided on the anode 120 prior to activation of the battery 100. Alternatively, in one implementation, the solid-electrolyte interphase layer 140 may form naturally, e.g., during operational cycling of the battery 100, on the anode 120. In some instances, the solid-electrolyte interphase layer 140 may include an outer layer of shielding material that can be applied to the anode 120 as a micro-coating. In this way, formation of the solid-electrolyte interphase layer 140 on portions of the anode 120 facing the electrolyte 130 may result from electrochemical reduction of the electrolyte 130, which in turn may reduce uncontrolled decomposition of the anode 120.

[0058] In some implementations, the battery 100 may include a barrier layer 142 that flanks the solid-electrolyte interphase layer 140, for example, as shown in FIG. 1. The barrier layer 142 may include a mechanical strength enhancer 144 coated and/or deposited on the anode 120. In some aspects, the mechanical strength enhancer 144 may provide structural support for the battery 100, may prevent lithium dendrite formation from the anode 120, and/or may prevent protrusion of lithium dendrite throughout the battery 100. In some implementations, the mechanical strength enhancer 144 may be formed as a protective coating over the anode 120, and may include one or more carbon allotropes, carbon nano-onions (CNOs), nanotubes (CNTs), reduced graphene oxide, graphene oxide (GO), and/or carbon nanodiamonds. In some instances, the solid-electrolyte interphase layer 140 may be formed within the mechanical strength enhancer 144.

[0059] In some implementations, the first substrate 101 and/or the second substrate 102 may be a solid copper metal foil and may influence the energy capacity, rate capability, lifespan, and long-term stability of the battery 100. For example, to control energy capacity and other performance attributes of the battery 100, the first substrate 101 and/or the second substrate 102 may be subject to etching, carbon coating, or other suitable treatment to increase electrochemical stability and/or electrical conductivity of the battery 100. In other implementations, the first substrate 101 and/or the

second substrate **102** may include or may be formed from a selection of aluminum, copper, nickel, titanium, stainless steel and/or carbonaceous materials depending on end-use applications and/or performance requirements of the battery **100**. For example, the first substrate **101** and/or the second substrate **102** may be individually tuned or tailored such that the battery **100** meets one or more performance requirements or metrics.

**[0060]** In some aspects, the first substrate **101** and/or the second substrate **102** may be at least partially foam-based or foam-derived, and can be selected from any one or more of metal foam, metal web, metal screen, perforated metal, or sheet-based three-dimensional (3D) structures. In other aspects, the first substrate **101** and/or the second substrate **102** may be a metal fiber mat, metal nanowire mat, conductive polymer nanofiber mat, conductive polymer foam, conductive polymer-coated fiber foam, carbon foam, graphite foam, or carbon aerogel. In some other aspects, the first substrate **101** and/or second substrate **102** may be carbon xerogel, graphene foam, graphene oxide foam, reduced graphene oxide foam, carbon fiber foam, graphite fiber foam, exfoliated graphite foam, or any combination thereof.

**[0061]** FIG. 2 shows another example battery **200**, according to some implementations. The battery **200** may be similar to the battery **100** of FIG. 1 in many respects, such that description of like elements is not repeated herein. In some implementations, the battery **200** may be a next-generation battery, such as a lithium-metal battery and/or a solid-state battery featuring a solid-state electrolyte. In other implementations, the battery **200** may include a liquid-phase electrolyte **230** and may therefore include any of the protective layers and/or electrolyte chemistries or compositions disclosed herein.

**[0062]** In some other implementations, the electrolyte **230** may be solid or substantially solid. For example, in some instances, the electrolyte **230** may begin in a gel phase and then later solidify upon activation of the battery **200**. The battery **200** may reduce specific capacity or energy losses associated with the polysulfide shuttle effect by replacing conventional carbon scaffolded anodes with a single solid metal layer of lithium deposited in an initially empty cavity. For example, while the anode **120** of the battery **100** of FIG. 1 may include carbon scaffolds, the anode **220** of the battery **200** of FIG. 2 may be a lithium-metal anode devoid of any carbon material. In one implementation, the lithium-metal anode may be formed as a single solid lithium metal layer and referred to as a “lithium metal anode.”

**[0063]** Energy density gains associated with various cathode materials may be based on whether lithium metal is pre-loaded into the cathode **210** and/or is prevalent in the electrolyte **230**. Either the cathode **210** and/or the electrolyte **230** may provide lithium available for lithiation of the anode **220**. For example, batteries having high-capacity cathodes may need thicker or energetically denser anodes in order to supply the increased quantities of lithium needed for usage by the high-capacity cathodes. In some implementations, the anode **220** may include scaffolded carbonaceous structures capable of being incrementally filled with lithium deposited therein. These carbonaceous structures may be capable of retaining greater amounts of lithium within the anode **220** as compared to conventional graphitic anodes, which may be limited to solely hosting lithium intercalated between alternating graphene layers or may be electroplated with lithium. For example, conventional graphitic anodes may use six

carbon atoms to hold a single lithium atom. In contrast, by using a pure lithium metal anode, such as the anode **220**, batteries disclosed herein may reduce or even eliminate carbon use in the anode **220**, which may allow the anode **220** to store greater amounts of lithium in a relatively smaller volume than conventional graphitic anodes. In this way, the energy density of the battery **200** may be greater than conventional batteries of a similar size.

**[0064]** Lithium metal anodes, such as the anode **220**, may be prepared to function with a solid-state electrolyte designed to inhibit the formation and growth of lithium dendrites from the anode. In some aspects, a solid-state separator **250** may further limit dendrite formation and growth. The separator **250** may have a similar ionic conductivity as the liquid-phase electrolyte **130** of FIG. 1 yet still reduce lithium dendrite formation. In some aspects, the separator **250** may be formed from a ceramic containing material and may, as a result, fail to chemically react with metallic lithium. As a result, the separator **250** may be used to control lithium ion transport through pores dispersed across the separator **250** while concurrently preventing a short-circuit by impeding the flow or passage of electrons through the electrolyte **230**.

**[0065]** In one implementation, a void space (not shown for simplicity) may be formed within the battery **200** at or near the anode **220**. Operational cycling of the battery **200** in this implementation may result in the deposition of lithium into the void space. As a result, the void space may become or transform into a lithium-containing region (such as a solid lithium metal layer) and function as the anode **220**. In some aspects, the void space may be created in response to chemical reactions between a metal-containing electrically inactive component and a graphene-containing component of the battery **200**. Specifically, the graphene-containing component may chemically react with lithium deposited into the void space during operational cycling and produce lithiated graphite ( $\text{LiC}_6$ ) or a patterned lithium metal. The lithiated graphite produced by the chemical reactions may generate or lead to the generation and/or liberation of lithium ions and/or electrons that can be used to carry electric charge or a “current” between the anode **220** and the cathode **210** during discharge cycles of the battery **200**.

**[0066]** And, in implementations for which the anode **220** is a solid lithium metal layer, the battery **200** may be able to hold more electroactive material and/or lithium per unit volume (as compared to batteries with scaffolded carbon and/or intercalated lithiated graphite anodes). In some aspects, the anode **220**, when prepared as a solid lithium metal layer, may result in the battery **200** having a higher energy density and/or specific capacity than batteries with scaffolded carbon and/or intercalated lithiated graphite anodes, thereby resulting in longer discharge cycle times and additional power output per unit time. In instances for which use of a solid-state electrolyte is not desired or not optimal, the electrolyte **230** of the battery **200** of FIG. 2 may be prepared with any of the liquid-phase electrolyte chemistries and/or compositions disclosed herein. In addition, or in the alternative, the electrolyte **230** may include lithium and/or lithium ions available for cyclical transport from the anode **220** to the cathode **210** and vice-versa during discharge and charge cycles, respectively.

**[0067]** To reduce the migration of polysulfides **282** generated from elemental sulfur **281** pre-loaded in the cathode **210** into the electrolyte **230**, the battery **200** may include one

or more unique polysulfide retention features. For example, given that polysulfides are soluble in the electrolyte **230**, some polysulfides may be expected to drift or migrate from the cathode **210** towards the anode **220** due to differences in electrochemical potential, chemical gradients, and/or other phenomena. The migration of polysulfides **282**, especially long-chain form polysulfides, may impede the transport of lithium ions from the anode **220** to the cathode **210**, which in turn may reduce the number of electrons available to generate an electric current that can power a load **272**, such as an electric vehicle (EV). In some aspects, lithium ions may be transported from one or more start positions **226** in or near the anode **220** along a transport pathway **225** to one or more end positions **227** in or near the cathode **210**, as depicted in the example of FIG. 2.

**[0068]** In some implementations, a polymeric network **285** may be disposed on the anode **220** to reduce the uncontrolled migration of polysulfides **282** from the anode **220** to the cathode **210**. The polymeric network **285** may include one or more layers of carbonaceous materials grafted with fluorinated polymer chains cross-linked with each other via the Wurtz reaction upon exposure to Lithium anode surface. The carbonaceous materials in the polymeric network **285**, which may include (but are not limited to) graphene, few layer graphene, FLG, many layer graphene, and MLG), may be chemically grafted with fluorinated polymer chains containing carbon-fluorine (C—F) bonds. These C—F bonds may chemically react with lithium metal from the surface of the anode **220** to produce highly ionic Carbon-Lithium bonds (C—Li). These formed C—Li bonds, in turn, may react with C—F bonds of polymer chains to form new Carbon-Carbon bonds that can also cross-link the polymer chains into (and thereby form) the polymeric network and generate lithium fluoride (LiF).

**[0069]** The resulting lithium fluoride may be uniformly distributed along the entire perimeter of the polymeric network **285**, such that lithium ions are uniformly consumed to produce an interface layer **283** that may form or otherwise include lithium fluoride during battery cycling. The interface layer **283** may extend along a surface or portion of the anode **220** facing the cathode **210**, as shown in FIG. 2. As a result, the lithium ions **225** are less likely to combine and/or react with each other and are more likely to combine and/or react with fluorine atoms made available by the fluorinated polymer chains in the polymeric network **285**. The resulting reduction of lithium-lithium chemical reactions decreases lithium-lithium bonding responsible for undesirable lithium-metal dendrite formation. In addition, in some implementations, the polymeric network **285** may replace the interphase layer **240** that either naturally or artificially develops between the anode **220** and the electrolyte **230**.

**[0070]** In one implementation, the interface layer **283** of the polymeric network **285** is in contact with the anode **220**, and a protective layer **284** is disposed on top of the interface layer **283** (such as between the interface layer **283** and the interface layer **240**). In some aspects, the interface layer **283** and the protective layer **284** may collectively define a gradient of cross-linked fluoropolymer chains of varying degrees of density, for example, as described with reference to FIG. 7.

**[0071]** In some other implementations, the battery **200** may include a protective lattice **280** disposed on the cathode **210**. The protective lattice **280** may include a tri-functional epoxy compound and a di-amine oligomer-based compound

that may chemically react with each other to produce nitrogen and oxygen atoms. The nitrogen and oxygen atoms made available by the protective lattice **280** can bind with the polysulfides **282**, thereby confining the polysulfides **282** within the cathode **210** and/or the protective lattice **280**. Either of the cathode **210** and/or the protective lattice **280** may include carbon-carbon bonds and/or regions capable of flexing and/or volumetrically expanding during operational cycling of the battery **200**, which may confine polysulfides **282** generated during the operational cycling to the cathode **210**.

**[0072]** The electrolyte **130** of FIG. 1 and the electrolyte **230** of FIG. 2 may be prepared according to one or more recipes disclosed herein. For example, a ternary solvent package used in the electrolyte **130** and/or the electrolyte **230** may include DME, DOL and TEGDME. In one implementation, a solvent mixture may be prepared by mixing 5800  $\mu\text{L}$  DME, 2900  $\mu\text{L}$  DOL and 1300  $\mu\text{L}$  TEGDME and stirring at room temperature (77° F. or 25° C.). Next, 0.01 mol (2,850.75 mg) of LiTFSI may be weighed. Afterwards, the 0.01 mol of LiTFSI may be dissolved in solvent mixture by stirring at room temperature to prepare approximately 10 mL 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume 1:4:1). Finally, approximately 223 mg LiNO<sub>3</sub> may be added to 10 mL solution to produce 10 mL 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=58:29:13) with approximately 2 wt.% LiNO<sub>3</sub>.

**[0073]** In addition, or the alternative, a ternary solvent package used in the electrolyte **130** and/or the electrolyte **230** may include DME, DOL, TEGDME, and TBT or MBT. A solvent mixture may be prepared by mixing 2,000  $\mu\text{L}$  DME, 8,000  $\mu\text{L}$  DOL and 2,000  $\mu\text{L}$  TEGDME and stirring at room temperature (68° F. or 25° C.). Next, 0.01 mol (2,850.75 mg) of LiTFSI may be weighed and dissolved in approximately 3 mL of the solvent mixture by stirring at room temperature. Next, the dissolved LiTFSI and an additional solvent mixture (~8,056 mg) may be mixed in a 10 mL volumetric flask to produce approximately 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume 1:4:1). Finally, approximately 0.05 mmol (~12.5 mg) TBT or MBT may be added to the 10 mL solution to produce 10 mL of 5M TBT or MBT solution.

**[0074]** FIG. 3 shows an example electrode **300**, according to some implementations. In various implementations, the electrode **300** may be one example of the cathode **110** and/or the anode **110** of the battery **100** of FIG. 1. In some other implementations, the electrode **300** may be one example of the cathode **210** of the battery **200** of FIG. 2. When the electrode **300** is implemented as a cathode (such as the cathode **110** of the battery **100** of FIG. 1), the electrode **300** may temporarily microconfine an electroactive material, such as elemental sulfur, which may decrease the amount of sulfur available for reacting with lithium to produce polysulfides. In some aspects, the electrode **300** may provide an excess supply of lithium and/or lithium ions that can compensate for first-cycle operational losses associated with lithium-based batteries.

**[0075]** In some implementations, the electrode **300** may be porous and receptive of a liquid-phase electrolyte, such as the electrolyte **130** of FIG. 1. Electroactive species, such as lithium ions **125** suspended in the electrolyte **130**, may chemically react with elemental sulfur pre-loaded into pores of the electrode **300** to produce polysulfides, which in turn may be trapped in the electrode **300** during battery cycling.

In some aspects, the electrode 300 may expand in volume along one or more flexure points to retain additional quantities of polysulfides created during battery cycling. By confining the polysulfides within the electrode 300, aspects of the subject matter disclosed herein may allow the lithium ions 125 to flow freely through the electrolyte 130 from the anode 120 to the cathode 110 during discharge cycles of the battery 100 (e.g., without being impeded by the polysulfides). For example, when lithium ions 125 reach the cathode 110 and react with elemental sulfur contained in or associated with the cathode 110, sulfur is reduced to lithium polysulfides ( $\text{Li}_2\text{S}_x$ ) at decreasing chain lengths according to the order  $\text{Li}_2\text{S}_5 \rightarrow \text{Li}_2\text{S}_6 \rightarrow \text{Li}_2\text{S}_4 \rightarrow \text{Li}_2\text{S}_2 \rightarrow \text{Li}_2\text{S}$ , where  $2 \leq x \leq 8$ ). Higher order polysulfides may be soluble in various types of solvents and/or electrolytes, thereby interfering with the lithium ion transport necessary for healthy battery operation. Retention of such higher order polysulfides by the electrode 300 thereby allows the lithium ions 125 to flow more freely through the electrolyte 130, which in turn may increase the number of electrons available to carry charge from the anode 120 to the cathode 110.

[0076] The electrode 300 may include a body region 301 defined by a width 305, and may include a first thin film 310 and a second thin film 320. The first thin film 310 may include a plurality of first aggregates 312 that join together to form a first porous structure 316 of the electrode 300. In some instances, the first porous structure 316 may have an electrical conductivity between approximately 0 and 500 S/m. In other instances, the first electrical conductivity may be between approximately 500 and 1,000 S/m. In some other instances, the first electrical conductivity may be greater than 1,000 S/m. In some aspects, the first aggregates 312 may include carbon nano-tubes (CNTs), carbon nano-onions (CNOs), flaky graphene, crinkled graphene, graphene grown on carbonaceous materials, and/or graphene grown on graphene.

[0077] In some implementations, the first aggregates 312 may be decorated with a plurality of first nanoparticles 314. In some instances, the first nanoparticles 314 may include tin, lithium alloy, iron, silver, cobalt, semiconducting materials and/or metals such as silicon and/or the like. In some aspects, CNTs, due to their ability to provide high exposed surface areas per unit volume and stability at relatively high temperatures (such as above 77° F. or 25° C.), may be used as a support material for the first nanoparticles 314. For example, the first nanoparticles 314 may be immobilized (such as by decoration, deposition, surface modification or the like) onto exposed surfaces of CNTs and/or other carbonaceous materials. The first nanoparticles 314 may react with chemically available carbon on exposed surfaces of the CNTs and/or other carbonaceous materials.

[0078] The second thin film 320 may include a plurality of second aggregates 322 that join together to form a second porous structure 326. In some instances, the electrical conductivities of the first porous structure 316 and/or the second porous structure 326 may be between approximately 0 S/m and 250 S/m. In instances for which the first porous structure 316 includes a higher concentration of aggregates than the second porous structure 326, the first porous structure 316 may have a higher electrical conductivity than the second porous structure 326. In one implementation, the first electrical conductivity may be between approximately 250 S/m and 500 S/m, while the second electrical conductivity may be between approximately 100 S/m and 250 S/m. In another

implementation, the second electrical conductivity may be between approximately 250 S/m and 500 S/m. In yet another implementation, the second electrical conductivity may be greater than 500 S/m. In some aspects, the second aggregates 322 may include CNTs, CNOs, flaky graphene, crinkled graphene, graphene grown on carbonaceous materials, and/or graphene grown on graphene.

[0079] The second aggregates 322 may be decorated with a plurality of second nanoparticles 324. In some implementations, the second nanoparticles 324 may include iron, silver, cobalt, semiconducting materials and/or metals such as silicon and/or the like. In some instances, CNTs may also be used as a support material for the second nanoparticles 324. For example, the second nanoparticles 324 may be immobilized (such as by decoration, deposition, surface modification or the like) onto exposed surfaces of CNTs and/or other carbonaceous materials. The second nanoparticles 324 may react with chemically available carbon on exposed surfaces of the CNTs and/or other carbonaceous materials.

[0080] In some aspects, the first thin film 310 and/or the second thin film 320 (as well as any additional thin films disposed on their respective immediately preceding thin film) may be created as a layer or region of material and/or aggregates. The layer or region may range from fractions of a nanometer to several microns in thickness, such as between approximately 0 and 5 microns, between approximately 5 and 10 microns, between approximately 10 and 15 microns, or greater than 15 microns. Any of the materials and/or aggregates disclosed herein, such as CNOs, may be incorporated into the first thin film 310 and/or the second thin film 320 to result in the described thickness levels.

[0081] In some implementations, the first thin film 310 may be deposited onto the second substrate 102 of FIG. 1 by chemical deposition, physical deposition, or grown layer-by-layer through techniques such as Frank-van der Merwe growth, Stranski-Krastonov growth, Volmer-Weber growth and/or the like. In other implementations, the first thin film 310 may be deposited onto the second substrate 102 by epitaxy or other suitable thin-film deposition process involving the epitaxial growth of materials. The second thin film 320 and/or subsequent thin films may be deposited onto their respective immediately preceding thin film in a manner similar to that described with reference to the first thin film 310.

[0082] In various implementations, each of the first aggregates 312 and/or the second aggregates 322 may be a relatively large particle formed by many relatively small particles bonded or fused together. As a result, the external surface area of the relatively large particle may be significantly smaller than combined surface areas of the many relatively small particles. The forces holding an aggregate together may be, for example, covalent, ionic bonds, or other types of chemical bonds resulting from the sintering or complex physical entanglement of former primary particles.

[0083] As discussed above, the first aggregates 312 may join together to form the first porous structure 316, and the second aggregates 322 may join together to form the second porous structure 326. The electrical conductivity of the first porous structure 316 may be based on the concentration level of the first aggregates 312 within the first porous structure 316, and the electrical conductivity of the second porous structure 326 may be based on the concentration level of the second aggregates 322 within the second porous

structure **326**. In some aspects, the concentration level of the first aggregates **312** may cause the first porous structure **316** to have a relatively high electrical conductivity, and the concentration level of the second aggregates **322** may cause the second porous structure **326** to have a relatively low electrical conductivity (such that the first porous structure **316** has a greater electrical conductivity than the second porous structure **326**). The resulting differences in electrical conductivities of the first and second porous structures **316** and **326** may create an electrical conductivity gradient across the electrode **300**. In some implementations, the electrical conductivity gradient may be used to control or adjust electrical conduction throughout the electrode **300** and/or one or more operations of the battery **100** of FIG. 1.

**[0084]** As used herein, the relatively small source particles may be referred to as “primary particles,” and the relatively large aggregates formed by the primary particles may be referred to as “secondary particles.” As shown in FIG. 1, FIGS. 8 to 10, and elsewhere throughout the present disclosure, the primary particles may be or include multiple graphene sheets, layers, regions, and/or nanoplatelets fused and/or joined together. Thus, in some instances, carbon nano-onions (CNOs), carbon nano-tubes (CNTs), and/or other tunable carbon materials may be used to form the primary particles. In some aspects, some aggregates may have a principal dimension (such as a length, a width, and/or a diameter) between approximately 500 nm and 25 pm. Also, some aggregates may include innately-formed smaller collections of primary particles, referred to as “innate particles,” of graphene sheets, layers, regions, and/or nanoplatelets joined together at orthogonal angles. In some instances, these innate particles may each have a respective dimension between approximately 50 nm and 250 nm.

**[0085]** The surface area and/or porosity of these innate particles may be imparted by secondary processes, such as carbon-activation by a thermal, plasma, or combined thermal-plasma process using one or more of steam, hydrogen gas, carbon dioxide, oxygen, ozone, KOH, ZnCl<sub>2</sub>, H<sub>3</sub>PO<sub>4</sub>, or other similar chemical agents alone or in combination. In some implementations, the first porous structure **316** and/or the second porous structure **326** may be produced from a carbonaceous gaseous species that can be controlled by gas-solid reactions under non-equilibrium conditions. Producing the first porous structure **316** and/or the second porous structure **326** in this manner may involve recombination of carbon-containing radicals formed from the controlled cooling of carbon-containing plasma species (which can be generated by excitation or compaction of feedstock carbon-containing gaseous and/or plasma species in a suitable chemical reactor).

**[0086]** In some implementations, the first aggregates **312** and/or the second aggregates **322** may have a percentage of carbon to other elements, except hydrogen, within each respective aggregate of greater than 99%. In some instances, a median size of each aggregate may be between approximately 0.1 microns and 50 microns. The first aggregates **312** and/or the second aggregates **322** may also include metal organic frameworks (MOFs).

**[0087]** In some implementations, the first porous structure **316** and second porous structure **326** may collectively define a host structure **328**, for example, as shown in FIG. 3. In some instances, the host structure **328** may be based on a carbon scaffold and/or may include decorated carbons, for example, as shown in FIG. 8. The host structure **328** may

provide structural definition to the electrode **300**. In some instances, the host structure **328** may be fabricated as a positive electrode and used in the cathode **110** of FIG. 1. In other implementations, the host structure **328** may be fabricated as a negative electrode and used in the anode **120** of FIG. 1. In some other implementations, the host structure **328** may include pores having different sizes, such as micropores, mesopores, and/or macropores defined by the IUPAC. In some instances, at least some of the micropores may have a width of approximately 1.5 nm, which may be large enough to allow sulfur to be pre-loaded into the electrode **300** and yet small enough to at least temporarily confine polysulfides within the electrode **300**.

**[0088]** The host structure **328**, when provided within the electrode **300** as shown in FIG. 3, may include microporous, mesoporous, and/or macroporous pathways created by exposed surfaces and/or contours of the first porous structure **316** and/or the second porous structure **326**. These pathways may allow the host structure **328** to receive an electrolyte, for example, by transporting lithium ions towards the cathode **110** of the battery **100**. Specifically, the electrolyte **130** may infiltrate the various porous pathways of the host structure **328** and uniformly disperse throughout the electrode **300** and/or other portions of the battery **100**. Infiltration of the electrolyte **130** into such regions of the host structure **328** may allow the lithium ions **125** migrating from the anode **120** towards the cathode **110** to react with elemental sulfur associated with the cathode **110** to form lithium-sulfur complexes. As a result, the elemental sulfur may retain additional quantities of lithium ions that would otherwise be achievable using non-sulfur chemistries such as lithium cobalt oxide (LiCoO) or other lithium-ion cells.

**[0089]** In some aspects, each of the first porous structure **316** and/or the second porous structure **326** may have a porosity based on one or more of a thermal, plasma, or combined thermal-plasma process using one or more of steam, hydrogen gas, carbon dioxide, oxygen, ozone, KOH, ZnCl<sub>2</sub>, H<sub>3</sub>PO<sub>4</sub>, or other similar chemical agents alone or in combination. For example, in one implementation, the macroporous pathways may have a principal dimension greater than 50 nm, the mesoporous pathways may have a principal dimension between approximately 20 nm and 50 nm, and the microporous pathways may have a principal dimension less than 4 nm. As such, the macroporous pathways and mesoporous pathways can provide tunable conduits for transporting lithium ions **125**, and the microporous pathways may confine active materials within the electrode **300**.

**[0090]** In some implementations, the electrode **300** may include one or more additional thin films (not shown for simplicity). Each of the one or more additional thin films may include individual aggregates interconnected with each other across different thin films, with at least some of the thin films having different concentration levels of aggregates. As a result, the concentration levels of any thin film may be varied (such as by gradation) to achieve particular electrical resistance (or conductance) values. For example, in some implementations, the concentration levels of aggregates may progressively decline between the first thin film **310** and the last thin film (such as in a direction **195** depicted in FIG. 1), and/or the individual thin films may have an average thickness between approximately 10 microns and approximately 200 microns. In addition, or in the alternative, the first thin film **310** may have a relatively high concentration of carbonaceous aggregates, and the second thin film **320** may

have a relatively low concentration of carbonaceous aggregates. In some aspects, the relatively high concentration of aggregates corresponds to a relatively low electrical resistance, and the relatively low concentration of aggregates corresponds to a relatively high electrical resistance.

[0091] The host structure 328 may be prepared with multiple active sites on exposed surfaces of the first aggregates 312 and/or the second aggregates 322. These active sites, as well as the exposed surfaces of the first aggregates 312 and/or the second aggregates 322, may facilitate ex-situ electrodeposition prior to incorporation of the electrode 300 into the battery 100. Electroplating is a process that can create a lithium layer 330 (including lithium on exposed surfaces of the host structure 328) through chemical reduction of metal cations by application and/or modulation of an electric current. In implementations for which the electrode 300 serves as the anode 120 of the battery 100 in FIG. 1, the host structure 328 may be electroplated such that the lithium layer 330 has a thickness between approximately 1 and 5 micrometers ( $\mu\text{m}$ ), 5  $\mu\text{m}$  and 20  $\mu\text{m}$ , or greater than 20  $\mu\text{m}$ . In some instances, ex-situ electrodeposition may be performed at a location separate from the battery 100 prior to the assembly of the battery 100.

[0092] In various implementations, excess lithium provided by the lithium layer 330 may increase the number of lithium ions 125 available for transport in the battery 100, thereby increasing the storage capacity, longevity, and performance of the battery 100 (as compared with traditional lithium-ion and/or lithium-sulfur batteries).

[0093] In some aspects, the lithium layer 330 may produce lithium-intercalated graphite ( $\text{LiC}_6$ ) and/or lithiated graphite based on chemical reactions with the first aggregates 312 and/or the second aggregates 322. Lithium intercalated between alternating graphene layers may migrate or be transported within the electrode 300 due to differences in electrochemical gradients during operational cycling of the battery 100, which in turn may increase the energy storage and power delivery of the battery 100.

[0094] FIG. 4 shows a diagram of a portion of an example battery 400 that includes a protective lattice 402, according to some implementations. In some implementations, the protective lattice 402 may be disposed on the anode 220 of the battery 200. In other implementations, the protective lattice 402 may be disposed on the cathode 210 of the battery 200 (or other suitable batteries). In some aspects, the protective lattice 402 may be one example of the protective lattice 280 of FIG. 2. The protective lattice 402 may function with many components (e.g., anode, cathode, current collectors associated, carbonaceous materials, electrolyte, and separator) in a manner similar to the battery 100 of FIG. 1 and/or the battery 200 of FIG. 2.

[0095] The protective lattice 402 may include a tri-functional epoxy compound and a di-amine oligomer-based compound that can chemically react with each other to produce a 3D lattice structure (e.g., as shown in FIG. 6 and FIG. 8). In some aspects, the protective lattice 402 may prevent polysulfide migration within the battery 400 by providing nitrogen and oxygen atoms that can chemically bind with lithium present in the polysulfides, thereby impeding the migration of polysulfides through the electrolyte 130. As a result, lithium ions 125 can be more freely transported from the anode 120 and the cathode 110 of FIG. 1, thereby increasing battery performance metrics.

[0096] Cyclical usage of the cathode 110 may cause the formation of cracks 404 that at least partially extend into the cathode 110. In one implementation, the protective lattice 402 may disperse throughout the cracks 404, thereby reducing susceptibility of the cathode 110 to rupture during volumetric expansion of the cathode 110 caused by the retention of polysulfides within the cathode 110 during cyclical usage. In one implementation, the protective lattice 402 of FIG. 4 may have a cross-linked, 3D structure based on chemical reactions between di-functional, or higher functionality Epoxy and Amine or Amide compounds. For example, the di-functional, or higher functionality Epoxy compound may be trimethylolpropane triglycidyl ether (TMPTE), tris(4-hydroxyphenyl)methane triglycidyl ether, or tris(2,3-epoxypropyl) isocyanurate, and di-functional, or higher functionality Amine compound may be dihydrazide sulfoxide (DHSO) or one of polyetheramines, for example JEFFAMINE® D-230 characterized by repeating oxypropylene units in the backbone.

[0097] In various implementations, the chemical compounds may be combined and reacted with each other in any number of quantities, amounts, ratios and/or compositions to achieve different performance capabilities relating to binding with polysulfides generated during operation of the host battery 400. For example, in one implementation, 113 mg of TMPTE and 134 mg of JEFFAMINE® D-230 polyetheramine may be mixed together and diluted with 1 mL to 10 mL of tetrahydrofuran (THF), or any other solvent. Additional amounts of TMPTE and/or JEFFAMINE may be mixed together and diluted in THF, or any other solvent, at an example ratio of 113 mg of TMPTE for every 134 mg of JEFFAMINE® D-230 polyetheramine. For this implementation, proof-of-concept (POC) data shows that the protective lattice 402 of FIG. 4 has a defined weight of approximately 2.6 wt. % of the cathode 110 of FIG. 1 or the cathode 210 of FIG. 2. In other implementations, the protective lattice 402 may have a weight of approximately 2 wt.% to 21 wt. % of the cathode 110 and/or the cathode 210, where an impedance increases of the cathode 110 and/or the cathode 210 may be expected at a weight level of approximately 10 wt.% or more for the protective lattice 402.

[0098] In various implementations, the protective lattice 402 may be fabricated based on a mole and/or molar ratio of  $-\text{NH}_2$  group and epoxy groups and may further accommodate various forms of cross-linking between di-functional, or higher functionality Epoxy and Amine or Amide compound. In some aspects, such forms of cross-linking may include a fully cross-linked stage, e.g., where one  $-\text{NH}_2$  group is chemically bonded with two epoxy groups and may further extend to configurations including one  $\text{NH}_2$  group chemically bonded with only one epoxy group. Still further, in one or more implementations, mixtures including excess quantities (above the ratios presented here) of  $-\text{NH}_2$  groups may be prepared to provide additional polysulfide binding capability for the protective lattice 402.

[0099] In some other implementations, the protective lattice 402 may be prepared by mixing 201 g of TMPTE with between 109 g and 283 g of JEFFAMINE® D-230 polyetheramine. The resulting mixture may be then diluted with 1 L to 20 L of a selected solvent (such as THF). The resultant diluted solution may be deposited and/or otherwise disposed on the cathode 110 to achieve a crosslinker content between 1 wt.% to 10 wt.%. Additional TMPTE and/or JEFFAMINE may be mixed together and diluted in THF, or

another suitable solvent, at an example ratio of 201 g of TMPTE for every 109 g to 283 g of JEFFAMINE® D-230 polyetheramine.

[0100] In still other implementations, the protective lattice **402** may be prepared by mixing 201 g of TMPTE with between 74 g and 278 g DHSO. The resulting mixture may be then diluted with 1 L to 20 L of a selected solvent (such as THF). The resultant diluted solution may be deposited and/or otherwise disposed on the cathode **110** to achieve a crosslinker content between 1 wt. % to 10 wt. %. Additional TMPTE and/or JEFFAMINE may be mixed together and diluted in THF, or another suitable solvent, at an example ratio of 201 g of TMPTE for every 201 g to 278 g of JEFFAMINE® D-230 polyetheramine.

[0101] In one implementation, di-functional, or higher functionality Epoxy compound may chemically react with di-functional, or higher functionality amine compound to produce the protective lattice **402** in a 3D cross-linked form, which may include both functional epoxy compounds and amine containing molecules. In some aspects, the protective lattice **402**, when deposited on the cathode **110** of FIG. 1 or the cathode **210** of FIG. 2, may have a thickness between approximately 1 nm and 5  $\mu\text{m}$ .

[0102] In some implementations, the protective lattice **402** may increase the structural integrity of the cathode **110** or the cathode **210**, may reduce surface roughness, and may retain polysulfides in the cathode. For example, in one implementation, the protective lattice **402** may serve as sheath on exposed surfaces of the cathode and bind with polysulfides to prevent their migration and diffusion into the electrolyte **130**. In this way, aspects of the subject matter disclosed herein may prevent (or at least reduce) battery capacity decay by suppressing the polysulfide shuttle effect. In some aspects, the protective lattice **402** may also fill the cracks **404** formed in the cathode of FIG. 4 to improve cathode coating integrity. In various implementations, the protective lattice **402** may be prepared by drop casting processes in the presence of a solvent, where the resultant solution can penetrate in cracks **404** of the cathode **110** and bind with polysulfides in the cathode **110** to prevent their migration and/or diffusion throughout the electrolyte **130**.

[0103] In various implementations, the protective lattice **402** may provide nitrogen atoms and/or oxygen atoms that can chemically bond with lithium in the polysulfides generated during operational battery cycling. In one example, the polysulfides may bond with available nitrogen atoms provided by, for example, DHSO. In another example, the polysulfides may bond with available oxygen atoms provided by, for example, DHSO. In yet another example, the polysulfides may bond with other available oxygen atoms.

[0104] In some other implementations, the recipes described above may be altered by replacing TMPTE with a tris(4-hydroxyphenyl)methane triglycidyl ether **910** and/or a tris(2,3-epoxypropyl) isocyanurate. In various implementations, the di-amine oligomer-based compound may be (or may include) a JEFFAMINE® D-230, or other polyetheramines containing polyether backbone normally based on either propylene oxide (PO), ethylene oxide (EO), or mixed PO/EO structure, for example JEFFAMINE® D-400, JEFFAMINE® T-403. The protective lattice **402** may also include various concentration levels of inert molecules, e.g., polyethylene glycol chains of various lengths, which may

allow to fine-tune mechanical properties of protective lattice and the chemical bonding of various atoms to lithium present in the polysulfides.

[0105] FIG. 5 shows a diagram of an anode structure **500** that includes a tin fluoride ( $\text{SnF}_2$ ) layer, according to some implementations. Specifically, the diagram depicts a cut-away schematic view of the anode structure **500** in which all of the components associated with a first region A have identical counterparts in a second region B, where the first and second regions A and B have opposite orientations around a current collector **520**. As such, the description below with reference to the components of first region A is equally applicable to the components of second region B. In some aspects, the anode **502** may be one example of the anode **120** of FIG. 1 and/or the anode **220** of FIG. 2.

[0106] As discussed, lithium-sulfur batteries, such as the battery **100** of FIG. 1 and the battery **200** of FIG. 2, operate as conversion-chemistry type electrochemical cells in that sulfur pre-loaded into the cathode may dissolve rapidly into the electrolyte prior to and during operation. Lithium, which may be provided by lithiated anodes and/or may be prevalent in the electrolyte, dissociates into lithium ions ( $\text{Li}^+$ ) suitable for transport from the anode to the cathode through the electrolyte. The production of lithium ions is associated with a corresponding release of electrons, which may flow through an external circuit to power a load, as described with reference to FIG. 1. However, when lithium disassociates into lithium ions and electrons, some of the lithium ions may undesirably react with polysulfides produced in the cathode, and therefore may no longer be available to generate an output current or voltage. This consumption of lithium ions by polysulfides reduces the overall capacity of the host cell or battery, and may also facilitate corrosion of the anode, which can result in cell failure.

[0107] In some implementations, the protective layer **516** may be provided as passivation coating that can reduce the chemical reactivity of the anode **502** during cell assembly or formation. In some aspects, the protective layer **516** may be permeable to lithium ions while concurrently protecting the anode **502** from corrosion caused by chemical reactions between lithium ions and polysulfides. In other implementations, the protective layer **516** may be an artificial solid-electrolyte interphase (A-SEI) that can replace naturally occurring SEIs and/or other types of conventional A-SEIs. In various implementations, the protective layer **516** may be deposited as a liner on top of one or more films disposed on the anode **502**. In some aspects, the protective layer **516** may be a self-generating layer that forms during electrochemical reactions associated with operational cycling of the battery. In some aspects, the protective layer **516** may have a thickness that is less than 5 microns. In other aspects, the protective layer **516** may have a thickness between 0.1 and 1.0 microns.

[0108] In various implementations, one or more engineered additives that may facilitate the formation and/or deposition of the protective layer **516** on the anode **502** may be provided within the electrolyte of the battery. In other implementations, the engineered additives may be an active ingredient of the protective layer **516**. In some aspects, the protective layer **516** may provide tin ions and/or fluoride ions that can prevent undesirable lithium growths from a first edge **518**<sub>1</sub> and a second edge **518**<sub>2</sub> of the anode.

[0109] A graded layer **514** may be formed and/or deposited onto the anode **502** beneath the protective layer **516**. In

various implementations, the graded layer **514** may prevent lithium contained in or associated with the anode **502** from participating in undesirable chemical interactions and/or reactions with the electrolyte **540** that can lead to the growth of lithium-containing dendrites from the anode **502**. The graded layer **514** may also facilitate the production of lithium fluoride based on chemical reactions between dissociated lithium ions and fluoride ions. As discussed, the presence of lithium fluoride in or near the anode **502** can decrease the polysulfide shuttle effect. For example, formation of lithium fluoride (e.g., form available lithium ions and fluorine ions) may occur uniformly across the entirety of the first edge **518**<sub>1</sub> and/or the second edge **518**<sub>2</sub> of the anode. In this way, localized regions of high lithium concentration in the electrolyte **540** near the anode **502** are substantially inhibited. As a result, lithium-lithium bonds contributing to the formation of lithium containing dendritic structures extending length-wise from the anode are correspondingly inhibited, thereby yielding free passage of lithium ions from the anode **502** into the electrolyte (e.g., as encountered during battery operational cycling). In some aspects, the uniform distribution of lithium throughout the graded layer **514** can increase a uniformity of a lithium-ion flux during battery operational cycling. In some aspects, the graded layer **514** may be approximately 5 nanometers (nm) in thickness.

**[0110]** In one or more implementations, the graded layer **514** may structurally reinforce the host battery in a manner that not only decreases or prevents lithium-containing dendritic growth from the anode **502** but also increases the ability of the anode **502** to expand and contract during operational cycling of the host battery without rupturing. In some aspects, the graded layer **514** has a 3D architecture with a graded concentration gradient (e.g., of one or more formative materials and/or ingredients including carbon, tin, and/or fluorine), which facilitates rapid lithium-ion transport. As a result, the graded layer **514** markedly improves overall battery efficiency and performance.

**[0111]** In some implementations, the graded layer **514** may provide an electrochemically desirable surface upon which the protective layer **516** may be grown or deposited. For example, in some aspects, the graded layer **514** may include compounds and/or organometallic compounds including (but not limited to) aluminum, gallium, indium, nickel, zinc, chromium, vanadium, titanium, and/or other metals. In other aspects, the graded layer **514** may include oxides, carbides and/or nitrides of aluminum, gallium, indium, nickel, zinc, chromium, vanadium, titanium, and/or other metals.

**[0112]** In some implementations, the graded layer **514** may include carbonaceous materials including (but not limited to) flaky graphene, few layer graphene (FLG), carbon nano onions (CNOs), graphene nanoplatelets, or carbon nanotubes (CNTs). In other implementations, the graded layer **514** may include carbon, oxygen, hydrogen, tin, fluorine and/or other suitable chemical compounds and/or molecules derived from tin fluoride and one or more carbonaceous materials. The graded layer **514** may be prepared and/or deposited either directly or indirectly on the anode **502** at a different concentration levels. For example, the graded layer **514** may include 5 wt. % carbonaceous materials with a balance of 95 wt. % tin fluoride, which may result in a relatively uniform disassociation of fluorine atoms and/or fluoride ions from the tin fluoride.

**[0113]** Other suitable ratios include: 5% carbonaceous materials with 95% tin fluoride; 10% carbonaceous materials with 90% tin fluoride, 15% carbonaceous materials with 85% tin fluoride, 20% carbonaceous materials with 80% tin fluoride, 25% carbonaceous materials with 75% tin fluoride, 30% carbonaceous materials with 70% tin fluoride, 35% carbonaceous materials with 65% tin fluoride, 40% carbonaceous materials with 60% tin fluoride, 45% carbonaceous materials with 55% tin fluoride, 50% carbonaceous materials with 50% tin fluoride, 55% carbonaceous materials with 45% tin fluoride, 60% carbonaceous materials with 40% tin fluoride, 65% carbonaceous materials with 35% tin fluoride, 70% carbonaceous materials with 30% tin fluoride, 75% carbonaceous materials with 25% tin fluoride, 80% carbonaceous materials with 20% tin fluoride, 85% carbonaceous materials with 15% tin fluoride, 90% carbonaceous materials with 10% tin fluoride, 95% carbonaceous materials with 5% tin fluoride. The fluorine atoms and/or fluoride ions may then uniformly react and combine with lithium ions to form lithium fluoride, as further discussed below.

**[0114]** In some implementations, lithium ions cycling between the anode **502** and the cathode (not shown in FIG. **5**) may produce a tin-lithium alloy region **512** within the graded layer **514**. In some aspects, operational cycling of the host battery may result in a uniform dispersion of lithium fluoride within the tin-lithium alloy region **512**. The uniform dispersion of lithium fluoride may facilitate a defluorination reaction of at least some of the tin fluoride within the tin fluoride layer **510** (and additional tin fluoride which may have dispersed into the graded layer **514** and/or the protective layer). The fluorine atoms and/or fluoride ions made available by the defluorination reaction may chemically bond with at least some of the lithium ions present in or near the anode **502**, thereby preventing at least some of the lithium ions from bonding with each other and creating a lithium dendritic growth from the anode **502**.

**[0115]** For example, at least a portion of the fluorine atoms and/or fluoride ions present in the tin fluoride may dissociate from the protective layer **516** and produce tin ions ( $\text{Sn}^{2+}$ ) and fluorine ions ( $2\text{F}^-$ ) via one or more chemical reactions. The fluorine atoms and/or fluoride ions dissociated from the protective layer **516** may chemically bond to at least some of the lithium ions present in the electrolyte **540** and/or dispersed throughout the protective layer **516** or the graded layer **514**. In some aspects, the dissociated fluorine atoms may form Li—F bonds or Li—F compounds in the tin-lithium alloy region **512**. In other aspects, the dissociated fluorine atoms may form a lithium fluoride layer **510** within the graded layer **514**.

**[0116]** In addition, in one implementation, at least some of the defluorinated tin fluoride may disperse uniformly throughout the graded layer **514** to produce lithium fluoride (LiF) crystals. The lithium fluoride crystals may act as an electrical insulator and prevent the flow of electrons from the anode **502** into the electrolyte **540** through the first edge **518**<sub>1</sub> and/or the second edge **518**<sub>2</sub> of the anode **502**.

**[0117]** In various implementations, the graded layer **514** may be deposited on the anode **502** by one or more of atomic layer deposition (ALD), chemical vapor deposition (CVD), or physical vapor deposition (PVD). For example, ALD may be used to deposit protective films on the anode **502** such as, for example, an ALD film that at least partially reacts with the electrolyte **540** during high-pressure bonding processes.

Accordingly, the ALD film may be used to produce the protective layer 516 or the graded layer 514 using an atomic plane available for lithium transfer. Such lithium transfer may be similar in principle to that observed for few layer graphene (FLG) or graphite, where alternating graphene layers in FLG or graphite intercalate lithium ions in various forms including as lithium titanium oxide (LTO), lithium iron phosphate ( $\text{PO}_3$ ) (LFP). The described forms of intercalated lithium, e.g., LTO and/or LFP, may be oriented to facilitate rapid lithium atom and/or lithium ion transport and/or diffusion, which may be conducive for the formation and/or synthesis of lithium fluoride (e.g., in the lithium fluoride layer 510 and/or elsewhere), as described earlier. Additional forms of intercalated lithium, e.g., perovskite lithium lanthanum titanate (LLTO), may also function to store lithium within the anode 502.

[0118] In some implementations, the graded layer 514 may include various distinct types and/or forms of carbon and/or carbonaceous materials, each having one or more physical attributes that can be selected or configured to adjust the reactivity of carbon with contaminants (such as polysulfides) present in the electrolyte 540 and/or the anode 502. In some aspects, the selectable physical attributes may include (but are not limited to) porosity, surface area, surface functionalization, or electric conductivity. In addition, the graded layer 514 may include binders or other additives that can be used to adjust one or more physical attributes of the carbonaceous materials to achieve a desired reactivity of carbon supplied by the carbonaceous materials with polysulfides present in the electrolyte 540 and/or the anode 502.

[0119] In one implementation, carbonaceous materials within the graded layer 514 may capture unwanted contaminants and thereby prevent the contaminants from chemically reacting with lithium available at exposed surfaces of the anode 502. Instead, the unwanted contaminants (e.g., polysulfides) may chemically react with various exposed surfaces of the carbonaceous materials within the graded layer 514 (e.g., through carbon—lithium interactions). In some implementations, the carbonaceous materials within the graded layer 514 may cohere to the available lithium. The degree of cohesion between the carbonaceous materials and the lithium ions may be selected or modified via chemical reactions induced during preparation of the graded layer 514.

[0120] In some implementations, various carbon allotropes may be incorporated within the graded layer 514 (such as in one or more portions of the tin-lithium alloy region 512 and/or the tin lithium fluoride layer 510). These carbon allotropes may be functionalized with one or more reactants and used to form a sealant layer and/or region at an interface of carbon nanodiamonds within the graded layer 514 and the electrolyte 540. In some aspects, the carbon nanodiamonds may increase the mechanical robustness of the anode 502 and/or the graded layer 514. In other aspects, the carbon nanodiamonds may also provide exposed carbonaceous surfaces that may be used to decrease the polysulfide shuttle effect by micro-confining and/or bonding with polysulfides present in the electrolyte 540 in a manner that retains the polysulfides within defined regions of the battery external to the anode 502.

[0121] Alternatively, in other implementations, the carbon nanodiamonds within the graded layer 514 may be replaced with carbons and/or carbonaceous materials including surfaces and/or regions having a specific  $L_d$  dimensions (e.g.,

$sp^2$  hybridized carbon), reduced graphene oxide (rGO), and/or graphene. In some aspects, employing the carbonaceous materials disclosed herein within a battery may increase carbon stacking and layer formation within the graded layer 514. Exfoliated and oxidized carbonaceous materials may also yield more uniform layered structures within the graded layer 514 (as compared to carbonaceous materials that have not been exfoliated and oxidized). In some aspects, solvents such as tetrabutylammonium hydroxide (TBA) and/or dimethyl formamide (DMF) treatments may be applied to the carbonaceous materials disclosed herein to increase the wetting of exposed carbonaceous surfaces within the graded layer 514.

[0122] In some implementations, slurries used to form the graded layer 514 may be doped to improve or otherwise influence the crystalline structure of carbonaceous materials within the graded layer 514. For example, addition of certain dopants may influence the crystalline structure of the carbonaceous materials in a certain corresponding way, and functional groups may be added (e.g., via grafting onto exposed carbon atoms within the carbonaceous materials) within the graded layer 514.

[0123] In some implementations, carbonaceous materials having exposed surfaces functionalized with one or more of fluorine-containing or silicon-containing functional groups may be included within the graded layer 514. In other implementations, carbonaceous materials having exposed surfaces functionalized with one or more of fluorine-containing or silicon-containing functional groups may be deposited beneath the graded layer 514 to form a stable SEI on at an interface between the graded layer 514 and the anode 502. In one implementation, the stable SEI may replace the protective layer 516. In some implementations, the graded layer 514 may be slurry cast and/or deposited using other techniques onto the anode 502 with lithium and carbon interphases, any of which may be functionalized with silicon and/or nitrogen to inhibit the diffusion and migration of polysulfides towards exposed surfaces of the anode 502. In addition, specific polymers and/or crosslinkers may be incorporated within the graded layer 514 to mechanically strengthen the graded layer 514, to improve lithium ion transport across the graded layer 514, or to increase the uniformity of lithium ion flux across the graded layer 514. Example polymers and/or polymeric materials suitable for incorporation within the graded layer 514 may include poly(ethylene oxide) and poly(ethyleneimine). Example crosslinkers suitable for incorporation within the graded layer 514 may include inorganic linkers (e.g., borate, aluminate, silicate), multifunctional organic molecules (e.g., diamines, diols), polyurea, or high molecular weight (MW) (e.g., >10,000 daltons) carboxymethyl cellulose (CMC).

[0124] Various fabrication methods may be employed to produce the graded layer 514. In one implementation, direct coating of the interface between the anode 502 and the electrolyte 540 prior to the deposition and/or formation of the graded layer 514 may be performed with a dispersion of carbonaceous materials and other chemicals dissolved in a carrier (e.g., a solvent, binder, polymer). In another implementation, deposition of the graded layer 514 may be performed as a separate operation, or may be added to various other active ingredients (e.g., metals, carbonaceous materials, tin fluoride and/or the like) into a slurry that can be cast onto the anode 502. Alternatively, in another implementation, the protective layer 516 may be transferred

directly onto the anode **502** by a calendar roll lamination processes. The protective layer **516** and/or the graded layer **514** may also incorporate partially-cured lithium ion conductive epoxies to, for example, increase adhesion with lithium better during the calendar roll lamination processes.

**[0125]** In one implementation, a carbon-inclusive layered structure (not shown in FIG. **5**) may be disposed on the anode **502** as a replacement for the graded layer **514**. The carbon-inclusive layered structure may include an atomic plane available for lithium transfer, and may uniformly transport lithium ions provided by the electrolyte **540** throughout the protective layer **516** in a manner that can guide the formation of lithium fluoride in various portions of the battery. In various implementations, the carbon-inclusive layered structure may include one or more arrangements of few layer graphene (FLG) or graphite and/or may intercalate with lithium and produce one or more reaction products including lithium tin oxide (LTO), lithium iron phosphate (LFP), or perovskite lithium lanthanum titanate (LLTO).

**[0126]** In some implementations, the lithium fluoride layer **510** may function as a protection layer against corrosion, including corrosion of copper-inclusive surfaces and/or regions of the protective layer **516**, the graded layer **514**, or the anode **502**. In some aspects, the lithium fluoride layer **510** may also provide a uniform seed layer suitable for lithium deposition, and thereby inhibiting dendrite formation. In addition, in some implementations, the lithium fluoride layer **510** may include one or more lithium ion intercalating compounds, any one or more having a low voltage penalty. Suitable lithium ion intercalating compounds may include graphitic carbon (e.g., graphite, graphene, reduced graphene oxide, rGO). In one implementation, during fabrication of the anode **502**, lithium ions may tend to intercalate prior to plating onto exposed carbonaceous surfaces within the lithium fluoride layer **510**. In this way, the lithium fluoride layer **510** will have a uniform Li distribution ready to act as a seed layer prior to initiation of lithium plating and/or electroplating operations.

**[0127]** In one implementation, one or more conformal coatings may be applied over portions of the anode **502** such that the resulting conformal coating contacts and conforms to the first edge **518<sub>1</sub>** and/or the second edge **518<sub>2</sub>** of the anode **502**. In some aspects, the conformal coating may begin as a first spacer edge protection region **530<sub>1</sub>** and a second spacer edge protection region **530<sub>2</sub>** that react or otherwise combine with one or more of the protective layer **516**, the tin-lithium alloy region **512**, and/or the lithium fluoride layer **510** to form a conformal coating **544** that at least partially seals and protects surfaces and/or interfaces between lithium in the anode **502** and various substances suspended in the electrolyte, e.g., copper (Cu). In some aspects, the dissociation of fluorine atoms from tin fluoride present in the conformal coating **544** may react with lithium in the anode **502** to form lithium fluoride, rather than form or grow into lithium dendrites. In this way, the conformal coating **544** may decrease lithium dendrite formation or growth from the anode **502**.

**[0128]** The conformal coating **544** may be deposited or disposed over the anode **502** at any number of different thicknesses. In some aspects, the conformal coating **544** may be less than 5  $\mu\text{m}$  thick. In other aspects, the conformal coating **544** may be less than 2  $\mu\text{m}$  thick. In some other aspects, the conformal coating **544** may be less than 1  $\mu\text{m}$  thick. These thickness levels may impede the migration of

polysulfides towards the anode **502** during battery cycling, thereby preventing at least some of the lithium ions from reacting with the polysulfides. Lithium ions that do not react with the polysulfides are available for transport from the anode to the cathode during discharge cycles of the battery.

**[0129]** The conformal coating **544** (as well as the protective layer **516** and the graded layer **514**) can uniquely regulate lithium ion flux toward the first edge **518<sub>1</sub>** and/or the second edge **518<sub>2</sub>** of the anode **502**, and thereby prevent corrosion of the anode **502**. Such regulation may function in a similar manner to gate spacers used during the fabrication of polysilicon (poly-Si) gates. Specifically, gate spacer or gate sidewall constructs may be used to protect and mechanically support polysilicon gates during the fabrication of integrated circuits (ICs). Similarly, edge protection provided by the conformal coating **544** for the anode **502** of FIG. **5** regulates lithium ion flux toward the first edge **518<sub>1</sub>** and/or the second edge **518<sub>2</sub>** of the anode **502**, and thereby prevents corrosion of the anode **502**. This type of edge protection provided by the conformal coating **544** for the anode **502** may equally apply to other battery and/or electrical cell formats and/or configurations such as (but not limited to) cylindrical cells, stacked cells, and/or the like, with various constructs engineered specifically to fit within the parameters of each of these designs.

**[0130]** In some implementations, fabrication and/or deposition of the conformal coating **544**, the protective layer **516**, and/or the graded layer **514** on the anode **502** may depend on the type of battery or cell construct in which the anode **502** is incorporated, e.g., cylindrical cells compared to pouch cells and/or prismatic cells. In one implementation, for cylindrical cells, metal anodes may be constructed from an electroactive material, typically metallic lithium, and/or lithium-containing alloys, such as graphitic and/or other carbonaceous composited including lithium, as well as any plenary uniform or multi-layer sheet of material. In one example, a solid metal lithium foil used as the anode **502** may be attached to a copper substrate used as the current collector **520** to facilitate electron transfer through a tab **546** to an external load, as depicted in the example of FIG. **5**. In other implementations, the battery **500** may include the anode **502** without the current collector **520**, where carbonaceous materials contained within the anode **502** may provide an electrically conductive medium coupled to a circuit.

**[0131]** In some implementations, the anode structure **500** may be incorporated into electrochemical cells and/or batteries by winding around a mandrel. Cylindrical cell layouts typically use double-sided anodes, such as the anode structure **500**. In some implementations, cylindrical cell constructions employing the anode structure **500** may use the conformal coating **544** to protect the first edge **518<sub>1</sub>** and/or the second edge **518<sub>2</sub>** of the anode **502**. The uniform protection provided by the conformal coating **544** may be referred to herein as “edge protection.” In one implementation, edge protection can be incorporated into a cell employing the anode structure **500** by extending the size and/or area of the protective layer **516** to overlap beyond any geometrically induced edge effects, e.g., surface roughness, of the anode.

**[0132]** In other implementations, the anode structure **500** may be incorporated into pouch cells and/or prismatic cells. Generally, two constructs of pouch and/or prismatic cells may be manufactured, including (1): jelly-roll type cells (e.g., seen in industry as lithium-polymer batteries), two

mandrel wound electrodes may be produced in a manner similar to cylindrical cells as discussed earlier; and (2): stacked plate type cells, which may be cut from a sheet of a pre-cast and/or pre-laminated prepared anode, leaving an unprotected edge of, for example, the anode 502 (when prepared in a stacked-plate type configuration) exposed and vulnerable to corrosion, fast ion fluxes and exposure within the cells. The conformal coating 544, in a stacked-plate type configuration, may protect the anode 502 and prevent lithium over-saturation in the electrolyte 540. In this way, the conformal coating 544 can control lithium plating on the anode 502 during operational cycling of the battery.

[0133] In some implementations, one or more chemical reactions may occur between the electrolyte 540 and the anode 502 (involving solvent decomposition and/or additive reactions) during cell assembly or cell rest period. These chemical reactions may assist in the production of the conformal coating 544. In some aspects, elevated and/or reduced temperatures (e.g., relative to room temperature and/or 20° C.) may be used as a stimulus for lithium-induced polymerization of the conformal coating 544. For example, the lithium-induced polymerization may occur in the presence of one or more catalysts and/or by using lithium metal, and its associated chemical reactivity, as an inducing agent to initiate free-radical based polymerization of constituent species within any one or more layers of the anode structure 500 and/or the conformal coating 544. In addition, electrochemical reactions under electrical bias in either the forward or reverse direction may be used to fabricate and/or deposit the conformal coating 544 onto the anode 502, as well as usage of secondary metals and/or salts as additives that may decompose to form an alloy on the first edge 518<sub>1</sub> and/or the second edge 518<sub>2</sub> of metallic lithium in the anode 502 exposed to the electrolyte 540. For example, suitable additives may contain one or more metallic species, e.g., desired for co-alloying with lithium or to be used as a blocking layer to reduce lithium transfer to the first edge 518<sub>1</sub> and/or the second edge 518<sub>2</sub> of the anode 502.

[0134] FIG. 6 shows a schematic diagram of an enlarged portion 600 of the anode structure 500 of FIG. 5, according to some implementations. The enlarged portion 600 illustrates placement of the first spacer edge protection region 530<sub>1</sub> and the second spacer edge protection region 530<sub>2</sub> (collectively referred to as the edge protection region 530 in FIG. 6) in a direction orthogonal to the first edge 518<sub>1</sub> and/or the second edge 518<sub>2</sub>, as shown in FIG. 5. As a result, the edge protection region 530, which may include various carbonaceous materials 610 organized into structures and/or lattices, may block lithium ions from undesirably escaping the anode 502 across the edge protection region 530. In this way, lithium ion dissociation, flux, transport, and/or other movement may be channeled effectively throughout the enlarged portion 600 of FIG. 6 (as well as the anode structure 500 of FIG. 5), thereby yielding optimal battery operational cycling. In some implementations, carbonaceous materials 610 used to produce the edge protection region may include few layer graphene (FLG), multi-layer graphene (MLG), graphite, carbon nano-tubes (CNTs), carbon nano-onions (CNOs) and/or the like. The carbonaceous materials 610 (e.g., shown in FIG. 8A, FIG. 8B, FIG. 9 and/or FIG. 10) may be synthesized, self-nucleated, or otherwise joined together at varying concentration levels to provide for complete tunability of the edge protection region 530. For example, the density, thickness, and/or composi-

tions of may be designed to reduce lithium ion permeation more than the protective layer 516 or the graded layer 514 to direct lithium ion permeation accordingly. In some implementations, the edge protection region 530 may be less than 5 μm thick. In other aspects, the edge protection region 530 may be less than 2 μm thick. In some other aspects, the edge protection region 530 may be less than 1 μm thick. In some implementations, a conductive additive 640 may be added to the carbonaceous materials 610, as well as a binder 620.

[0135] FIG. 7 shows a diagram of a polymeric network 710, according to some implementations. In some aspects, the polymeric network 710 may be one example of the polymeric network 285 of FIG. 2. The polymeric network 710 may be disposed on an anode 702. The anode 702 may be formed as an alkali metal layer having one or more exposed surfaces that include any number of alkali metal-containing nanostructures or microstructures. The alkali metal may include (but is not limited to) lithium, sodium, zinc, indium and/or gallium. The anode 710 may release alkali ions during operational cycling of the battery.

[0136] A layer 714 of carbonaceous materials may be grafted with fluorinated polymer chains and deposited over one or more exposed surfaces of the anode 702. The grafting may be based on (e.g., initiated by) activation of carbonaceous material with one or more radical initiators, for example, benzoyl peroxide (BPO) or azobisisobutyronitrile (AIBN), followed by reaction with monomer molecules. The polymeric network 710 may be based on the fluorinated polymer chains cross-linked with one another and carbonaceous materials of the layer 714 such that the layer 714 is consumed during generation of the polymeric network 710. In some implementations, the polymeric network 710 may have a thickness approximately between 0.001 μm and 5 μm and include between approximately 0.001 wt. % to 2 wt. % of the fluorinated polymer chains. In some other implementations, the cross-linked polymeric network 710 may include between approximately 5 wt. % to 100 wt. % of the plurality of carbonaceous materials grafted with fluorinated polymer chains and a balance of fluorinated polymers, or one or more non-fluorinated polymers, or one or more cross-linkable monomers, or combinations thereof. In one implementation, carbonaceous materials grafted with fluorinated polymer chains may include 5 wt. % to 50 wt. % of fluorinated polymer chains and a balance of carbonaceous material.

[0137] During battery cycling, carbon-fluorine bonds within the polymeric network 710 may chemically react with newly forming Lithium metal and convert into carbon-Lithium bonds (C—Li). These C—Li bonds may, in turn, react with carbon-fluorine bonds within the polymeric network 710 via a Wurtz reaction 750, to further cross-link polymeric network by newly formed C—C bonds and to form an alkali-metal containing fluoride (such as lithium fluoride (LiF)). Additional polymeric network cross-linking leading to uniform formation of the alkali-metal containing fluoride may thereby suppress alkali metal dendrite formation 740 associated with the anode 702, thereby improving battery performance and longevity. In one implementation, grafting of fluorinated m/acrylate (FMA) to one or more exposed graphene surfaces of carbonaceous materials in the layer 714 may be performed in an organic solution, e.g., leading to the formation of graphene-graft-poly-FMA and/or the like. Incorporation of carbon-fluorine bonds on exposed graphene surfaces may enable the Wurtz reaction 750 to occur between carbon-fluorine bonds and metallic surface of

an alkali metal (e.g., lithium) provided by the anode **702**. In this way, completion of the Wurtz reaction **750** may result in the formation of the polymeric network **710**. In some aspects, the polymeric network **710** may include a density gradient **716** pursuant to completion of the Wurtz reaction **750**. The density gradient **716** may include interconnected graphene flakes and may be infused with one or more metal-fluoride salts formed in-situ. In addition, layer porosity and/or mechanical properties may be tuned by carbon loading and/or a combination of functionalized carbons, each having a unique and/or distinct physical structure.

**[0138]** In some implementations, carbonaceous materials within the density gradient **716** may include one or more of flat graphene, wrinkled graphene, a plurality of carbon nano-tubes (CNTs), or a plurality of carbon nano-onions (CNOs) (e.g., as depicted in FIG. **8A** and/ FIG. **8B** and as shown in the micrographs of FIG. **9** and FIG. **10**). In one implementation, graphene nanoplatelets may be dispersed throughout and isolated from each other within the polymeric network **710**. The dispersion of the graphene nanoplatelets includes one or more different concentration levels. In one implementation, the dispersion of the graphene nanoplatelets may include at least some of the carbonaceous materials functionalized with at least some of the fluorinated polymer chains.

**[0139]** For example, the fluorinated polymer chains may include one or more acrylate or methacrylate monomers including 2,2,3,3,4,4,5,5,6,6,7,7-Dodecafluoroheptyl acrylate (DFHA), 3,3,4,4,5,5,6,6,7,7,8,8,9,9,10,10,10-Heptadecafluorodecyl methacrylate (HDFDMA), 2,2,3,3,4,4,5,5-Octafluoropentyl methacrylate (OFPMA), Tetrafluoropropyl methacrylate (TFPM), 3-[3,3,3-Trifluoro-2-hydroxy-2-(trifluoromethyl)propyl]bicyclo[2.2.1]hept-2-yl methacrylate (HFA monomer), or vinyl-based monomers including 2,3,4,5,6-Pentafluorostyrene (PFSt).

**[0140]** In some implementations, fluorinated polymer chains may be grafted to a surface of the layer of carbonaceous materials and may thereby chemically interact with the one or more surfaces of the alkali metal of the anode via the Wurtz reaction **750**. In organic chemistry, organometallic chemistry, and inorganic main-group polymers, the Wurtz reaction is a coupling reaction, whereby two alkyl halides are reacted with sodium metal (or some other metal) in dry ether solution to form a higher alkane. In this reaction alkyl halides are treated with alkali metal, for example, sodium metal in dry ethereal (free from moisture) solution to produce higher alkanes. In case of Sodium intermediate product of the Wurtz reaction are highly polar and highly reactive Carbon-Sodium metal bonds, which in turn are chemically reacting with Carbon-Halide bonds to yield newly formed C—C bonds and Sodium Halide. A formation of new Carbon-Carbon bonds allows to use the Wurtz reaction for the preparation of higher alkanes containing even number of carbon atoms, for example:



**[0141]** Other metals have also been used to influence Wurtz coupling, among them silver, zinc, iron, activated copper, indium and a mixture of manganese and copper chloride. The related reaction dealing with aryl halides is called the Wurtz-Fittig reaction. This can be explained by the formation of free radical intermediate and its subsequent disproportionation to give alkene. The Wurtz reaction **750** occurs through a free-radical mechanism that makes pos-

sible side reactions producing alkene products. In some implementations, chemical interactions associated with the Wurtz reaction described above may form an alkali metal fluoride, e.g., lithium fluoride.

**[0142]** In one implementation, the polymeric network **710** may include an interface layer **718** in contact with the anode **702**. A protective layer **720** may be disposed on top of the interface layer **718**, which may be based on the Wurtz reaction **750** at an interface between the anode **702** and the polymeric network **710**. The interface layer **718** may have a relatively high cross-linking density (e.g., of fluorinated polymers and/or the like), a high metal-fluoride concentration, and a relatively low carbon-fluorine bond concentration. In contrast to the interface layer **718**, the protective layer **720** may have a relatively low cross-linking density, a low metal-fluoride concentration, and a high carbon-fluorine bond concentration.

**[0143]** In some implementations, the interface layer **718** may include cross-linkable monomers such as methacrylate (MA), acrylate, vinyl functional groups, or a combination of epoxy and amine functional groups. In one implementation, the protective layer **720** may be characterized by the density gradient **716**. In this way, the density gradient **716** may be associated with one or more self-healing properties of the protective layer **720** and/or may strengthen the polymeric network **710**. In some implementations, the strengthened polymeric network **720** may further suppress alkali metal dendrite formation **740** from the anode **702** during battery cycling.

**[0144]** Operationally, the interface layer **718** may suppress alkali metal dendrite formation **740** associated with the anode **702** by uniformly producing metal-fluorides, e.g., lithium fluoride, at an interface across the length of the anode **702**. The uniform production of metal fluorides causes dendrite surface dissolution, e.g., via conversion into metal-fluorides, ultimately suppressing alkali metal dendrite formation **740**. In addition, cross-linking of fluorinated polymer chains over remaining dendrites may further suppress alkali metal dendrite formation **740**. In some implementations, the density gradient **716** may be tuned to control the degree of cross-linking between the fluorinated polymer chains.

**[0145]** FIG. **8A** shows a simplified cutaway view of an example carbonaceous particle **800** with graded porosity, according to some implementations. The carbonaceous particle **800** may be synthesized in a reactor, and output in a controlled manner to produce the cathode **110** and/or anode **120** of FIG. **1**, the cathode **210** and/or anode **220** of FIG. **2**, or the electrode **300** of FIG. **3**. The carbonaceous particle **800**, which may also be referred to as a composition of matter, includes a plurality of regions nested within each other. Each region may include at least a first porosity region **811** and a second porosity region **812**. The first porosity region **811** may include a plurality of first pores **801**, and the second porosity region **812** may include a plurality of second pores **802**. In some aspects, each region may be separated from immediate adjacent regions by at least some of the first pores **801**. The first pores **801** may be dispersed throughout the first porosity region **811** of the carbonaceous particle **800**, and the second pores **802** may be dispersed throughout the second porosity region **812** of the carbonaceous particle **800**. In this way, the first pores **801** may be associated with a first pore density, and the second pores **802** may be associated with a second pore density that is different

than the first pore density. In some aspects, the first pore density may be between approximately 0.0 cubic centimeters (cc)/g and 2.0 cc/g, and the second pore density may be between approximately 1.5 and 5.0 cc/g. In some aspects, the first pores **801** may be configured to retain polysulfides **820**, and the second pores **802** may provide exit pathways from the carbonaceous particle **800**.

[0146] A group of carbonaceous particles **800** may be joined together to form a carbonaceous aggregate (not shown for simplicity), and a group of carbonaceous aggregates may be joined together to form a carbonaceous agglomerate (not shown for simplicity). In some implementations, the first and second pores **801** and **802** may be dispersed throughout aggregates formed by respective groups of the carbonaceous particles **800**. In some aspects, the first porosity region **811** may be at least partially encapsulated by the second porosity region **812** such that a respective agglomerate may include some of the first pores **801** and/or some of the second pores **802**.

[0147] In some implementations, the carbonaceous particle **800** may have a principal dimension "A" in an approximate range between 20 nm and 150 nm, an aggregate formed by a group of the carbonaceous particle **800** may have a principal dimension in an approximate range between 20 nm and 10  $\mu\text{m}$ , and an agglomerate formed by a group of aggregates may have a principal dimension in an approximate range between 0.1  $\mu\text{m}$  and 1,000  $\mu\text{m}$ . In some aspects, at least some of the first pores **801** and the second pores **802** has a principal dimension in an approximate range between 1.3 nm and 32.3 nm. In one implementation, each of the first pores **801** has a principal dimension in an approximate range between 0 nm and 100 nm.

[0148] The carbonaceous particle **800** may also include a plurality of deformable regions **813** distributed along a perimeter **810** of the carbonaceous particle **800**. The carbonaceous particle **800** may conduct electricity along joined boundaries with (such as the perimeter **810**) one or more other carbonaceous particles. The carbonaceous particle **800** may also confine polysulfides **820** within the first pores **801** and/or at one or more blocking regions **822**, thereby inhibiting the migration of polysulfides **820** towards the anode and increasing the rate at which lithium ions can be transported from the anode to the cathode of a host battery.

[0149] In some implementations, the carbonaceous particle **800** may have a surface area of exposed carbon surfaces in an approximate range between 10  $\text{m}^2/\text{g}$  to 3,000  $\text{m}^2/\text{g}$ . In other implementations, the carbonaceous particle **800** may have a composite surface area including sulfur **824** micro-confined within a number of the first pores **801** and/or a number of the second pores **802**. As used herein, the first and second pores **801** and **802** that micro-confine polysulfides **820** may be referred to as "functional pores." In some aspects, one or more of the carbonaceous particles, the aggregates formed by corresponding groups of carbonaceous particles, or the agglomerates formed by corresponding groups of aggregates may include one or more exposed carbon surfaces configured to nucleate the sulfur **824**. The composite surface area may be in an approximate range between 10  $\text{m}^2/\text{g}$  to 3,000  $\text{m}^2/\text{g}$ , and the carbonaceous particle **800** may have a sulfur to carbon weight ratio between approximately 1:5 to 10:1. In some aspects, the carbonaceous particle **800** may have an electrical conductivity in an approximate range between 100 S/m to 20,000 S/m at a pressure of 12,000 pounds per square inch (psi).

[0150] In some implementations, the carbonaceous particle **800** may include a surfactant or a polymer that includes one or more of styrene butadiene rubber, polyvinylidene fluoride, poly acrylic acid, carboxyl methyl cellulose, polyvinylpyrrolidone, and/or polyvinyl acetate that can act as a binder to join a group of the carbonaceous particles **800** together. In other implementations, the carbonaceous particle **800** may include a gel-phase electrolyte or a solid-phase electrolyte disposed within at least some of the pores **801** or **802**.

[0151] FIG. 8B shows a diagram of an example of a tri-zone particle **850**, according to some implementations. In various implementations, the tri-zone particle **850** may be one example of the carbonaceous particle **800** of FIG. 8A. The tri-zone particle **850** may include three discrete zones such as (but not limited to) a first zone **851**, a second zone **852**, and a third zone **853**. In some aspects, each of the zones **851-853** surrounds and/or encapsulates a preceding zone. For example, the first zone **851** may be surrounded by or encapsulated by the second zone **852**, and the second zone **852** may be surrounded by or encapsulated by the third zone **853**. The first zone **851** may correspond to an inner region of the particle **850**, the second zone **852** may correspond to an intermediate transition region of the particle **850**, and the third zone **853** may correspond to an outer region of the particle **850**. In some aspects, the tri-zone particle **850** may include a permeable shell **855** that deforms in response to contact with one or more adjacent non-tri-zone particles and/or tri-zone particles **850**.

[0152] In some implementations, the first zone **851** may have a relatively low density, a relatively low electrical conductivity, and a relatively high porosity, the second zone **852** may have an intermediate density, an intermediate electrical conductivity, and an intermediate porosity, and the third zone **853** may have a relatively high density, a relatively high electrical conductivity, and a relatively low porosity. In some aspects, the first zone **851** may have a density of carbonaceous material between approximately 1.5 g/cc and 5.0 g/cc, the second zone **852** may have a density of carbonaceous material between approximately 0.5 g/cc and 3.0 g/cc, and the third zone **853** may have a density of carbonaceous material between approximately 0.0 and 1.5 g/cc. In other aspects, the first zone **851** may include pores having a width between approximately 0 and 40 nm, the second zone **852** may include pores having a width between approximately 0 and 35 nm, and the third zone **853** may include pores having a width between approximately 0 and 30 nm. In some other implementations, the second zone **852** may not be defined for the tri-zone particle **850**. In one implementation, the first zone **851** may have a principal dimension  $D_1$  between approximately 0 nm and 100 nm, the second zone **852** may have a principal dimension  $D_2$  between approximately 20 nm and 150 nm, and the third zone **853** may have a principal dimension  $D_3$  of approximately 200 nm.

[0153] Aspects of the present disclosure recognize that the unique layout of the tri-zone particle **850** and the relative dimensions, porosities, and electrical conductivities of the first zone **851**, the second zone **852**, and the third zone **853** can be selected and/or modified to achieve a desired balance between minimizing the polysulfide shuttle effect and maximizing the specific capacity of a host battery. Specifically, in some aspects, the pores may decrease in size and volume from one zone to other. In some implementations, the

tri-zone particle may consist entirely of one zone with a range of pore sizes and pores distributions (e.g., pore density). For the example of FIG. 8B, the pores 861 associated with the first zone 851 or the first porosity region have relatively large widths and may be defined as macropores, the pores 862 associated with the second zone 851 or the second porosity region have intermediate-sized widths and may be defined as mesopores, and the pores 863 associated with the third zone 853 or the third porosity region have relatively small widths and may be defined as micropores.

[0154] A group of tri-zone particles 850 may be joined together to form an aggregate (not shown for simplicity), and a group of the aggregates may be joined together to form an agglomerate (not shown for simplicity). In some implementations, a plurality of mesopores may be interspersed throughout the aggregates formed by respective groups of the carbonaceous particles 800. In some aspects, the first porosity region 811 may be at least partially encapsulated by the second porosity region 812 such that a respective aggregate may include one or more mesopores and one or more macropores. In one implementation, each mesopore may have a principal dimension between 3.3 nanometers (nm) and 19.3 nm, and each macropore may have a principal dimension between 0.1  $\mu\text{m}$  and 1,000  $\mu\text{m}$ . In some instances, the tri-zone particle 850 may include carbon fragments intertwined with each other and separated from one another by at least some of the mesopores.

[0155] In some implementations, the tri-zone particle 850 may include a surfactant or a polymer that includes one or more of styrene butadiene rubber, polyvinylidene fluoride, poly acrylic acid, carboxyl methyl cellulose, polyvinylpyrrolidone, and/or polyvinyl acetate that can act as a binder to join a group of the carbonaceous materials together. In other implementations, the tri-zone particle 850 may include a gel-phase electrolyte or a solid-phase electrolyte disposed within at least some of the pores.

[0156] In some implementations, the tri-zone particle 850 may have a surface area of exposed carbonaceous surfaces in an approximate range between 10  $\text{m}^2/\text{g}$  to 3,000  $\text{m}^2/\text{g}$  and/or a composite surface area (including sulfur microconfined within pores) in an approximate range between 10  $\text{m}^2/\text{g}$  to 3,000  $\text{m}^2/\text{g}$ . In one implementation, a composition of matter including a multitude of tri-zone particles 850 may have an electrical conductivity in an approximate range between 100 S/m to 20,000 S/m at a pressure of 12,000 pounds per square inch (psi) and a sulfur to carbon weight ratio between approximately 1:5 to 10:1.

[0157] FIG. 8C shows an example step function 800C representative of the average pore volumes in each of the regions of the tri-zone particle 850 of FIG. 8B, according to some implementations. As discussed, the pores distributed throughout the tri-zone particle 850 may have different sizes, volumes, or distributions. In some implementations, the average pore volume may decrease based on a distance between a center of the tri-zone particle 850 and an adjacent zone, for example, such that pores associated with the first zone 851 or the first porosity region have a relatively large volume or pore size, pores associated with the second zone 852 or the second porosity region have an intermediate volume, and pores associated with the third zone 853 or the third porosity region have a relatively small volume. The interior region has a higher pore volume than the regions near the periphery. The region with higher pore volume provides for high sulfur loading whereas the lower pore

volume outer regions mitigate the migration of polysulfides during cell cycling. In the example of FIG. 8C, the average pore volume in the inner region is approximately 3 cc/g, the average pore volume in the outermost region is  $-0.5$  cc/g and the average pore volume in the intermediate region is between 0.5 cc/g and 3 cc/g.

[0158] FIG. 8D shows a graph 800D depicting an example distribution of pore volume versus pore width of carbonaceous particles described herein. As depicted in the graph 800D, pores associated with a relatively high pore volume may have a relatively low pore width, for example, such that the pore width generally increases as the pore volume decreases. In some aspects, pores having a pore width less than approximately 1.0 nm may be referred to as micropores, pores having a pore width between approximately 3 and 11 nm may be referred to as mesopores, and pores having a pore width greater than approximately 24 nm may be referred to as macropores.

[0159] FIG. 9A shows a micrograph 900 of a plurality of carbonaceous structures 902, according to some implementations. In some implementations, each of the carbonaceous structures 902 may have a substantially hollow a core region surrounded by various monolithic carbon growths and/or layering. In some aspects, the monolithic carbon growths and/or layering may be examples of the monolithic carbon growths and/or layering described with reference to FIGS. 8A and 8B. In some instances, the carbonaceous structures 902 may include several concentric multi-layered fullerenes and/or similarly shaped carbonaceous structures organized at varying levels of density and/or concentration. For example, the actual final shape, size, and graphene configuration of each of the carbonaceous structures 902 may depend on various manufacturing processes. The carbonaceous structures 902 may, in some aspects, demonstrate poor water solubility. As such, in some implementations, non-covalent functionalization may be utilized to alter one or more dispersibility properties of the carbonaceous structures 902 without affecting the intrinsic properties of the underlying carbon nanomaterial. In some aspects, the underlying carbon nanomaterial may be formative a  $\text{sp}^2$  carbon nanomaterial. In some implementations, each of the carbonaceous structures 902 may have a diameter between approximately 20 and 500 nm. In various implementations, groups of the carbonaceous structures 902 may coalesce and/or join together to form aggregates 904. In addition, groups of the aggregates 904 may coalesce and/or join together to form agglomerates 906. In some aspects, one or more of the carbonaceous structures 902, the aggregates 904, and/or the agglomerates 906 may be used to form the anode and/or the cathode of the battery 100 of FIG. 1, the battery 200 of FIG. 2, or the electrode 300 of FIG. 3.

[0160] FIG. 9B shows a micrograph 950 of an aggregate formed of carbonaceous material, according to some implementations. In some implementations, the aggregate 960 may be an example of one of the aggregates 904 of FIG. 9. In one implementation, exterior carbonaceous shell-type structures 952 may fuse together with carbons provided by other carbonaceous shell-type structures 954 to form a carbonaceous structure 956. A group of the carbonaceous structures 956 may coalesce and/or join with one another to form the aggregate 1010. In some aspects, a core region 958 of each of the carbonaceous structures 956 may be tunable, for example, in that the core region 958 may include various defined concentration levels of interconnected graphene

structures, as described with reference to FIG. 8A and/or FIG. 8B. In some implementations, some of the carbonaceous structures 956 may have a first concentration of interconnected carbons approximately between 0.1 g/cc and 2.3 g/cc at or near the exterior carbonaceous structure 952. Each of the carbonaceous structures 956 may have pores to transport lithium ions extending inwardly from toward the core region 1008.

[0161] In some implementations, the pores in each of the carbonaceous structures 956 may have a width or dimension between approximately 0.0 nm and 0.5 nm, between approximately 0.0 and 0.1 nm, between approximately 0.0 and 6.0 nm, or between approximately 0.0 and 35 nm. Each carbonaceous structures 956 may also have a second concentration at or near the core region 958 that is different than the first concentration. For example, the second concentration may include several relatively lower-density carbonaceous regions arranged concentrically. In one implementation, the second concentration may be lower than the first concentration at between approximately 0.0 g/cc and 1.0 g/cc or between approximately 1.0 g/cc and 1.5 g/cc. In some aspects, the relationship between the first concentration and the second concentration may be used to achieve a balance between confining sulfur or polysulfides within a respective electrode and maximizing the transport of lithium ions. For example, sulfur and/or polysulfides may travel through the first concentration and be at least temporarily confined within and/or interspersed throughout the second concentration during operational cycling of a lithium-sulfur battery.

[0162] In some implementations, at least some of the carbonaceous structures 956 may include CNO oxides organized as a monolithic and/or interconnected growths and be produced in a thermal reactor. For example, the carbonaceous structures 956 may be decorated with cobalt nanoparticles according to the following example recipe: cobalt(II) acetate ( $C_4H_6CoO_4$ ), the cobalt salt of acetic acid (often found as tetrahydrate  $Co(CH_3CO_2)_2 \cdot 4H_2O$ , which may be abbreviated as  $Co(OAc)_2 \cdot 4H_2O$ , may be flowed into the thermal reactor at a ratio of approximately 59.60 wt % corresponding to 40.40 wt % carbon (referring to carbon in CNO form), resulting in the functionalization of active sites on the CNO oxides with cobalt, showing cobalt-decorated CNOs at a 15,000 $\times$  level, respectively. In some implementations, suitable gas mixtures used to produce Carbon #29 and/or the cobalt-decorated CNOs may include the following steps:

[0163] Ar purge 0.75 standard cubic feet per minute (scfm) for 30 min;

[0164] Ar purge changed to 0.25 scfm for run;

[0165] temperature increase: 25° C. to 300° C. 20 mins; and

[0166] temperature increase: 300°-500° C. 15 mins.

[0167] Carbonaceous materials described with reference to FIGS. 9A and 9B may include or otherwise be formed from one or more instances of graphene, which may include a single layer of carbon atoms with each atom bound to three neighbors in a honeycomb structure. The single layer may be a discrete material restricted in one dimension, such as within or at a surface of a condensed phase. For example, graphene may grow outwardly only in the x and y planes (and not in the z plane). In this way, graphene may be a two-dimensional (2D) material, including one or several

layers with the atoms in each layer strongly bonded (such as by a plurality of carbon-carbon bonds) to neighboring atoms in the same layer.

[0168] In some implementations, graphene nanoplatelets (e.g., formative structures included in each of the carbonaceous structures 956) may include multiple instances of graphene, such as a first graphene layer, a second graphene layer, and a third graphene layer, all stacked on top of each other in a vertical direction. Each of the graphene nanoplatelets, which may be referred to as a GNP, may have a thickness between 1 nm and 3 nm, and may have lateral dimensions ranging from approximately 100 nm to 100  $\mu$ m. In some implementations, graphene nanoplatelets may be produced by multiple plasma spray torches arranged sequentially by roll-to-roll (R2R) production. In some aspects, R2R production may include deposition upon a continuous substrate that is processed as a rolled sheet, including transfer of 2D material(s) to a separate substrate. In some instances, the R2R production may be used to form the first thin film 310 and/or the second thin film 320 of the electrode 300 of FIG. 3, for example, such that the concentration level of the first aggregates 312 within the first thin film 310 is different than the concentration level of the second aggregates 322 within the second thin film 320. That is, the plasma spray torches used in the R2R processes may spray carbonaceous materials at different concentration levels to create the first thin film 310 and/or the second thin film 320 using specific concentration levels of graphene nanoplatelets. Therefore, R2R processes may provide a fine level of tunability for the battery 100 of FIG. 1 and/or the battery 200 of FIG. 2.

[0169] FIGS. 10A and 10B show transmission electron microscope (TEM) images 1000 and 1050, respectively, of carbonaceous particles treated with carbon dioxide ( $CO_2$ ), according to some implementations. The carbonaceous particles shown in FIGS. 10A and 10B may include or otherwise be formed from one or more instances of graphene, which may include a single layer of carbon atoms with each atom bound to three neighbors in a honeycomb structure.

[0170] FIG. 11 shows a diagram 1100 depicting carbon porosity types of various carbonaceous aggregates, according to some implementations. In various implementations, the carbonaceous aggregates described with reference to FIG. 11 may be examples of the aggregates 904 of FIG. 9A and/or the aggregates 956 of FIG. 9B. In some aspects, the carbonaceous aggregates described with reference to FIG. 11 may be used to form the electrode 300 of FIG. 3. As discussed, the aggregates may be formed from or may include a group of carbonaceous structures such as the carbonaceous structure 902 of FIG. 9A or the carbonaceous structures 956 of FIG. 9B. In some aspects, the carbonaceous structures may be CNOs.

[0171] The carbonaceous structures may be used to form an electrode (such as the electrode 300 of FIG. 3) having any of the porosity types shown in the diagram 1100. For example, the electrode may include any of a porosity type I 1110, a porosity type II 1120, and a porosity type III 1130. In some implementations, the porosity type I 1110 may include a first pore 1111, a second pore 1112, and a third pore 1113, all sized with a principal dimension of less than 5 nm to retain polysulfides within the electrode. Some polysulfides may grow in size upon forming larger complexes and become immovably lodged within pores of the porosity type I 1110. In some implementations, aggregates may be joined together to create pores of the porosity type II 1120 and/or

porosity type III **1130** that can retain larger polysulfides and/or polysulfide complexes.

[0172] FIG. **12** shows a graph **1200** depicting pore size versus pore distribution of an example electrode, according to some implementations. As used herein, “Carbon 1” refers to structured carbonaceous materials including mostly micropores (such as less than 5 nm in principal dimension), and “Carbon 2” refers to structured carbonaceous materials including mostly mesopores (such as between approximately 20 nm to 50 nm in principal dimension). In some implementations, an electrode suitable for use in one of the batteries disclosed herein may be prepared to have the pore size versus pore distribution depicted in the graph **1200**.

[0173] FIG. **13** shows a first graph **1300** and a second graph **1310** depicting battery performance per cycle number, according to some implementations. Specifically, the first graph **1300** shows the specific discharge capacity of an example battery employing an electrolyte **1302** disclosed herein relative to the specific discharge capacity of a conventional battery employing a conventional electrolyte. The second graph shows the capacity retention of the battery employing the electrolyte **1302** relative to the capacity retention of the battery employing the conventional electrolyte. In some aspects, the electrolyte **1302** may be one example of the electrolyte **130** of FIG. **1** or the electrolyte **230** of FIG. **2**. In the first graph **1300** and the second graph **1310**, the conventional electrolyte is prepared as 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=1:1:1) with 2 wt. % LiNO<sub>3</sub>.

[0174] FIG. **14** shows a bar chart **1400** depicting battery performance per cycle number, according to some implementations. Specifically, the bar chart **1400** depicts the specific discharge capacity per cycle number of an example battery employing an electrolyte **1402** disclosed herein relative to the specific discharge capacity per cycle number of a conventional battery employing a conventional electrolyte. In some aspects, the electrolyte **1402** may be one example of the electrolyte **130** of FIG. **1** or the electrolyte **230** of FIG. **2**. In the graph **1400**, the conventional electrolyte is prepared as 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=1:1:1). The bar chart **1400** shows that employing the electrolyte **1402** in an example battery (such as the battery **100** of FIG. **1** or the battery **200** of FIG. **2**) may increase the specific discharge capacity of the battery by approximately 28% at the 3<sup>rd</sup> cycle number, by approximately 30% at the 50<sup>th</sup> cycle number, and by approximately 39% at the 60<sup>th</sup> as compared to a battery employing the conventional electrolyte.

[0175] FIG. **15** shows a first graph **1500** and a second graph **1510** depicting battery performance per cycle number, according to some implementations. Specifically, the first graph **1500** shows the electrode discharge capacity per cycle number of an example lithium-sulfur coin cell employing an electrolyte **1502** disclosed herein relative to the electrode discharge capacity per cycle number of an example lithium-sulfur coin cell battery employing a conventional electrolyte, and the second graph **1510** shows the capacity retention per cycle number of the lithium-sulfur coin cell battery employing the electrolyte **1502** relative to the electrode discharge capacity per cycle number of the lithium-sulfur coin cell battery employing the conventional electrolyte. In some aspects, the electrolyte **1502** may be one example of the electrolyte **130** of FIG. **1** or the electrolyte **230** of FIG. **2**. The lithium-sulfur coin cell battery is cycled at a dis-

charge rate of 1C (such as fully discharged within one hour), at 100% depth-of-discharge (DOD) and is kept at approximately at room temperature (68° F. or 20° C.). The conventional electrolyte is prepared as 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=1:1:1) with 2 wt. % LiNO<sub>3</sub>.

[0176] FIG. **16** shows a graph **1600** depicting electrode discharge capacity per cycle number, according to some implementations. Specifically, the graph **1600** depicts the electrode discharge capacity per cycle number of an example battery employing an electrolyte **1602** disclosed herein relative to the electrode discharge capacity of a conventional battery employing a conventional electrolyte. In some aspects, the electrolyte **1602** may be one example of the electrolyte **130** of FIG. **1** or the electrolyte **230** of FIG. **2**. The conventional electrolyte is prepared as 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=1:1:1) with 2 wt. % LiNO<sub>3</sub>, and the electrolyte **1602** is prepared as 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=58:29:13) with approximately 2 wt. % LiNO<sub>3</sub>.

[0177] FIG. **17** shows another graph **1700** depicting electrode discharge capacity per cycle number, according to some implementations. Specifically, the graph **1700** depicts the electrode discharge capacity per cycle number of an example battery employing an electrolyte **1702** and solvent package **1704** disclosed herein relative to the electrode discharge capacity of a conventional battery employing a conventional electrolyte and solvent package. The conventional electrolyte is prepared as 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=1:1:1) with approximately 2 wt. % LiNO<sub>3</sub>, and the electrolyte **1702** is prepared as 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=58:29:13) with 2 wt. % LiNO<sub>3</sub>. The conventional solvent package is prepared as 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=1:1:1), and the solvent package **1704** is prepared as 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=58:29:13).

[0178] FIG. **18** shows a graph **1800** depicting specific discharge capacity per cycle number for various TBT-containing electrolyte mixtures, according to some implementations. As shown in the graph **1800**, “181” indicates an electrolyte without any TBT additions, resulting in a 0 M TBT concentration level, “181-25TBT” indicates an electrolyte prepared at a 25 M TBT concentration level and so on and so forth. In some implementations, a 5M TBT concentration level may result in an approximate 70 mAh/g discharge capacity increase relative to the electrolyte without any TBT additions.

[0179] FIG. **19** shows a first graph **1900** depicting electrode discharge capacity per cycle number and a second graph **1910** depicting electrode capacity retention per cycle number, according to some implementations. Specifically, the first graph **1900** depicts the electrode discharge capacity per cycle number of an example battery that includes a protective lattice disclosed herein relative to the electrode discharge capacity of an example battery that does not include the protective lattice disclosed herein. The second graph **1910** depicts the electrode capacity retention per cycle number of an example battery that includes the protective lattice disclosed herein relative to the electrode capacity retention of an example battery that does not include the protective lattice disclosed herein. In some aspects, the protective lattice may be one example of the protective lattice **402** of FIG. **4**. Performance results for both the first

graph 1900 and the second graph 1910 include usage of an electrolyte prepared with 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=58:29:13) with 2 wt.% LiNO<sub>3</sub>.

[0180] FIG. 20 shows a first graph 2000 depicting electrode discharge capacity per cycle number and a second graph 2010 depicting electrode capacity retention per cycle number, according to other implementations. Specifically, the first graph 2000 depicts the electrode discharge capacity per cycle number of an example battery that includes the polymeric network of FIG. 7. The second graph 2010 depicts the discharge capacity retention per cycle number of an example battery that includes the polymeric network of FIG. 7. The battery may be one example of the battery 100 of FIG. 1 or the battery 200 of FIG. 2. Performance results for both the first graph 2000 and the second graph 2010 include usage of an electrolyte prepared with 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=58:29:13) with 2 wt.% LiNO<sub>3</sub>.

[0181] FIG. 21 shows a first graph 2100 depicting electrode discharge capacity per cycle number and a second graph 2110 depicting electrode capacity retention per cycle number, according to some other implementations. Specifically, the first graph 2100 depicts the electrode discharge capacity per cycle number of an example battery that includes the protective layer 516 of FIG. 5. The second graph 2110 depicts the discharge capacity retention per cycle number of an example battery that includes the protective layer 516 of FIG. 5. The battery may be one example of the battery 100 of FIG. 1 or the battery 200 of FIG. 2. Performance results for both the first graph 1900 and the second graph 1910 include usage of an electrolyte prepared with 1 M LiTFSI in DME:DOL:TEGDME (volume: volume: volume=58:29:13) with 2 wt.% LiNO<sub>3</sub>.

[0182] As used herein, a phrase referring to “at least one of” or “one or more of” a list of items refers to any combination of those items, including single members. For example, “at least one of: a, b, or c” is intended to cover the possibilities of: a only, b only, c only, a combination of a and b, a combination of a and c, a combination of b and c, and a combination of a and b and c.

[0183] The various illustrative components, logic, logical blocks, modules, circuits, operations, and algorithm processes described in connection with the implementations disclosed herein may be implemented as electronic hardware, firmware, software, or combinations of hardware, firmware, or software, including the structures disclosed in this specification and the structural equivalents thereof. The interchangeability of hardware, firmware and software has been described generally, in terms of functionality, and illustrated in the various illustrative components, blocks, modules, circuits and processes described above. Whether such functionality is implemented in hardware, firmware or software depends upon the application and design constraints imposed on the overall system.

[0184] Various modifications to the implementations described in this disclosure may be readily apparent to persons having ordinary skill in the art, and the generic principles defined herein may be applied to other implementations without departing from the spirit or scope of this disclosure. Thus, the claims are not intended to be limited to the implementations shown herein but are to be accorded the widest scope consistent with this disclosure, the principles and the novel features disclosed herein.

[0185] Additionally, various features that are described in this specification in the context of separate implementations also can be implemented in combination in a single implementation. Conversely, various features that are described in the context of a single implementation also can be implemented in multiple implementations separately or in any suitable subcombination. As such, although features may be described above in combination with one another, and even initially claimed as such, one or more features from a claimed combination can in some cases be excised from the combination, and the claimed combination may be directed to a subcombination or variation of a subcombination.

[0186] Similarly, while operations are depicted in the drawings in a particular order, this should not be understood as requiring that such operations be performed in the particular order shown or in sequential order, or that all illustrated operations be performed, to achieve desirable results. Further, the drawings may schematically depict one more example processes in the form of a flowchart or flow diagram. However, other operations that are not depicted can be incorporated in the example processes that are schematically illustrated. For example, one or more additional operations can be performed before, after, simultaneously, or between any of the illustrated operations. In some circumstances, multitasking and parallel processing may be advantageous. Moreover, the separation of various system components in the implementations described above should not be understood as requiring such separation in all implementations, and it should be understood that the described program components and systems can generally be integrated together in a single product or packaged into multiple products.

What is claimed is:

1. A battery comprising:
  - a anode configured to output a plurality of lithium ions during cycling of the battery;
  - a graded interface layer disposed on the anode and comprising:
    - a tin fluoride layer; and
    - a tin-lithium alloy region formed between the tin fluoride layer and the anode, the tin-lithium alloy region configured to produce a lithium fluoride uniformly dispersed between the anode and the tin fluoride layer during the cycling of the battery;
  - a cathode positioned opposite to the anode;
  - an electrolyte dispersed throughout the cathode and the anode; and
  - a separator positioned between the anode and cathode.
2. The battery of claim 1, further comprising lithium electrodeposited on one or more exposed surfaces of the anode.
3. The battery of claim 1, wherein the tin fluoride layer is configured to provide one or more of a plurality of tin ions or a plurality of fluoride ions during the cycling of the battery.
4. The battery of claim 3, wherein formation of the lithium fluoride is based on chemical reactions between the plurality of lithium ions and the plurality of fluoride ions.
5. The battery of claim 1, wherein the lithium fluoride is an insulator.
6. The battery of claim 1, wherein the lithium fluoride is configured to inhibit dendritic growth of lithium from the anode.

7. The battery of claim 1, further comprising an artificial solid-electrolyte interphase disposed on the anode.

8. The battery of claim 7, wherein any one or more of the tin fluoride layer, the tin-lithium alloy region, or the lithium fluoride is configured to grow the artificial solid-electrolyte interphase during the cycling of the battery.

9. The battery of claim 1, wherein the graded interface layer further comprises organometallic compounds.

10. The battery of claim 9, wherein the organometallic compounds include one or more of aluminum, gallium, indium, copper, nickel, zinc, chromium, vanadium, or titanium.

11. The battery of claim 10, wherein the organometallic compounds includes one or more of oxides, carbides, or nitrides or of any one or more of aluminum, gallium, indium, copper, nickel, zinc, chromium, vanadium, or titanium.

12. The battery of claim 1, wherein the graded interface layer is deposited on the anode by one or more of atomic layer deposition (ALD), chemical vapor deposition (CVD), or physical vapor deposition (PVD).

13. The battery of claim 1, wherein the graded interface layer further comprises a carbon-inclusive layered structure.

14. The battery of claim 13, wherein the carbon-inclusive layered structure includes an atomic plane available for lithium transfer.

15. The battery of claim 13, wherein the carbon-inclusive layered structure is configured to transport lithium ions provided by the electrolyte.

16. The battery of claim 13, wherein the carbon-inclusive layered structure includes one or more arrangements of few layer graphene (FLG) or graphite.

17. The battery of claim 16, wherein the FLG or the graphite is configured to produce one or more of lithium tin oxide (LTO), lithium iron phosphate (LFP), or lithium lanthanum titanate perovskite by intercalating with the lithium ions.

18. The battery of claim 16, wherein the FLG or the graphite includes one or more of carbonaceous materials, additives, or a binder.

19. The battery of claim 1, wherein the graded interface layer includes a plurality of carbonaceous materials including one or more of flaky graphene, few layer graphene (FLG), carbon nano onions (CNOs), graphene nanoplatelets, or carbon nanotubes (CNTs).

20. The battery of claim 19, wherein the carbonaceous materials adhere to at least some of the plurality of lithium ions.

\* \* \* \* \*