

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
30 April 2015 (30.04.2015)

(10) International Publication Number
WO 2015/059280 A1

- (51) **International Patent Classification:**
C08F 10/02 (2006.01) C08F 110/02 (2006.01)
C08F 4/659 (2006.01)
- (21) **International Application Number:** PCT/EP2014/072859
- (22) **International Filing Date:** 24 October 2014 (24.10.2014)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:** 13190220.7 25 October 2013 (25.10.2013) EP
- (71) **Applicant:** DSM IP ASSETS B.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).
- (72) **Inventors:** SEVERN, John Richard; P.O. Box 4, NL-6100 AA Echt (NL). BERTHOUD, Romain; P.O. Box 4, NL-6100 AA Echt (NL). KIDD, Timothy James; P.O. Box 4, NL-6100 AA Echt (NL).
- (74) **Agent:** MEESEN, Patric Holger; DSM IP, P.O. Box 4, NL-6100 AA Echt (NL).
- (81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).
- Published:**
— with international search report (Art. 21(3))



WO 2015/059280 A1

(54) **Title:** PREPARATION OF ULTRA HIGH MOLECULAR WEIGHT ETHYLENE COPOLYMER

(57) **Abstract:** The invention relates to a process for the preparation of a particulate ultra high molecular weight polyethylene (pUH-MWPE) copolymer, comprising the steps of preparing a magnesium containing carrier, loading the carrier with an organometallic compound forming a supported catalyst and contacting the supported catalyst with ethylene and at least one olefinic co-monomer under polymerization conditions, wherein the organometallic compound is of the formula $R^3_3P=N-TiCpX_n$.

PREPARATION OF ULTRA HIGH MOLECULAR WEIGHT ETHYLENE COPOLYMER

The invention relates to a method for the preparation of a particulate ultra high molecular weight polyethylene (pUHMWPE) by copolymerization of ethylene and an olefinic co-monomer. The invention further relates to a pUHMWPE comprising a copolymerized co-monomer and to high transparency molded articles comprising the said pUHMWPE.

A process for the preparation of an UHMWPE is disclosed in WO2009/063084. WO2009/063084 discloses a process for the preparation of ultra high molecular weight polyethylene by preparing a single site catalyst supported by a magnesium containing carrier, said catalyst comprising an organometallic compound and an activator, and polymerizing ethylene and an alpha-olefin in the presence of the single site supported catalyst.

The process disclosed in WO2009/063084 provides UHMWPE polymers with good mechanical properties and transparency of molded articles comprising the UHMWPE. However, the UHMWPE produced by the processes described in WO2009/063084 show poor productivity of the catalyst supported by a magnesium containing carrier. Productivity of single site supported catalysts are known to have low productivity especially when compared to the well established Ziegler-Natta systems. Drawbacks of the low productivity provided the process as described in WO2009/063084 may be an economically unviable processes, a UHMWPE with high ash content, high residual titanium content and/or small particle sizes.

US6,528,671 describes a homogeneous catalyst system for the production of polyolefins comprising phosphinimine transition metal compound, a co-catalyst and optionally an activator. However such homogeneous catalytic polymerization process is subject to fowling problems while the produced polyethylenes are bare of any morphology, rendering their use in commercial processes difficult at best.

EP0890581 describes the production of particulate polyethylene using a phosphinimine cyclopentadienyl metal compound on a silica. The reported productivity of the catalyst system is achieved at the detriment of the particle size and morphology of the polyethylene powder. The non-spherical morphology and high particle size of the polyethylene powder is detrimental for a commercial use in the field of UHMWPE.

Furthermore technology reviews in the field of supported single site catalyst, i.e. organometallic catalyst supported by a carrier, have been published in the last decades. Such reviews are for example reported as chapter 4 and chapter 6 of the book "Tailor-made polymers. Via immobilization of alpha-olefin polymerization catalysts" by John R. Severn and John C. Chadwick, **2008 WILEY-VCH**, Weinheim or *Immobilizing single-site alpha-olefin polymerization catalysts* in Chem. Rev. **2005**, *105*, 4073-4147. These reviews highlight the fact that in the field of polyolefin polymerization, no empirical routes apply and each process and product needs a specific a support / catalyst / cocatalyst combinations.

Therefore, there is a need for a process for preparing pUHMWPE having good balance between mechanical properties of the pUHMWPE, transparency of molded article of the pUHMWPE and productivity of the employed supported organometallic compound.

It is an objective of the present invention to provide a process for polymerization having a good balance of above mentioned properties.

It may be a further objective of the present invention to further optimize transparency of a molded article comprising the pUHMWPE.

Surprisingly, the objective is reached by the process according to the present invention, which will be described in detail below.

In one embodiment of the present invention, there is provided a process for the preparation of particulate UHMWPE with a $MgCl_2$ supported single-site titanium catalysts according to claim 1.

Surprisingly with the process according to the invention a particulate UHMWPE with a good balance between mechanical properties of the pUHMWPE and transparency of molded article of the UHMWPE is obtained at a good productivity of the employed supported organometallic compound. The particulate UHMWPE shows a co-monomer content of at least 0.05 short chain branches per thousand total carbon atoms (SCB/1000TC) with a co-monomer partition factor (C_{pf}) of at least 0.8 combined with low ash content. A further advantage is that the particulate UHMWPE obtained by the process of the present invention has an optimized particle size (D_{50}) of between 50 and 500 μm and may have a narrow particle size distribution (SPAN). This results in particulate UHMWPE that can be beneficial for further processing such as sintering.

In particular the process for preparation of a particulate ultra high molecular weight polyethylene of the present invention comprises the steps of

- a) preparing a magnesium containing carrier by interaction of a solution of an organomagnesium compound having composition $MgR^1_{2.n}MgCl_{2.m}R^2_2O$ where $n = 0.37-0.7$, $m = 1.1-3.5$, R^1 is each an aromatic or aliphatic hydrocarbyl residue and R^2_2O is an aliphatic ether, with a chlorinating agent at a molar ratio Mg/Cl of at most 0.5, wherein Mg represents the Mg of the organomagnesium compound and Cl the Cl of the chlorinating agent;
- b) loading the magnesium containing carrier with a organometallic compound forming a supported catalyst,
- c) contacting the supported catalyst with ethylene and at least one olefinic co-monomer under polymerization conditions,
- wherein** the organometallic compound is a compound of the formula $R^3_3P=N-TiCpX_n$, wherein each R^3 is independently selected from the group consisting of
- a hydrogen atom,
 - a halogen atom,
 - a C_{1-20} hydrocarbyl radicals optionally substituted by at least one halogen atom,
 - a C_{1-8} alkoxy radical,
 - a C_{6-10} aryl or aryloxy radical,
 - an amido radical,
 - a silyl radical of the formula $-Si-(R^4)_3$
 - and a germanyl radical of the formula $-Ge-(R^4)_3$
- wherein each R^3 is independently selected from the group consisting of hydrogen, a C_{1-8} alkyl or alkoxy radical, C_{6-10} aryl or aryloxy radicals,
- Cp** is a cyclopentadienyl ligand;
- X** is an activatable ligand and **n** is 1 or 2, depending upon the valence of Ti and the valence of X, preferably, X is selected from the group consisting of Cl, Br, Me and Et if $n = 2$ or X is a substituted or unsubstituted butadiene if $n = 1$.

By activatable ligand in the context of the present invention is referred to a ligand which may be activated by a cocatalyst or "activator" (e.g. an aluminoxane) to facilitate olefin polymerization. Activatable ligands may independently be selected from the group consisting of a hydrogen atom, a halogen atom, a C_{1-10} hydrocarbyl radical, a C_{1-10} alkoxy radical, a C_{5-10} aryl oxide radical and; each of which said hydrocarbyl, alkoxy, and aryl oxide radicals may be unsubstituted by or further substituted by a halogen atom, a C_{1-8} alkyl radical, silyl radical, a C_{1-8} alkoxy radical, a C_{6-10} aryl or aryloxy radical, an amido radical which is unsubstituted or substituted by

up to two C₁₋₈ alkyl radicals; a phosphide radical which is unsubstituted or substituted by up to two C₁₋₈ alkyl radicals. The preferred catalysts contain a Ti atom in the highest oxidation state (i.e. 4+). Thus, the preferred catalyst contains two activatable ligands. In some instances, the metal of the catalyst component may not be in the highest
5 oxidation state. For example, a titanium (III) component would contain only one activatable ligand.

Two X ligands may also be joined to one another and form for example a substituted or unsubstituted diene ligand (i.e. 1,3-diene); or a delocalized heteroatom containing group such as an acetate or acetamidinate group.

10 In a convenient embodiment of the invention, each X is independently selected from the group consisting of a halide atom, an alkyl radical and a benzyl radical

The preparation of the magnesium containing carrier is preferably carried out at a temperature in the range from 5 to 80°C. The preparation is typically
15 carried out in dry aprotic, hydrocarbon solvent.

The chlorinating agent can be any type of chlorinated compound able to provide at least one chlorine to the organomagnesium compound, preferably compounds with covalently bound chlorine such as chlorinated aliphatic or aromatic hydrocarbons. Preferably the chlorinating agent is a chlorine-containing compound of
20 composition Y_kACl_{4-k}, where Y = OR⁵ or R⁵ group with R⁵ being a C₁₋₂₀ hydrocarbyl radicals optionally substituted by at least one halogen atom, A being Si or C atom and k = 0 to 2. Preferably the chlorinating agent is a hydrocarbyl halide silane with A = Si, k = 1 or 2 or phenyl trichloro methane. Magnesium containing carriers produced by said preferred chlorinating agents have the advantage of being obtained in higher yield or
25 deliver supported catalysts with tunable average particle size, particle size distribution, and further increased productivity.

The organomagnesium compound MgR¹₂.nMgCl₂.mR²₂O may have a broad molecular composition defined by the ranges of n = 0.37-0.7 and m = 1.1-3.5. It will be obvious to the skilled person that said compounds will have complex structures
30 allowing for the decimal nature of n and m. Preferably n = 0.4-0.65, more preferably 0.45 to 0.6 and m is preferably 1.5-2.5, more preferably 1.8-2.1 and most preferably m = 2. Each R¹ is an aromatic or aliphatic hydrocarbyl residue. Preferably R¹ is an aryl group (Ar), wherein the aryl group preferably comprises an aromatic structure with 6 to 10 carbon atoms. Optionally the aromatic structure is substituted by at least one C₁ to
35 C₈ alkyl group. Aliphatic R¹ residues may be selected from linear or branched alkyl

residues with 1 to 10 carbon atoms such as methyl, ethyl, n-propyl, i-propoyl, n-butyl, i-butyl or t-butyl. R^2O is an aliphatic ether. By aliphatic ether is understood that R^1 is a hydrocarbyl residue bound to the oxygen ether atom via an aliphatic carbon atom.

Preferably R^2 is $R = i-Am, n-Bu$.

5 In a preferred embodiment, the molar ratio of Mg of the organomagnesium compound to Cl of the chlorinating agent in the preparation of the magnesium containing carrier is at most 0.4, more preferably at most 0.3. The molar ratio is not particularly limited but for practical reasons the ratio may be at least 0.01, more preferably at least 0.02 and most preferably at least 0.05.

10 By the process of the invention, a magnesium containing carrier is obtained after step a). Said intermediate magnesium containing carrier may be isolated and stored for later use or subjected immediately to the further steps of the process. Preferably, the magnesium containing carrier has particle size, expressed as D50, from 2 to 30 μm . By D50 is understood in the present application the median particle size
15 diameter. Preferably the D50 is at least 2 micron, more preferably at least 3 micron and most preferably at least 5 micron. A D50 of the magnesium containing carrier within the preferred ranges may provide an optimum handling of the obtained particulate UHMWPE in commercial equipment. The magnesium containing carrier preferably has a narrow particle size distribution (SPAN) from 0 to 10, more preferably from 0.1 to 5,
20 even more preferably from 0.3 to 2 and most preferably from 0.4 to 1. In a further preferred embodiment, the particle size distribution is at most 5, preferably at most 2 and most preferably at most 1, bearing in mind that a monomodal particle size distribution has the value of 0.

A supported catalyst is prepared by loading the magnesium
25 containing carrier with a organometallic compound. This is generally performed by treatment of a suspension of the magnesium containing carrier with a solution of the organometallic compound in a hydrocarbon solvent. The molar ratio of the organometallic compound to Mg may be from 0.001 to 1, preferably from 0.005 to 0.5 and most preferably from 0.01-0.1. The loading of the magnesium containing carrier is
30 preferably carried out at a temperatures between 20°C and 100°C. Preferably the magnesium containing carrier is suspended in the solvent used for the preparation of said carrier in step a) and may further contain residues from the carrier preparation step. In a preferred embodiment, reagents from the synthesis are removed from the carrier by for example washing and filtration with suitable solvents before the carrier is
35 isolated as a powder or brought again into a suspension. The solvent of the suspension

and the solvent of the organometallic compound may be the same or different. Suitable solvents for the suspension and/or solution of the organometallic compound are aliphatic and aromatic hydrocarbons, preferably with a boiling point between 20°C and 200°C. Preferably the solvents are individually selected from the list consisting of
5 pentane, hexane, heptane, isoparaffine mixture, toluene and xylene as well as their isomers.

The organometallic compound is of the general formula $R^3_3P=N-TiCpX_n$, wherein **each** R^3 is independently selected from the group consisting of a hydrogen atom, a halogen atom, a C_{1-20} hydrocarbyl radicals optionally substituted by
10 at least one halogen atom, a C_{1-8} alkoxy radical, a C_{6-10} aryl or aryloxy radical, an amido radical, a silyl radical of the formula $-Si-(R^4)_3$ and a germanyl radical of the formula $-Ge-(R^4)_3$ wherein each R^3 is independently selected from the group consisting of hydrogen, a C_{1-8} alkyl or alkoxy radical, C_{6-10} aryl or aryloxy radicals,
Cp is a cyclopentadienyl ligand; **X** is an activatable ligand and **n** is 1 or 2, depending
15 upon the valence of Ti and the valence of X, preferably, X is selected from the group consisting of Cl, Br, Me and Et if $n = 2$ or X is a substituted or unsubstituted butadiene if $n = 1$.

The preferred phosphinimine ligand ($R^3_3P=N-$) are those in which each R^3 is a hydrocarbyl radical. A particularly preferred phosphinimine ligand is tri-
20 (tertiary butyl) phosphinimine (i.e. where each R^3 is a tertiary butyl group).

As used herein, the term cyclopentadienyl ligand is meant to broadly convey its conventional meaning, namely a ligand having a five carbon ring which is bonded to the metal via eta-5 bonding. Thus, the term "cyclopentadienyl" includes unsubstituted cyclopentadienyl, substituted cyclopentadienyl, unsubstituted indenyl,
25 substituted indenyl, unsubstituted fluorenyl and substituted fluorenyl. An exemplary list of substituents for a cyclopentadienyl ligand includes the group consisting of C_{1-10} hydrocarbyl radical (which hydrocarbyl substituents are unsubstituted or further substituted); a halogen atom, C_{1-8} alkoxy radical, a C_{6-10} aryl or aryloxy radical; an amido radical which is unsubstituted or substituted by up to two C_{1-8} alkyl radicals; a
30 phosphido radical which is unsubstituted or substituted by up to two C_{1-8} alkyl radicals; a silyl radical of the formula $-Si-(R^4)_3$ and a germanyl radical of the formula $-Ge-(R^4)_3$ wherein each R^4 is independently selected from the group consisting of hydrogen, a C_{1-8} alkyl or alkoxy radical, C_{6-10} aryl or aryloxy radicals. Preferably Cp is unsubstituted cyclopentadienyl or pentamethylcyclopentadienyl.

In a most preferred embodiment of the process of the invention the organometallic compound is of the formula $t\text{Bu}_3\text{P}=\text{N}-\text{TiCp}^*\text{X}_2$, wherein Cp^* is pentamethylcyclopentadienyl and X is selected from the group consisting of Cl, Br, Me and Et. It was found that the supported catalyst prepared with such organometallic
5 compound may results in higher productivity of particulate UHMWPE.

In a further preferred embodiment, the process of the invention comprises the step of treating the magnesium containing carrier, the organometallic compound and/or the supported catalyst with an activator selected from the list of alumoxanes, alkyl aluminums, alkyl aluminum halides, anionic compounds of boron or
10 aluminum, boranes such as trialkylboron and triarylboron compounds, borates, and mixtures thereof, preferably the activator is alumoxanes or alkyl aluminums. Well known boranes and borates used as activator in the preparation of polyolefins are described in *Chem. Rev.*, **2000**, *100*, 1391 by E. Y-X. Chen and T.J. Marks which is herein included by reference. By such treatment even higher yields of particulate
15 UHMWPE may be obtained.

The alumoxane may be of the overall formula:
 $(\text{R}^5)_2\text{AlO}(\text{R}^5\text{AlO})_p\text{Al}(\text{R}^5)_2$ wherein each R^5 is independently selected from the group consisting of C_{1-20} hydrocarbonyl radicals and p is from 0 to 50, preferably R^5 is a C_{1-4} radical and p is from 5 to 30. Methylalumoxane (or "MAO") in which most of the R
20 groups in the compounds of the mixture are methyl is the preferred alumoxane. Alumoxanes are also readily available articles of commerce generally as a solution in a hydrocarbon solvent.

The alumoxane, when employed, is preferably added at an aluminum to titanium mole ratio of from 20:1 to 1000:1. Preferred ratios are from 50:1 to 250:1.
25

In the context of the present invention alkyl aluminums and alkyl aluminum halides are represented by the general formula AlR_q^6X_r , wherein Al is an aluminium atom in the trivalent valence state, each R^6 is an alkyl residue, X is a halogen atom, q and r are natural numbers of 1-3 with the provision that $q + r = 3$. Typical examples are trialkyl aluminum such as triethyl aluminum, triisobutylaluminum,
30 trihexyl aluminum and trioctyl aluminum; dialkyl aluminum hydrides such as diethyl aluminum hydride and diisobutyl aluminum hydride; dialkyl aluminum halides such as diethyl aluminum chloride; mixtures of a trialkyl aluminum and a dialkyl aluminum halide such as a mixture of triethyl aluminum and diethyl aluminum chloride.

In the context of the application, trialkylboron compounds and triarylboron compounds are boranes represented by the general formula BR^7_3 , wherein B is a boron atom in the trivalent valence state and each R^7 is respectively an alkyl or aryl residue. Preferably the alkyl or aryl residues are substituted with at least on
5 halogen atom. A most preferred triaryl boron compound is tris pentafluorophenyl borane.

In the context of the present application borates are boron containing compounds of the formula $[R^8]^+[B(R^9)_4]^-$ wherein B is a boron atom, R^8 is a cyclic C_{5-7} aromatic cation or a triphenyl methyl cation and each R^9 is independently selected from
10 the group consisting of phenyl radicals which are unsubstituted or substituted with from 1 to 5 substituents selected from the group consisting of a fluorine atom, a C_{1-4} alkyl or alkoxy radical which is unsubstituted or substituted by fluorine atoms; and a silyl radical of the formula $-Si-(R^{10})_3$; wherein each R^{10} is independently selected from the group consisting of a hydrogen atom and a C_{1-4} alkyl radical.

15 In step c) of the process of the present invention the supported catalyst is contacted with ethylene and at least one olefinic co-monomer under polymerization conditions.

The polymerization may be carried out under various conditions such as at temperatures between 20°C and 100°C in the presence of an inert hydrocarbon
20 solvent, such as a C_{5-12} hydrocarbon which may be unsubstituted or substituted by a C_{1-4} alkyl group such as pentane, methyl pentane, hexane, heptane, toluene, octane, cyclohexane, methylcyclohexane, pentamethylheptane and hydrogenated naphtha or under gas phase conditions without a hydrocarbon diluent at temperatures from 20 to 160°C , preferably from 40°C to 100°C . Low temperatures may result in a decreased
25 polymerization activity, whereas high temperatures may result in degradation of the catalyst system, lowering of the molecular weight and/or a loss of the particulate morphology of the UHMWPE due to a loss of cohesion of the produced UHMWPE. The polymer molecular weight may be regulated by the use of chain transfer agents and/or hydrogen. A polymerization pressure is not particularly limited, and a pressure of
30 usually ambient pressure to about 10 MPa, preferably about 50 kPa to 5 MPa and most preferably from about 100 kPa and 1.5 MPa is adopted, from the industrial and economic viewpoints. As a polymerization type, either a batch type or a continuous type can be employed. Preferably slurry polymerization using an inert hydrocarbon solvent such as propane, butane, isobutane, pentane, hexane, heptane and octane, or
35 gaseous polymerization can be employed. Generally the reactors should be operated

under conditions to achieve a thorough mixing of the reactants. Preferably a batch process is used with the advantage that particle size distribution as well as, molecular weight distribution and monomer feeds may be advantageously controlled.

The monomers used in the process according to the invention for the preparation of the particulate UHMWPE may be dissolved/dispersed in the solvent either prior to being fed to the reactor or for gaseous monomers the monomer may be fed to the reactor so that it will dissolve in the reaction mixture. Prior to mixing, the solvent and monomers are preferably purified to remove potential catalyst poisons such as water or oxygen. The feedstock purification follows standard practices in the art, e.g. molecular sieves, alumina beds and oxygen and CO(S) removal catalysts are used for the purification of monomers. The solvent itself as well is preferably treated in a similar manner.

The feedstock may be heated or cooled prior to feeding to the polymerization and the reaction may be heated or cooled by external means.

Generally, the catalyst components may be added as a separate suspension to the reactor or premixed before adding to the reactor.

After the polymerization, polymerization can be stopped by adding a polymerization terminator such as alcohols, water, oxygen, carbon monoxide or carbon dioxide, removing the monomers, or stopping the addition of the monomers.

In the context of the present invention an olefinic co-monomer represents a hydrocarbon with at least one polymerizable C-C double bond. Preferably the co-monomer is selected from the group consisting of an alpha-olefin with at least 3 carbon atoms, a cyclic olefin having 5 to 20 carbon atoms and a linear, branched or cyclic diene having 4 to 20 carbon atoms. An alpha-olefin refers to an alpha-olefin having 3 or more carbon atoms, preferably from 3 to 20 carbon atoms. Preferred alpha-olefins include linear mono-olefins such as propylene, butene-1, pentene-1, hexene-1, heptene-1, octene-1 and decene-1; branched monoolefins such as 3-methyl butene-1, 3-methyl pentene-1 and 4-methyl pentene-1; vinyl cyclohexane, and the like. Alpha-olefins may be used alone, or in a combination of two or more.

In a preferred embodiment, the alpha-olefin has between 3 and 12 carbon atoms. Even more preferably the alpha-olefin is selected from the group consisting of propene, butene-1, hexene-1, octene-1. Most preferably butene-1, hexene-1 are copolymerized. The applicant found that these alpha-olefins may readily copolymerize and may show optimized transparency in the molded articles comprising the UHMWPE according to the invention.

During the polymerization reaction, the supported catalyst is contacted with up to about 1000 mol/kmol of the co-monomer based on the total amount of ethylene and co-monomer present, more preferably from about 1 to about 1000 mol/kmol, most preferably from about 2 to 500 and in particular from about 5 to about 100 mol/kmol. In general, increased content of co-monomer will provide UHMWPE with higher co-monomer content providing amongst others molded articles with optimized transparency.

The invention also relates to the ultrahigh molecular weight polyethylene obtainable by the process according to the invention.

The UHMWPE that may be obtained by the process of the present invention has good mechanical properties while being polymerized with a good productivity of the employed supported organometallic compound. Hereby, for the first time according to the knowledge of the inventors, a UHMWPE has been provided with an optimized combination of mechanical properties and UHMWPE characteristics such as molecular weight distribution, co-monomer distribution, particles size and catalyst residues. Optionally particle size distribution and particle morphology may be optimized.

Hence the present application also relates to an ultra high molecular weight polyethylene (UHMWPE) having an intrinsic viscosity (IV) of at least 4 dl/g, a co-monomer content of a least 0.05 SCB/1000TC, a co-monomer partition factor (C_{pt}) of at least 0.8, a median particle size D50 of between 50 and 500 μm and a total ash content of less than 1000 ppm.

Preferably the UHMWPE has a co-monomer content of at least 0.1 short chain branches per thousand total carbon atoms (SCB/1000TC), more preferably at least 0.5 SCB/1000TC and most preferably at least 1 SCB/1000TC. The co-monomer content of the UHMWPE is not particularly limited but for practical reasons may be less than 50 SCB/1000TC, preferably less than 25 SCB/1000TC. By short chain branches in the present application are understood the branches originating from the co-polymerized co-monomer and potential short chain branches introduced by the catalyst via irregular ethylene incorporation. Further details about the calculation of the SCB is given with the Methods. Higher co-monomer levels may further increase the transparency of the molded articles comprising the UHMWPE.

In a preferred embodiment, the UHMWPE has a homogeneous distribution of the co-monomer over the molecular weight range of the polymeric composition. Such homogeneity is expressed by the means of the co-monomer

partitioning factor (C_{pf}) as described further below. Further details about measurement techniques and calculation may be obtained from WO97/44371 which is included herein by reference. A perfectly homogeneous co-monomer distribution over the molecular weight is expressed by a C_{pf} of 1, while C_{pf} values of below or above 1
5 characterize co-monomer distributions with an increased level of co-monomer present in the low or high molecular fraction of the UHMWPE respectively. The C_{pf} of the present UHMWPE is preferably of between 0.8 and 1.1, more preferably between 0.85 and 1.07, even more preferably between 0.9 and 1.05 and most preferably between 0.95 and 1.03. It was observed that UHMWPE having a C_{pf} in the preferred ranges may
10 have an improved efficiency of the present co-monomer. Such improved efficiency may be reflected in equal material properties being achieved at a lower amount of co-monomer in the UHMWPE. A material property that may benefit from the increased co-monomer efficiency may for example be the transparency of a molded article.

The ultra-high molar weight polyethylene according to the invention
15 has an intrinsic viscosity (IV, as measured on solution in decalin at 135°C) of at least about 4 dl/g, preferably at least about 8, more preferably at least about 12 dl/g, to provide articles comprising the UHMWPE with optimal mechanical properties. The UHMWPE according to the invention may have an IV of at most 50 dl/g, preferably at most 40 dl/g. Intrinsic viscosity is a measure for molecular weight (also called molar
20 mass) that can more easily be determined than actual molecular weight parameters like M_n and M_w . There are several empirical relations between IV and M_w . Based on the equation $M_w = 5.37 * 10^4 [IV]^{1.37}$ (see EP 0504954 A1) an IV of 4 or 8 dl/g would be equivalent to M_w of about 360 or 930 kg/mol, respectively. When the intrinsic viscosity is too small, the strength necessary for using various molded articles from the ultrahigh
25 molecular weight polyethylene sometimes cannot be obtained, and when it is too large, the process ability, etc. upon molding is sometimes worsen.

In one preferred embodiment, the UHMWPE of the invention has a molecular weight distribution M_w/M_n of less than 4.0, preferably less than 3.5, more preferably less than 3.0 and most preferably less than 2.8. Such preferred UHMWPE
30 may demonstrate even further improved mechanical properties of articles comprising the UHMWPE. By molecular weight distribution (MWD) in the context of the present application is understood the ratio of M_w/M_n . Since there may be conflicting teachings in the literature about the way to measure M_w and/or M_n values for a UHMWPE, resulting in a discrepancy of the MWD, the herein understood MWD is the one as measured by
35 SEC technique as further described in the experimental section. The MWD of the

particulate UHMWPE according to the invention has no particularly low limit. The theoretical limit is the one of a monodisperse polymer with an MWD of 1, preferably the MWD is at least 1.1.

Preferably, the UHMWPE is a linear polyethylene with less than one
5 long chain branch (LCB) per 100 total carbon atoms, and preferably less than one LCB per 300 total carbon atoms; an LCB is herein defined as a branch containing at least 20 carbon atoms.

The UHMWPE of the invention has a median particle diameter (D50)
10 from 50 to 500 micron. It is preferably from 60 to 300 micron, more preferably from 65 to 200 micron. Too low particle sizes lead to dust and safety issues in the process whereas too high particle sizes may negatively impact the processability of the UHMWPE by for example by uneven sintering.

In a further preferred embodiment, the UHMWPE of the invention has
15 a particle size distribution parameter (SPAN) of at most 3, preferably at most 2.5 and even more preferably at most 2 and most preferably at most 1. The SPAN is expressed by the equation $SPAN = (D90 - D10) / D50$ wherein D90, D10 and D50 are particle sizes at 90%, 10% and 50% in a volume cumulative distribution, respectively, while D50 is also referred to as the median diameter. The smaller the value is, the narrower the particle size distribution is.

20 The morphology of the UHMWPE of the invention may be influenced by the magnesium containing carrier prepared during the process of the invention. It was observed that the supported catalyst may yield UHMWPE of substantially spheroidal shape. By substantially spheroidal shape in the context of the present invention is meant that the largest diameter of an individual UHMWPE particle is at
25 most 1.5 times the average diameter of said particle, preferably at most 1.4 times the average diameter and most preferably at most 1.2 times the average diameter of said particle. By largest diameter of a particle is understood the diameter of the smallest possible sphere that would circumscribe the entire particle. By average diameter of a particle is understood the diameter of the sphere that can comprise the mass of the
30 concerned particle. Such spheroidal morphology stands for example in contrast to oblong or granular particles or particles of irregular shape as often obtained from most of oxide-based carriers such as silica carriers. Spheroidal morphology of the UHMWPE particles provides products with good powder bulk density.

In a preferred embodiment, the UHMWPE of the invention may have
35 a residual Ti-content of less than 10 ppm, preferably less than 7 ppm, more preferably

less than 5 ppm and most preferably less than 2 ppm. Lower residual Ti levels are a result of an increased productivity of the supported catalyst and may allow UHMWPE with an increased stability.

In one preferred embodiment, the level of any residual active catalyst metal is less than 10 ppm, preferably less than 8 ppm, more preferably less than 7 ppm and most preferably less than 5 ppm. In a yet preferred embodiment, the combined level of residual active catalyst metals is less than 25 ppm, preferably less than 20 ppm, more preferably less than 15 ppm and most preferably less than 10 ppm. By active catalyst metal is herein understood metals that are commonly used for the production of polyolefins, especially the metals of groups 4 to 7 of the periodic table of elements, more especially the metals of group 4, i.e. Ti, Zr and Hf. The respective levels of Ti, Zr, and/or Hf are measured by Neutron Activation Analysis (NAA).

The UHMWPE of the invention is further characterized by a residual ash content of less than 1000 ppm, preferably less than 600 ppm, more preferably less than 300 ppm and most preferably less than 100 ppm. Lower residual ash levels are a further result of an increased productivity of the supported catalyst and may provide UHMWPE having improved color neutrality. The residual ash content of the particulate UHMWPE is calculated based on the amount of supported catalyst in mg and the respective polyethylene yield of said catalyst in kg during the polymerization. The skilled person will be aware that residual ash content can be approximated by the sum of the elements identified by Neutron Activation Analysis (NAA) or X-ray fluorescence (XRF) or other analytical means available in the art.

The UHMWPE may be prepared by a catalyst supported by a magnesium containing carrier as described above. Such carrier as well as therefrom prepared UHMWPE is substantially free of silica, though small amounts of silicon may be present in the UHMWPE depending upon the used chlorinating agent. Hence the UHMWPE of the present invention may have a Si-content of less than 100 ppm, preferably less than 60 ppm, more preferably less than 40, more preferably less than 30, even more preferably less than 20 and most preferably less than 10 ppm. The residual Si-content of the particulate UHMWPE is calculated based on the amount of Silicon (in mg) present in the supported catalyst and the respective polyethylene yield of said catalyst in kg during the polymerization. As above, NAA and XRF are suitable method to confirm absence or residual Si levels.

In a yet further preferred embodiment, the UHMWPE of the invention has an apparent bulk density of at least 300 kg/m³. It is preferably from 350 to 550

kg/m³, more preferably from 380 to 530 kg/m³, further more preferably from 390 to 520 kg/m³. It was found that UHMWPE with bulk densities in the mentioned ranges may provide good handling characteristics.

The ultrahigh molecular weight polyethylene of the present invention
5 is eminently suitable for the manufacture of molded articles such as tapes, films and fibers with improved mechanical and/or optical properties. Accordingly, the present invention also pertains to a process for manufacturing of molded UHMWPE articles, preferably tapes, films and fibers from the UHMWPE of the invention.

A suitable method for producing a molded article from the UHMWPE
10 according to the invention is a gel spinning process as described in for example GB-A-2042414, GB-A-2051667, EP 0205960 A and WO 01/73173 A1, and in "Advanced Fibre Spinning Technology", Ed. T. Nakajima, Woodhead Publ. Ltd (1994), ISBN 185573 182 7. In short, the gel spinning process comprises preparing a solution of a polymer of high intrinsic viscosity, extruding the solution into a tape, film or fiber at a
15 temperature above the dissolving temperature, cooling down the tape, film or fiber below the gelling temperature, thereby at least partly gelling the tape, film or fiber, and drawing the film, tape or fiber before, during and/or after at least partial removal of the solvent.

The present application also pertains to products which contain a
20 molded article of the invention, such as ropes, cables, nets, fabrics, and protective appliances such as ballistic resistant articles.

The present invention will be elucidated by the following examples, without being limited thereto or thereby.

25 Experimental

The organometallic compound Cp*Ti[(t-Bu)₃PN]Cl₂ (I) was produced according to the method described in Douglas W. Stephan et al in *Organometallics*, **2003**, 22, 1937–1947, which is hereby included by reference.

30 Preparation of magnesium containing carrier and supported catalyst.

Example 1: Preparation of the magnesium containing carrier.

In a 1L reactor equipped a thermostat, internal temperature control and a mechanical stirrer. 130 mL of PhMgCl in dibutylether (0.53 mol Mg/L) was stirred at 500 rpm at 10°C. 75 mL of a 3.7 M solution of PhSiCl₃ in PhCl was added drop wise
35 at a rate of 75 ml/hour. The reaction mixture was stirred for 30 minutes at 10°C, then

heated at a rate of 1°C/min to 60°C, and finally stirred for a further 30 minutes at 60°C. Heptane washings were then performed until the supernatant is clean. The support obtained has a median particle size 10.2 µm and a span of 0.96 as measured by Malvern Laser light scattering.

5

Example 2: Pre-treatment of the magnesium containing carrier by an alkyl aluminum compound

A toluene suspension of the MgCl₂ support from Example 1 and MAO_{10%wt} (0.138 mol in toluene) was stirred at 300 rpm and 60°C for 1 hour. The resulting solid was washed thoroughly with toluene at 60°C until the supernatant is clean.

10

Example 3: Supporting of the organometallic compound

In a 1L reactor, ~5g of solid from Example 2 in toluene is stirred at 300 rpm and at room temperature. 40 mL of 0.02 M toluene solution of compound (I) is added and the mixture is allowed to react for 1 hour. Toluene washings are then performed until the supernatant is colorless. The solid is finally slurried in 250 mL of heptane.

15

20 Example 4:

Supported catalyst is prepared as described in example 3 from a support with a d₅₀ of 5.5 µm obtained by the process of example 1 at a higher stirring rate.

25 Comparative Experiment A:

A MgCl₂ support prepared as described in Example 1 slurried in heptane is contacted at 60°C with 0.09 mol TiCl₄ for 1h. Heptane washings were then performed until the supernatant is clean.

30 Comparative Experiment B:

A conventional Ziegler-Natta catalyst is used, which has been prepared according to example 1 of EP1749574, and has a d₅₀ of 3.9 µm.

Comparative experiment C:

A 2nd conventional Ziegler-Natta catalyst is used, which has a d50 of 5.6 μm .

Comparative experiment D:

5 A 3rd conventional Ziegler-Natta catalyst is used, of the same catalyst family as in C. Exp. C, which has a d50 of 5.0 μm .

General polymerization procedure:

10 Batch polymerizations were carried out in a stirred reactor of 2, 10 (D, VII and IX) or 55L (B, C, X, XI). The reaction temperature was set to the desired value and controlled by a Lauda thermostat. The feed streams (solvent and ethylene) were purified with various adsorption media to remove catalyst killing impurities such as water, oxygen and polar compounds as is known by someone skilled in the art. In an inert atmosphere the previously dried reactor is filled with 1, 4.5 or 25L heptane. After
15 the solvent has reached the desired temperature, the scavenger components and co-monomers are added and after 5 minutes the supported catalyst is added. Next the ethylene stream is fed into the reactor to reach and maintain a total pressure of 500, 7000 or 1000 kPa. After the desired polymerization time, the contents of the reactor is collected, filtered and dried under vacuum at 50°C for at least 12 hours. The polymer is
20 weighted and samples are analyzed.

In the case of copolymerization with propene (polymerization V and VI), co-monomer is added in mixture with ethylene. The reactor set-up used enables to both maintain a constant feed rate and constant pressure over the whole polymerization time, the unconverted feed (> 75 %) being vented-off, preventing any
25 compositional drift due to the high incorporation of propene.

Polymerization conditions and evaluation of the UHMWPE prepared with the catalyst systems described in Comparative experiments A to D and the Examples 3 and 4 can be found in table 1a and 1b respectively.

Polymerization Reaction	Catalyst	Cat [mg]	Scavenger TEA [mmol/L]	Temperature [°C]	Co-monomer	Co-monomer [g]	Pressure [MPa]	Time [h:m]	Yield [g]	Cat Yield [gpol/gcat]	Productivity [gpol/gcat*h]
A	C.Exp.A	15	0.9	60	1-C ₆ =	47	0.5	1:43	200	13336	7769
B	C.Exp.B	150	1.0	65	1-C ₄ =	305	0.7	5:15	10010	66716	12708
C	C.Exp.C	610	0.5	65	1-C ₄ =	163	0.7	3:34	10714	17559	4923
D	C.Exp.D	50	1.0	60	1-C ₄ =	100	0.5	9:06	1375	27500	3022
I	Ex. 3	100	0.9	60	1-C ₆ =	27	0.5	2:00	214	2136	1068
II	Ex. 3	100	0.9	60	1-C ₆ =	68	0.5	1:37	282	2815	1741
III	Ex. 3	100	0.9	60	1-C ₈ =	30	0.5	2:00	214	2140	1070
IV	Ex. 3	100	2.8	60	1-C ₈ =	30	0.5	1:40	260	2600	1560
V	Ex. 3	67	1.0	40	C ₃ =	*	0.5	1:40	30	449	269
VI	Ex. 3	100	1.0	40	C ₃ =	**	1.0	1:55	190	1896	989
VII	Ex. 3	200	0.9	60	1-C ₄ =	79	0.5	1:16	479	2390	1865
VIII	Ex. 3	99	0.9	60	1-C ₆ =	14	0.5	2:22	245	2464	1041
IX	Ex. 3	199	0.9	60	1-C ₄ =	42	0.5	1:35	521	2618	1654
X	Ex. 4	551	1.0	50	1-C ₄ =	450	1.0	7:10	5417	9835	1372
XI	Ex. 4	551	1.0	60	1-C ₄ =	75	1.0	5:33	9270	16830	3032

* Feed composition contains 42%wt of C₃=

** Feed composition contains 14%wt of C₃=

Polymerization Reaction	Catalyst	D50 [μm]	SPAN	Calculated Ash content [ppm]	Bulk density [g/L]	DF [s]	Branching [SCB/1000TC]	ES [N/m^2]	IV [dl/g]	Mn [kg/mol]	Mw [kg/mol]	Mw/Mn	Transmission [%]	Density [kg/m^3]	C_{pt} [-]
A	C.Exp. A	211.8	1.19	75	362	20	1.5	0.12	-	210	1500	6.9	70.4	925.2	0.76
B	C.Exp. B	160.9	0.82	15	325	25	1.4	0.192	-	270	2000	7.3	70	924.3	0.76
C	C.Exp. C	149.4	0.83	57	406	25	2.6	0.177	-	220	2000	9	70	922	-
D	C.Exp. D	150.3	0.91	36	348	26	2.5	0.231	-	260	2400	9.2	70.6	921.5	-
I	Ex. 3	155.1	0.81	468	295	38	1.9	-	-	530	1400	2.6	76.6	-	-
II	Ex. 3	170	0.88	355	279	36	4.4	-	7.4	260	690	2.7	79.4	914	0.93
III	Ex. 3	155.6	0.8	467	310	33	0.7	-	16	-	-	-	73.3	917.9	-
IV	Ex. 3	153.9	0.81	385	314	33	0.7	-	12.7	-	-	-	72.7	919	-
V	Ex. 3	97.1	0.89	2227	-	-	32.5	-	-	1100	3100	2.8	-	-	-
VI	Ex. 3	143.2	0.81	527	300	34	8.7	-	-	1900	4600	2.4	77.3	912.6	-
VII	Ex. 3	142.9	0.9	418	288	35	5.1	-	-	220	550	2.5	78.8	917.5	-
VIII	Ex. 3	143	0.97	406	311	33	0.8	-	-	650	1900	2.9	74	917.9	-
IX	Ex. 3	115.6	0.92	382	348	32	3.5	-	-	310	800	2.6	77.7	918.3	0.96
X	Ex. 4	124.8	0.92	102	397	29	2.6	0.314	-	780	2100	2.7	76.7	917.3	-
XI	Ex. 4	153	0.83	59	413	26	0.5	0.658	-	1500	3400	2.3	70.1	918.3	-

Table 1b

Test methods**Density:**

Density was measured in accordance to ISO 1183.

5 **Transmission:**

Transmission was measured in accordance to ASTM D1003.

SEC-MALS:

10 The molecular mass distributions (M_n , M_w , M_z , M_w/M_n) were measured using a PL-210 Size Exclusion Chromatograph coupled to a multi-band infrared detector (IR5 PolymerChar) and a multi-angle light scattering (MALS) detector (laser wavelength 690 nm) from Wyatt (type DAWN EOS). Two PL-Mixed A columns were used. 1,2,4-trichlorobenzene was used as the solvent, the flow rate was 0.5 ml/min, and the measuring temperature was 160°C. Data acquisition and calculations
15 were carried out via Wyatt (Astra) software. The UHMWPE should be completely dissolved under such conditions that polymer degradation is prevented by methods known to a person skilled in the art.

Co-monomer content (Short chain branches per 1000 total carbon (SCB/1000TC):

20 Co-monomer incorporation over the molar mass was obtained from infrared data collected with infrared detector IR5. The detector and analytical techniques are described by Ortin et al. (Journal of Chromatography A, 1257, **2012**, 66-73). The detector contains band filters which allow separating CH_3 and CH_2 signals during chromatographic run and determine the number of methyl groups per one
25 thousand total carbons over the molar mass distribution. The detector is calibrated with polyethylene short chain branching calibration standards characterized by NMR. The standards are samples with different co-monomer type (methyl, ethyl, and butyl). The actual short chain branching information (SCB/1000TC) is obtained by correcting
30 $\text{CH}_3/1000$ TC ratio assuming two methyl end-groups per each chain.

Co-monomer Partitioning Factor (C_{pf}):

In order to characterize the degree to which the co-monomer is distributed across the molecular weight of the polymer, the GPC with on-line IR was used to calculate a parameter named co-monomer partition factor, C_{pf} . M_n and M_w were
35 determined using standard techniques from the GPC data.

The co-monomer partitioning factor (C_{pf}) is calculated from GPC-IR data. It characterizes the ratio of the average co-monomer content of the higher molecular weight fractions to the average co-monomer content of the lower molecular weight fractions. Higher and lower molecular weight are defined as being above or below the molar mass having the highest population in the molecular weight distribution, the maximum peak. The maximum peak is determined by the top of the differential molar mass distribution curve of the given UHMWPE. C_{pf} is calculated from the equation 1:

$$C_{pf} = \frac{\frac{\sum_{i=1}^n w_i c_i}{\sum_{i=1}^n w_i}}{\frac{\sum_{j=1}^m w_j c_j}{\sum_{j=1}^m w_j}} \quad \text{Equation 1}$$

where: c_i is the co-monomer content and w_i is the normalized weight fraction as determined by GPC-IR for the n IR data points above the maximum peak molecular weight. c_j is the co-monomer content and w_j is the normalized weight fraction as determined by GPC-IR for the m IR data points below the maximum peak molecular weight. Only those weight fractions, w_i or w_j which have associated co-monomer content values are used to calculate C_{pf} . For a valid calculation, it is required that n and m are greater than or equal to 3. IR data corresponding to molecular weight fractions with a height in the molecular weight distribution of less than 10% of the peak molecular weight are not included in the calculation due to the uncertainties present in such data.

Bulk density

is determined according to DIN 53466;ISO 60 at 23°C and 50% relative humidity.

Particle size and span:

The average particle size of the polymer is determined in accordance with ISO 13320-2, using a Malvern™ LLD particle size analyzer. The span defined as $(D90-D10)/D50$ was also determined using the Malvern™ LLD particle size analyzer.

The average size of the catalyst is determined using a Malvern™ LLD particle size analyzer.

Dry flow (DF):

- 5 The dry flow in seconds was measured according to the method described in ASTM D 1895-69, Method A; 23°C and 50% relative humidity.

Intrinsic Viscosity (IV):

- 10 The Intrinsic Viscosity is determined according to method PTC-179 (Hercules Inc. Rev. Apr. 29, 1982) at 135 °C in decalin, the dissolution time being 16 hours, with BHT (Butylated Hydroxy Toluene) as anti-oxidant in an amount of 2 g/l solution, by extrapolating the viscosity as measured at different concentrations to zero concentration;

15 **Elongational stress (ES)**

of an UHMWPE is measured according to ISO 11542-2A

CLAIMS

1. Process for preparation of a particulate ultra high molecular weight polyethylene (pUHMWPE), comprising the steps of
- 5 a) preparing a magnesium containing carrier by interaction of a solution of an organomagnesium compound having composition $MgR^1_{2.n}MgCl_{2.m}R^2_{2O}$ where $n = 0.37-0.7$, $m = 1.1-3.5$, R^1 is each an aromatic or aliphatic hydrocarbyl residue and R^2_{2O} is an aliphatic ether, with a chlorinating agent at a molar ratio Mg/Cl of at most 0.5, wherein Mg represents the Mg
- 10 of the organomagnesium compound and Cl the Cl of the chlorinating agent;
- b) loading the magnesium containing carrier with a organometallic compound forming a supported catalyst,
- c) contacting the supported catalyst with ethylene and at least one olefinic
- 15 co-monomer under polymerization conditions,
- wherein** the organometallic compound is a compound of the formula $R^3_3P=N-TiCpX_n$, wherein
- each R^3 is independently selected from the group consisting of
- 20 a hydrogen atom,
- a halogen atom,
- a C_{1-20} hydrocarbyl radicals optionally substituted by at least one halogen atom,
- a C_{1-8} alkoxy radical,
- a C_{6-10} aryl or aryloxy radical,
- 25 an amido radical,
- a silyl radical of the formula $-Si-(R^4)_3$
- and a germanyl radical of the formula $-Ge-(R^4)_3$
- wherein each R^4 is independently selected from the group consisting of hydrogen, a C_{1-8} alkyl or alkoxy radical, C_{6-10} aryl or aryloxy radicals,
- 30 Cp is a cyclopentadienyl ligand;
- X is an activatable ligand and n is 1 or 2, depending upon the valence of Ti and the valence of X, preferably, X is selected from the group consisting of Cl, Br, Me and Et if $n = 2$ or X is a substituted or unsubstituted butadiene if $n = 1$.
2. The process of claim 1 wherein the co-monomer is selected from the group
- 35 consisting of an alpha-olefin with at least 3 carbon atoms, a cyclic olefin

- having 5 to 20 carbon atoms and a linear, branched or cyclic diene having 4 to 20 carbon atoms.
3. The process of claim 1 or 2 comprising the step of treating the magnesium containing carrier or the organometallic compound with an activator selected from the list of alumoxanes, alkyl aluminiums, alkyl aluminum halides, anionic compounds of boron or aluminum, trialkylboron compounds, triarylboron compounds, borates, and mixtures thereof, preferably the activator is alumoxanes or alkyl aluminums.
 4. The process according to any of the preceding claims wherein the magnesium containing carrier has a D50 of 2 to 30 μm .
 5. The process of any of the preceding claims wherein the chlorinating agent is a chlorine-containing compound of composition $\text{Y}_k\text{ACl}_{4-k}$, where $\text{Y} = \text{OR}^5$ or R^5 group with R^5 being a C_{1-20} hydrocarbyl radicals optionally substituted by at least one halogen atom, A being Si or C atom and $k = 0$ to 2.
 6. The process of any of the preceding claims wherein the organometallic compound is of the formula ${}^t\text{Bu}_3\text{P}=\text{N}-\text{TiCp}^*\text{X}_2$, wherein Cp^* is pentamethylcyclopentadienyl and X is selected from the group consisting of Cl, Br, Me and Et.
 7. The ultrahigh molecular weight polyethylene obtainable by any of the processes according to claims 1 to 6.
 8. Particulate ultra high molecular weight polyethylene (pUHMWPE) having an intrinsic viscosity (IV) of at least 4 dl/g, a co-monomer content of at least 0.05 SCB/1000TC, a co-monomer partition factor (C_{pf}) of at least 0.8, a median particle size D50 of between 50 and 500 μm , a total ash content of less than 1000 ppm.
 9. pUHMWPE according to claim 8, wherein the polymer has a molecular weight distribution, M_w/M_n , of less than 4.0.
 10. pUHMWPE according to claim 8 or 9, wherein the co-monomer selected from the group consisting of an alpha-olefin with at least 3 carbon atoms, a cyclic olefin having 5 to 20 carbon atoms and a linear, branched or cyclic diene having 4 to 20 carbon atoms.
 11. pUHMWPE according to any of the claims 8 to 10 wherein the UHMWPE has a residual Si-content of less than 100 ppm.

12. pUHMWPE according to any of the claims 8-11 wherein the UHMWPE has an apparent bulk density of at least 300 kg/m^3 .
13. Process for manufacturing of a molded UHMWPE articles comprising the pUHMWPE of any of the claims 8-12.
- 5 14. The process according to claim 13 wherein the molded article is a fiber, tape or film.
15. A product comprising the molded articles according to claim 13 or 14, preferably the article is selected from the group consisting of ropes, cables, nets, fabrics, and protective appliances such as ballistic resistant articles.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2014/072859

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08F10/02 C08F4/659
ADD. C08F110/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2008/058749 A2 (DSM IP ASSETS BV [NL]; BORESKOVA INST KATALIZA SIBIR [RU]; KIDD TIMOTH) 22 May 2008 (2008-05-22) the whole document	1-15
A	EP 0 890 581 A1 (NOVA CHEM INT SA [CH]) 13 January 1999 (1999-01-13) examples 13-15	1-15
A	US 6 528 671 B1 (NABIKA MASAOKI [JP]) 4 March 2003 (2003-03-04) examples 2,3	1-15
X	CN 102 219 870 A (SHANGHAI INST ORGANIC CHEM) 19 October 2011 (2011-10-19) tables 2-4,5-7	8-15
	----- -/--	

Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>
---	---

Date of the actual completion of the international search 9 December 2014	Date of mailing of the international search report 23/12/2014
--	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Balmer, J
--	-------------------------------------

INTERNATIONAL SEARCH REPORT

International application No PCT/EP2014/072859

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2003/119661 A1 (GAO XIAOLIANG [CA] ET AL) 26 June 2003 (2003-06-26) examples 12,15 <p style="text-align: center;">-----</p>	8-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2014/072859

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
WO 2008058749	A2	22-05-2008	BR PI0718890 A2	08-07-2014
			CN 101631806 A	20-01-2010
			EP 2081969 A2	29-07-2009
			JP 2010510334 A	02-04-2010
			RU 2320410 C1	27-03-2008
			US 2010143719 A1	10-06-2010
			WO 2008058749 A2	22-05-2008
			WO 2008060189 A2	22-05-2008
EP 0890581	A1	13-01-1999	AT 235518 T	15-04-2003
			AU 740558 B2	08-11-2001
			AU 7192098 A	21-01-1999
			BR 9802353 A	14-12-1999
			CA 2210131 A1	09-01-1999
			CN 1206015 A	27-01-1999
			DE 69812485 D1	30-04-2003
			DE 69812485 T2	04-03-2004
			EP 0890581 A1	13-01-1999
			ES 2196493 T3	16-12-2003
			FI 981404 A	10-01-1999
			JP 4237298 B2	11-03-2009
			JP H1171420 A	16-03-1999
			NO 983151 A	11-01-1999
			RU 2203908 C2	10-05-2003
US 5965677 A	12-10-1999			
US 6528671	B1	04-03-2003	DE 10048968 A1	19-04-2001
			JP 4122655 B2	23-07-2008
			JP 2001106716 A	17-04-2001
			US 6528671 B1	04-03-2003
			US 2003109730 A1	12-06-2003
CN 102219870	A	19-10-2011	CN 102030844 A	27-04-2011
			CN 102219869 A	19-10-2011
			CN 102219870 A	19-10-2011
US 2003119661	A1	26-06-2003	AU 2002325742 A1	01-04-2003
			BR 0212565 A	13-10-2004
			CA 2357385 A1	17-03-2003
			CN 1561349 A	05-01-2005
			EP 1427761 A2	16-06-2004
			JP 2005502777 A	27-01-2005
			KR 20040035793 A	29-04-2004
			US 2003119661 A1	26-06-2003
			WO 03025027 A2	27-03-2003