



US012046587B2

(12) **United States Patent**
Lee et al.

(10) **Patent No.:** **US 12,046,587 B2**
(45) **Date of Patent:** **Jul. 23, 2024**

(54) **LIGHT EMITTING DEVICE FOR DISPLAY AND DISPLAY APPARATUS HAVING THE SAME**
(71) Applicant: **SEOUL VIOSYS CO., LTD.**, Ansan-si (KR)
(72) Inventors: **Seom Geun Lee**, Ansan-si (KR); **Seong Kyu Jang**, Ansan-si (KR); **Yong Woo Ryu**, Ansan-si (KR); **Jong Hyeon Chae**, Ansan-si (KR)
(73) Assignee: **SEOUL VIOSYS CO., LTD.**, Ansan-si (KR)
(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **18/226,779**
(22) Filed: **Jul. 27, 2023**

(65) **Prior Publication Data**
US 2023/0369301 A1 Nov. 16, 2023

Related U.S. Application Data
(63) Continuation of application No. 17/902,893, filed on Sep. 4, 2022, now Pat. No. 11,756,940, which is a (Continued)

(51) **Int. Cl.**
H01L 25/075 (2006.01)
H01L 33/42 (2010.01)
H01L 33/62 (2010.01)
(52) **U.S. Cl.**
CPC **H01L 25/0756** (2013.01); **H01L 25/0753** (2013.01); **H01L 33/42** (2013.01); **H01L 33/62** (2013.01)


(58) **Field of Classification Search**
CPC . H01L 25/0756; H01L 25/0753; H01L 33/42; H01L 33/62; H01L 24/24;
(Continued)

(56) **References Cited**
U.S. PATENT DOCUMENTS
9,680,063 B2 6/2017 Miyachi et al.
10,170,666 B2 1/2019 Cha et al.
(Continued)
FOREIGN PATENT DOCUMENTS
JP 2016-219453 12/2016
JP 2018-148074 9/2018
KR 10-2017-0115142 10/2017
OTHER PUBLICATIONS
International Search Report issued on Mar. 3, 2021 in International Application No. PCT/KR2020/015940 (With English Translation).
(Continued)

Primary Examiner — Victor A Mandala
(74) *Attorney, Agent, or Firm* — Oblon, McClelland, Maier & Neustadt, L.L.P.

(57) **ABSTRACT**
A light emitting module including a circuit board and a lighting emitting device thereon and including first, second, and third LED stacks each including first and second conductivity type semiconductor layers, a first bonding layer between the second and third LED stacks, a second bonding layer between the first and second LED stacks, a first planarization layer between the second bonding layer and the third LED stack, a second planarization layer on the first LED stack, a lower conductive material extending along sides of the first planarization layer, the second LED stack, the first bonding layer, and electrically connected to the first conductivity type semiconductor layers of each LED stack, respectively, and an upper conductive material between the circuit board and the lower conductive material.

17 Claims, 67 Drawing Sheets



Related U.S. Application Data

continuation of application No. 17/096,289, filed on Nov. 12, 2020, now Pat. No. 11,437,353.

(60) Provisional application No. 62/935,741, filed on Nov. 15, 2019.

(58) **Field of Classification Search**

CPC H01L 24/16; H01L 24/29; H01L 24/32; H01L 24/81; H01L 24/83; H01L 2224/131; H01L 2224/13109; H01L 23/481; H01L 24/82; H01L 25/167; H01L 2933/0066; H01L 27/15; H01L 33/0093; H01L 33/0095; H01L 33/44; H01L 2224/16227; H01L 2224/24051; H01L 2224/24146; H01L 2224/244; H01L 2224/245; H01L 2224/29186; H01L 2224/29188; H01L 2224/2919; H01L 2224/83851; H01L 2224/83399; H01L 2224/32145; H01L 2224/32227; H01L 2224/73217; H01L 2224/73267; H01L 2224/81005; H01L 2224/81193; H01L 2224/82106; H01L 2224/83192; H01L 2924/12041; H01L 27/156; H01L 24/31; H01L 2224/293; H01L 2224/81399; H01L 2224/83101; H01L 2924/00014; H01L 2224/2929; H01L 2924/05442; H01L 2924/01052; H01L 2924/0504; H01L 2924/01022; H01L 2924/0132; H01L 2924/01032; H01L 2924/01079; H01L 2924/05432; H01L 2924/01028; H01L 2924/0635; H01L 2924/07025

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2008/0251799 A1 10/2008 Ikezawa
 2010/0123163 A1* 5/2010 Ohtorii H01L 23/49838
 257/E33.056

2011/0284822 A1* 11/2011 Jung H01L 33/56
 257/E33.012
 2014/0252382 A1 9/2014 Hashimoto et al.
 2015/0076446 A1 3/2015 Suh, II et al.
 2016/0336479 A1 11/2016 Miyachi et al.
 2017/0288093 A1 10/2017 Cha et al.
 2019/0164944 A1* 5/2019 Chae H01L 25/0756
 2019/0165037 A1* 5/2019 Chae H01L 33/10
 2019/0189596 A1* 6/2019 Chae H01L 25/0756
 2019/0198485 A1* 6/2019 Chae H01L 33/42
 2019/0214373 A1* 7/2019 Kim H01L 33/08
 2019/0229234 A1 7/2019 Zou et al.
 2020/0091389 A1* 3/2020 Jang H01L 33/50
 2020/0144326 A1* 5/2020 Lee H01L 27/15
 2020/0144470 A1* 5/2020 Jang H01L 33/62
 2020/0176655 A1* 6/2020 Iguchi H01L 33/62
 2020/0212017 A1* 7/2020 Oh H01L 33/62
 2020/0258872 A1* 8/2020 Lee H01L 33/62
 2020/0266233 A1* 8/2020 Iguchi H01L 33/06
 2020/0266318 A1* 8/2020 Lee H01L 25/0753
 2020/0295228 A1* 9/2020 Jang H01L 33/62
 2020/0373348 A1* 11/2020 Lee H01L 33/62
 2021/0043678 A1* 2/2021 Chae H01L 25/0756
 2021/0057481 A1* 2/2021 Chae H01L 33/62
 2021/0125972 A1* 4/2021 Jang H01L 27/153
 2021/0126043 A1* 4/2021 Lee H01L 27/15
 2021/0175280 A1* 6/2021 Chae H01L 33/44
 2021/0202567 A1* 7/2021 Kim H01L 27/156
 2021/0265326 A1* 8/2021 Lee H01L 24/05
 2021/0351229 A1* 11/2021 Lee H01L 25/0756

OTHER PUBLICATIONS

Notice of Allowance dated Apr. 28, 2022, in U.S. Appl. No. 17/096,289.

Notice of Allowance dated Jul. 21, 2023, in U.S. Appl. No. 17/902,893.

Extended European Search Report issued Dec. 19, 2023, in corresponding European Patent Application No. 20887672.2, 12 pages.

* cited by examiner

FIG. 1






FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5B




FIG. 5C




FIG. 6A




FIG. 6B




FIG. 6C




FIG. 7A




FIG. 7B




FIG. 7C




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 9A




FIG. 9B




FIG. 9C




FIG. 10A




FIG. 10B




FIG. 10C




FIG. 11A




FIG. 11B




FIG. 11C




FIG. 12A




FIG. 12B




FIG. 12C




FIG. 13A




FIG. 13B




FIG. 13C




FIG. 14A




FIG. 14B




FIG. 14C




FIG. 15A




FIG. 15B




FIG. 15C




FIG. 16A




FIG. 16B




FIG. 16C




FIG. 17A




FIG. 17B




FIG. 17C




FIG. 17D




FIG. 18




FIG. 19




FIG. 20

200




FIG. 21A




FIG. 21B




FIG. 22A




FIG. 22B




FIG. 22C




FIG. 23A




FIG. 23B




FIG. 23C




FIG. 24A




FIG. 24B




FIG. 24C




FIG. 25A




FIG. 25B




FIG. 25C




FIG. 26A




FIG. 26B




FIG. 26C




FIG. 27A




FIG. 27B




FIG. 27C




FIG. 28




FIG. 29A




FIG. 29B




FIG. 29C





FIG. 30



**LIGHT EMITTING DEVICE FOR DISPLAY
AND DISPLAY APPARATUS HAVING THE
SAME**

CROSS-REFERENCE TO RELATED
APPLICATIONS

This application is a Continuation of U.S. patent application Ser. No. 17/902,893, filed on Sep. 4, 2022, which is a Continuation of U.S. patent application Ser. No. 17/096,289, filed on Nov. 12, 2020, now issued as U.S. Pat. No. 11,437,353, which claims priority from the benefit of U.S. Provisional Application No. 62/935,741, filed on Nov. 15, 2019, each of which is hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND

Field

Exemplary embodiments of the invention relate generally to a light emitting device for a display and a display apparatus, and, more particularly, to a light emitting device having a stack structure of LEDs for a display and a display apparatus including the same.

Discussion of the Background

As an inorganic light source, light emitting diodes have been used in various fields including displays, vehicular lamps, general lighting, and the like. With various advantages of light emitting diodes over conventional light sources, such as longer lifespan, lower power consumption, and rapid response, light emitting diodes have been replacing conventional light sources.

Light emitting diodes have been generally used as back-light light sources in display apparatuses. However, LED displays that directly display images using the light emitting diodes have been recently developed.

In general, a display apparatus realizes various colors through mixture of blue, green, and red light. In order to display various images, the display apparatus includes a plurality of pixels each having sub-pixels corresponding to blue, green and red light, respectively. In this manner, a color of a certain pixel is determined based on the colors of the sub-pixels so that images can be displayed through combination of such pixels.

Since LEDs can emit various colors depending upon materials thereof, a display apparatus may be provided by arranging individual LED chips emitting blue, green, and red light on a two-dimensional plane. However, when one LED chip is arranged in each sub-pixel, the number of LED chips may be increased, which may require excessive time for a mounting process during manufacture.

Moreover, when the sub-pixels are arranged on a two-dimensional plane in the display apparatus, a relatively large area is occupied by one pixel that includes the sub-pixels for blue, green, and red light. Accordingly, an area of each LED chip may need to be reduced to arrange the sub-pixels in a restricted area. However, reduction in size of LED chips may cause difficulty in mounting the LED chips, as well as reducing luminous areas of the LED chips.

The above information disclosed in this Background section is only for understanding of the background of the inventive concepts, and, therefore, it may contain information that does not constitute prior art.

SUMMARY

Light emitting devices for a display constructed according to exemplary embodiments of the invention are capable of increasing an area of each sub-pixel in a restricted pixel area and a display apparatus including the same.

Exemplary embodiments also provide a light emitting device for a display that is capable of reducing a time for a mounting process and a display apparatus including the same.

Exemplary embodiments also provide a light emitting device for a display and a display apparatus that is capable of increasing the production yield.

Additional features of the inventive concepts will be set forth in the description which follows, and in part will be apparent from the description, or may be learned by practice of the inventive concepts.

A light emitting device according to an exemplary embodiment includes a first LED stack, a second LED stack disposed under the first LED stack, and a third LED stack disposed under the second LED stack, each of the first, second, and third LED stacks including a first conductivity type semiconductor layer and a second conductivity type semiconductor layer, a first bonding layer interposed between the second LED stack and the third LED stack, a second bonding layer interposed between the first LED stack and the second LED stack, a first planarization layer interposed between the second bonding layer and the second LED stack, a second planarization layer disposed on the first LED stack, lower buried vias passing through the first planarization layer, the second LED stack, and the first bonding layer and electrically connected to the first conductivity type semiconductor layer and the second conductivity type semiconductor layer of the third LED stack, respectively, and upper buried vias passing through the second planarization layer and the first LED stack, in which a width of an upper end of each of the lower buried vias and the upper buried vias is greater than a width of a corresponding through hole.

The first, second, and third LED stacks may be configured to emit red light, blue light, and green light, respectively.

The light emitting device may further include lower connectors covering the lower buried vias, in which at least one of the upper buried vias may be connected to the lower connectors.

The lower buried vias may include a first lower buried via and a second lower buried via, the upper buried vias may include a first upper buried via, a second upper buried via, a third upper buried via, and a fourth upper buried via, the first and second upper buried vias overlapping the with first and second lower buried vias.

The light emitting device may further include a third lower connector spaced apart from the lower buried vias and electrically connected to the second conductivity type semiconductor layer of the second LED stack, in which the third upper buried via may be electrically connected to the third lower connector.

The first planarization layer may include a plurality of regions spaced apart from each other, one region of the first planarization layer may be interposed between the second LED stack and the third lower connector, and the third lower connector may be electrically connected to the second LED stack around the one region of the first planarization layer.

The lower buried vias may further include a third lower buried via passing through the first planarization layer and the second conductivity type semiconductor layer of the second LED stack, the third lower buried via being electrically

cally connected to the first conductivity type semiconductor layer of the second LED stack, and the third lower buried via may be electrically connected to one of the lower connectors.

The first planarization layer may be continuously disposed on the second LED stack.

The lower buried vias and the upper buried vias may be surrounded by sidewall insulation layers inside corresponding through holes, respectively.

The sidewall insulation layers may have a gradually decreasing thickness as being closer to bottoms of the through holes.

The light emitting device may further include a first transparent electrode in ohmic contact with the second conductivity type semiconductor layer of the first LED stack, a second transparent electrode in ohmic contact with the second conductivity type semiconductor layer of the second LED stack, and a third transparent electrode in ohmic contact with the second conductivity type semiconductor layer of the third LED stack, in which the second transparent electrode may have openings exposing the second conductivity type semiconductor layer of the second LED stack, and the lower buried vias may be formed within the circumference of the openings of the second transparent electrode in a plan view.

The light emitting device may further include a plurality of upper connectors disposed on the first LED stack, in which the upper connectors may cover the upper buried vias to be electrically connected to the upper buried vias, respectively.

The light emitting device may further include bump pads disposed on the upper connectors, respectively.

The bump pads may include a first bump pad commonly electrically connected to the first, second, and third LED stacks, and second, third, and fourth bump pads electrically connected to the second conductivity type semiconductor layers of the first, second, and third LED stacks, respectively.

The light emitting device may further include a first electrode pad disposed on the first conductivity type semiconductor layer of the first LED stack, in which one of the upper connectors electrically may connect the upper buried via and the first electrode pad.

The upper connectors may include Au or an Au alloy.

Upper surfaces of the lower buried vias may be substantially flush with an upper surface of the first planarization layer, and upper surfaces of the upper buried vias may be substantially flush with an upper surface of the second planarization layer.

Each of the first, second, and third LED stacks may not include a growth substrate.

The light emitting device may further include a lower insulation layer interposed between the third LED stack and the first bonding layer and contacting the first bonding layer, and an intermediate insulation layer interposed between the second LED stack and the second bonding layer and contacting the second bonding layer.

A display apparatus according to another exemplary embodiment includes a circuit board, and a plurality of light emitting devices arranged on the circuit board, each of the light emitting devices including a first LED stack, a second LED stack disposed under the first LED stack, a third LED stack disposed under the second LED stack and including a first conductivity type semiconductor layer and a second conductivity type semiconductor layer, a first bonding layer interposed between the second LED stack and the third LED stack, a second bonding layer interposed between the first

LED stack and the second LED stack, a first planarization layer interposed between the second bonding layer and the second LED stack, a second planarization layer disposed on the first LED stack, lower buried vias passing through the first planarization layer, the second LED stack, and the first bonding layer and electrically connected to the first conductivity type semiconductor layer and the second conductivity type semiconductor layer of the third LED stack, respectively, and upper buried vias passing through the second planarization layer and the first LED stack, in which a width of an upper end of each of the lower buried vias and the upper buried vias is greater than that of a corresponding through hole.

It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate exemplary embodiments of the invention, and together with the description serve to explain the inventive concepts.

FIG. 1 shows schematic perspective views of display apparatuses according to exemplary embodiments.

FIG. 2 is a schematic plan view of a display panel according to an exemplary embodiment.

FIG. 3 is a schematic plan view of a light emitting device according to an exemplary embodiment.

FIGS. 4A and 4B are schematic cross-sectional views taken along lines A-A' and B-B' of FIG. 3, respectively.

FIGS. 5A, 5B, and 5C are schematic cross-sectional views of first, second, and third LED stacks grown on growth substrates, respectively, according to an exemplary embodiment.

FIGS. 6A, 6B, 6C, 7A, 7B, 7C, 8A, 8B, 8C, 9A, 9B, 9C, 10A, 10B, 10C, 11A, 11B, 11C, 12A, 12B, 12C, 13A, 13B, 13C, 14A, 14B, 14C, 15A, 15B, 15C, 16A, 16B, and 16C are schematic plan views and cross-sectional views illustrating a method of manufacturing a light emitting device for a display according to an exemplary embodiment.

FIGS. 17A, 17B, 17C, and 17D are schematic cross-sectional views illustrating a process of forming a buried via according to exemplary embodiments.

FIG. 18 is a SEM image illustrating a via buried in a contact hole.

FIG. 19 is a SEM image illustrating a buried via.

FIG. 20 is a schematic plan view of a light emitting device according to another exemplary embodiment.

FIGS. 21A and 21B are schematic cross-sectional views taken along lines C-C' and D-D' of FIG. 20, respectively.

FIGS. 22A, 22B, 22C, 23A, 23B, 23C, 24A, 24B, 24C, 25A, 25B, 25C, 26A, 26B, 26C, 27A, 27B, and 27C are schematic plan views and cross-sectional views illustrating a method of manufacturing a light emitting device for a display according to another exemplary embodiment.

FIG. 28 is a schematic cross-sectional view of a light emitting device mounted on a circuit board.

FIGS. 29A, 29B, and 29C are schematic cross-sectional views illustrating a method of transferring a light emitting device to a circuit board according to an exemplary embodiment.

FIG. 30 is a schematic cross-sectional view illustrating a method of transferring a light emitting device to a circuit board according to another exemplary embodiment.

DETAILED DESCRIPTION

In the following description, for the purposes of explanation, numerous specific details are set forth in order to provide a thorough understanding of various exemplary embodiments or implementations of the invention. As used herein “embodiments” and “implementations” are interchangeable words that are non-limiting examples of devices or methods employing one or more of the inventive concepts disclosed herein. It is apparent, however, that various exemplary embodiments may be practiced without these specific details or with one or more equivalent arrangements. In other instances, well-known structures and devices are shown in block diagram form in order to avoid unnecessarily obscuring various exemplary embodiments. Further, various exemplary embodiments may be different, but do not have to be exclusive. For example, specific shapes, configurations, and characteristics of an exemplary embodiment may be used or implemented in another exemplary embodiment without departing from the inventive concepts.

Unless otherwise specified, the illustrated exemplary embodiments are to be understood as providing exemplary features of varying detail of some ways in which the inventive concepts may be implemented in practice. Therefore, unless otherwise specified, the features, components, modules, layers, films, panels, regions, and/or aspects, etc. (hereinafter individually or collectively referred to as “elements”), of the various embodiments may be otherwise combined, separated, interchanged, and/or rearranged without departing from the inventive concepts.

The use of cross-hatching and/or shading in the accompanying drawings is generally provided to clarify boundaries between adjacent elements. As such, neither the presence nor the absence of cross-hatching or shading conveys or indicates any preference or requirement for particular materials, material properties, dimensions, proportions, commonalities between illustrated elements, and/or any other characteristic, attribute, property, etc., of the elements, unless specified. Further, in the accompanying drawings, the size and relative sizes of elements may be exaggerated for clarity and/or descriptive purposes. When an exemplary embodiment may be implemented differently, a specific process order may be performed differently from the described order. For example, two consecutively described processes may be performed substantially at the same time or performed in an order opposite to the described order. Also, like reference numerals denote like elements.

When an element, such as a layer, is referred to as being “on,” “connected to,” or “coupled to” another element or layer, it may be directly on, connected to, or coupled to the other element or layer or intervening elements or layers may be present. When, however, an element or layer is referred to as being “directly on,” “directly connected to,” or “directly coupled to” another element or layer, there are no intervening elements or layers present. To this end, the term “connected” may refer to physical, electrical, and/or fluid connection, with or without intervening elements. Further, the D1-axis, the D2-axis, and the D3-axis are not limited to three axes of a rectangular coordinate system, such as the x, y, and z-axes, and may be interpreted in a broader sense. For example, the D1-axis, the D2-axis, and the D3-axis may be perpendicular to one another, or may represent different directions that are not perpendicular to one another. For the

purposes of this disclosure, “at least one of X, Y, and Z” and “at least one selected from the group consisting of X, Y, and Z” may be construed as X only, Y only, Z only, or any combination of two or more of X, Y, and Z, such as, for instance, XYZ, XYY, YZ, and ZZ. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items.

Although the terms “first,” “second,” etc. may be used herein to describe various types of elements, these elements should not be limited by these terms. These terms are used to distinguish one element from another element. Thus, a first element discussed below could be termed a second element without departing from the teachings of the disclosure.

Spatially relative terms, such as “beneath,” “below,” “under,” “lower,” “above,” “upper,” “over,” “higher,” “side” (e.g., as in “sidewall”), and the like, may be used herein for descriptive purposes, and, thereby, to describe one element relationship to another element(s) as illustrated in the drawings. Spatially relative terms are intended to encompass different orientations of an apparatus in use, operation, and/or manufacture in addition to the orientation depicted in the drawings. For example, if the apparatus in the drawings is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the exemplary term “below” can encompass both an orientation of above and below. Furthermore, the apparatus may be otherwise oriented (e.g., rotated 90 degrees or at other orientations), and, as such, the spatially relative descriptors used herein interpreted accordingly.

The terminology used herein is for the purpose of describing particular embodiments and is not intended to be limiting. As used herein, the singular forms, “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. Moreover, the terms “comprises,” “comprising,” “includes,” and/or “including,” when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components, and/or groups thereof, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof. It is also noted that, as used herein, the terms “substantially,” “about,” and other similar terms, are used as terms of approximation and not as terms of degree, and, as such, are utilized to account for inherent deviations in measured, calculated, and/or provided values that would be recognized by one of ordinary skill in the art.

Various exemplary embodiments are described herein with reference to sectional and/or exploded illustrations that are schematic illustrations of idealized exemplary embodiments and/or intermediate structures. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, exemplary embodiments disclosed herein should not necessarily be construed as limited to the particular illustrated shapes of regions, but are to include deviations in shapes that result from, for instance, manufacturing. In this manner, regions illustrated in the drawings may be schematic in nature and the shapes of these regions may not reflect actual shapes of regions of a device and, as such, are not necessarily intended to be limiting.

Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this disclosure is a part. Terms, such as those defined in commonly used dictionaries, should be interpreted as

having a meaning that is consistent with their meaning in the context of the relevant art and should not be interpreted in an idealized or overly formal sense, unless expressly so defined herein.

Hereinafter, exemplary embodiments of the inventive concepts will be described in detail with reference to the accompanying drawings.

FIG. 1 shows schematic perspective views illustrating display apparatuses according to exemplary embodiments.

A light emitting device according to an exemplary embodiment may be used in a VR display apparatus, such as a smart watch **1000a** or a VR headset **1000b**, or an AR display apparatus, such as augmented reality glasses **1000c**, without being limited thereto.

A display panel for implementing an image may be mounted on a display apparatus. FIG. 2 is a schematic plan view of a display panel according to an exemplary embodiment.

Referring to FIG. 2, the display panel includes a circuit board **101** and light emitting devices **100**.

The circuit board **101** may include a circuit for passive matrix driving or active matrix driving. In an exemplary embodiment, the circuit board **101** may include interconnection lines and resistors therein. In another exemplary embodiment, the circuit board **101** may include interconnection lines, transistors, and capacitors. The circuit board **101** may also have pads disposed on an upper surface thereof to allow electrical connection to the circuit therein.

A plurality of light emitting devices **100** is arranged on the circuit board **101**. Each of the light emitting devices **100** may form one pixel. The light emitting device **100** includes bump pads **73**, and the bump pads **73** are electrically connected to the circuit board **101**. For example, the bump pads **73** may be bonded to pads exposed on the circuit board **101**.

An interval between the light emitting devices **100** may be greater than at least a width of the light emitting device **100**.

A configuration of the light emitting device **100** according to an exemplary embodiment will be described with reference to FIGS. 3, 4A, and 4B. FIG. 3 is a schematic plan view of the light emitting device **100** according to an exemplary embodiment, and FIGS. 4A and 4B are schematic cross-sectional views taken along lines A-A' and B-B' of FIG. 3, respectively.

Hereinafter, although bump pads **73a**, **73b**, **73c**, and **73d** are exemplarily illustrated and described as being disposed at an upper side in the drawings, the inventive concepts are not limited thereto. For example, in another exemplary embodiment, the light emitting device **100** may be flip-bonded on the circuit board **101** shown in FIG. 2. In this case, the bump pads **73a**, **73b**, **73c**, and **73d** may be disposed at a lower side. Furthermore, in some exemplary embodiments, the bump pads **73a**, **73b**, **73c**, and **73d** may be omitted. In addition, in other exemplary embodiments, the substrate **41** may be omitted.

Referring to FIGS. 3, 4A and 4B, the light emitting device **100** may include a first LED stack **23**, a second LED stack **33**, a third LED stack **43**, and a first transparent electrode **25**, a second transparent electrode **35**, a third transparent electrode **45**, a first n-electrode pad **27a**, a second n-electrode pad **37a**, a third n-electrode pad **47a**, a lower p-electrode pad **47b**, first, second, and third lower connectors **39a**, **39b**, and **39c**, lower buried vias **55a** and **55b**, upper buried vias **65a**, **65b**, **65c**, and **65d**, a first sidewall insulation layer **53**, first, second, third, and fourth upper connectors **67a**, **67b**, **67c**, and **67d**, a first bonding layer **49**, a second bonding layer **59**, a lower insulation layer **48**, an intermediate insulation layer

58, an upper insulation layer **71**, a lower planarization layer **51**, an upper planarization layer **61**, and bump pads **73a**, **73b**, **73c**, and **73d**. Furthermore, the light emitting device **100** may include through holes **23h1**, **23h2**, **23h3**, and **23h4** passing through the first LED stack **23**, and through holes **33h1** and **33h2** passing through the second LED stack **33**.

As shown in FIGS. 4A and 4B, the first, second, and third LED stacks **23**, **33**, and **43** according to an exemplary embodiment are stacked in the vertical direction. The first, second, and third LED stacks **23**, **33**, and **43** may be grown on different growth substrates from each other. According to the illustrated exemplary embodiment, each of the growth substrates may be removed from the final light emitting device **100**. As such, the light emitting device **100** does not include the growth substrates of the first, second, and third LED stacks **23**, **33**, and **43**. However, the inventive concepts are not limited thereto, and in some exemplary embodiments, at least one of the growth substrates may be included in the light emitting device **100**.

Hereinafter, the second LED stack is described as being disposed under the first LED stack, and the third LED stack is described as being disposed under the second LED stack, however, in some exemplary embodiments, the light emitting device may be flip-bonded. In this case, upper and lower positions of these first, second, and third LED stacks may be reversed.

Each of the first LED stack **23**, the second LED stack **33**, and the third LED stack **43** includes a first conductivity type semiconductor layer **23a**, **33a**, or **43a**, a second conductivity type semiconductor layer **23b**, **33b**, or **43b**, and an active layer interposed therebetween. In particular, the active layer may have a multiple quantum well structure.

The second LED stack **33** is disposed under the first LED stack **23**, and the third LED stack **43** is disposed under the second LED stack **33**. Light generated in the first, second, and third LED stacks **23**, **33**, and **43** may be emitted to the outside through the third LED stack **43**.

In an exemplary embodiment, the first LED stack **23** may emit light having a longer wavelength than those emitted from the second and third LED stacks **33** and **43**, and the second LED stack **33** may emit light having a longer wavelength than that emitted from the third LED stack **43**. For example, the first LED stack **23** may be an inorganic light emitting diode emitting red light, the second LED stack **33** may be an inorganic light emitting diode emitting green light, and the third LED stack **43** may be an inorganic light emitting diode emitting blue light.

In another exemplary embodiment, to adjust a color mixing ratio of light emitted from the first, second, and third LED stacks **23**, **33**, and **43**, the second LED stack **33** may emit light having a shorter wavelength than that emitted from the third LED stack **43**. As such, luminous intensity of light emitted from the second LED stack **33** may be reduced and luminous intensity of light emitted from the third LED stack **43** may be increased. In this manner, it is possible to dramatically change a luminous intensity ratio of light emitted from the first, second, and third LED stacks **23**, **33**, and **43**. For example, the first LED stack **23** may be configured to emit red light, the second LED stack **33** may be configured to emit blue light, and the third LED stack **43** may be configured to emit green light.

Hereinafter, although the second LED stack **33** is exemplarily described as emitting light having a shorter wavelength than that emitted from the third LED stack **43**, such as blue light, the inventive concepts are not limited thereto. In some exemplary embodiments, the second LED stack **33**

may emit light of a longer wavelength than that emitted from the third LED stack **43**, such as green light.

The first LED stack **23** may include an AlGaInP-based well layer, the second LED stack **33** may include an AlGaInN-based well layer, and the third LED stack **43** may include an AlGaInP or AlGaInN-based well layer.

Since the first LED stack **23** emits light having a longer wavelength than that emitted from the second and third LED stacks **33** and **43**, light generated in the first LED stack **23** may be emitted to the outside through the second and third LED stacks **33** and **43**. In addition, since the second LED stack **33** emits light having a shorter wavelength than that emitted from the third LED stack **43**, a portion of light generated in the second LED stack **33** may be absorbed by the third LED stack **43** and lost, and thus, luminous intensity of light generated in the second LED stack **33** may be reduced. Meanwhile, since light generated in the third LED stack **43** is emitted to the outside without passing through the first and second LED stacks **23** and **33**, luminous intensity thereof may be increased.

The first conductivity type semiconductor layer **23a**, **33a**, or **43a** of each of the LED stacks **23**, **33**, and **43** may be an n-type semiconductor layer, and the second conductivity type semiconductor layer **23b**, **33b** or **43b** thereof may be a p-type semiconductor layer. According to the illustrated exemplary embodiment, an upper surface of the first LED stack **23** is an n-type semiconductor layer **23b**, an upper surface of the second LED stack **33** is a p-type semiconductor layer **33b**, and an upper surface of the third LED stack **43** is a p-type semiconductor layer **43b**. As such, a stack sequence in the first LED stack **23** is reversed from those in the second LED stack **33** and the third LED stack **43**. The semiconductor layers of the second LED stack **33** are stacked in the same order as the semiconductor layers of the third LED stack **43**, and thus, process stability may be ensured. This will be described in detail later with reference to a manufacturing method.

The second LED stack **33** includes a mesa etching region, in which the second conductivity type semiconductor layer **33b** is removed to expose an upper surface of the first conductivity type semiconductor layer **33a**. As shown in FIGS. **3** and **4B**, the second n-electrode pad **37a** may be disposed on the first conductivity type semiconductor layer **33a** exposed in the mesa etching region. The third LED stack **43** may also include a mesa etching region, in which the second conductivity type semiconductor layer **43b** is removed to expose an upper surface of the first conductivity type semiconductor layer **43a**, and a third n-electrode pad **47** may be disposed on the exposed first conductivity type semiconductor layer **43a**. However, the first LED stack **23** may not include a mesa etching region.

The third LED stack **43** may have a flat lower surface, but the inventive concepts are not limited thereto. For example, the third LED stack **43** may include irregularities on a surface of the first conductivity type semiconductor layer **43a**, and light extraction efficiency may be improved by the irregularities. The surface irregularities of the first conductivity type semiconductor layer **43a** may be formed when separating a patterned sapphire substrate, but may also be formed by texturing after the growth substrate is removed therefrom. In some exemplary embodiments, the second LED stack **33** may also have the first conductivity type semiconductor layer **33a** having a textured surface.

In the illustrated exemplary embodiment, the first LED stack **23**, the second LED stack **33**, and the third LED stack **43** may be overlapped with one another, and may have a light emitting area of substantially similar size. However, the

light emitting areas of the first, second, and third LED stacks **23**, **33**, and **43** may be adjusted by the mesa etching region, the through holes **23h1**, **23h2**, **23h3**, and **23h4**, and the through holes **33h1** and **33h2**. For example, the light emitting areas of the first and third LED stacks **23** and **43** may be larger than that of the second LED stack **33**, and thus, luminous intensity of light generated in the first LED stack **23** or the third LED stack **43** may be further increased compared to that of light generated in the second LED stack **33**.

The first transparent electrode **25** may be disposed between the first LED stack **23** and the second LED stack **33**. The first transparent electrode **25** is in ohmic contact with the second conductivity type semiconductor layer **23b** of the first LED stack **23** and transmits light generated in the first LED stack **23**. The first transparent electrode **25** may be formed using a metal layer or a transparent oxide layer, such as indium tin oxide (ITO). The first transparent electrode **25** may cover an entire surface of the second conductivity type semiconductor layer **23b** of the first LED stack **23**, and a side surface thereof may be substantially flush with a side surface of the first LED stack **23**. In particular, a side surface of the first transparent electrode **25** may not be covered with the second bonding layer **59**. Furthermore, the through holes **23h1**, **23h2**, and **23h3** may pass through the first transparent electrode **25**, and thus, the first transparent electrode **25** may be exposed to sidewalls of the through holes **23h1**, **23h2**, and **23h3**. Meanwhile, the through hole **23h4** may expose an upper surface of the first transparent electrode **25**. However, the inventive concepts are not limited thereto, and in some exemplary embodiments, the first transparent electrode **25** may be partially removed along an edge of the first LED stack **23**, so that the side surface of the first transparent electrode **25** may be covered with the second bonding layer **59**. In addition, since the first transparent electrode **25** may be removed by patterning in advance in a region where the through holes **23h1**, **23h2**, and **23h3** are formed, the first transparent electrode **25** may be prevented from being exposed to sidewalls of the through holes **23h1**, **23h2**, and **23h3**.

The second transparent electrode **35** is in ohmic contact with the second conductivity type semiconductor layer **33b** of the second LED stack **33**. The second transparent electrode **35** contacts the upper surface of the second LED stack **33** between the first LED stack **23** and the second LED stack **33**. The second transparent electrode **35** may be formed of a metal layer or a conductive oxide layer that is transparent to red light. The conductive oxide layer may include SnO₂, InO₂, ITO, ZnO, IZO, or the like. In particular, the second transparent electrode **35** may be formed of ZnO, which may be formed as a single crystal on the second LED stack **33** and has favorable electrical and optical characteristics as compared with the metal layer or other conductive oxide layers. Moreover, since ZnO has a strong adhesion to the second LED stack **33**, the light emitting device may have improved reliability.

The second transparent electrode **35** may be partially removed along an edge of the second LED stack **33**, and accordingly, an outer side surface of the second transparent electrode **35** may not be exposed to the outside, but covered with the intermediate insulation layer **58**. More particularly, the side surface of the second transparent electrode **35** may be recessed inwardly than that of the second LED stack **33**, and a region where the second transparent electrode **35** is recessed may be filled with the intermediate insulation layer **58** and/or the second bonding layer **59**. Meanwhile, the second transparent electrode **35** may also be recessed near

the mesa etching region of the second LED stack **33**, and the recessed region may be filled with the intermediate insulation layer **58** or the second bonding layer **59**.

The third transparent electrode **45** is in ohmic contact with the second conductivity type semiconductor layer **43b** of the third LED stack **43**. The third transparent electrode **45** may be disposed between the second LED stack **33** and the third LED stack **43**, and contacts the upper surface of the third LED stack **43**. The third transparent electrode **45** may be formed of a metal layer or a conductive oxide layer that is transparent to red light and green light, for example. The conductive oxide layer may include SnO₂, InO₂, ITO, ZnO, IZO, or the like. In particular, the third transparent electrode **45** may be formed of ZnO, which may be formed as a single crystal on the third LED stack **43** and has favorable electrical and optical characteristics as compared with the metal layer or other conductive oxide layers. In addition, since ZnO has a strong adhesion to the third LED stack **43**, the light emitting device may have improved reliability.

The third transparent electrode **45** may be partially removed along an edge of the third LED stack **43**, and accordingly, an outer side surface of the third transparent electrode **45** may not be exposed to the outside, but covered with the lower insulation layer **48** or the first bonding layer **49**. More particularly, the side surface of the third transparent electrode **45** may be recessed inwardly than that of the third LED stack **43**, and a region where the third transparent electrode **45** is recessed may be filled with the lower insulation layer **48** and/or the first bonding layer **49**. Meanwhile, the third transparent electrode **45** may also be recessed near the mesa etching region of the third LED stack **43**, and the recessed region may be filled with the lower insulation layer **48** or the first bonding layer **49**.

The second transparent electrode **35** and the third transparent electrode **45** are recessed as described above, and thus, the side surfaces of the second transparent electrode **35** and the third transparent electrode **45** may be prevented from being exposed to an etching gas, thereby improving the production yield of the light emitting device **100**.

According to an exemplary embodiment, the second transparent electrode **35** and the third transparent electrode **45** may include the same conductive oxide layer, for example, ZnO, and the first transparent electrode **25** may be formed of a different conductive oxide layer from the second and third transparent electrodes **35** and **45**, such as ITO. However, the inventive concepts are not limited thereto, and in some exemplary embodiments, each of the first, second, and third transparent electrodes **25**, **35**, and **45** may include the same material, or at least one of the first, second, and third transparent electrodes **25**, **35**, and **45** may include a different material.

The first n-electrode pad **27a** is in ohmic contact with the first conductivity type semiconductor layer **23a** of the first LED stack **23**. The first n-electrode pad **27a** may include, for example, AuGe or AuTe.

The second n-electrode pad **37a** is in ohmic contact with the first conductivity type semiconductor layer **33a** of the second LED stack **33**. The second n-electrode pad **37a** may be disposed on the first conductivity type semiconductor layer **33a** exposed by mesa etching. The second n-electrode pad **37a** may be formed of, for example, Cr/Au/Ti.

The third n-electrode pad **47a** is in ohmic contact with the first conductivity type semiconductor layer **43a** of the third LED stack **43**. The third n-electrode pad **47a** may be disposed on the first conductivity type semiconductor layer **43a** exposed through the second conductivity type semiconductor layer **43b**, that is, in the mesa etching region. The

third n-electrode pad **47a** may be formed of, for example, Cr/Au/Ti. An upper surface of the third n-electrode pad **47a** may be placed higher than that of the second conductivity type semiconductor layer **43b**, and further, higher than that of the third transparent electrode **45**. For example, a thickness of the third n-electrode pad **47a** may be about 2 μm or more. The third n-electrode pad **47a** may have a shape of a truncated cone, but is not limited thereto. The third n-electrode pad **47a** in other exemplary embodiments may have various shapes, such as a square pyramid, a cylindrical shape, or a cylindrical shape.

The lower p-electrode pad **47b** may include substantially the same material as the third n-electrode pad **47a**. An upper surface of the lower p-electrode pad **47b** may be located at substantially the same elevation as the third n-electrode pad **47a**, and, accordingly, a thickness of the lower p-electrode pad **47b** may be less than that of the third n-electrode pad **47a**. More particularly, the thickness of the lower p-electrode pad **47b** may be approximately equal to a thickness of a portion of the third n-electrode pad **47a** protruding above the third transparent electrode **45**. For example, the thickness of the lower p-electrode pad **47b** may be about 1.2 μm or less. Since the upper surface of the lower p-electrode pad **47b** is located at substantially the same elevation as that of the third n-electrode pad **47a**, the lower p-electrode pad **47b** and the third n-electrode pad **47a** may be simultaneously exposed when the through holes **33h1** and **33h2** are formed. When the elevations of the third n-electrode pad **47a** and the lower p-electrode pad **47b** are different, any one of the electrode pads may be damaged in the etching process. As such, the elevations of the third n-electrode pad **47a** and the lower p-electrode pad **47b** are set to be approximately equal, so as to prevent any one of the electrode pads from being damaged during the etching process or the like.

The lower insulation layer **48** covers the upper surface of the third LED stack **43**. The lower insulation layer **48** may also cover the third transparent electrode **45**, and may cover the third n-electrode pad **47a** and the lower p-electrode pad **47b**. The lower insulation layer **48** may have openings exposing the third n-electrode pad **47a** and the lower p-electrode pad **47b**. The lower insulation layer **48** may protect the third LED stack **43** and the third transparent electrode **45**. Further, the lower insulation layer **48** may include a material capable of improving adhesion to the first bonding layer **49**, such as SiO₂. In some exemplary embodiments, the lower insulation layer **48** may be omitted.

The first bonding layer **49** couples the second LED stack **33** to the third LED stack **43**. The first bonding layer **49** may be disposed between the first conductivity type semiconductor layer **33a** and the third transparent electrode **45**. The first bonding layer **49** may contact the lower insulation layer **48**, and may partially contact the third n-electrode pad **47a** and the lower p-electrode pad **47b**. When the lower insulation layer **48** is omitted, the first bonding layer **49** may partially contact the third transparent electrode **45** and the first conductivity type semiconductor layer **43a** exposed in the mesa etching region.

The first bonding layer **49** may be formed of a transparent organic material layer, or may be formed of a transparent inorganic material layer. For example, the organic material layer may include SU8, poly methylmethacrylate (PMMA), polyimide, parylene, benzocyclobutene (BCB), or the like, and the inorganic material layer may include Al₂O₃, SiO₂, SiN_x, or the like. In addition, the first bonding layer **49** may be formed of spin-on-glass (SOG).

The first planarization layer **51** may be disposed on the second LED stack **33**. In particular, the first planarization

layer **51** is disposed on an upper region of the second conductivity type semiconductor layer **33b** and spaced apart from the mesa etching region. The first planarization layer **51** may be divided into a plurality of islands by patterning. In the illustrated exemplary embodiment, the first planarization layer **51** is divided into three regions.

The through holes **33h1** and **33h2** may pass through the first planarization layer **51**, the second LED stack **33**, and the first bonding layer **49**, and expose the third n-electrode pad **47a** and the lower p-electrode pad **47b**.

The first sidewall insulation layer **53** covers sidewalls of the through holes **33h1** and **33h2** and has openings exposing bottoms of the through holes **33h1** and **33h2**. The first sidewall insulation layer **53** may be formed using, for example, a chemical vapor deposition technique or an atomic layer deposition technique, and may be formed of, for example, Al_2O_3 , SiO_2 , Si_3N_4 , or the like.

The lower buried vias **55a** and **55b** may fill the through holes **33h1** and **33h2**, respectively. The lower buried vias **55a** and **55b** are insulated from the second LED stack **33** by the first sidewall insulation layer **53**. The lower buried via **55a** may be electrically connected to the third n-electrode pad **47a**, and the lower buried via **55b** may be electrically connected to the lower p-electrode pad **47b**.

The lower buried vias **55a** and **55b** may be formed using a chemical mechanical polishing technique. For example, after forming a seed layer and filling the through holes **33h1** and **33h2** with a conductive material such as Cu using a plating technique, the lower buried vias **55a** and **55b** may be formed by removing metal layers on the first planarization layer **51** using the chemical mechanical polishing technique. As shown in FIGS. **4A** and **4B**, the lower buried vias **55a** and **55b** may have a relatively wider width at inlets of the through holes **33h1** and **33h2**, and thus, the electrical connection may be strengthened.

The lower buried vias **55a** and **55b** may be formed together through the same process. As such, upper surfaces of the lower buried vias **55a** and **55b** may be substantially flush with the first planarization layer **51**. However, the inventive concepts are not limited thereto, and the lower buried vias may be formed through different processes from one another. A detailed process of forming the lower buried vias will be described in more detail later.

The intermediate insulation layer **58** is formed on the second LED stack **33** and covers the second transparent electrode **35**, the first planarization layer **51**, and the second n-electrode pad **37a**. The intermediate insulation layer **58** may also cover the mesa etching region of the second LED stack **33**. The intermediate insulation layer **58** may have openings exposing the lower buried vias **55a** and **55b** and the second n-electrode pad **37a**. The intermediate insulation layer **58** may be formed of, for example, SiO_2 . The intermediate insulation layer **58** may protect the second LED stack **33** and the second transparent electrode **35**, and further, may improve adhesion of the second bonding layer **59**.

The lower connectors **39a**, **39b**, and **39c** are disposed on each region of the first planarization layer **51**. The first lower connector **39a** may be electrically connected to the lower buried via **55a**, and may also extend in the lateral direction to be electrically connected to the second n-electrode pad **37a**. As such, the first conductivity type semiconductor layer **43a** of the third LED stack **43** and the first conductivity type semiconductor layer **33a** of the second LED stack **33** may be commonly electrically connected. The first lower connector **39a** may cover the lower buried via **55a**.

The second lower connector **39b** is electrically connected to the lower buried via **55b**. The second lower connector **39b** may cover the lower buried via **55b**.

The third lower connector **39c** is electrically connected to the second transparent electrode **35**. The third lower connector **39c** may be formed to surround the first planarization layer **51** as shown in FIG. **4A**, and may be connected to the second transparent electrode **35** along a periphery of the first planarization layer **51**. Since the third lower connector **39c** is disposed on the first planarization layer **51**, an elevation of an upper end of the third lower connector **39c** may be set to be approximately equal to that of the first lower connector **39a** or the second lower connector **39b**.

The second bonding layer **59** couples the first LED stack **23** to the second LED stack **33**. The second bonding layer **59** may be disposed between the first transparent electrode **25** and the intermediate insulation layer **58**. The second bonding layer **59** may also cover the first, second, and third lower connectors **39a**, **39b**, and **39c**. The second bonding layer **59** may include substantially the same material that forms the first bonding layer **49** described above, and thus, repeated descriptions thereof will be omitted to avoid redundancy.

The second planarization layer **61** covers the first LED stack **23**. Unlike the first planarization layer **51**, the second planarization layer **61** may be formed continuously. The second planarization layer **61** may be formed of an aluminum oxide film, a silicon oxide film, or a silicon nitride film. The second planarization layer **61** may have an opening exposing the first n-electrode pad **27a**.

The through holes **23h1**, **23h2**, **23h3**, and **23h4** pass through the second planarization layer **61** and the first LED stack **23**. Further, the through holes **23h1**, **23h2**, and **23h3** may pass through the first transparent electrode **25** and the second bonding layer **59** to expose the lower connectors **39a**, **39b**, and **39c**, and the through hole **23h4** may expose the first transparent electrode **25**. For example, the through hole **23h1** provides a passage for electrical connection to the lower buried via **55a**, the through hole **23h2** provides a passage for electrical connection to the lower buried via **55b**, and the through hole **23h3** provides a passage for electrical connection to the second transparent electrode **35**.

The through hole **23h4** provides a passage for electrical connection to the first transparent electrode **25**. The through hole **23h4** may not pass through the first transparent electrode **25**. However, the inventive concepts are not limited thereto, and in some exemplary embodiments, the through hole **23h4** may pass through the first transparent electrode **25** as long as the through hole **23h4** provides the passage for electrical connection to the first transparent electrode **25**.

The second sidewall insulation layer **63** covers the sidewalls of the through holes **23h1**, **23h2**, **23h3**, and **23h4**, and has openings exposing the bottoms of the through holes **23h1**, **23h2**, **23h3**, and **23h4**. In the illustrated exemplary embodiment, the second sidewall insulation layer **63** is not formed on a sidewall of an opening **61a** of the second planarization layer **61**, but the inventive concepts are not limited thereto. In some exemplary embodiments, the second sidewall insulation layer **63** may also be formed on the sidewall of the opening **61a** of the second planarization layer **61**. The second sidewall insulation layer **63** may be formed using, for example, a chemical vapor deposition technique or an atomic layer deposition technique, and may be formed of, for example, Al_2O_3 , SiO_2 , Si_3N_4 , or the like.

The upper buried vias **65a**, **65b**, **65c**, and **65d** may fill the through holes **23h1**, **23h2**, **23h3**, and **23h4**, respectively. The

upper buried vias **65a**, **65b**, **65c**, and **65d** are electrically insulated from the first LED stack **23** by the second sidewall insulation layer **63**.

The upper buried via **65a** may be electrically connected to the lower buried via **55a** through the first lower connector **39a**, the upper buried via **65b** may be electrically connected to the lower buried via **55b** through the second lower connector **39b**, and the upper buried via **65c** may be electrically connected to the second transparent electrode **35** through the third lower connector **39c**. Also, the upper buried via **65d** may be electrically connected to the first transparent electrode **25**.

The upper buried vias **65a**, **65b**, **65c**, and **65d** may be formed using a chemical mechanical polishing technique. For example, after forming a seed layer and filling the through holes **23h1**, **23h2**, **23h3**, and **23h4** using a plating technique, the upper buried vias **65a**, **65b**, **65c**, and **65d** may be formed by removing metal layers on the second planarization layer **61** using the chemical mechanical polishing technique. Furthermore, a metal barrier layer may be formed before forming the seed layer.

The upper buried vias **65a**, **65b**, **65c**, and **65d** may be substantially flush with the second planarization layer **61** that may be formed together through the same process. However, the inventive concepts are not limited thereto, and the upper buried vias **65a**, **65b**, **65c**, and **65d** may be formed through different processes from each other.

The first upper connector **67a**, the second upper connector **67b**, the third upper connector **67c**, and the fourth upper connector **67d** are disposed on the second planarization layer **61**. The first upper connector **67a** may be electrically connected to the upper buried via **65a**, the second upper connector **67b** may be electrically connected to the upper buried via **65b**, the third upper connector **67c** may be electrically connected to the upper buried via **65c**, and the fourth upper connector **67d** may be electrically connected to the upper buried via **65d**. As shown, the first, second, third, and fourth upper connectors **67a**, **67b**, **67c**, and **67d** may cover the upper buried vias **65a**, **65b**, **65c**, and **65d**, respectively. The first upper connector **67a** may be electrically connected to the first n-electrode pad **27a** through the opening **61a** of the second planarization layer **61**. As such, the first conductivity type semiconductor layers **23a**, **33a**, **43a** of the first, second, and third LED stacks **23**, **33**, and **43** are commonly electrically connected to one another.

The first upper connector **67a**, the second upper connector **67b**, the third upper connector **67c**, and the fourth upper connector **67d** may be formed of substantially the same material, for example, AuGe/Ni/Au/Ti, in the same process.

The upper insulation layer **71** may cover the first LED stack **23** and the second planarization layer **61**, and may cover the first, second, third, and fourth upper connectors **67a**, **67b**, **67c**, and **67d**. The upper insulation layer **71** may also cover the side surface of the first transparent electrode **25**. The upper insulation layer **71** may have openings **71a** exposing the first upper connector **67a**, the second upper connector **67b**, the third upper connector **67c**, and the fourth upper connector **67d**. The openings **71a** of the upper insulation layer **71** may be generally disposed on flat surfaces of the first upper connector **67a**, the second upper connector **67b**, the third upper connector **67c**, and the fourth upper connector **67d**. The upper insulation layer **71** may be formed of a silicon oxide film or a silicon nitride film, and may be formed to be thinner than the second planarization layer **61** to be about 400 nm thick, without being limited thereto.

Each of the bump pads **73a**, **73b**, **73c**, and **73d** may be disposed on the first upper connector **67a**, the second upper

connector **67b**, and the third upper connector **67c**, and the fourth upper connector **67d**, and is electrically connected thereto through the openings **71a** of the upper insulation layer **71**.

The first bump pad **73a** is electrically connected to the upper buried vias **65a** and the first n-electrode pad **27a** through the first upper connector **67a**, and accordingly, is commonly electrically connected to the first conductivity type semiconductor layers **23a**, **33a**, **43a** of the LED stacks **23**, **33**, and **43**.

The second bump pad **73b** may be electrically connected to the second conductivity type semiconductor layer **43b** of the third LED stack **43** through the second upper connector **67b**, the upper buried via **65b**, the second lower connector **39b**, the lower buried via **55b**, the lower p-electrode pad **47b**, and the transparent electrode **45**.

The third bump pad **73c** may be electrically connected to the second conductivity type semiconductor layer **33b** of the second LED stack **33** through the third upper connector **67c**, the upper buried via **65c**, the third lower connector **39c**, and the second transparent electrode **35**.

The fourth bump pad **73d** may be electrically connected to the second conductivity type semiconductor layer **23b** of the first LED stack **23** through the fourth upper connector **67d** and the first transparent electrode **25**.

As such, each of the second to fourth bump pads **73b**, **73c**, and **73d** may be electrically connected to the second conductivity type semiconductor layers **23b**, **33b**, and **43b** of the first, second, and third LED stacks **23**, **33**, and **43**, and the first bump pad **73a** may be commonly electrically connected to the first conductivity type semiconductor layers **23a**, **33a**, and **43a** of the first, second, and third LED stacks **23**, **33**, and **43**.

The bump pads **73a**, **73b**, **73c**, and **73d** may cover the openings **71a** of the upper insulation layer **71**, and portions of the bump pads **73a**, **73b**, **73c**, and **73d** may be disposed on the upper insulation layer **71**. Alternatively, the bump pads **73a**, **73b**, **73c**, and **73d** may be disposed in the openings **71a**, and thus, upper surfaces of the bump pads may be flat.

The bump pads **73a**, **73b**, **73c**, and **73d** may be formed of Au/In. For example, Au may be formed to have a thickness of about 3 μm , and In may be formed to have a thickness of about 1 μm . According to an exemplary embodiment, the light emitting device **100** may be bonded to the pads on the circuit board **101** using In. However, the inventive concepts are not limited thereto, and in some exemplary embodiments, the light emitting device **100** may be bonded to the pads using Pb or AuSn of the bump pads.

According to the illustrated exemplary embodiment, the first LED stack **23** is electrically connected to the bump pads **73a** and **73d**, the second LED stack **33** is electrically connected to the bump pads **73a** and **73c**, and the third LED stack **43** is electrically connected to the bump pads **73a** and **73b**. Accordingly, cathodes of the first LED stack **23**, the second LED stack **33**, and the third LED stack **43** are commonly electrically connected to the first bump pad **73a**, and anodes thereof are electrically connected to the second to fourth bump pads **73b**, **73c**, and **73d**, respectively. Accordingly, the first, second, and third LED stacks **23**, **33**, and **43** may be driven independently.

As described above, the light emitting device **100** according to the illustrated exemplary embodiment includes the bump pads **73a**, **73b**, **73c**, and **73d**, but the inventive concepts are not limited thereto. In some exemplary embodiments, the bump pads may be omitted. In particular, when the light emitting device is bonded to the circuit board using an anisotropic conductive film or anisotropic conductive

paste, the bump pads may be omitted, and upper connectors **67a**, **67b**, **67c**, and **67d** may be directly bonded to the circuit board. As such, a bonding area may be increased.

Hereinafter, a method of manufacturing the light emitting device **100** will be described in detail. A structure of the light emitting device **100** will also be described in more detail through the manufacturing method described below. FIGS. **5A**, **5B**, and **5C** are schematic cross-sectional views of the first, second, and third LED stacks **23**, **33**, and **43** grown on growth substrates, respectively, according to an exemplary embodiment.

First, referring to FIG. **5A**, a first LED stack **23** including a first conductivity type semiconductor layer **23a** and a second conductivity type semiconductor layer **23b** is grown on a first substrate **21**. An active layer may be interposed between the first conductivity type semiconductor layer **23a** and the second conductivity type semiconductor layer **23b**.

The first substrate **21** may be a substrate capable of growing the first LED stack **23** thereon, such as a GaAs substrate. The first conductivity type semiconductor layer **23a** and the second conductivity type semiconductor layer **23b** may be formed of an AlGaInAs-based or AlGaInP-based semiconductor layer, and the active layer may include, for example, an AlGaInP-based well layer. A composition ratio of AlGaInP may be determined so that the first LED stack **23** emits red light, for example.

A first transparent electrode **25** may be formed on the second conductivity type semiconductor layer **23b**. As described above, the first transparent electrode **25** may be formed of a metal layer or a conductive oxide layer that transmits light generated by the first LED stack **23**, for example, red light. The first transparent electrode **25** may be formed of, for example, indium-tin oxide (ITO).

Referring to FIG. **5B**, a second LED stack **33** including a first conductivity type semiconductor layer **33a** and a second conductivity type semiconductor layer **33b** is grown on a second substrate **31**. An active layer may be interposed between the first conductivity type semiconductor layer **33a** and the second conductivity type semiconductor layer **33b**.

The second substrate **31** may be a substrate capable of growing the second LED stack **33** thereon, such as a sapphire substrate, a SiC substrate, or a GaN substrate. In an exemplary embodiment, the second substrate **31** may be a flat sapphire substrate, but may be a patterned sapphire substrate in other exemplar embodiments. The first conductivity type semiconductor layer **33a** and the second conductivity type semiconductor layer **33b** may be formed of an AlGaInN-based semiconductor layer, and the active layer may include, for example, an AlGaInN-based well layer. A composition ratio of AlGaInN may be determined so that the second LED stack **33** emits blue light, for example.

A second transparent electrode **35** may be formed on the second conductivity type semiconductor layer **33b**. As described above, the second transparent electrode **35** may be formed of a metal layer or a conductive oxide layer that transmits light generated by the first LED stack **23**, for example, red light. In particular, the second transparent electrode **35** may be formed of ZnO.

Referring to FIG. **5C**, a third LED stack **43** including a first conductivity type semiconductor layer **43a** and a second conductivity type semiconductor layer **43b** is grown on a third substrate **41**. An active layer may be interposed between the first conductivity type semiconductor layer **43a** and the second conductivity type semiconductor layer **43b**.

The third substrate **41** may be a substrate capable of growing the third LED stack **43** thereon, such as a sapphire substrate, a GaN substrate, or a GaAs substrate. The first

conductivity type semiconductor layer **43a** and the second conductivity type semiconductor layer **43b** may be formed of an AlGaInAs-based or AlGaInP-based semiconductor layer, or an AlGaInN-based semiconductor layer, and the active layer may include, for example, an AlGaInP-based well layer or AlGaInN-based well layer. A composition ratio of AlGaInP or AlGaInN may be determined so that the third LED stack **43** emits green light, for example.

A third transparent electrode **45** may be formed on the second conductivity type semiconductor layer **43b**. As described above, the third transparent electrode **45** may be formed of a metal layer or a conductive oxide layer that transmits light generated in the first and second LED stacks **23** and **33**, for example, red light and blue light. In particular, the third transparent electrode **45** may be formed of ZnO.

The first, second, and third LED stacks **23**, **33**, and **43** are grown on the different growth substrates **21**, **31**, and **41**, respectively. As such, the order of manufacturing the first, second, and third LED stacks **23**, **33**, and **43** is not particularly limited.

Hereinafter, a method of manufacturing the light emitting device **100** using first, second, and third LED stacks **23**, **33**, and **43** grown on growth substrates **21**, **31**, and **41** will be described. Hereinafter, although a region of a single light emitting device **100** will be mainly illustrated and described, a plurality of light emitting devices **100** may be manufactured in a batch in the same manufacturing process using the LED stacks **23**, **33**, and **43** grown on the growth substrates **21**, **31**, and **41**.

FIGS. **6A**, **6B**, **6C**, **7A**, **7B**, **7C**, **8A**, **8B**, **8C**, **9A**, **9B**, **9C**, **10A**, **10B**, **10C**, **11A**, **11B**, **11C**, **12A**, **12B**, **12C**, **13A**, **13B**, **13C**, **14A**, **14B**, **14C**, **15A**, **15B**, **15C**, **16A**, **16B**, and **16C** are schematic plan views and cross-sectional views illustrating a method of manufacturing a light emitting device for a display according to an exemplary embodiment. Lines A-A' and B-B' along which the above cross-sectional views are taken correspond to lines A-A' and B-B' of FIG. **3**.

Referring to FIGS. **6A**, **6B**, and **6C**, the third transparent electrode **45** and the second conductivity type semiconductor layer **43b** of the third LED stack **43** are patterned to expose the first conductivity type semiconductor layer **43a** using photo and etching techniques. This process corresponds to, for example, a mesa etching process. A photoresist pattern may be used as an etching mask. For example, after the etching mask is formed, the third transparent electrode **45** may be etched first by a wet etching technique, and then the second conductivity type semiconductor layer **43b** may be etched by a dry etching technique using the same etching mask. In this manner, the third transparent electrode **45** may be recessed from a mesa etching region. FIG. **6A** exemplarily shows an edge of the mesa and does not show an edge of the third transparent electrode **45** to simplify illustration. However, since the third transparent electrode **45** is wet etched using the same etching mask, the edge of the third transparent electrode **45** may also be recessed from the edge of the mesa toward an inner side of the mesa. Since the same etching mask is used, the number of photo processes may not be increased, thereby reducing the process costs. However, the inventive concepts are not limited thereto, and the etching mask for etching the mesa etching process may be different from the etching mask for etching the third transparent electrode **45**.

Subsequently, a third n-electrode pad **47a** and a lower p-electrode pad **47b** are formed on the first conductivity type semiconductor layer **43a** and the third transparent electrode **45**, respectively. The third n-electrode pad **47a** and the lower p-electrode pad **47b** may be formed to have different thick-

nesses. In particular, an upper surface of the third n-electrode pad **47a** and that of the lower p-electrode pad **47b** may be located at substantially the same elevation.

An isolation region for defining a light emitting device region may be formed. For example, the first conductivity type semiconductor layer **43a** may be removed along the isolation region and an upper surface of the substrate **41** may be exposed.

Further, a lower insulation layer **48** may be formed on the third LED stack **43**. The lower insulation layer **48** may cover the exposed upper surface of the substrate **41** and may cover upper and side surfaces of the third transparent electrode **45** and the third LED stack **43**. Further, openings exposing the third n-electrode pad **47a** and the lower p-electrode pad **47b** may be formed in the lower insulation layer **48**.

Referring to FIGS. **7A**, **7B**, and **7C**, the second LED stack **33** shown in FIG. **5B** is bonded onto the third LED stack **43** described with reference to FIGS. **6A**, **6B**, and **6C**. The second LED stack **33** is bonded to a temporary substrate using a temporary bonding/debonding (TBDB) technique, and the second substrate **31** is removed from the second LED stack **33**. The second substrate **31** may be removed using, for example, a laser lift off technique. After the second substrate **31** is removed, a roughened surface may be formed on a surface of the first conductivity type semiconductor layer **33a**. Thereafter, the first conductivity type semiconductor layer **33a** of the second LED stack **33** bonded to the temporary substrate may be disposed to face the third LED stack **43** and bonded to the third LED stack **43**. The second LED stack **33** and the third LED stack **43** are bonded to each other by a first bonding layer **49**. After bonding the second LED stack **33** to the third LED stack **43**, the temporary substrate may be removed using the laser lift off technique. Accordingly, the second LED stack **33** may be disposed on the third LED stack **43**, in which the second transparent electrode **35** may form an upper surface.

Subsequently, openings **35a** and **35b** may be formed by patterning the second transparent electrode **35**. The opening **35a** is disposed over the third n-electrode pad **47a**, and the opening **35b** is disposed over the lower p-electrode pad **47b**. By forming the openings **35a** and **35b** in advance, the second transparent electrode **35** may be prevented from being exposed when forming the through holes **33h1** and **33h2** in subsequent process.

Referring to FIGS. **8A**, **8B**, and **8C**, a first planarization layer **51** is formed on the second transparent electrode **35**. The first planarization layer **51** may have a substantially flat upper surface, and may function as an insulation layer.

Subsequently, through holes **33h1** and **33h2** passing through the first planarization layer **51**, the second LED stack **33**, and the first bonding layer **49** are formed. The through holes **33h1** and **33h2** are respectively formed within the circumference of the openings **35a** and **35b** of the second transparent electrode **35** in a plan view, and thus, the second transparent electrode **35** is not exposed to sidewalls of the through holes **33h1** and **33h2**. The through holes **33h1** and **33h2** expose the third n-electrode pad **47a** and the lower p-electrode pad **47b**, respectively.

A first sidewall insulation layer **53** is formed. The first sidewall insulation layer **53** may be formed first to cover an upper portion of the first planarization layer **51** and sidewalls and bottom surfaces of the through holes **33h1** and **33h2**. For example, the first sidewall insulation layer **53** may be formed using a chemical vapor deposition technique or an atomic layer deposition technique.

Subsequently, the first sidewall insulation layer **53** is blanket etched using a dry etching technique. As such, the

first sidewall insulation layer **53** formed on the bottom of the through holes **33h1** and **33h2** is removed to expose the third n-electrode pad **47a** and the lower p-electrode pad **47b**. The first sidewall insulation layer **53** formed on the first planarization layer **51** may be completely removed during blanket etching, and a portion of the first planarization layer **51** near inlets of the through holes **33h1** and **33h2** may also be removed. As such, the inlets of the through holes **33h1** and **33h2** may have a wider width than that of the bottom thereof. This will be described in detail later with reference to FIGS. **17A** to **17D**.

Thereafter, lower buried vias **55a** and **55b** filling the through holes **33h1** and **33h2** may be formed using a seed layer and a plating technique. The seed layer and the plating layer formed on the first planarization layer **51** may be removed using a chemical mechanical polishing technique.

Referring to FIGS. **9A**, **9B**, and **9C**, the first planarization layer **51** may be patterned to remove a portion of the first planarization layer **51**, such that the retained first planarization layer **51** has an island shape in a plurality of regions. The first planarization layer **51** may be retained in regions where the lower buried vias **55a** and **55b** are formed, and a portion of the first planarization layer **51** may also be retained in a region where a lower connector **39c** connected to the second transparent electrode layer **35** is to be formed. In this manner, the upper surface of the second transparent electrode **35** is exposed by patterning the first planarization layer **51**.

Referring to FIGS. **10A**, **10B**, and **10C**, the second transparent electrode **35** and the second conductivity type semiconductor layer **33b** are partially removed through mesa etching to expose the first conductivity type semiconductor layer **33a**. The second transparent electrode **35** and the second conductivity type semiconductor layer **33b** may be patterned by using photo and etching techniques. This process may be performed using the wet etching and the dry etching techniques in substantially the same manner as the mesa etching process, during which the third transparent electrode **45** and the second conductivity type semiconductor layer **43b** are etched as described above.

For example, after the etching mask is formed, the second transparent electrode may be etched first by the wet etching technique, and then the second conductivity type semiconductor layer **33b** may be etched by the dry etching technique using the same etching mask. Accordingly, the second transparent electrode **35** may be recessed from the mesa etching region. FIG. **11A** exemplarily shows an edge of the mesa, and does not show an edge of the second transparent electrode **35** to simplify illustration. However, since the second transparent electrode **35** is wet etched using the same etching mask, the edge of the second transparent electrode **35** may also be recessed from the edge of the mesa toward an inner side of the mesa. In this manner, since the same etching mask is used, the number of photo processes may not be increased, thereby reducing the process costs. However, the inventive concepts are not limited thereto, and in some exemplary embodiments, the etching mask for etching the mesa etching process and the etching mask for etching the second transparent electrode **35** may be different from each other.

The mesa etching region of the second LED stack **33** may be partially overlapped with that of the third LED stack **43**, but the mesa etching regions of the second LED stack **33** and the third LED stack **43** are generally separated from each other. In particular, a portion of the mesa etching region of the second LED stack **33** may be spaced apart from the third n-electrode pad **47a** and the lower p-electrode pad **47b** in the

lateral direction. A second n-electrode pad **37a** may be formed on the first conductivity type semiconductor layer **33a** exposed by mesa etching.

An intermediate insulation layer **58** may be formed on the second LED stack **33**. The intermediate insulation layer **58** may cover a portion of the first conductivity type semiconductor layer **33a** exposed by mesa etching. The intermediate insulation layer **58** may also cover the second conductivity type semiconductor layer **33b**, the second transparent electrode **35**, the first planarization layer **51**, and the second n-electrode pad **37a**. The intermediate insulation layer **58** may have openings **58a** and **58b** exposing the lower buried vias **55a** and **55b**, and also have an opening **58d** exposing the second n-electrode pad **37a**. In addition, the intermediate insulation layer **58** may have an opening **58c** exposing the first planarization layer **51** disposed apart from the lower buried vias **55a** and **55b** and a surrounding region thereof.

Referring to FIGS. **11A**, **11B**, and **11C**, lower connectors **39a**, **39b**, and **39c** are formed on the first planarization layer **51**. The first lower connector **39a** may be electrically connected to the lower buried via **55a** and also extend in the lateral direction to be electrically connected to the second n-electrode pad **37a**. The first lower connector **39a** may be insulated from the second transparent electrode **35** and the second conductivity type semiconductor layer **33b** by the intermediate insulation layer **58**.

Referring to FIGS. **12A**, **12B**, and **12C**, an isolation region for defining a light emitting device region may be formed. For example, the first conductivity type semiconductor layer **33a** may be removed along the isolation region, and an upper surface of the first bonding layer **49** may be exposed. In some exemplary embodiments, an insulation layer covering a side surface of the first conductivity type semiconductor layer **33a** may be added in addition to the intermediate insulation layer **58**. This insulation layer may be formed to have openings exposing the lower connectors **39a**, **39b**, and **39c**.

Referring to FIGS. **13A**, **13B**, and **13C**, the first LED stack **23** described with FIG. **5A** is bonded to the second LED stack **33**. The first LED stack **23** and the second LED stack **33** may be bonded using a second bonding layer **59**, so that the first transparent electrode **25** faces the second LED stack **33**. Accordingly, the second bonding layer **59** is in contact with the first transparent electrode **25**, and is also in contact with the intermediate insulation layer **58**, and the lower connectors **39a**, **39b**, and **39c**.

A first substrate **21** is removed from the first LED stack **23**. The first substrate **21** may be removed using, for example, an etching technique. After the first substrate **21** is removed, a first n-electrode pad **27a** may be formed on a portion of a region of the first conductivity type semiconductor layer **23a**. The first n-electrode pad **27a** may be formed to be in ohmic contact with the first conductivity type semiconductor layer **23a**.

Referring to FIGS. **14A**, **14B**, and **14C**, a second planarization layer **61** covering the first LED stack **23** and the first n-electrode pad **27a** is formed. The second planarization layer **61** is formed to have a substantially flat upper surface.

Subsequently, through holes **23h1**, **23h2**, **23h3**, and **23h4** passing through the second planarization layer **61** and the first LED stack **23** are formed. The through holes **23h1**, **23h2**, and **23h3** may pass through the first transparent electrode **25** and the second bonding layer **59** to expose the lower connectors **39a**, **39b**, and **39c**, respectively. The through hole **23h4** may expose the first transparent electrode **25**.

The through holes **23h1**, **23h2**, and **23h3** may be formed together through the same process, and the through hole **23h4** may be formed through a process different from that of forming the through holes **23h1**, **23h2**, and **23h3**.

Subsequently, a second sidewall insulation layer **63** and upper buried vias **65a**, **65b**, **65c**, and **65d** are formed. Since a process of forming the second sidewall insulation layer **63** and the upper buried vias **65a**, **65b**, **65c**, and **65d** is substantially similar to that of forming the first sidewall insulation layer **53** and the lower buried vias **55a** and **55b**, repeated descriptions thereof will be omitted.

Referring to FIGS. **15A**, **15B**, and **15C**, an opening **61a** exposing the first n-electrode pad **27a** is formed by patterning the second planarization layer **61**. The second planarization layer **61** may be patterned using photo and etching techniques.

Subsequently, upper connectors **67a**, **67b**, **67c**, and **67d** are formed. The upper connectors **67a**, **67b**, **67c**, and **67d** may include a reflective metal layer, and thus, light generated in the first LED stack **23** may be reflected to improve light extraction efficiency. For example, the upper connectors **67a**, **67b**, **67c**, and **67d** may include Au or an Au alloy.

The upper connector **67a** may electrically connect the upper buried via **65a** to the first n-electrode pad **27a**. The upper connectors **67b**, **67c**, and **67d** may be connected to the upper buried vias **65b**, **65c**, and **65d**, respectively.

Referring to FIGS. **16A**, **16B**, and **16C**, the second planarization layer **61**, the first LED stack **23**, and the first transparent electrode **25** may be etched along the isolation region. For example, the second planarization layer **61** may be patterned in advance, and then, the first LED stack **23** and the first transparent electrode **25** may be patterned to divide the light emitting device regions. The second planarization layer **61** may be patterned in advance along the isolation region when forming the opening **61a**. As such, an upper surface of the second bonding layer **59** may be exposed.

Thereafter, an upper insulation layer **71** is formed. The upper insulation layer **71** may cover the first transparent electrode **25**, the first LED stack **23**, the second planarization layer **61**, and further, cover the upper connectors **67a**, **67b**, **67c**, and **67d**. Moreover, the upper insulation layer **71** may be patterned to have openings **71a** exposing the upper connectors **67a**, **67b**, **67c**, and **67d**.

Subsequently, bump pads **73a**, **73b**, **73c**, and **73d** covering the openings **71a** may be formed. The first bump pad **73a** is disposed on the first upper connector **67a**, the second bump pad **73b** is disposed on the second upper connector **67b**, and the third bump pad **73c** is disposed on the third upper connector **67c**. The fourth bump pad **73d** is disposed on the fourth upper connector **67d**.

Thereafter, a plurality of light emitting devices **100** separated from one another is formed on the substrate **41** by removing the first and second bonding layers **49** and **59** along the isolation region, and the light emitting device **100** separated from the substrate **41** is provided by bonding the light emitting device **100** onto a circuit board **101** and separating the substrate **41**. A schematic cross-sectional view of the light emitting device **100** bonded to the circuit board **101** is exemplarily shown in FIG. **28**, which will be described in detail later.

The light emitting device **100** according to an exemplary embodiment achieve electrical connection using buried vias **55a**, **55b**, **65a**, **65b**, **65c**, and **65d**. Hereinafter, a process of forming the buried vias will be described in more detail.

FIGS. **17A**, **17B**, **17C**, and **17D** are schematic cross-sectional views illustrating a process of forming a buried via according to exemplary embodiments.

First, referring to FIG. 17A, a planarization layer 51 or 61 is formed on an underlying layer S. The underlying layer S may include a first LED stack 23 or a second LED stack 33. A hard mask defining an etching region is formed by patterning the planarization layer 51 or 61, and a through hole H may be formed using the hard mask as an etching mask. The through hole H may expose an element for electrical connection, for example, the third n-electrode pad 47a, the lower p-electrode pad 47b, or the lower connectors 39a, 39b, and 39c.

Referring to FIG. 17B, subsequently, a sidewall insulation layer 53 or 63 is formed. The sidewall insulation layer 53 or 63 may be formed on an upper surface of the planarization layer 51 or 61, and further, may be formed on a sidewall and a bottom of the through hole H. The sidewall insulation layer 53 or 63 may be formed thicker at an inlet than at the bottom of the through hole H due to characteristics of layer coverage.

Referring to FIG. 17C, the sidewall insulation layer 53 or 63 is blanket etched using a dry etching technique. The sidewall insulation layer disposed on the bottom of the through hole H is removed by blanket etching, and the sidewall insulation layer disposed on the upper surface of the planarization layer 51 or 61 is also removed. Further, a portion of the planarization layer 51 or 61 near the inlet of the through hole H may also be removed. As such, a width W2 of the inlet may be greater than a width W1 of the through hole H. Since the width W2 of the inlet is increased, the subsequent process of forming a buried via using a plating technology may be facilitated.

Referring to FIG. 17D, a seed layer may be formed in the planarization layer 51 or 61 and the through hole H, and a plating layer filling the through hole H may be formed using a plating technique. Subsequently, by removing the plating layer and the seed layer on the planarization layer 51 or 61 using a chemical etching technique, a buried via 55 or 65 as shown in FIG. 17D may be formed.

FIG. 18 is a SEM image illustrating a via buried in a contact hole. FIG. 18 shows an image, after the through hole H was formed and then the buried via was formed as described with reference to FIGS. 17A to 17D, but before the plating layer on the upper surface of the planarization layer is removed using a chemical mechanical polishing technique.

Referring to FIG. 18, it can be seen that the through hole is well buried by the plating layer. Further, it can be seen that the width W2 of the inlet of the through hole is wider than the width W1 of the through hole, and it can also be seen that a thickness of the sidewall insulation layer becomes thinner as being closer to the bottom of the through hole.

FIG. 19 is a SEM image illustrating a buried via formed using a chemical mechanical polishing technique. FIG. 19 shows a shape of the buried via after removing the seed layer and the plating layer using the chemical mechanical polishing technique, after forming a hole in a silicon substrate, depositing the sidewall insulation layer, and forming the seed layer and the plating layer. In this case, the buried via was formed without blanket etching the sidewall insulation layer.

Referring to FIG. 19, it can be seen that an upper surface of the buried via is flush with an upper surface of the sidewall insulation layer surrounding the buried via, and thus, the buried via may be formed in the through hole using the chemical mechanical polishing technique.

FIG. 20 is a schematic plan view illustrating a light emitting device 200 according to another exemplary

embodiment, and FIGS. 21A and 21B are schematic cross-sectional views taken along lines C-C' and D-D' of FIG. 20, respectively.

Referring to FIGS. 20, 21A, and 21B, the light emitting device 200 according to the illustrated exemplary embodiment is substantially similar to the light emitting device 100 described above, except that a first planarization layer 151 is formed continuously, unlike the first planarization layer 51 of the light emitting device 100 that is divided in to multiple regions to have an island shape. As such, the second LED stack 33 does not have a mesa etching region exposing the first conductivity type semiconductor layer 33a, and the second n-electrode pad 37a shown in FIG. 4B that is in ohmic contact with the first conductivity type semiconductor layer 33a is omitted.

A through hole 33h3 exposing the first conductivity type semiconductor layer 33a is formed passing through the first planarization layer 151 and the second conductivity type semiconductor layer 33b, and the lower buried via 55c fills the through hole 33h3. The lower connector 39a commonly electrically connects the first conductivity type semiconductor layers 33a and 43a by electrically connecting the lower buried via 55a and the lower buried via 55c.

The second transparent electrode 35 may be patterned in advance so as not to be exposed to the sidewalls of the through holes 33h1, 33h2, and 33h3 while covering the upper surface of the second conductivity type semiconductor layer 33b. For example, the second transparent electrode 35 may be patterned to have openings in regions where the through holes 33h1, 33h2, and 33h3 are to be formed before forming the first planarization layer 151.

In the illustrated exemplary embodiment, the upper p-electrode pad 37b may be disposed on the second transparent electrode 35, and the lower connector 39c may be electrically connected to the upper p-electrode pad 37b. The first planarization layer 151 may have an opening exposing the upper p-electrode pad 37b to allow electrical connection of the lower connector 39c.

In the illustrated exemplary embodiment, the intermediate insulation layer 58 is omitted, but the inventive concepts are not limited thereto. For example, in some exemplary embodiments, an intermediate insulation layer covering the second LED stack 33, the first planarization layer 151, and the lower connectors 39a, 39b, and 39c may be added. The intermediate insulation layer may have openings exposing the lower connectors 39a, 39b, and 39c to allow electrical connection of the upper buried vias 65a, 65b, and 65c.

According to the illustrated exemplary embodiment, the lower connector 39a may be formed on a flat surface of the first planarization layer 151 by continuously forming the first planarization layer 151 and forming the lower buried via 55c.

FIGS. 22A, 22B, 22C, 23A, 23B, 23C, 24A, 24B, 24C, 25A, 25B, 25C, 26A, 26B, 26C, 27A, 27B, and 27C are schematic plan views and cross-sectional views illustrating a method of manufacturing a light emitting device for a display according to another exemplary embodiment. Lines C-C' and D-D' along which the cross-sectional views are taken correspond to lines C-C' and D-D' of FIG. 20.

First, as described above with reference to FIGS. 5A, 5B, and 5C, a first LED stack 23, a second LED stack 33, and a third LED stack 43 are grown on substrates 21, 31 and 41, respectively, and transparent electrodes 25, 35 and 45 are formed.

Subsequently, referring to FIGS. 22A, 22B, and 22C, as described above with reference to FIGS. 6A, 6B, and 6C, a first conductivity type semiconductor layer 43a is exposed

through a mesa etching process, and a third n-electrode pad **47a** and a lower p-electrode pad **47b** are formed on the first conductivity type semiconductor layer **43a** and a third transparent electrode **45**, respectively. In addition, an isolation region for defining a light emitting device region may be formed, and a lower insulation layer **48** may be formed.

Referring to FIGS. **23A**, **23B**, and **23C**, as described above with reference to FIGS. **6A**, **6B**, and **6C**, first, the second LED stack **33** described with reference to FIG. **5B** is bonded on the third LED stack **43**.

Subsequently, openings **35a**, **35b**, and **35c** exposing the second conductivity type semiconductor layer **33b** may be formed by patterning a second transparent electrode **35**. The opening **35a** is disposed over the third n-electrode pad **47a**, and the opening **35b** is disposed over the lower p-electrode pad **47b**. In the illustrated exemplary embodiment, a mesa etching process for exposing the first conductivity type semiconductor layer **33a** is omitted. However, an opening **35c** is added in the upper region where the second n-electrode pad **37a** is formed in FIG. **10C**. In addition, the second transparent electrode **35** may be removed in advance along the isolation region and may be separated in units of the light emitting device **200** region.

Further, an upper p-electrode pad **37b** is formed on the second transparent electrode **35**. The upper p-electrode pad **37b** may be in ohmic contact with the second transparent electrode **35**. In another exemplary embodiment, the upper p-electrode pad **37b** may be omitted.

Referring to FIGS. **24A**, **24B**, and **24C**, a first planarization layer **151** covering the second transparent electrode **35** is formed. The first planarization layer **151** covers an upper p-electrode pad **27b** and covers the openings **35a**, **35b**, and **35c**.

Subsequently, through holes **33h1** and **33h2** passing through the first planarization layer **151**, the second LED stack **33**, and the first bonding layer **49**, and a through hole **33h3** passing through the first planarization layer **151** and the second conductivity type semiconductor layer **33b** to expose the first conductivity type semiconductor layer **33a** are formed. The through holes **33h1** and **33h2** are respectively formed within the circumference of the openings **35a** and **35b** of the second transparent electrode **35** in a plan view, and the through hole **33h3** is formed with the circumference of the opening **35c** of the second transparent electrode **35** in a plan view.

Thereafter, a first sidewall insulation layer **53** and lower buried vias **55a**, **55b**, and **55c** may be formed. The lower buried vias **55a** and **55b** are substantially the same as those described with reference to FIGS. **8A**, **8B**, and **8C**, and thus, repeated descriptions thereof will be omitted. Meanwhile, the lower buried via **55c** is electrically connected to the first conductivity type semiconductor layer **33a**.

Referring to FIGS. **25A**, **25B**, and **25C**, lower connectors **39a**, **39b**, and **39c** are formed on the first planarization layer **151**. The first lower connector **39a** may be electrically connected to the lower buried via **55a** and extend in the lateral direction to be also electrically connected to the lower buried via **55c**. The first lower connector **39a** may be insulated from the second transparent electrode **35** and the second conductivity type semiconductor layer **33b** by the first planarization layer **151**.

In the illustrated exemplary embodiment, the third lower connector **39c** may be electrically connected to the upper p-electrode pad **37b** exposed through an opening of the first planarization layer **151**. The first planarization layer **151** may be patterned in advance to expose the upper p-electrode pad **37b**. When the upper p-electrode pad **37b** is omitted in

other exemplary embodiments, the third lower connector **39c** may be directly connected to the second transparent electrode **35**.

The first planarization layer **151** may also be removed along the isolation region, and thus, the second conductivity type semiconductor layer **33b** may be exposed as shown in FIGS. **25B** and **25C**.

Referring to FIGS. **26A**, **26B**, and **26C**, an isolation region for defining a light emitting device region may be formed. For example, the second conductivity type semiconductor layer **33b** and the first conductivity type semiconductor layer **33a** may be removed along the isolation region, and an upper surface of the first bonding layer **49** may be exposed. In some exemplary embodiments, an insulation layer covering the second LED stack **33**, the first planarization layer **151**, and the lower connectors **39a**, **39b**, and **39c** may be added. This insulation layer may be formed to have openings exposing the lower connectors **39a**, **39b**, and **39c**.

Referring to FIGS. **27A**, **27B**, and **27C**, the first LED stack **23** described in FIG. **5A** is bonded to the second LED stack **33**, and through the same process as described with reference to FIGS. **13A**, **13B**, **13C**, **14A**, **14B**, **14C**, **15A**, **15B**, **15C**, **16A**, **16B**, and **16C**, a first n-electrode pad **27a**, a second planarization layer **61**, upper buried vias **65a**, **65b**, **65c**, and **65d**, upper connectors **67a**, **67b**, **67c**, and **67d**, an upper insulation layer **71**, and bump pads **73a**, **73b**, **73c**, and **73d** are formed. Since these processes are substantially the same as those described above with reference to FIGS. **13A** to **16C**, repeated description thereof will be omitted.

Subsequently, a plurality of light emitting devices **200** separated from one another is formed on a substrate **41** by removing the first and second bonding layers **49** and **59** along the isolation region, and the light emitting device **200** separated from the substrate **41** is provided by bonding the light emitting device **100** onto a circuit board **101** and separating the substrate **41**.

Although FIG. **28** exemplarily illustrates a single light emitting device **100** disposed on the circuit board **101**, however, a plurality of light emitting devices **100** may be mounted on the circuit board **101**. Each of the light emitting devices **100** may form one pixel capable of emitting any one of blue light, green light, and red light, and a plurality of pixels is arranged on the circuit board **101** to provide a display panel. FIG. **28** exemplarily illustrates the light emitting device **100**, but the light emitting device **200** may be disposed in other exemplary embodiments.

The plurality of light emitting devices **100** may be formed on the substrate **41**, and the light emitting devices **100** may be transferred onto the circuit board **101** in a group, rather than individually. FIGS. **29A**, **29B**, and **29C** are schematic cross-sectional views illustrating a method of transferring the light emitting device to the circuit board according to an exemplary embodiment. Hereinafter, a method of transferring the light emitting devices **100** or **200** formed on the substrate **41** to the circuit board **101** in a group will be described.

Referring to FIG. **29A**, as described in FIGS. **16A**, **16B**, and **16C**, when the manufacturing process of the light emitting device **100** on the substrate **41** is completed, the plurality of light emitting devices **100** is isolated from each other, and arranged on the substrate **41** by an isolation trench.

The circuit board **101** having pads on an upper surface thereof is provided. The pads are arranged on the circuit board **101** to correspond to locations where the pixels for a display are to be arranged. In general, an interval between

the light emitting devices **100** arranged on the substrate **41** may be denser than that of the pixels on the circuit board **101**.

Referring to FIG. **29B**, bump pads of the light emitting devices **100** are selectively bonded to the pads of the circuit board **101**. The bump pads and the pads may be bonded using solder bonding or In bonding, for example. In this case, the light emitting devices **100** located between pixel regions may be spaced apart from the circuit board **101**, since these light emitting devices **100** do not have pads of the circuit board **101** to be bonded to.

Subsequently, the substrate **41** is irradiated with a laser. The laser is selectively irradiated onto the light emitting devices **100** bonded to the pads. To this end, a mask having openings for selectively exposing the light emitting devices **100** may be formed on the substrate **41**.

Thereafter, the light emitting devices **100** are transferred to the circuit board **101** by separating the light emitting devices **100** irradiated with the laser from the substrate **41**. Accordingly, as shown in FIG. **29C**, the display panel in which the light emitting devices **100** are arranged on the circuit board **101** is provided. The display panel may be mounted on various display apparatuses as described with reference to FIG. **1**.

FIG. **30** is a schematic cross-sectional view illustrating a method of transferring a light emitting device according to another exemplary embodiment.

Referring to FIG. **30**, light emitting devices according to the illustrated exemplary embodiment are bonded to pads using an anisotropic conductive adhesive film or an anisotropic conductive adhesive paste. In particular, an anisotropic conductive adhesive film or adhesive paste **121** may be provided on the pads, and the light emitting devices **100** may be adhered to the pads through the anisotropic conductive adhesive film or adhesive paste **121**. The light emitting devices **100** are electrically connected to the pads by the anisotropic conductive adhesive film or a conductive material in the adhesive paste **121**.

In the illustrated exemplary embodiment, bump pads **73a**, **73b**, **73c**, and **73d** may be omitted, and upper connectors **67a**, **67b**, **67c**, and **67d** may be electrically connected to the pads through a conductive material.

According to exemplary embodiments, the first, second, and third LED stacks are stacked one above another, and thus, the light emitting device may have an increased luminous area of each sub-pixel without increasing a pixel area. Furthermore, since the widths of the upper ends of the buried vias are increased, electrical connection of the buried vias may be facilitated.

The light emitting device according to exemplary embodiments may further include lower connectors covering the lower buried vias, in which portions of the upper buried vias may be connected to the lower connectors. The lower connectors may enhance electrical connection of the upper buried vias, and reliability of a process of forming the upper buried vias may be improved.

According to exemplary embodiments, the lower buried vias and portions of the upper buried vias are overlapped, which may reduce light loss due to the buried vias.

Although certain exemplary embodiments and implementations have been described herein, other embodiments and modifications will be apparent from this description. Accordingly, the inventive concepts are not limited to such embodiments, but rather to the broader scope of the appended claims and various obvious modifications and equivalent arrangements as would be apparent to a person of ordinary skill in the art.

What is claimed is:

1. A light emitting module, comprising:
 - a circuit board; and
 - a light emitter disposed on the circuit board, the light emitter comprising:
 - a first LED stack, a second LED stack disposed on the first LED stack, and a third LED stack disposed on the second LED stack;
 - an upper planarization layer covering an upper surface of the third LED stack;
 - an upper connector disposed on the third LED stack;
 - an upper conductive material disposed on the third LED stack and electrically connected to the upper connector; and
 - an insulator covering the upper planarization layer, wherein the upper conductive material includes a first region having a first width, and includes a second region having a second width greater than the first width, wherein the first region is located closer to the third LED stack than the second region is located to the third LED stack, and wherein the upper conductive material includes a convex shape.
2. The light emitting module according to claim 1, wherein the upper conductive material includes a third region having a third width, and wherein the second width is greater than the third width.
3. The light emitting module according to claim 2, wherein the second region is positioned between the first region and the third region.
4. The light emitting module according to claim 1, wherein an upper end of the upper conductive material faces the circuit board.
5. The light emitting module according to claim 1, wherein the first LED stack is a first conductivity type semiconductor layer and the second LED stack is a second conductivity type semiconductor layer.
6. The light emitting module according to claim 1, wherein the insulator covers side surfaces of each of the first LED stack, the second LED stack and the third LED stack.
7. The light emitting module according to claim 1, wherein at least one surface of the light emitting device is formed with irregularities.
8. A light emitting module, comprising:
 - a circuit board; and
 - a light emitter disposed on the circuit board, the light emitter comprising:
 - a first LED stack, a second LED stack disposed on the first LED stack, and a third LED stack disposed on the second LED stack;
 - an upper planarization layer covering an upper surface of the third LED stack;
 - an upper connector disposed on the third LED stack;
 - an upper conductive material disposed on the third LED stack and electrically connected to the upper connector; and
 - an insulator covering the upper planarization layer, wherein the upper conductive material has at least a first region and a second region, the first region and the second region having different widths, and wherein a width of the upper conductive material is continuously non-planar from a first end of the upper conductive material to a second end of the upper conductive material opposite the first end.

29

9. The light emitting module according to claim 8, wherein an upper end of the upper conductive material faces the circuit board.

10. The light emitting module according to claim 8, wherein the first LED stack is a first conductivity type semiconductor layer and the second LED stack is a second conductivity type semiconductor layer.

11. The light emitting module according to claim 8, wherein the insulator covers side surfaces of each of the first LED stack, the second LED stack and the third LED stack.

12. The light emitting module according to claim 8, wherein at least one surface of the light emitting device is formed with irregularities.

13. A light emitting module, comprising:

a circuit board; and

a light emitter disposed on the circuit board, the light emitter comprising:

a first LED stack, a second LED layer stack disposed on the first LED stack, and a third LED stack disposed on the second LED stack;

an upper planarization layer covering an upper surface of the third LED stack;

an upper connector disposed on the third LED stack;

30

an upper conductive material disposed on the third LED stack and electrically connected to the upper connector; and

an insulator covering the upper planarization layer, wherein an upper region of the upper conductive material has an inclined surface, and

wherein the upper conductive material includes a convex shape.

14. The light emitting module according to claim 13, wherein the inclined surface forms a non-zero angle with respect to the third LED stack.

15. The light emitting module according to claim 13, wherein an upper end of the upper conductive material faces the circuit board.

16. The light emitting module according to claim 13, wherein the first LED stack is a first conductivity type semiconductor layer and the second LED stack is a second conductivity type semiconductor layer.

17. The light emitting module according to claim 13, wherein the insulator covers side surfaces of each of the first LED stack, the second LED stack and the third LED stack.

* * * * *