

(19)



(11)

EP 3 381 678 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:

14.08.2024 Bulletin 2024/33

(51) International Patent Classification (IPC):

B32B 15/09 ^(2006.01) **B32B 15/20** ^(2006.01)
B32B 37/10 ^(2006.01) **B32B 37/12** ^(2006.01)
H01K 1/02 ^(2006.01)

(21) Application number: **18164741.3**

(52) Cooperative Patent Classification (CPC):

B32B 7/12; B32B 15/06; B32B 15/08;
B32B 15/082; B32B 15/085; B32B 15/088;
B32B 15/09; B32B 15/092; B32B 15/095;
B32B 15/098; B32B 15/20; B32B 25/04;
B32B 25/14; B32B 25/16; B32B 25/20; (Cont.)

(22) Date of filing: **28.03.2018**

(54) LAMINATED BODY AND METHOD OF PRODUCING SHAPED ARTICLE

LAMINIERTER KÖRPER UND VERFAHREN ZUR HERSTELLUNG EINES GEFORMTEN ARTIKELS
 CORPS STRATIFIÉ ET PROCÉDÉ DE PRODUCTION D'ARTICLE FORMÉ

(84) Designated Contracting States:

AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR

(56) References cited:

EP-A1- 2 581 220 US-A- 5 573 857

- **DATABASE WPI Week 201663, Derwent World Patents Index; AN 2016-56925X, XP002782692**

(30) Priority: **31.03.2017 JP 2017070415**

(43) Date of publication of application:

03.10.2018 Bulletin 2018/40

(73) Proprietor: **JX Advanced Metals Corporation**

Tokyo 105-8417 (JP)

(72) Inventor: **TANAKA, Koichiro**

Hitachi-shi, Ibaraki 317-0056 (JP)

(74) Representative: **Mewburn Ellis LLP**

Aurora Building
Counterslip
Bristol BS1 6BX (GB)

EP 3 381 678 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

(52) Cooperative Patent Classification (CPC): (Cont.)

B32B 27/06; B32B 27/16; B32B 27/281;
B32B 27/283; B32B 27/302; B32B 27/304;
B32B 27/306; B32B 27/308; B32B 27/32;
B32B 27/34; B32B 27/36; B32B 27/365;
B32B 27/38; B32B 27/40; B32B 27/42;
B32B 38/12; H05K 9/0084; B32B 2250/03;
B32B 2250/40; B32B 2250/42; B32B 2255/06;
B32B 2255/10; B32B 2255/205; B32B 2255/26;
B32B 2262/0269; B32B 2262/101; B32B 2262/106;
B32B 2307/202; B32B 2307/204; B32B 2307/208;
B32B 2307/212; B32B 2307/306; B32B 2307/50;

B32B 2307/54; B32B 2307/712; B32B 2307/732;
B32B 2307/748; B32B 2307/752; B32B 2309/105;
B32B 2367/00; B32B 2457/00; B32B 2605/00

Description

TECHNICAL FIELD

5 **[0001]** The present invention relates to a laminated body of at least one metal foil and resin layers, which is suitable for drawing. The present invention also relates to a method of producing a shaped article using the laminated body.

BACKGROUND ART

10 **[0002]** Recently, high attention has been widely focused on global environmental issues, and environmentally-friendly motor vehicles equipped with secondary batteries such as electric vehicles and hybrid vehicles have progressively prevailed. These motor vehicles often employ a mode of converting direct current generated from the mounted secondary battery into alternating current through an inverter, and then supplying required electric power to the alternating current motor to provide driving force. Electromagnetic waves are generated due to switching operation of the inverter and the like. The electromagnetic waves are emitted not only from the motor vehicles but also from many electric and electronic devices including communication devices, displays and medical devices.

15 **[0003]** The electromagnetic waves may cause erroneous operation of precision devices, and cause radio disturbance of on-board audio equipment, radio equipment and the like. An adverse effect on a human body is further concerned. Therefore, countermeasures have been taken to cover the electric/electronic devices such as inverters with an electromagnetic wave shielding material formed by press-forming a metal sheet (for example, Japanese Patent Application Publication No. 2003-285002 A).

20 **[0004]** Weight reduction is required for many electric and electronic devices, which is also required for electromagnetic wave shielding materials. It is desired to reduce the thickness of the metal sheet for the weight reduction. However, if the thickness of the metal sheet is reduced, then ductility will be decreased, which cause a problem that the metal sheet is broken during a molding process. Therefore, there has been proposed a technique for improving an electromagnetic wave shielding property, a weight reduction property and formability by alternately laminating metal foils and resin layers

25 **[0005]** Drawing is known for a method of molding a laminated body of a metal foil and a resin layer. The drawing is a working method of forming bottomed containers having various shapes such as cylinders, square tubes, cones, and the like from a single metal sheet, which is said to be the highest degree of difficulty among press forming processes. Referring to FIG. 1, molds called a punch 10, a die 12 and a blank holder 14 are used for the drawing. The punch 10 is lowered in a state where a blank (a molding material) 16 is sandwiched between the plane surface of the die and the surface of the blank holder while applying predetermined force (blank holding force) to press the blank 16 into a die hole 18, so that the blank 16 is molded into a bottomed shape.

30 **[0006]** In the drawing, a certain area of the molding material is extended, as well as the molding material is molded by inflow of the molding material from the periphery of the die hole. The bottom surface of the container has a smaller strain because the bottom surface of the container is restrained by being brought into close contact with the punch, and the molding material flows in an upper portion of the side wall of the container, so that the plate thickness of the upper portion increases. Although the plate thickness decreases in a lower portion of the side wall because tensile strain is applied, the decrease in the plate thickness is smaller than that of stretch forming. Further, if the material is thin at the inflow portion, the portion will buckle to form wrinkles. In order to prevent this, the blank holding force must be increased. The increasing of the blank holding force results in increased friction between the mold and the molding material, increased resistance to material inflow, and easy breakage. Accordingly, there has been a problem that for a thinner molding material, particularly a molding material having a thickness of 500 μm or less, wrinkles are generated in the side wall of the container when the blank holding force is small, whereas the molding material is broken when the blank holding force is large. Therefore, there has been no choice but to increase the plate thickness.

35 **[0007]** To solve this problem, a technique of improving drawability has been proposed. In the technique, the drawability is improved by laminating a metal foil and a resin layer to increase the strength of a material while making the metal foil itself thin, and at the same time adjusting a dynamic friction coefficient of the resin layer. For example, Japanese Patent No. 4580079 B discloses that fine irregularity having a height of 0.1 to 25 μm is provided on a surface of an unstretched thermoplastic resin film, thereby lowering the dynamic friction coefficient and increasing a height limit during deep drawing. Further, Japanese Patent No. 5474678 B proposes that a thermal bonding polyolefin resin layer is formed on a first surface of a stainless steel foil and a urethane resin layer containing polyethylene-fluorine resin particles is formed on a second surface of the stainless steel foil. The polyethylene-fluoro resin particles are dispersed in the urethane resin layer to provide a dynamic friction coefficient of 0.2 or less on the surface, thereby imparting lubricity and improving the drawability.

CITATION LIST

Patent Literatures

5 **[0008]**

Patent Document 1: Japanese Patent Application Publication No. 2003-285002 A

Patent Document 2: Japanese Patent Application Publication No. 2017-5214 A

Patent Document 3: Japanese Patent No. 4580079 B

10 Patent Document 4: Japanese Patent No. 5474678 B

[0009] EP 2581220 A1 proposes a copper foil complex.

[0010] US 5573857 proposes a shielding tape.

[0011] WO 2016140244 proposes a method for manufacturing a shielding tape.

15

SUMMARY OF INVENTION

Technical Problem

20 **[0012]** The use of the laminated body of the metal foil and the resin layer as an electromagnetic wave shielding material is useful in terms of weight reduction. However, there would be a need for a thinner metal foil in order to achieve further weight reduction. Particularly, the drawing of a thinner metal foil into a complicated shape cannot cope with only by adjusting the dynamic friction force conventionally proposed, and there would be a need for further technical improvement. The present invention has been made in view of the above circumstances. An object of the present invention is to provide

25 a laminated body of at least one metal foil and resin layers, which is suitable for drawing. Another object of the present invention is to provide a method of producing a shaped article using such a laminated body, more particularly a drawn article.

Solution to Problem

30

[0013] When a tensile stress is applied to a single metal foil, the entire metal foil is not uniformly deformed but is locally deformed. The stress concentrates on the local deformed portion and results in breakage, so that the ductility is not high. On the other hand, the resin layer tends to be uniformly deformed as a whole, so that it has higher ductility than that of the metal foil. When the metal foil and the resin layer are laminated in close contact with each other, the resin

35 layer supports the metal foil, so that the metal foil is also uniformly deformed, the ductility is improved and the breakage during molding is suppressed. The ductility is further improved by supporting both surfaces of the metal foil by the resin layers, as compared with the supporting of only one surface of the metal foil by the resin layer.

[0014] Further, in the drawing, whether or not molding is possible is determined by a balance between the inflow resistance of the molding material and the strength of the molding material to be brought into contact with shoulder portion of the punch. The inflow resistance is determined by the blank holding force and some properties (strength, dynamic friction coefficient of the surface, r value) of the molding material. As described above, for the thinner molding material, the blank holding force should be increased in order to suppress the generation of wrinkles, so that the inflow resistance exceeds the strength of the molding material to be brought into contact with the shoulders of the punch, and as a result, the molding material is often broken at the shoulders of the punch. However, if the blank holding force is

45 decreased, the wrinkles are generated, so that a shaped article with good appearance cannot be obtained.

[0015] Because of these problems, the thinner metal foil could not be molded by the drawing. However, as a result of extensive studies, the present inventor has found that a laminated body in which at least one metal foil and resin layers are laminated can achieve both of lower inflow resistance and higher strength when 5% strain stress of the laminated body and tensile strength of the metal foil in the laminated body satisfy a predetermined relationship, and can have improved drawability. The present invention has been completed on the basis of the findings.

50

[0016] Thus, in one aspect, the present invention provides a laminated body as set forth in claim 1.

[0017] In one embodiment of the laminated body according to the present invention, the laminated body has an r value (Lankford value) at a logarithmic strain of 0.4 of from 0.7 to 4.0.

[0018] In another embodiment of the laminated body according to the present invention, the surfaces of the resin layers forming both outermost layers comprise a dynamic friction coefficient of from 0.15 to 0.45.

55

[0019] In yet another embodiment of the laminated body according to the present invention, both sides of each metal foil are closely laminated to the resin layers with an adhesive strength of 0.2 N/mm or more, respectively.

[0020] In another aspect, the present invention provides a method of producing a shaped article comprising molding

the laminated body according to the present invention.

[0021] In one embodiment of the method of producing the shaped article according to the present invention, the method comprises carrying out the molding by drawing.

5 Advantageous Effects of Invention

[0022] According to the present invention, it is possible to obtain a thin and light laminated body having improved drawability. The laminated body can be molded to use a shaped article for various packaging materials, as well as the laminated body can be suitably utilized as an electromagnetic wave shielding material for electrical and electronic devices, because the laminated body contains the metal foil as a component.

BRIEF DESCRIPTION OF DRAWINGS

[0023] FIG. 1 is a schematic view for explaining drawing.

DESCRIPTION OF EMBODIMENTS

(1. Metal Foil)

[0024] Materials of the metal foil(s) forming the laminated body according to the present invention are selected from the group of: copper, copper alloy, aluminum, nickel, iron and stainless steel. Metal materials with high conductivity are preferred in terms of improving a shielding property against an alternating magnetic field and an alternating electric field. Specifically, the metal foil may be preferably formed by a metal having a conductivity of 1.0×10^6 S/m (a value at 20 °C; the same will apply hereinafter) or more. The conductivity of the metal may be more preferably 10.0×10^6 S/m or more, and still more preferably 30.0×10^6 S/m or more, and most preferably 50.0×10^6 S/m or more. Examples of the metals include iron having a conductivity of about 9.9×10^6 S/m, nickel having a conductivity of about 14.5×10^6 S/m, aluminum having a conductivity of about 39.6×10^6 S/m, copper having a conductivity of about 58.0×10^6 S/m, and silver having a conductivity of about 61.4×10^6 S/m. In view of both electric conductivity and costs, aluminum or copper may be preferably employed for practical use. All of the metal foils forming the laminated body according to the present invention may be made of the same metal, or different metals may be used for each layer. Further, alloys containing the metals mentioned above may be used.

[0025] Various surface-treated layers may be formed on the surface(s) of the metal foil(s) for the purpose of adhesion promotion, environmental resistance, heat resistance and rust prevention. For example, the metal foil(s) may be subjected to Au plating, Ag plating, Sn plating, Ni plating, Zn plating, Sn alloy plating (Sn-Ag, Sn-Ni, Sn-Cu, and the like), a chromate treatment or the like, in order to improve environmental resistance and heat resistance that will be required when the metal surface is the outermost layer. These treatments may be combined. The Sn plating or the Sn alloy plating may be preferred in terms of costs. Further, the metal foil(s) may be subjected to the chromate treatment, a roughening treatment, Ni plating or the like in order to improve adhesion between the metal foil and the resin layer. These treatments may be combined. The roughening treatment may be preferred because it will easily provide the adhesion. Further, it is possible to provide at least one metal layer having high relative magnetic permeability in order to improve the shielding effect against the direct current magnetic field. Examples of the metal layer having high relative magnetic permeability include Fe-Ni alloy plating, Ni plating, and the like.

[0026] When using the copper foil, copper having a high purity may be preferred because it will improve the shielding performance. The purity may be preferably 99.5% by mass or more, and more preferably 99.8% by mass or more. Examples of the copper foil that can be used include rolled copper foils, electrolytic copper foils, metallized copper foils and the like. Among them, the rolled copper foils may be preferred because they have good flexibility and formability (the formability encompasses drawability; the same applies hereinafter). When at least one alloy element is added to the copper foil to form a copper alloy foil, the total content of the alloy element(s) and unavoidable impurities may be less than 0.5% by mass. In particular, the copper foil may preferably contain one or more selected from the group consisting of Sn, Mn, Cr, Zn, Zr, Mg, Ni, Si, and Ag in the total amount of from 200 to 2000 ppm by mass, in order to improve elongation as compared with a pure copper foil having the same thickness.

[0027] The thickness of the metal foil(s) forming the laminated body according to the present invention is 4 μm or more per foil. The thickness of less than 4 μm may lead to difficulty of handling, as well as significantly decreased ductility of the metal foil, resulting in insufficient formability of the laminated body. Also, if the thickness of one foil is less than 4 μm , the lamination of a large number of metal foils will be required for obtaining the excellent electromagnetic shielding effect, thereby causing a problem of an increase in manufacturing costs. From such viewpoints, the thickness of one metal foil may be preferably 10 μm or more, and more preferably 15 μm or more, and still more preferably 20 μm or more, and even more preferably 25 μm or more, and still more preferably 30 μm or more. On the other hand, if the

thickness of one foil exceeds 100 μm , the strength will be excessively increased, so that the effect of weight reduction may be deteriorated. Therefore, the thickness of one foil is 100 μm or less, and preferably 50 μm or less, and more preferably 45 μm or less, and even more preferably 40 μm or less.

[0028] Although one metal foil may be used for the laminated body, a plurality of metal foils forming the laminated body may be preferably laminated via resin layers, in terms of improving the formability and shielding performance. More preferably, three or more metal foils are laminated via the resin layers in terms of ensuring the excellent electromagnetic wave shielding property while decreasing the total thickness of the metal foils. The lamination of three or more metal foils significantly improves the shielding effect as compared with the single metal foil layer or two metal foil layers laminated via a resin layer, even if the metal foil(s) have the same total thickness. Even if the metal foils are directly stacked, the shielding effect will be improved due to an increase in the total thickness of the metal foils, but a remarkable improvement effect cannot be obtained. In other words, when a plurality of metal foils forming the laminated body are laminated via the resin layers, the total thickness of the metal foils needed to obtain the same electromagnetic wave shielding effect can be decreased, thereby achieving both of the weight reduction of the laminated body and the electromagnetic wave shielding effect.

[0029] The reason would be that the presence of the resin layers between the metal foils increases the number of reflections of electromagnetic waves to attenuate the electromagnetic waves. However, although the lamination of an increased number of metal foils tends to improve the electromagnetic shielding property, the increased number of the laminated metal foils increases the number of lamination steps, which will lead to an increase in manufacturing costs and will not provide further improvement of the shielding effect. Therefore, the number of the metal foils forming the laminated body may be preferably 5 or less, and more preferably 4 or less.

[0030] Therefore, in one embodiment of the laminated body according to the present invention, the total thickness of the metal foils may be 100 μm or less, or 80 μm or less, or 60 μm or less, or 40 μm or less. In one embodiment of the laminated body according to the present invention, the total thickness of the metal foils may be 4 μm or more, 8 μm or more, 12 μm or more, or 16 μm or more.

(2. Resin Layer)

[0031] In general, resin layer have higher ductility than metal foils. Therefore, by supporting both surfaces of each metal foil by resin layers, the ductility of the metal foil can be remarkably improved and the formability of the laminated body can be significantly improved. Even if the metal foils are directly stacked to each other, the effect of improving the formability cannot be obtained.

[0032] Resin layers having a larger impedance difference from the metal layer may be preferred in order to obtain the excellent electromagnetic shielding effect. To generate the larger impedance difference, the resin layers should have a smaller relative dielectric constant. More specifically, the relative dielectric constant may preferably be 10 (a value at 20 $^{\circ}\text{C}$; the same will apply hereinafter) or less, and more preferably 5.0 or less, and still more preferably 3.5 or less. In principle, the relative dielectric constant is never smaller than 1.0. For generally available materials, the relative dielectric constant is at least about 2.0. Even if the relative dielectric constant is lowered to be close to 1.0, the increase in the shielding effect is limited, while a special and expensive material must be used. In view of the balance between the cost and the effect, the relative dielectric constant may preferably be 2.0 or more, and more preferably 2.2 or more.

[0033] For materials making up the resin layers, synthetic resins are used for their processability. Further, for the materials making up the resin layers, those in the form of film are used. The resin layer may contain fiber reinforcing materials such as carbon fibers, glass fibers and aramid fibers. In terms of availability and processability, the synthetic resins used in the present invention include PET (polyethylene terephthalate), polyamides and polyimides. PET, polyamides and polyimides are used for their tensile strength and ductility. All the resin layers used in the laminated body according to the present invention may be made of the same resin or they may be made of different resins for each layer.

[0034] The surfaces of the resin layers may be subjected to various surface treatments for the purpose of promoting adhesion to the metal foil, or the like. For example, the adhesion to the metal foil can be enhanced by performing primer coating or corona treatment on the surfaces of the resin films bonded to the metal foil.

[0035] In terms of enhancing the effect of improving the ductility of the metal foil, the total thickness of the resin layers is 18 μm or more, and more preferably 20 μm or more, and more preferably 40 μm or more, and still more preferably 80 μm or more, and even more preferably 100 μm or more. However, the total thickness of the resin layers may preferably be 500 μm or less, and more preferably 400 μm or less, and more preferably 300 μm or less, in terms of cost reduction.

[0036] Also, in view of ease of handling, the thickness of one resin layer is 9 μm or more, and preferably 10 μm or more, and more preferably 20 μm or more, and still more preferably 40 μm or more, and even more preferably 80 μm or more, and even more preferably 100 μm or more. However, if the thickness of one resin layer is excessively increased, the costs will be increased. Therefore, the thickness of one resin layer is 500 μm or less, and may be preferably 250 μm or less, and more preferably 200 μm or less.

[0037] Closely laminating the resin layers and the metal foil(s) is performed by bonding with an adhesive. The adhesive

will result in lower strength than the resin films as described below. Therefore, it is necessary to appropriately select the thickness or tensile elasticity of the adhesive so as not to inhibit the effect of improving the ductility of the metal foil that will be obtained by laminating the resin layers thereon. There are resin materials in which the thermocompression bonding is difficult, such as PET. Therefore, in the present invention, adhesive is used.

[0038] In general, adhesives have lower strength than resin films. Therefore, the adhesive layer having excessively large thickness tends to prevent improvement of the ductility of the metal foil that will be obtained by laminating of the resin layers thereon. On the other hand, if the adhesive layer is too thin, it will be difficult to apply the adhesive to the entire boundary surface between the metal foil and the resin film, and an unbonded portion will be formed. Therefore, the thickness of the adhesive layer may preferably be 1 μm or more and 20 μm or less, and more preferably 1.5 μm or more and 15 μm or less, and still more preferably 2 μm or more and 10 μm or less.

[0039] The strength of the adhesive layer may be increased so as not to prevent improvement of the ductility of the metal foil that will be obtained by laminating the resin layers thereon. However, if the strength is excessively increased, the ductility of the adhesive layer will tend to be decreased, thereby conversely preventing the improvement of the ductility. On the other hand, if the adhesive layer is too soft, the improvement of the ductility will be prevented, even within the thickness range as described above. The tensile elasticity of the adhesive layer may preferably be from 1 MPa to 1500 MPa, and more preferably from 3 MPa to 1000 MPa, and still more preferably from 5 MPa to 800 MPa. In the present invention, the tensile elasticity of the adhesive layer is measured according to JIS K7161-1: 2014, on an adhesive film obtained by applying the adhesive to be measured onto a substrate such as a film, drying and curing the adhesive, and then being peeled off from the substrate.

[0040] If the resin layers and the metal foil forming the laminated body are peeled off during the drawing, the effect of improving ductility cannot be obtained. Therefore, it is desirable that both sides of each metal foil are closely laminated to the resin layers with an adhesive strength of 0.2 N/mm or more, and preferably 0.4 N/mm or more, and even more preferably 0.6 N/mm or more, respectively.

[0041] In the present invention, the adhesive strength between the metal foil and the resin layer is measured by a 180° peel test according to JIS-C 5016: 1994. First, a sample having a width of 12.7 mm is prepared from the laminated body. One surface of the sample was fixed to a stainless steel plate, and measurement is carried out by peeling off the metal foil (plus the resin layer) from the resin layer at a peeling angle of 180° and at a rate of 50 mm/min in a direction perpendicular to the width direction of the sample.

(3. Laminated body)

[0042] The laminated body has a structure in which one, preferably two or more, and more preferably three or more metal foils, is/are closely laminated via the resin layers. In this case, each metal foil may preferably have such a structure that both surfaces of each metal foil are closely laminated to the resin layers, in order to improve the ductility of the metal foil to provide improved formability of the laminated body. In other words, embodiments where both outermost layers are formed of the resin layers, and embodiments where the resin layers and the metal foils are alternately laminated one by one is more preferable than embodiments where the metal foil(s) form(s) the outermost layer(s) of the laminated body, and embodiments where the inner layers of the laminated body have a position(s) in which a plurality of metal foils are laminated without interposing the resin layer(s).

[0043] Examples of the laminated structure of the laminated body include the following structures:

- (1) a resin layer / a metal foil / a resin layer;
- (2) a resin layer / a metal foil / a resin layer / a metal foil / a resin layer; and
- (3) a resin layer / a metal foil / a resin layer / a metal foil / a resin layer / a metal foil / a resin layer.

[0044] Here, it should be understood that a single "resin layer" as used herein includes a laminated body of a plurality of resin layers without interposing a metal foil(s). In other words, in the present invention, a plurality of resin layers laminated via no metal foil(s) are considered to be the single resin layer. Further, in the present invention, the adhesive layer is also considered to be the resin layer.

[0045] Therefore, for example, when the laminated body has a laminated structure as shown in the following item (4), a laminated portion of "a resin film / an adhesive layer" is considered to be a single "resin layer", and the laminated body is considered to have a laminated structure as shown in the following item (4').

[0046] (4) (a resin film / an adhesive layer) / a metal foil / (an adhesive layer / a resin film layer); (4') a resin layer / a metal foil / a resin layer.

[0047] Similarly, when the laminated body has a laminated structure as shown in the following item (5), a laminated portion of "a resin film / an adhesive layer" and a laminated portion of "an adhesive layer / a resin film / an adhesive layer" are considered to be a single "resin layer", respectively, and the laminated body is considered to have a laminated structure as shown in the following (5').

(5) (a resin film / an adhesive layer) / a metal foil / (an adhesive layer / a resin film layer / an adhesive layer) / a metal foil / (an adhesive layer / a resin film);

(5') a resin layer / a metal foil / a resin layer / a metal foil / a resin layer.

5 **[0048]** In terms of improving the formability of the laminated body, the thickness of the laminated body is 25 μm or more, and preferably 50 μm or more, and more preferably 100 μm or more. However, in terms of weight reduction, the thickness of the laminated body is 500 μm or less, and preferably 400 μm or less, and more preferably 300 μm or less.

10 **[0049]** In the drawing, as the strength, specifically 5% strain stress, of the molding material is decreased, bending resistance and unbending resistance at the shoulder portion of the die is decreased accordingly. Since the resistance at the shoulder portion of the die are increased as a drawing depth becomes deeper, it is important to reduce the resistance when deeply drawing the molding material. According to the test results obtained by the present inventor, assuming that a nominal stress at a nominal strain of 5% (which may be referred to as "5% strain stress of the laminated body", hereinafter) when performing a tensile test according to JIS K 7127: 1999 is defined as σ_Y (MPa), the value of σ_Y is 150 MPa or less, and preferably 135 MPa or less, and more preferably 120 MPa or less. On the other hand, if the value of σ_Y is too small, buckling tends to occur at the inflow portion of the material and wrinkles tends to be generated. Therefore, the value of σ_Y is 60 MPa or more, and preferably 70 MPa or more, and more preferably 80 MPa or more.

15 **[0050]** In the present invention, the 5% strain stress (σ_Y) of the laminated body is measured by the following method. Four samples each having a width of 12.7 mm \times a length of 150 mm are cut out of the laminated body. The tensile direction of the laminated body is changed by varying the longitudinal directions of the samples such that the longitudinal direction of the second sample differs by 30°, the longitudinal direction of the third sample differs by 60°, and the longitudinal direction of the fourth sample differs by 90°, relative to the longitudinal direction of the first sample. The 5% strain stress (σ_Y) of each sample is measured by subjecting each sample to a tensile test in the longitudinal direction of each sample at a temperature of 25 °C and at a tensile rate of 50 mm/min in accordance with JIS K 7127: 1999, and an average value for the four samples is considered to be the measured value.

20 **[0051]** Further, if the strength of the molding material to be brought into contact with the shoulder portion of the punch is sufficiently high relative to the resistance at the shoulder portion of the die, the molding material is not broken and can be deeply drawn. Here, a nominal stress at a nominal strain at which the metal foil(s) in the laminated body is broken when the tensile test according to JIS K 7127: 1999 is performed on the laminated body (the nominal strain may be referred to as "tensile strength (σ_b) of the metal foil in the laminated body", hereinafter) is defined as σ_b (MPa). According to the examination results obtained by the present inventor, the laminated body is hardly broken and the drawability are significantly improved when the 5% strain stress of the laminated body (σ_Y) and the tensile strength (σ_b) of the metal foil(s) in the laminated body satisfy the relationship: $1.4 \leq \sigma_b / \sigma_Y$. Preferably, they may satisfy the relationship: $1.5 \leq \sigma_b / \sigma_Y$, and more preferably the relationship: $1.6 \leq \sigma_b / \sigma_Y$. Although the upper limit of the ratio σ_b / σ_Y is not specifically set, it is usually 3.0 or less. In the laminated body, the value of σ_b is larger than the tensile strength of the metal foil alone, because both surfaces of the metal foil are supported by the resin layers.

25 **[0052]** In the present invention, the tensile strength (σ_b) of the metal foil in the laminated body is measured by the following method. Four samples each having a width of 12.7 mm \times a length of 150 mm are cut out of the laminated body. The tensile direction of the laminated body is changed by varying the longitudinal directions of the samples such that the longitudinal direction of the second sample differs by 30°, the longitudinal direction of the third sample differs by 60°, and the longitudinal direction of the fourth sample differs by 90°, relative to the longitudinal direction of the first sample. The tensile strength (σ_b) of the metal foil in each sample is measured by subjecting each sample to a tensile test in the longitudinal direction of each sample at a temperature of 25 °C and at a tensile rate of 50 mm/min in accordance with JIS K 7127: 1999, and an average value for the four samples is considered to be the measured value.

30 **[0053]** It is preferable that in addition to the σ_Y and σ_b / σ_Y , an r value (Lankford value) of the laminated body is appropriately adjusted in order to reduce the blank holding force. The r value (Lankford value) is a value which is obtained by dividing "logarithmic strain in the plate width direction" at the time of application of strain in the longitudinal direction by "logarithmic strain in the plate thickness direction", and which indicates that deformation in the plate width direction tends to occur as the value is larger. When a drawing force is applied, a material having a larger r value tends to shrink in the circumferential direction, and wrinkles due to buckling are hardly generated, so that a decreased blank holding force can be chosen. According to the examination results obtained by the present inventor, the r value of the laminated body at the logarithmic strain of 0.4 is preferably 0.7 or more, and more preferably 1.0 or more, and even more preferably 1.1 or more, and still more preferably at least 1.2. On the other hand, if the r value is too large, the material tends to excessively shrink in the circumferential direction and causes the wrinkles. Therefore, the r value of the laminated body at the logarithmic strain of 0.4 may preferably be 4.0 or less, and more preferably 3.5 or less, and still more preferably 3.0 or less.

35 **[0054]** In the present invention, the r value is measured by the following method. Four samples each having a width of 12.7 mm \times a length of 150 mm and each marked with 2.5 mm square lattice throughout its surface are cut out of the laminated body. The tensile direction of the laminated body is changed by varying the longitudinal directions of the

5 samples such that the longitudinal direction of the second sample differs by 30°, the longitudinal direction of the third sample differs by 60°, and the longitudinal direction of the fourth sample differs by 90°, relative to the longitudinal direction of the first sample. Each lattice is composed of sides parallel to the longitudinal direction of each sample and sides in a direction perpendicular to the longitudinal direction of each sample. In accordance with JIS K 7127: 1999, the logarithmic strain of 0.4 is applied to each sample in the longitudinal direction of each sample at a tensile rate of 50 mm/min and at a temperature of 25 °C, and then unloaded. The lattice near the center of each sample is selected and displacements in the longitudinal direction and in the width direction are measured by means of a toolmaker's microscope. Further, assuming that the volume of the laminated body is constant before and after the tensile test, the thickness of each sample is calculated from the displacements in the longitudinal direction and in the width direction. The r value of each sample is calculated from the actually measured displacement in the width direction and the calculated thickness, and an average value for the four samples is considered to be the measured value.

10 **[0055]** When a dynamic friction coefficient between the molding material and the die as well as a dynamic friction coefficient between the molding material and the blank holder are small during the drawing, the frictional force can be reduced even if the blank holding force is increased, so that the molding material is hardly broken during the drawing. Therefore, the dynamic friction coefficient of the surface of the resin layers that form both outermost layers of the laminated body may preferably be 0.45 or less, and more preferably 0.40 or less, and even more preferably 0.35 or less. However, the dynamic friction coefficient of the surface of the resin layers that form both outermost layers of the laminated body is excessively small, the inflow resistance will be excessively decreased, which causes the wrinkles. Therefore, the dynamic friction coefficient may preferably be 0.15 or more, and more preferably 0.18 or more, and still more preferably 0.2 or more. In the present invention, the dynamic friction coefficient is measured in accordance with JIS K 7125: 1999.

20 **[0056]** As used herein, the "stress" refers to "nominal stress" and the "strain" refers to "nominal strain", unless otherwise noted.

25 **[0057]** Properties of the laminated body depend on properties of the resin layers, properties of the metal foil(s) and a volume ratio of both. Therefore, parameters such as the 5% strain stress (σ_Y), the ratio σ_b / σ_Y , the r value and the dynamic friction coefficient of the laminated body can be controlled by adjusting the properties of the resin layers, the properties of the metal foil(s), and the volume ratio of both.

30 **[0058]** The 5% strain stress (σ_Y) of the laminated body becomes higher by increasing the 5% strain stress (σ_Y) of the resin layer(s), increasing the 5% strain stress (σ_Y) of the metal foil(s) or increasing the thickness of either the resin layer(s) or the metal foil(s) having higher 5% strain stress (σ_Y). Conversely, the 5% strain stress (σ_Y) of the laminated body becomes lower by decreasing the 5% strain stress (σ_Y) of the resin layer(s), decreasing the 5% strain stress (σ_Y) of the metal foil(s), or increasing the thickness of either the resin layer(s) or the metal foil(s) having lower 5% strain stress (σ_Y). For example, the 5% strain stress (σ_Y) of a biaxially stretched film such as a PET film is generally increased as the draw ratio is increased, and is decreased as the draw ratio is decreased. The 5% strain stress (σ_Y) of the resin layer(s) can also be adjusted by incorporating plural types of monomers to copolymerize them. The 5% strain stress (σ_Y) of the metal foil(s) is increased as the degree of rolling is increased, and is decreased as the degree of rolling is decreased. The 5% strain stress (σ_Y) can also be changed by adding an element(s) to the metal foil(s).

35 **[0059]** When the ductility of the laminated body is increased, work hardening until breakage is increased so that the ratio σ_b / σ_Y is increased. To increase the work hardening of the laminated body, a resin exhibiting large work hardening may be used. For example, in a biaxially stretched resin, the work hardening can be increased by decreasing the draw ratio or by blending monomers which inhibit crystallization during stretching. Also, it is necessary to optimize the combination of the resin layer and the metal foil in order to increase the ductility. In general, the resin layer has higher ductility. Therefore, the ductility can be increased by increasing the volume fraction of the resin layer.

40 **[0060]** The r value of the metal foil can be adjusted by adding an element(s) or depending on the producing methods. For example, the r value is increased as the rolling reduction ratio of the final rolling is increased. The r value of the resin layer can be controlled by adjusting the draw ratio, the drawing rate, the temperature during the drawing, the proportion between the draw ratio in the longitudinal direction and the draw ratio in the width direction, and the like.

45 **[0061]** The dynamic friction coefficient of the surface of the resin layer varies depending on the composition of the resin and additives, and resins having various values are commercially available. The dynamic friction coefficient can be changed while maintaining the mechanical properties by forming a separate layer with a thickness of several nanometers having a molecular structure different from the resin layer on the outermost surface of the resin layer (primer treatment).

50 **[0062]** Various shaped articles can be produced by molding, especially drawing, the laminated body according to the present invention. The resulting shaped article can be used as a packaging material. The laminated body according to the present invention can be suitably used as an electromagnetic wave shielding material for electric and electronic devices. In particular, the laminated body according to the present invention can be suitably used for applications of shielding electromagnetic waves emitted from electric/electronic devices (for example, inverters, communication devices, resonators, electron tubes/discharge lamps, electric heating devices, electric motors, generators, electronic components, printed circuits, medical devices and the like).

EXAM PLES

[0063] Examples of the present invention are described below together with comparative examples, which are provided for better understanding of the present invention and its advantages, and are not intended to limit the invention.

(1. Preparation of Metal Foil)

[0064] The following materials were prepared as metal foils. The conductivity was measured by the double bridge method of JIS C 2525: 1999.

Cu: a rolled copper foil (electric conductivity at 20 °C: 58.0×10^6 S/m; thickness: see Table 1); only in Example 14, an electrolytic copper foil (conductivity at 20 °C: 58.0×10^6 S/m; thickness: see Table 1)

* For the rolled copper foil, "a pure copper foil" with no added element and "a copper alloy foil" with 0.2 wt% of Ag added, which decreased the 5% strain stress, were used. It should be noted that there is substantially no change in the conductivity because of the addition of a minor amount of Ag.

Al: an aluminum foil (conductivity at 20 °C: 39.6×10^6 S/m; thickness: see Table 1)

Ni: a nickel foil (conductivity at 20 °C: 14.5×10^6 S/m; thickness: see Table 1)

Fe: an iron foil (conductivity at 20 °C: 9.9×10^6 S/m; thickness: see Table 1)

SUS: a stainless steel foil (conductivity at 20 °C: 1.4×10^6 S/m; thickness: see Table 1)

<Surface Treatment>

[0065] The surface treatment was carried out on both surfaces of the metal foil according to the conditions as described in Table 1 depending on the test numbers. In the tables, the symbol "-" means that no surface treatment was carried out.

[0066] Roughening Treatment: using a roughening treatment solution (Cu: from 10 to 25 g/L; H₂SO₄: from 20 to 100 g/L; temperature: from 25 to 35 °C), electrolysis was performed at a current density of from 30 to 70 A/dm² for 1 to 5 seconds. Then, Ni-Co plating was performed at a temperature of from 30 to 50 °C and at a current density of from 1 to 4 A/dm² using a Ni-Co plating solution (Co ion concentration: from 5 to 15 g/L; Ni ion concentration: from 5 to 15 g / L).

[0067] Silane Treatment: the immersion treatment in an epoxysilane treatment solution (epoxy silane: an aqueous solution of 0.1 to 2 wt%) was carried out.

[0068] Chromate Treatment: electrolysis was carried out at a current density of from 0.5 to 2 A/dm² using a chromate bath (K₂Cr₂O₇: from 0.5 to 5 g/L; temperature: from 50 to 60 °C).

[0069] Ni Plating + Chromate Treatment: using a Ni plating bath (watts bath with a Ni ion concentration of from 15 to 25 g/L), Ni plating was carried out at a plating solution temperature of from 30 to 50 °C and at a current density of from 1 to 4 A/dm², and the chromate treatment was then carried out in the same way as described above.

(2. Preparation of Resin Layer)

[0070] The following materials were prepared as resin films. All of them are commercially available products. The relative dielectric constant was measured by the method B described in the standard JIS C2151: 2006.

PET: a polyethylene terephthalate film (relative dielectric constant at 20 °C: from 3.0 to 3.5; melting point: 220 °C; thickness: see Table 1)

* For PET, the 5% strain stress, the r value and the dynamic friction coefficient of the PET film alone were changed by using PET films having various grades from multiple manufacturers. By changing the 5% strain stress, the r value and the dynamic friction coefficient of the PET film alone, the 5% strain stress, the r value and the dynamic friction coefficient of the laminated body are also changed.

PI: a polyimide film (relative dielectric constant at 20 °C: 3.5; melting point: none; thickness: see Table 1)

PA: a polyamide film (relative dielectric constant at 20 °C: 6.0; melting point: 300 °C; thickness: see Table 1)

[0071] In addition, the following isocyanate-curing type polyurethane adhesive was prepared as the adhesive.

[0072] Adhesive: a main agent: RU-80; a curing agent: H-5, all of which are available from Rock Paint Co., Ltd.

[0073] The tensile elasticity after curing of the adhesive was measured using a precision universal testing apparatus AGS-X available from Shimadzu Corporation according to the method as described above and was found that it was 600 MPa.

(3. Preparation of Laminated body)

5 [0074] Various laminated bodies having the laminated structures as shown in Table 1 were produced using the metal foils and the resin films as described above. In Table 1, the order of members described in the column of "Laminated Structure" and the order of members described in the column of "Thickness of Each Member" are the same. The metal foil and the resin film were laminated such that the areas of the bonding surfaces were the same and they did not protrude from each other. In Examples where the PET was used for the resin layer, the adhesive was applied onto the bonding surface of the PET by means of a bar coater (available from Daiichi Rika Co., Ltd.). The thickness of the adhesive layer was adjusted by the solid content of the adhesive and the count of the bar coater. The adhesive was then dried at 80 °C for 1 minute to volatilize excess solvent. The metal foil was attached, and then maintained at 40 °C for 7 days to promote the curing reaction such that the metal foil and the resin layer were closely laminated. In this case, one resin layer is made of a laminated body of PET and an adhesive layer, according to the definition as described above.

(4. Tensile Test)

15 [0075] For each laminated body obtained by the above procedures, four samples each having a width of 12.7 mm × a length of 150 mm were cut out. The tensile direction of the laminated body was changed by varying the longitudinal directions of the samples such that the longitudinal direction of the second sample differed by 30°, the longitudinal direction of the third sample differed by 60°, and the longitudinal direction of the fourth sample differed by 90°, relative to the longitudinal direction of the first sample. The 5% strain stress (σ_Y) of each sample and the tensile strength (σ_b) of the metal foil in each sample were measured by subjecting each sample to a tensile test in the longitudinal direction of each sample at a temperature of 25 °C and at a tensile rate of 50 mm/min, using a tensile tester Model AGS-X available from Shimadzu Corporation, in accordance with JIS K 7127: 1999, and average values for the four samples were considered to be the 5% strain stress (σ_Y) of the laminated body and the tensile strength (σ_b) of the metal foil in the laminated body. The results are shown in Table 1.

(5. Measurement of r value)

30 [0076] For each laminated body obtained by the above procedures, four samples each having a width of 12.7 mm × a length of 150 mm and each marked with 2.5 mm square lattice throughout its surface were cut out. The tensile direction of the laminated body was changed by varying the longitudinal directions of the samples such that the longitudinal direction of the second sample differed by 30°, the longitudinal direction of the third sample differed by 60°, and the longitudinal direction of the fourth sample differed by 90°, relative to the longitudinal direction of the first sample. Each lattice was composed of sides parallel to the longitudinal direction of each sample and sides in a direction perpendicular to the longitudinal direction of each sample. In accordance with JIS K 7127: 1999, the logarithmic strain of 0.4 was applied to each sample in the longitudinal direction of each sample at a tensile rate of 50 mm/min and at a temperature of 25 °C, using a tensile tester Model AGS-X available from Shimadzu Corporation, and then unloaded. The lattice near the center of each sample was selected and displacements in the longitudinal direction and in the width direction were measured by means of a toolmaker's microscope. Further, assuming that the volume of the laminated body was constant before and after the tensile test, the thickness of each sample was calculated from the displacements in the longitudinal direction and in the width direction. The r value of each sample was calculated from the actually measured displacements in the width direction and the calculated thickness, and an average value for the four samples was considered to be the measured value for the r value. The results are shown in Table 1.

(6. Dynamic Friction Coefficient)

45 [0077] Using a surface property measuring instrument (TYPE-HEIDON-14, available from Shinto Scientific Co., Ltd.), the dynamic friction coefficient according to JIS K 7125: 1999 was determined by measuring a load generated when a steel ball having a diameter of 10 mm was pressed against the surface of each laminated body obtained by the above procedures under a load of 1 N and slid at a rate of 150 mm/min. The results are shown in Table 1.

(7. Molding Test)

55 [0078] Circular blanks having a diameter of from 50 to 65 mm were prepared from each laminated body obtained by the above procedures. Each blank was subjected to a molding test for drawing into a cylindrical article using a punch having a diameter of 30 mm. A plurality of punches and dies were prepared, and clearance (a gap when the punch entered the die), punch shoulder R, and die shoulder R were adjusted according to the thickness of the blank. The presence or absence of wrinkle and crack of the shaped article after the molding test was observed. Cracks was confirmed

EP 3 381 678 B1

by observing not only the outermost layer of the shaped article, but also the interior with X-ray CT (micro-CT scanner, TOSCANER 32251 μ hd, available from TOSHIBA IT CONTROL SYSTEMS CORPORATION; a tube current of 120 μ A; a tube voltage of 80 kV). The drawing height of the shaped article that was most deeply drawn, among those that could be drawn without generating wrinkle and crack, was measured. The shaped article having a drawing depth of 12 mm or more was represented by "◎" (a double circle), the shaped article having a drawing depth of 9 mm or more and less than 12 mm was represented by "○" (a single circle), the shaped article having a drawing depth of 6 mm or more and less than 9 mm was represented by "△" (a triangle), and the shaped article having a drawing depth of less than 6 mm was represented by "×" (a cross). The results are shown in Table 1.

(8. Adhesive Strength)

[0079] For the laminated bodies according to Examples 1 to 3, the adhesive strength between the metal foil and the resin layer was measured by a 180° peel test according to JIS-C 5016: 1994. First, a sample having a width of 12.7 mm was prepared from each laminated body. One surface of each sample was fixed to a stainless steel plate, and measurement was carried out by peeling off the metal foil (plus the resin layer) from the resin layer at a peeling angle of 180° and at a rate of 50 mm/min in a direction perpendicular to the width direction of the sample. The results are shown in Table 1. Among the adhesive strengths in Table 1, the values on the left side represent the adhesive strength between the resin layer on the left side and the metal foil at the center, and the values on the right side represent the adhesive strength between the resin layer on the right side and the metal foil at the center.

[Table 1-1]

	Laminate					
	Laminated Structure	Surface Treatment of Metal Foil	Thickness of Each Member	Thickness of Each Adhesive layer	Adhesive Strength between Metal Foil and Resin Layer	Total Thickness
			Mm	μ m	N/mm	mm
Example 1	PET/Copper Alloy Foil/PET	Roughening Treatment	200, 70, 200	10	0.62, 0.63	490
Example 2	PET/Pure Copper Foil/PET	Roughening Treatment	100, 18, 100	6	0.61, 0.58	230
Example 3	PET/Copper Alloy Foil/PET		50, 18, 50	3	0.38, 0.42	124
Example 4	PET/Pure Copper Foil/PET	Roughening Treatment	50, 18, 50	3	-	124
Example 5	PET/Pure Copper Foil/PET	Roughening Treatment	25, 9, 25	3	-	65
Example 6	PET/Copper Alloy Foil/PET	Roughening Treatment	50, 18, 50	10	-	183
Example 7	PET/Pure Copper Foil/PET	Roughening Treatment	38, 18, 38	3	-	100
Example 8	PET/Copper Alloy Foil/PET	Roughening Treatment	50, 18, 50	3	-	124
Example 9	PET/Copper Alloy Foil/PET	Roughening Treatment	50, 18, 50	3	-	124
Example 10	PET/Copper Alloy Foil/PET	Roughening Treatment	50, 18, 50	10	-	138
Example 11	PET/Copper Alloy Foil/PET	Chromate Treatment	50, 18, 50	3	-	124

EP 3 381 678 B1

(continued)

	Laminate						
	Laminated Structure	Surface Treatment of Metal Foil	Thickness of Each Member	Thickness of Each Adhesive layer	Adhesive Strength between Metal Foil and Resin Layer	Total Thickness	
			Mm	μm			N/mm
5	Example 12	PET/Electrolytic Copper Foil/PET	Roughening Treatment	100, 18, 100	10	-	238
10	Example 13	PET/SUS/PET	-	100, 20, 100	10	-	240
15	Example 14	PET/FE/PET	-	100, 20, 100	6	-	232
20	Example 15	PET/Ni/PET	-	100, 20, 100	10	-	240
25	Example 16	PET/Al/PET	-	25, 10, 25	3	-	66
30	Example 17	PET/Al/PET	-	50, 20, 50	3	-	126
35	Example 18	PET/Copper Alloy Foil/PET/Copper Alloy Foil/PET	Roughening Treatment	50, 18, 50, 18, 50, 18, 50	3	-	272
40	Example 19	PET/Copper Alloy Foil/PET/Copper Alloy Foil/PET	Roughening Treatment	100, 35, 100, 35, 100	10	-	410
45	Example 20	PET/Al/PET/Al/PET	-	50, 20, 50, 20, 50	3	-	202
50	Example 21	PET/Copper Alloy Foil/PET	Roughening Treatment	25, 9, 25	3	-	65
55	Example 22	PET/Copper Alloy Foil/PET	Roughening Treatment	50, 18, 50	6	-	130
	Example 23	PET/Copper Alloy Foil/PET	Ni Plating + Chromate Treatment	50, 18, 50	3	-	124
	Example 24	PET/Copper Alloy Foil/PET	Roughening Treatment	100, 18, 100	10	-	238
	Comparative Example 1	PET/Pure Copper Foil/PET	Roughening Treatment	50, 18, 50	3	-	124
	Comparative Example 2	PET/Copper Alloy Foil/PET	Roughening Treatment	100, 18, 100	10	-	238
	Comparative Example 3	SUS	-	150	0	-	150
	Comparative Example 4	Pure Copper	-	200	0	-	200
	Comparative Example 5	Al	-	200	0	-	200

EP 3 381 678 B1

[Table 1-2]

	Properties				Results of Drawing	
	αY	$\sigma_b / \sigma Y$	r value	Dynamic Friction Coefficient	Drawing depth	Evaluation
	MPa				mm	
Example 1	85	1.65	2.02	0.32	157	◎
Example 2	100	1.7	2.02	0.32	15.6	◎
Example 3	75	1.52	1.5	0.25	11	○
Example 4	92	1.99	3	0.29	13.7	◎
Example 5	90	1.96	3	0.29	12.3	◎
Example 6	74	1.59	0.7	0.28	8.7	△
Example 7	85	1.88	3.8	0.29	15.3	◎
Example 8	75	1.52	1.5	0.45	117	○
Example 9	75	1.52	1.5	0.15	14.4	◎
Example 10	64	1.45	1.3	0.3	7.7	△
Example 11	81	1.42	1.5	0.3	11	○
Example 12	102	1.55	2.02	0.32	10.4	○
Example 13	110	1.44	2.02	0.32	11.5	○
Example 14	105	1.52	2.02	0.32	10.6	○
Example 15	111	1.42	2.02	0.32	9.4	○
Example 16	88	1.64	3	0.29	12.9	◎
Example 17	88	1.8	3	0.29	14.5	◎
Example 18	86	1.36	3	0.29	14	◎
Example 19	89	1.52	2.02	0.32	11.2	○
Example 20	85	1.77	3	0.29	15.1	◎
Example 21	86	1.41	0.6	0.32	6.3	△
Example 22	75	1.52	1.5	0.48	7.7	△
Example 23	146	1.4	1.3	0.3	8.5	△
Example 24	132	1.42	1.3	0.3	9.2	○
Comparative Example 1	82	1.2	1.2	0.15	5_6	X
Comparative Example 2	38	1.4	0.9	0.15	4.9	X
Comparative Example 3	205	2.5	1.1	0.3	4.6	X
Comparative Example 4	200	1.1	0.9	0.3	4.3	X
Comparative Example 5	167	2.1	0.9	U.3	4.4	X

(9. Discussion)

[0080] The laminated bodies according to Examples 1 to 24 each had the appropriate thickness, σY and $\sigma_b / \sigma Y$. Therefore, the drawability was excellent. Further, the laminated bodies in which all of σY , $\sigma_b / \sigma Y$, the r value and the dynamic friction coefficient were suitable exhibited the highest evaluation for the drawability.

[0081] On the other hand, Comparative Example 1 had inappropriate $\sigma_b / \sigma Y$ and thus exhibited poor drawability as compared with Examples. Comparative Examples 2 to 5 had inappropriate σY values and thus exhibited poor drawability as compared with Examples.

Claims

- 5 1. A laminated body comprising at least one metal foil and at least two resin layers, the laminated body having a thickness of 25 to 500 μm , each metal foil having a thickness of 4 to 100 μm , and each resin layer having a thickness of 9 to 500 μm ,

wherein both surfaces of each metal foil are closely laminated to the resin layers with an adhesive;
 wherein each resin layer is at least one selected from the group of a polyethylene terephthalate film, a polyimide film and a polyamide film;

10 wherein each metal foil is at least one selected from the group of a copper foil, a copper alloy foil, an aluminum foil, a nickel foil, iron foil and a stainless steel foil; and

wherein the relationships: $60 \leq \sigma_Y \leq 150$, and $1.4 \leq \sigma_b / \sigma_Y$ are satisfied, in which σ_Y represents a nominal stress (MPa) at a nominal strain of 5% when a tensile test according to JIS K 7127: 1999 is performed on the laminated body, and σ_b represents a nominal stress (MPa) at a nominal strain at which the metal foil in the laminated body is broken when a tensile test according to JIS K 7127: 1999 is performed on the laminated body.

2. The laminated body according to claim 1, wherein the laminated body has an r value (Lankford value) at a logarithmic strain of 0.4 of from 0.7 to 4.0.

- 20 3. The laminated body according to claim 1 or 2, wherein the surfaces of the resin layers forming both outermost layers comprise a dynamic friction coefficient of from 0.15 to 0.45.

4. The laminated body according to any one of claims 1 to 3, wherein both sides of each metal foil are closely laminated to the resin layers with an adhesive strength of 0.2 N/mm or more, respectively.

- 25 5. A method of producing a shaped article, comprising molding the laminated body according to any one of claims 1 to 4.

6. The method of producing the shaped article according to claim 5, wherein the method comprises carrying out the molding by drawing.

Patentansprüche

- 35 1. Laminatkörper, der zumindest eine Metallfolie und zumindest zwei Harzschichten umfasst, wobei der Laminatkörper eine Dicke von 25 bis 500 μm aufweist, jede Metallfolie eine Dicke von 4 bis 100 μm aufweist und jede Harzschicht eine Dicke von 9 bis 500 μm aufweist,

wobei beide Oberflächen jeder Metallfolie mit einem Kleber dicht an die Harzschichten laminiert sind;
 wobei jede Harzschicht zumindest eine, ausgewählt aus der aus einem Polyethylenterephthalat-Film, einem Polyimid-Film und einem Polyamid-Film bestehenden Gruppe ist;

40 wobei jede Metallfolie zumindest eine, ausgewählt aus der aus einer Kupferfolie, einer Kupferlegierungsfolie, einer Aluminiumfolie, einer Nickelfolie, einer Eisenfolie und einer Edelstahlfolie bestehenden Gruppe ist; und

wobei die Beziehungen: $60 \leq \sigma_Y \leq 150$ und $1,4 \leq \sigma_b / \sigma_Y$ erfüllt sind, wobei σ_Y für die Nominalbeanspruchung (MPa) bei einer Nominaldehnung von 5 % steht, wenn eine Zugprüfung gemäß JIS K 7127: 1999 mit dem Laminatkörper durchgeführt wird, und σ_b für die Nominalbeanspruchung (MPa) bei einer Nominaldehnung steht, bei der die Metallfolie im Laminatkörper reißt, wenn eine Zugprüfung gemäß JIS K 7127: 1999 mit dem Laminatkörper durchgeführt wird.

- 50 2. Laminatkörper nach Anspruch 1, wobei der Laminatkörper einen r-Wert (Lankford-Wert) bei einer logarithmischen Dehnung von 0,4 von 0,7 bis 4,0 aufweist.

3. Laminatkörper nach Anspruch 1 oder 2, wobei die Oberflächen der Harzschichten, welche die äußersten Schichten bilden, einen dynamischen Reibungskoeffizienten von 0,15 bis 0,45 aufweisen.

- 55 4. Laminatkörper nach einem der Ansprüche 1 bis 3, wobei beide Seiten jeder Metallfolie mit einer Haftfestigkeit von 0,2 N/mm bzw. mehr dicht an die Harzschichten laminiert sind.

5. Verfahren zur Herstellung eines Formkörpers, welches das Formen eines Laminatkörpers nach einem der Ansprüche

1 bis 4 umfasst.

6. Verfahren zur Herstellung eines Formkörpers nach Anspruch 5, wobei das Verfahren das Ausführen des Formens durch Verstrecken umfasst.

5

Revendications

1. Corps stratifié comprenant au moins une feuille métallique et au moins deux couches de résine, le corps stratifié présentant une épaisseur de 25 à 500 μm , chaque feuille métallique présentant une épaisseur de 4 à 100 μm , et chaque couche de résine présentant une épaisseur de 9 à 500 μm ,

10

dans lequel les deux surfaces de chaque feuille métallique sont stratifiées de manière serrée sur les couches de résine à l'aide d'un adhésif ;

15

dans lequel chaque couche de résine est au moins une sélectionnée dans le groupe constitué par un film de polyéthylène téréphtalate, un film de polyimide et un film de polyamide ;

dans lequel chaque feuille de métal est au moins une feuille sélectionnée dans le groupe constitué d'une feuille de cuivre, d'une feuille d'alliage de cuivre, d'une feuille d'aluminium, d'une feuille de nickel, d'une feuille de fer et d'une feuille d'acier inoxydable ; et

20

dans lequel les relations : $60 \leq \sigma_Y \leq 150$, et $1,4 \leq \sigma_b / \sigma_Y$ sont satisfaites, dans lequel σ_Y représente une contrainte nominale (MPa) à une déformation nominale de 5 % lorsqu'un test de traction selon JIS K 7127 : 1999 est effectué sur le corps stratifié, et σ_b représente une contrainte nominale (MPa) à une déformation nominale à laquelle la feuille métallique dans le corps stratifié est cassée lors d'un test de traction selon JIS K 7127 : 1999 est effectué sur le corps stratifié.

25

2. Corps stratifié selon la revendication 1, dans lequel le corps stratifié présente une valeur r (valeur de Lankford), à une déformation logarithmique de 0,4, de 0,7 à 4,0.

3. Corps stratifié selon la revendication 1 ou 2, dans lequel les surfaces des couches de résine formant les deux couches les plus externes comprennent un coefficient de frottement dynamique compris entre 0,15 et 0,45.

30

4. Corps stratifié selon l'une quelconque des revendications 1 à 3, dans lequel les deux côtés de chaque feuille métallique sont stratifiés de manière serrée sur les couches de résine à l'aide d'une force d'adhérence, respectivement, de 0,2 N/mm ou plus.

35

5. Procédé de production d'un article formé, comprenant le moulage du corps stratifié selon l'une quelconque des revendications 1 à 4.

6. Procédé de production de l'article formé selon la revendication 5, dans lequel le procédé comprend la réalisation du moulage par étirage.


40

45

50

55

[FIG. 1]



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2003285002 A [0003] [0008]
- JP 2017005214 A [0004] [0008]
- JP 4580079 B [0007] [0008]
- JP 5474678 B [0007] [0008]
- EP 2581220 A1 [0009]
- US 5573857 A [0010]
- WO 2016140244 A [0011]