



(11) **EP 3 620 217 A1**

(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 153(4) EPC

(43) Date of publication:
11.03.2020 Bulletin 2020/11

(51) Int Cl.:
B01D 19/04 ^(2006.01) **C08F 220/18** ^(2006.01)
C08F 283/06 ^(2006.01) **C08F 210/14** ^(2006.01)

(21) Application number: **17908375.3**

(86) International application number:
PCT/CN2017/117874

(22) Date of filing: **22.12.2017**

(87) International publication number:
WO 2018/201736 (08.11.2018 Gazette 2018/45)

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR
Designated Extension States:
BA ME
Designated Validation States:
MA MD TN

(72) Inventors:
• **ZHANG, Zhen**
Nanjing
Jiangsu 210027 (CN)
• **LIU, Yang**
Nanjing
Jiangsu 210027 (CN)
• **CAO, Tian**
Nanjing
Jiangsu 210027 (CN)

(30) Priority: **05.05.2017 CN 201710312000**

(71) Applicant: **Jiangsu Sixin Scientific-Technological Application Research Institute Co., Ltd.**
Nanjing, Jiangsu 210027 (CN)

(74) Representative: **Proi World Intellectual Property GmbH**
Obermattweg 12
6052 Hergiswil, Kanton Nidwalden (CH)

(54) **NON-SILICON DEFOAMER**

(57) The present invention belongs to the technical field of fine chemical engineering, and discloses a non-silicon defoaming agent, comprising an acrylate polymer, an organic solvent carrier, hydrophobic particles and defoaming auxiliaries; and the acrylate polymer is prepared from following raw material components: monomer-1, monomer-2, unsaturated terminated polyether, alkene, diluent and initiator. The present invention further discloses a preparing method for the non-silicon defoaming agent. The present invention further discloses the application of the non-silicon defoaming agent to the defoaming and foam inhibiting in systems rich in anionic surfactants. The defoaming agent in the present invention takes the acrylate polymer as the main active substance and has excellent defoaming and foam inhibiting performance. By dropwise adding monomers, the defoaming performance of the acrylate polymer is improved, by using unsaturated terminated polyether to modify, the hydrophilia of the acrylate polymer is improved, the instant defoaming capacity is further improved, and by the alkene with the carbon atoms of 6-22 to modify, the foam inhibiting performance of the defoaming agent is improved.

EP 3 620 217 A1

Description**BACKGROUND**5 **Technical Field**

[0001] The present invention belongs to the technical field of preparations of fine chemical engineering, relates to a fine chemical preparation, in particular to a non-silicon defoaming agent, specifically to say, a non-silicon defoaming agent containing an acrylate polymer and the application thereof in the systems rich in anionic surfactants in the industries of papermaking, water treatment, textile and the like.

Related Art

15 [0002] A defoaming agent is a composition for controlling foams in various working procedures in industrial production. In industrial production, particularly papermaking, water treatment and textile, since the system has rich water and added massive chemical auxiliaries, in addition, large amount of mechanical energy generated in processes such as stirring, washing and thickening, foams are extremely easily generated. Liquid mediums (for example, water), chemical auxiliaries (for example, surfactants), air source and mechanical energy are main reasons why the foams are generated in the industry.

20 [0003] Development of the defoaming agents is to eliminate unnecessary foams in industrial production. The defoaming agents are mainly divided into non-silicon defoaming agents and organic silicon defoaming agents, common non-silicon defoaming agents take mineral oil, polyether, amide or fatty alcohol as an active substance, and the organic silicon defoaming agent take polysiloxane as an active substance.

25 [0004] The defoaming agent described in Patent CN10051850C is prepared from organic hydrocarbon, white carbon black, silicon polyether and an emulsifier, is improved in the defoaming and foam inhibiting performance, and can be applied to the working procedures of papermaking, cloth coating, circuit panel developing, metal cleaning and the like. Patent CN101991975B provides a mineral oil defoaming agent, which is prepared from mineral oil, fatty acid metal soap, fatty acid amide, white carbon black, defoaming auxiliary and an emulsifier, and has better defoaming and foam inhibiting effects in the processes such as papermaking and water treatment. The defoaming agents mentioned in above patents belong to the mineral oil defoaming agent, namely, the defoaming agent taking the mineral oil as a carrier, but the mineral oil which is a hydrocarbon oil substance by the way can generate the harmful substance tetrachlorodibenzo-p-dioxin, which harms the environment and a human body, and is defective in the defoaming capacity in a system rich in anionic surfactants.

30 [0005] As the main active substance of the mineral oil defoaming agent, alkyldene amide for example, EBS is commonly used, and ther diamides or a mixture of the diamides can also be used in such defoaming agent. Patent Application CN101362063 describes a defoaming agent which is prepared from plant oil, EBS and other types of amides and is mainly used in the textile printing and dyeing industry. Patent CN102976429B describes a defoaming agent which is mainly used for water treatment and is mainly prepared from the EBS, liquid paraffin, kerosene, simethicone and white carbon black. In a use process, the EBS in such mineral oil defoaming agent has higher hydrophobicity, and is thus easy to deposit and affects production efficiency and product quality.

35 [0006] Patent CN103603215A describes an organic silicon defoaming agent for textile printing and dyeing, which is prepared by reaction between silicone grease and polyether modified polysiloxane in presence of an organic tin catalyst. Patent CN102002242B describes an organic silicon emulsion defoaming agent which is prepared from polysiloxane composition, fatty alcohol polyether, emulsifier, polyether modified polysiloxane and water and issuitable for the industries such as papermaking and textile. The defoaming agents mentioned in above patents all adopt silicone grease as an active substance, however, due to the hydrophobicity of the silicone grease, the silicone grease will be gradually separated out in a use process of the defoaming agent and will be massively separated out in a case of long term accumulation of the defoaming agent, thus, the product quality is affected on one aspect and the silicone grease is deposited on a device and is hard to wash, even device blockage is caused. Hence, although it is widely believed that the silicone grease has the characteristics of defoaming rapidness and defoaming durability, the defoaming agent product containing the silicone grease is avoided in many industrial productions.

40 [0007] Therefore, demands on the defoaming agent without hydrocarbon oil, EBS or silicone grease become more and more. Patent CN101638871B describes a defoaming agent which is prepared from fatty acid methyl ester derivative, polyether and natural grease, and is suitable for a papermaking wet end procedure, papermaking sewage treatment and elimination of other water phase foams. Patent CN102126763A describes a defoaming agent which is prepared from polyether and lower alcohol and is mainly used for treatment of garbage penetrating fluid. Above patents do not use the mineral oil and avoid the damage of the mineral oil to the environment, but the non-silicon defoaming agent taking the polyether or fatty acid as the active substance is not entirely satisfactory in the defoaming and foam inhibiting

performance in the systems rich in anionic surfactants, and the defoaming capacity cannot meet the requirements of industrial production. So researchers improve the defoaming agent based on the existing defoaming agent on one aspect and develop a new defoaming agent to fundamentally solve the problem, and an acrylate defoaming agent is a research hot spot.

5 **[0008]** Patent US5152925 describes a defoaming agent taking acrylic resin as a main defoaming active substance, wherein an acrylate polymer mainly takes the acrylic resin prepared by a hydroxyl group-containing acrylic monomer in an organic diluent DIDP as a main active substance, and is applied to coarse pulp washing and other papermaking procedures. Patent CN102428142B also mentions the defoaming agent prepared by taking the acrylate polymer as a main active substance, wherein the acrylate polymer is prepared from monomers of iso-octyl acrylate, hydroxyalkyl acrylate and acrylic acid in the organic diluent DIOA, and the prepared acrylate polymer serves as the main active substance of the defoaming agent and is compounded with white carbon black and alkyl silicone oil, and is applied to the industries of petroleum, water treatment, pigments and coating, food and beverage machining, mining, textile, agriculture and papermaking. Such defoaming agent can solve the problems of environment harmness and silicon separating out and residue, but the defoaming performance of the defoaming agent prepared by current technology still has greater improving potential. Therefore, the improvement of the defoaming and foam inhibiting performance of the acrylate polymer defoaming agent still has important meaning.

SUMMARY

20 **[0009]** The present invention introduces a defoaming agent taking an acrylate polymer as a main active substance, and the defoaming agent has excellent defoaming and foam inhibiting performance, and is particularly suitable for the systems rich in anionic surfactants. According to the acrylate polymer, based on the alkyl acrylate and/or alkyl methacrylate and hydroxyalkyl acrylate and/or hydroxyalkyl methylacrylate, through dropwise adding monomers step by step, the defoaming performance of the polymer is improved, secondly, unsaturated terminated polyether is used for modification to improve the hydrophilia of the acrylate polymer, thus improving the dispersive power of the acrylate polymer in water and further improving the instant defoaming capacity; and finally, by modifying through the alkenes with the carbon atoms of 6-22, the foam inhibiting performance of the defoaming agent is improved due to the hydrophobic performance of the alkenes. Through a specific polymerization process, the defoaming capacity of the synthesized acrylate polymer is further improved. The defoaming agent in the present invention further contains an organic solvent carrier, hydrophobic particles, defoaming auxiliaries and the like.

30 **[0010]** Aims of the present invention are realized by following technical solutions:

A non-silicon defoaming agent comprises an acrylate polymer, an organic solvent carrier, hydrophobic particles and defoaming auxiliaries; the use level of the acrylate polymer is 15-70% of the total mass of the defoaming agent, the use level of the organic solvent carrier is 10-70% of the total mass of the defoaming agent, the use level of the hydrophobic particles is 0.1-15% of the total mass of the defoaming agent, and the use level of the defoaming auxiliaries is 1-25% of the total mass of the defoaming agent;

40 the acrylate polymer is prepared from following raw material components: monomer-1, monomer-2, unsaturated terminated polyether, alkene, diluent and initiator; the total use level of the monomer-1 and monomer-2 is 20-70% of the total mass of the raw material components, the use level of the unsaturated terminated polyether is 1-10% of the total mass of the raw material components, the use level of the alkene is 1-8% of the total mass of the raw material components the use level of the diluent is 20-75% of the total mass of the raw material components, and the use level of the initiator is 0.2-1 % of the total mass of the raw material components.

45 **[0011]** Preferably, use level of the acrylate polymer is 20-60% of the total mass of the defoaming agent, the use level of the organic solvent carrier is 10-70% of the total mass of the defoaming agent, the use level of the hydrophobic particles is 0.5-10% of the total mass of the defoaming agent, and the use level of the defoaming auxiliaries is 2-20% of the total mass of the defoaming agent.

50 **[0012]** Preferably, the total use level of the monomer-1 and monomer-2 is 20-60% of the total mass of the raw material components, the use level of the unsaturated terminated polyether is 1-8% of the total mass of the raw material components, the use level of the alkene is 1-8% of the total mass of the raw material components the use level of the diluent is 30-70% of the total mass of the raw material components, and the use level of the initiator is 0.4-0.8% of the total mass of the raw material components.

55 **[0013]** A preparing method of the acrylate polymer described in the present invention comprises:

(1), mixing the monomer-1, monomer-2 and unsaturated terminated polyether which are 70-90% of the total use level of the monomer-1 with the initiator which is 50-70% of the total use level of the initiator to cause the initiator to be

fully dissolved and form a mixture a;

(2), mixing the alkene with the initiator which is 5-15% of the total use level of the initiator to fully dissolve the initiator and form a mixture b;

(3), mixing the rest monomer-1 with the initiator which is 2-15% of the total use level of the initiator to fully dissolve the initiator and form a mixture c;

(4), at 60-100 °C, fully dissolving the initiator which is 8-15 of the total use level of the initiator in the diluent, and releasing free radicals to form a mixture d;

(5), at 60-100°C, in order to prevent the generation of excessive free radicals which cause severe polymerization and further cause danger, dropwise adding the mixture a into the mixture d, controlling the dropwise adding time to be 1-5h, and forming a mixture e; during dropwise adding, enabling the temperature to be 60-100°C by circulated water or ice bath;

(6), after completely dropwise adding the mixture a, at 60-100 °C, similarly, in order to prevent the generation of excessive free radicals which cause severe polymerization and further cause danger, dropwise adding the mixture b into the mixture e, controlling the dropwise adding time to be 1-2h, and forming a mixture f; during dropwise adding, enabling the temperature to be 60-100 °C by circulated water or ice bath;

(7), after completely dropwise adding the mixture b, at 60-100°C, dropwise adding the mixture c into the mixture f, controlling the dropwise adding time to be 1-2h, and forming a mixture g; during dropwise adding, enabling the temperature to be 60-100°C by circulated water or ice bath;

(8), after completely dropwise adding the mixture c, at 60-100°C, adding the rest initiator into the mixture g, then regulating the temperature to 80-120°C and performing thermal insulation at such temperature for 1-3h; and


(9), distilling for 0.5-3h at the vacuum degree of -0.09--0.1MPa and the temperature of 90-110°C to remove micro molecular impurities, thus obtaining the acrylate polymer.

[0014] The micromolecular impurities in the present invention refer to the unreacted monomer-1 and monomer-2 and other micromolecular raw material components.

A. Monomers

[0015] The monomers are monomers which vinyl-containing non-ionic monomers which can form a polymer capable of being in an organic solvent, these monomers can be mixed with two by two or more for use, for example, acrylate ester, methylacrylate ester, hydroxyalkyl acrylate, hydroxyalkyl methylacrylate, fumaric acid diester, maleic acid diester, which comprise but are not limited to: methyl acrylate, ethyl acrylate, butyl acrylate, dodecyl acrylate, octadecyl acrylate, iso-octyl acrylate, methyl methacrylate, ethyl methylacrylate, butyl methacrylate, dodecyl methacrylate, octadecyl methylacrylate, iso-octyl methacrylate, hydroxyethyl acrylate, hydroxypropyl acrylate, hydroxyethyl methylacrylate, hydroxypropyl methacrylate, dimethyl fumarate, diethyl fumarate, dibutyl fumarate, diisopropyl fumarate, diethyl maleate, bis(2-ethylhexyl) maleate and dioctyl maleate, and can also comprise styrene, acrylonitrile, acetic acid vinyl ester, acrylic acid and methacrylic acid.

[0016] The monomer-1 is alkyl acrylate or octadecyl methacrylate; the monomer-2 is hydroxyalkyl acrylate or hydroxyalkyl methylacrylate as shown in following general formulas:



wherein, R is H or methyl; R⁰ is a straight chain or a branched chain alkyl of 1-20 carbon atoms, and any position of


which at least contains one hydroxy; those skilled in the art know that the straight chain or a branched chain alkyl of 1-20 carbon atoms, any position of which at least contains one hydroxyl, comprises but is not limited to 1-hydroxyethyl, 2-ethoxy, 1-hydroxypropyl, 2-hydroxypropyl, 3-hydroxypropyl, 1-hydroxyl isopropyl, 2-hydroxyl isopropyl, 3-hydroxyl isopropyl, 1-hydroxyl butyl, 2-hydroxyl butyl, 3-hydroxylbutyl or 4-hydroxylbutyl.

[0017] Preferably, the monomer-1 is iso-octyl acrylate or iso-octyl methacrylate; the monomer-2 is hydroxyethyl acrylate or hydroxyethyl methylacrylate.

[0018] The ratio (mass ratio) of the monomer-1 to the monomer-2 is controlled between 1:1-4:1.

B. Unsaturated terminated polyether


[0019] The unsaturated terminated polyether is as shown in the following general formula:



wherein, R¹ is an alkyl or phenyl with 1-4 carbon atoms or the group as shown in CH₃(CH₂)_xCO-, the subscript x is an integer between 8-16 (namely an acyl formed by a C10-C18 straight chain saturated fatty acid); m and n are integers, and the ratio of the subscript m to n is 1:9-3-2; and the molecular weight of the unsaturated terminated polyether is between 400-2500.

C. Alkene

[0020] The alkene is as shown in the following general formula:



wherein, R² is a straight chain or branched chain alkyl with 4-20 carbon atoms.

D. Diluent

[0021] Proper diluent instances used for the present invention can be selected from but are not limited to di-iso-decylphthalate, diisooctyl adipate, diisooctyl adipate, dioctyl adipate, 2-ethyl-1-hexyl alcohol, isooctanol, polyethylene glycol with the molecular weight of 300-2000, polypropylene glycol with the molecular weight of 300-2000, and polytetramethylene glycol with the molecular weight of 300-2000, which can be singly used or combined for use. Preferably, the diluent is the polypropylene glycol with the molecular weight of 300-2000.

E. Initiator

[0022] Initiator instances used for generating free radicals in the present invention are selected from but are not limited to 2,2'-azobis(2-methyl propionitrile), 2,2'-azobis(2,4-dimethyl valeronitrile), 2,2'-azobis(2-methyl butyronitrile) and benzoyl peroxide, or a redox initiator system can be used, for example, a bromate/sulfide or peroxydisulfate/ferrous system. Preferably, the initiator is benzoyl peroxide.

G. Organic solvent carrier

[0023] Proper organic solvent carrier instances used for the present invention can be selected from but are not limited to di-iso-decylphthalate, diisooctyl adipate, diisooctyl adipate, dioctyl adipate, 2-ethyl-1-hexyl alcohol, isooctanol, polytetramethylene glycol with the molecular weight of 300-2000, polybutylene with the molecular weight of 400-2000, polyethylene glycol with the molecular weight of 300-2000 or polyether ester formed by the polyethylene glycol and fatty acid, and polypropylene glycol with the molecular weight of 300-2000 or polyether ester formed by the polyethylene glycol and fatty acid, which can be singly used or combined for use; and preferably, the organic solvent carrier is the polypropylene glycol with the molecular weight of 300-2000.

H. Hydrophobic particles

[0024] The hydrophobic particles are inorganic hydrophobic particles, and specific instances comprise but are not limited to fatty acid magnesium salt, fatty acid calcium salt, fatty acid aluminum salt, fatty acid zinc salt or hydrophobic precipitation-method white carbon black with the specific area of 20-500m²/g, which can be singly used or combined for use; and preferably, the hydrophobic particles are the hydrophobic precipitation-method white carbon black with the

specific area of 20-500m²/g.

I. Defoaming auxiliaries

5 **[0025]** The defoaming auxiliaries are selected from but are not limited to alkoxy polysiloxane, alkyl modified polysiloxane, fluorine modified polysiloxane, sulphur modified polysiloxane, polyether-modified polysiloxane or hydroxyl modified polysiloxane; and preferably, the defoaming auxiliaries are selected from polyether-modified polysiloxane or alkyl modified polysiloxane.

10 **[0026]** The preparing method for the non-silicon defoaming agent comprises the following steps: uniformly mixing the acrylate polymer, the organic solvent carrier, the hydrophobic particles and the defoaming auxiliaries, thus obtaining the defoaming agent in the present invention.

[0027] At normal temperature, (20-30°C), the acrylate polymer, the organic solvent carrier, the hydrophobic particles and the defoaming auxiliaries are uniformly mixed to prepare the non-silicon defoaming agent of the present invention in a stirring manner or other manners such as ultrasonic.

15 **[0028]** The non-silicon defoaming agent in the present invention is applied to the defoaming and foam inhibiting of systems rich in anionic surfactants, for example, to the defoaming and foam inhibiting of industries of papermaking, water treatment and the like.

The present has the beneficial effects:

20 **[0029]** The defoaming agent in the present invention takes the acrylate polymer as the main active substance, and the defoaming agent has excellent defoaming and foam inhibiting performance, and is particularly suitable for the systems rich in anionic surfactants. According to the acrylate polymer, based on the alkyl acrylate and/or alkyl methacrylate and hydroxyalkyl acrylate and/or hydroxyalkyl methylacrylate, through dropwise adding monomers step by step, the defoaming performance of the polymer is improved, secondly, unsaturated terminated polyether is used for modification to improve the hydrophilia of the acrylate polymer, thus improving the dispersive power of the acrylate polymer in water and further improving the instant defoaming capacity; and finally, by modifying through the alkenes with the carbon atoms of 6-22, the foam inhibiting performance of the defoaming agent is improved due to the hydrophobic performance of the alkenes.

DETAILED DESCRIPTION

[0030] In following embodiments, the instances of the acrylate polymer F are as follows:

Acrylate polymer F	Monomer-1	Monomer-2	Unsaturated terminated polyether	Alkene	Diluent	Initiator
F1	Iso-octyl acrylate	Hydroxyethyl acrylate	B1	C1	PPG 1000	Benzoyl peroxide
F2	Iso-octyl acrylate	Hydroxyethyl methylacrylate	B2	C2	PPG600	Benzoyl peroxide
F3	Iso-octyl methacrylate	Hydroxyethyl acrylate	B3	C3	PPG2000	Benzoyl peroxide
F4	Iso-octyl methacrylate	Hydroxyethyl methylacrylate	B4	C4	PPG400	Benzoyl peroxide

[0031] In following embodiments, the instances of the unsaturated terminated polyether B are as follows:

Unsaturated terminated polyether B	R ¹	m	n
B1	-CH ₃	16	24
B2	-CH ₂ (CH ₂) ₂ CH ₃	2	18
B3	-C ₆ H ₅	3	3
B4	CH ₃ (CH ₂) ₁₀ CO-	12	8

EP 3 620 217 A1

[0032] In following embodiments, the instances of the unsaturated terminated polyether B are as follows:

Alkene C	R ²
C1	-(CH ₂) ₁₃ CH ₃
C2	-(CH ₂) ₇ CH ₃
C3	-(CH ₂) ₁₉ CH ₃
C4	-(CH ₂) ₃ CH ₃

Embodiment 1

[0033]

(1) mixing 80g of iso-octyl acrylate, 100g of hydroxyethyl acrylate, 80g of unsaturated terminated polyether B1 and 4.8g of benzoyl peroxide, and fully dissolving the benzoyl peroxide by stirring to form a mixture a1;

(2) mixing 50g of alkene C1 and 0.8g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture b1;

(3) mixing rest 20g of iso-octyl acrylate and 0.8g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture c1;

(4) adding 0.8g of benzoyl peroxide into 662g of diluent PPG1000 while stirring, after complete adding of the benzoyl peroxide, heating to 80°C, performing thermal insulation for 10min to fully dissolve the benzoyl peroxide and form a mixture d1;

(5) under cooling of circulated cooling water, keeping the temperature of the mixture d1 at 80°C, dropwise adding the mixture a1 into the mixture d1 while stirring, and completely dropwise adding within 3h to form a mixture e1;

(6) after complete dropwise adding of the mixture a1, under cooling of the circulated cooling water, continuing to keep the temperature at 80°C, continuing to dropwise add the mixture b1 into the mixture e1, and completely dropwise adding within 1.5h to form a mixture f1;

(7) after complete dropwise adding of the mixture b1, under cooling of the circulated cooling water, continuing to keep the temperature at 80°C, continuing to dropwise add mixture c1 into the mixture f1, and completely dropwise adding within 1.5h to form a mixture g1;

(8) after complete dropwise adding of the mixture c1, under cooling of the circulated cooling water, continuing to keep the temperature at 80°C, adding rest 0.8g of benzoyl peroxide into the mixture g1, after adding the benzoyl peroxide, controlling the temperature at 120°C, and performing thermal insulation for 1h; and

(9) finally, distilling for 2h at the vacuum degree of -0.09MPa and the temperature of 100°C to remove micromolecular impurities, thus obtaining the acrylate polymer F1.

Embodiment 2

[0034]

(1) mixing 320g of iso-octyl acrylate, 200g of hydroxyethylmethacrylate, 10g of unsaturated terminated polyether B2 and 2.4g of benzoyl peroxide, and fully dissolving the benzoyl peroxide by stirring to form a mixture a2;

(2) mixing 40g of alkene C2 and 0.4g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture b2;

(3) mixing rest 80g of iso-octyl acrylate and 0.4g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture c2;

EP 3 620 217 A1

(4) adding 0.4g of benzoyl peroxide into 346g of diluent PPG600 while stirring, after complete adding of the benzoyl peroxide, heating to 100°C, performing thermal insulation for 10min to fully dissolve the benzoyl peroxide and form a mixture d2;

5 (5) under cooling of circulated cooling water, keeping the temperature of the mixture d2 at 100°C, dropwise adding the mixture a2 into the mixture d2 while stirring, and completely dropwise adding within 5h to form a mixture e2;

(6) after complete dropwise adding of the mixture a2, under cooling of the circulated cooling water, continuing to keep the temperature at 100°C, continuing to dropwise add the mixture b2 into the mixture e2, and completely dropwise adding within 2h to form a mixture f2;

10 (7) after complete dropwise adding of the mixture b2, under cooling of the circulated cooling water, continuing to keep the temperature at 100°C, continuing to dropwise add mixture c2 into the mixture f2, and completely dropwise adding within 1h to form a mixture g2;

15 (8) after complete dropwise adding of the mixture c2, under cooling of the circulated cooling water, continuing to keep the temperature at 100°C, adding rest 0.4g of benzoyl peroxide into the mixture g2, after adding the benzoyl peroxide, controlling the temperature at 100°C, and performing thermal insulation for 3h; and

20 (9) finally, distilling for 1h at the vacuum degree of -0.09MPa and the temperature of 100°C to remove micromolecular impurities, thus obtaining the acrylate polymer F2.

Embodiment 3

25 **[0035]**

(1) mixing 240g of iso-octyl methacrylate, 100g of hydroxyethyl acrylate, 50g of unsaturated terminated polyether B3 and 3.6g of benzoyl peroxide, and fully dissolving the benzoyl peroxide by stirring to form a mixture a3;

30 (2) mixing 80g of alkene C3 and 0.6g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture b3;

(3) mixing rest 60g of iso-octyl methacrylate and 0.6g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture c3;

35 (4) adding 0.6g of benzoyl peroxide into 464g of diluent PPG2000 while stirring, after complete adding of the benzoyl peroxide, heating to 60°C, performing thermal insulation for 20min to fully dissolve the benzoyl peroxide and form a mixture d3;

40 (5) under cooling of circulated cooling water, keeping the temperature of the mixture d3 at 60 °C, dropwise adding the mixture a3 into the mixture d3 while stirring, and completely dropwise adding within 1h to form a mixture e3;

(6) after complete dropwise adding of the mixture a3, under cooling of the circulated cooling water, continuing to keep the temperature at 60°C, continuing to dropwise add the mixture b3 into the mixture e3, and completely dropwise adding within 1h to form a mixture f3;

45 (7) after complete dropwise adding of the mixture b3, under cooling of the circulated cooling water, continuing to keep the temperature at 60°C, continuing to dropwise add mixture c3 into the mixture f3, and completely dropwise adding within 2h to form a mixture g3;

50 (8) after complete dropwise adding of the mixture c3, under cooling of the circulated cooling water, continuing to keep the temperature at 60°C, adding rest 0.6g of benzoyl peroxide into the mixture g3, after adding the benzoyl peroxide, controlling the temperature at 80°C, and performing thermal insulation for 2h; and

55 (9) finally, distilling for 3h at the vacuum degree of -0.1MPa and the temperature of 100°C to remove micromolecular impurities, thus obtaining the acrylate polymer F3.

EP 3 620 217 A1

Embodiment 4

[0036]

- 5 (1) mixing 320g of iso-octyl methacrylate, 100g of hydroxyethyl methacrylate, 40g of unsaturated terminated polyether B4 and 3g of benzoyl peroxide, and fully dissolving the benzoyl peroxide by stirring to form a mixture a4;
- (2) mixing 10g of alkene C4 and 0.5g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture b4;
- 10 (3) mixing rest 80g of iso-octyl methacrylate and 0.5g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture c4;
- (4) adding 0.5g of benzoyl peroxide into 445g of diluent PPG400 while stirring, after complete adding of the benzoyl peroxide, heating to 90 °C, performing thermal insulation for 15min to fully dissolve the benzoyl peroxide and form a mixture d4;
- 15 (5) under cooling of circulated cooling water, keeping the temperature of the mixture d4 at 90°C, dropwise adding the mixture a4 into the mixture d4 while stirring, and completely dropwise adding within 2h to form a mixture e4;
- 20 (6) after complete dropwise adding of the mixture a4, under cooling of the circulated cooling water, continuing to keep the temperature at 90°C, continuing to dropwise add the mixture b4 into the mixture e4, and completely dropwise adding within 2h to form a mixture f4;
- 25 (7) after complete dropwise adding of the mixture b4, under cooling of the circulated cooling water, continuing to keep the temperature at 90°C, continuing to dropwise add mixture c4 into the mixture f4, and completely dropwise adding within 2h to form a mixture g4;
- 30 (8) after complete dropwise adding of the mixture c4, under cooling of the circulated cooling water, continuing to keep the temperature at 90°C, adding rest 0.5g of benzoyl peroxide into the mixture g4, after adding the benzoyl peroxide, controlling the temperature at 90°C, and performing thermal insulation for 2h; and
- (9) finally, distilling for 0.5h at the vacuum degree of -0.1MPa and the temperature of 100°C to remove micromolecular impurities, thus obtaining the acrylate polymer F4.
- 35

Embodiment 5

[0037]

40

AH1	
Acrylate polymer F1	60
PPG 1000	30
Hydrophobic precipitation-method white carbon black Sipernat®D10	5
Alkyl modified polysiloxane	5
$\text{CH}_3(\text{CH}_2)_{15}\text{Si}(\text{CH}_3)_2[\text{OSi}(\text{CH}_3)_2]_{20}\text{OSi}(\text{CH}_3)_2(\text{CH}_2)_{15}\text{CH}_3$	

45

- 50 [0038] The acrylate polymer F1 prepared in the embodiment 1, PPG1000, hydrophobic precipitation-method white carbon black Sipernat®D10 and alkyl modified polysiloxane are mixed uniformly according to above proportion to prepare a non-silicon defoaming agent AH1.

Embodiment 6

55

[0039]

EP 3 620 217 A1

AH2	
Acrylate polymer F2	20
PPG600	60
Hydrophobic precipitation-method white carbon black Sipernat®D 13	10
Alkyl modified polysiloxane $\text{CH}_3(\text{CH}_2)_9\text{Si}(\text{CH}_3)_2[\text{OSi}(\text{CH}_3)_2]_{50}\text{OSi}(\text{CH}_3)_2(\text{CH}_2)_9\text{CH}_3$	10

[0040] The acrylate polymer F2 prepared in the embodiment 2, PPG600, hydrophobic precipitation-method white carbon black Sipernat®D13 and alkyl modified polysiloxane are mixed uniformly according to above proportion to prepare a non-silicon defoaming agent AH2.

Embodiment 7

[0041]

AH3	
Acrylate polymer F3	60
PPG2000	10
Hydrophobic precipitation-method white carbon black Sipernat®D17	10
Alkyl modified polysiloxane $\text{CH}_3(\text{CH}_2)_{11}\text{Si}(\text{CH}_3)_2[\text{OSi}(\text{CH}_3)_2]_{45}\text{OSi}(\text{CH}_3)_2(\text{CH}_2)_{11}\text{CH}_3$	20

[0042] The acrylate polymer F3 prepared in the embodiment 3, PPG2000, hydrophobic precipitation-method white carbon black Sipernat®D17 and alkyl modified polysiloxane are mixed uniformly according to above proportion to prepare a non-silicon defoaming agent AH3.

Embodiment 8

[0043]

AH4	
Acrylate polymer F4	47.5
PPG400	50
Hydrophobic precipitation-method white carbon black Zeofoam®163-2	0.5
Polyether-modified polysiloxane	2
$\text{CH}_3(\text{PO})_{12}(\text{EO})_{18}(\text{CH}_2)_3\text{Si}(\text{CH}_3)_2[\text{OSi}(\text{CH}_3)_2]_{80}\text{OSi}(\text{CH}_3)_2(\text{CH}_2)_3(\text{EO})_{18}(\text{PO})_{12}\text{CH}_3$	

[0044] The acrylate polymer F4 prepared in the embodiment 4, PPG400, hydrophobic precipitation-method white carbon black Zeofoam®163-2 and polyether-modified polysiloxane are mixed uniformly according to above proportion to prepare a non-silicon defoaming agent AH4.

Contrast example 1

[0045]

(1) mixing 144g of iso-octyl acrylate, 100g of hydroxyethyl acrylate and 4.8g of benzoyl peroxide, and fully dissolving the benzoyl peroxide by stirring to form a mixture a-l;

(2) mixing 50g of alkene Cl and 0.8g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture b-l;

EP 3 620 217 A1

(3) mixing rest 36g of iso-octyl acrylate and 0.8g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture c-I;

5 (4) adding 0.8g of benzoyl peroxide into 662g of diluent PPG-1000 while stirring, after complete adding of the benzoyl peroxide, heating to 80°C, performing thermal insulation for 10min to fully dissolve the benzoyl peroxide and form a mixture d-I;

10 (5) under cooling of circulated cooling water, keeping the temperature of the mixture d-I at 80°C, dropwise adding the mixture a-I into the mixture d-I while stirring, and completely dropwise adding within 3h to form a mixture e-I;

(6) after complete dropwise adding of the mixture a-I, under cooling of the circulated cooling water, continuing to keep the temperature at 80°C, continuing to dropwise add the mixture b-I into the mixture e-I, and completely dropwise adding within 1h to form a mixture f-I;

15 (7) after complete dropwise adding of the mixture b-I, under cooling of the circulated cooling water, continuing to keep the temperature at 80°C, continuing to dropwise add mixture c-I into the mixture f-I, and completely dropwise adding within 1h to form a mixture g-I;

20 (8) after complete dropwise adding of the mixture c-I, under cooling of the circulated cooling water, continuing to keep the temperature at 80°C, adding rest 0.8g of benzoyl peroxide into the mixture g-I, after adding the benzoyl peroxide, controlling the temperature at 100°C, and performing thermal insulation for 2h; and

25 (9) finally, distilling for 2h at the vacuum degree of -0.09MPa and the temperature of -100°C to remove micromolecular impurities, thus obtaining the acrylate polymer F-I.

Contrast example 2

[0046]

30 (1) mixing 320g of iso-octyl acrylate, 200g of hydroxyethylmethacrylate, 10g of unsaturated terminated polyether B2 and 2.4g of benzoyl peroxide, and fully dissolving the benzoyl peroxide by stirring to form a mixture a-II;

35 (2) mixing rest 80g of iso-octyl acrylate and 0.4g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture c-II;

(3) adding 0.4g of benzoyl peroxide into 386.4g of diluent PPG600 while stirring, after complete adding of the benzoyl peroxide, heating to 100°C, performing thermal insulation for 10min to fully dissolve the benzoyl peroxide and form a mixture d-II;

40 (4) under cooling of circulated cooling water, keeping the temperature of the mixture d-II at 100°C, dropwise adding the mixture a-II into the mixture d-II while stirring, and completely dropwise adding within 5h to form a mixture e-II;

45 (5) after complete dropwise adding of the mixture a-II, under cooling of the circulated cooling water, continuing to keep the temperature at 100°C, continuing to dropwise add the mixture c-II into the mixture e-II, and completely dropwise adding within 1h to form a mixture g-II;

50 (6) after complete dropwise adding of the mixture c-II, under cooling of the circulated cooling water, continuing to keep the temperature at 100°C, adding rest 0.4g of benzoyl peroxide into the mixture g-II, after adding the benzoyl peroxide, controlling the temperature at 100°C, and performing thermal insulation for 2h; and

(7) finally, distilling for 1h at the vacuum degree of -0.09MPa and the temperature of 100°C to remove micromolecular impurities, thus obtaining the acrylate polymer F-II.

55 Contrast example 3

[0047]

(1) mixing 240g of iso-octyl methacrylate, 100g of hydroxyethyl acrylate and 3.6g of benzoyl peroxide, and fully

EP 3 620 217 A1

dissolving the benzoyl peroxide by stirring to form a mixture a-III;

(2) mixing rest 60g of iso-octyl methylacrylate and 0.6g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture c-III;

(3) adding 0.6g of benzoyl peroxide into 594.6g of diluent PPG2000 while stirring, after complete adding of the benzoyl peroxide, heating to 60°C, performing thermal insulation for 10min to fully dissolve the benzoyl peroxide and form a mixture d-III;

(4) under cooling of circulated cooling water, keeping the temperature of the mixture d-III at 60°C, dropwise adding the mixture a-III into the mixture d-III while stirring, and completely dropwise adding within 1h to form a mixture e-III;

(5) after complete dropwise adding of the mixture a-III, under cooling of the circulated cooling water, continuing to keep the temperature at 60°C, continuing to dropwise add the mixture c-III into the mixture f-III, and completely dropwise adding within 2h to form a mixture g-III;

(6) after complete dropwise adding of the mixture c-III, under cooling of the circulated cooling water, continuing to keep the temperature at 60°C, adding rest 0.6g of benzoyl peroxide into the mixture g-III, after adding the benzoyl peroxide, controlling the temperature at 120°C, and performing thermal insulation for 2h; and

(7) finally, distilling for 3h at the vacuum degree of -0.1MPa and the temperature of 100°C to remove micromolecular impurities, thus obtaining the acrylate polymer F-III.

Contrast example 4

[0048]

(1) mixing 400g of iso-octyl methylacrylate, 100g of hydroxyethyl methylacrylate, 40g of unsaturated terminated polyether B4 and 3g of benzoyl peroxide, and fully dissolving the benzoyl peroxide by stirring to form a mixture a-IV;

(2) mixing 10g of alkene C4 and 0.5g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture b-IV;

(3) adding 0.5g of benzoyl peroxide into 445.5g of diluent PPG400 while stirring, after complete adding of the benzoyl peroxide, heating to 90°C, performing thermal insulation for 10min to fully dissolve the benzoyl peroxide and form a mixture d-IV;

(4) under cooling of circulated cooling water, keeping the temperature of the mixture d-IV at 90 °C, dropwise adding the mixture a-IV into the mixture d-IV while stirring, and completely dropwise adding within 2h to form a mixture e-IV;

(5) after complete dropwise adding of the mixture a-IV, under cooling of the circulated cooling water, continuing to keep the temperature at 90°C, continuing to dropwise add the mixture b-IV into the mixture e-IV, and completely dropwise adding within 2h to form a mixture f-IV;

(6), after complete dropwise adding of the mixture b-IV, under cooling of the circulated cooling water, continuing to keep the temperature at 90°C, adding rest 0.5g of benzoyl peroxide into the mixture f-IV, controlling the temperature at 90°C, and performing thermal insulation for 2h; and

(7) finally, distilling for 0.5h at the vacuum degree of -0.1MPa and the temperature of 100°C to remove micromolecular impurities, thus obtaining the acrylate polymer F-IV.

Contrast example 5

[0049]

(1) mixing 80g of iso-octyl acrylate, 100g of hydro xyethyl methylacrylate, 80g of unsaturated terminated polyether B2, 50g of alkene C2 and 5.6g of benzoyl peroxide, and fully dissolving the benzoyl peroxide by stirring to form a mixture a-V;

EP 3 620 217 A1

(2) mixing rest 20g of iso-octyl acrylate and 0.8g of benzoyl peroxide through stirring to fully dissolve the benzoyl peroxide and form a mixture c-V;

(3) adding 0.8g of benzoyl peroxide into 662g of diluent PPG600 while stirring, after complete adding of the benzoyl peroxide, heating to 100°C, performing thermal insulation for 10min to fully dissolve the benzoyl peroxide and form a mixture d-V;

(4) under cooling of circulated cooling water, keeping the temperature of the mixture d-V at 100°C, dropwise adding the mixture a-V into the mixture d-V while stirring, and completely dropwise adding within 5h to form a mixture e-V;

(5) after complete dropwise adding of the mixture a-V, under cooling of the circulated cooling water, continuing to keep the temperature at 100°C, continuing to dropwise add the mixture c-V into the mixture e-V, and completely dropwise adding within 1h to form a mixture g-V;

(6) after complete dropwise adding of the mixture c-V, under cooling of the circulated cooling water, continuing to keep the temperature at 100°C, adding rest 0.8g of benzoyl peroxide into the mixture g-V, after adding the benzoyl peroxide, controlling the temperature at 100°C, and performing thermal insulation for 2h; and

(7) finally, distilling for 1h at the vacuum degree of -0.09MPa and the temperature of 100°C to remove micromolecular impurities, thus obtaining the acrylate polymer F-V.

Contrast example 6

[0050]

AH-I	
Acrylate polymer F-I	60
PPG1000	30
Hydrophobic precipitation-method white carbon black Zeofoam®163-2	5
Alkyl modified polysiloxane (same as embodiment 5)	5

[0051] The acrylate polymer F-I prepared in the contrast example 1, PPG1000, hydrophobic precipitation-method white carbon black Zeofoam® 163-2 and alkyl modified polysiloxane are mixed uniformly according to above proportion to prepare a defoaming agent AH-I.

Contrast example 7

[0052]

AH-II	
Acrylate polymer F-II	20
PPG600	60
Hydrophobic precipitation-method white carbon black Sipernat®D 10	10
Alkyl modified polysiloxane (same as embodiment 6)	10

[0053] The acrylate polymer F-II prepared in the contrast example 2, PPG600, hydrophobic precipitation-method white carbon black Sipernat®D10 and alkyl modified polysiloxane are mixed uniformly according to above proportion and stirred for 0.5-2h under normal temperature to prepare a defoaming agent AH-II.

Contrast example 8

[0054]

EP 3 620 217 A1

AH-III	
Acrylate polymer F-III	60
PPG2000	10
Hydrophobic precipitation-method white carbon black Sipernat®D13	10
Alkyl modified polysiloxane (same as embodiment 7)	20

[0055] The acrylate polymer F-III prepared in the contrast example 3, PPG2000, hydrophobic precipitation-method white carbon black Sipernat®D13 and alkyl modified polysiloxane are mixed uniformly according to above proportion to prepare a defoaming agent AH-III.

Contrast example 9

[0056]

AH-IV	
Acrylate polymer F-IV	47.5
PPG400	50
Hydrophobic precipitation-method white carbon black Sipernat®D 17	0.5
Alkyl modified polysiloxane (same as embodiment 7)	2

[0057] The acrylate polymer F-IV prepared in the contrast example 4, PPG400, hydrophobic precipitation-method white carbon black Sipernat®D 17 and alkyl modified polysiloxane are mixed uniformly according to above proportion to prepare a defoaming agent AH-IV.

Contrast example 10

[0058]

AH-V	
Acrylate polymer F-V	20
PPG600	60
Hydrophobic precipitation-method white carbon black Sipernat®D 17	10
Alkyl modified polysiloxane (same as embodiment 5)	10

[0059] The acrylate polymer F-V prepared in the contrast example 5, PPG600, hydrophobic precipitation-method white carbon black Sipernat®D 17 and alkyl modified polysiloxane are mixed uniformly according to above proportion to prepare a defoaming agent AH-V.

Contrast example 11

[0060]

AH-VI	
Mineral oil	85
White carbon black Sipernat®D10	8
EBS	3
Oleic acid polyoxyethylene(10EO)ether	4

EP 3 620 217 A1

[0061] The mineral oil, white carbon black Sipernat®D10, EBS and Oleic acid polyoxyethylene(10EO)ether are mixed uniformly according to above proportion to prepare a defoaming agent AH-VI.

Contrast example 12

5

[0062] Compared with the embodiment C23 in Patent CN101189282B, in the embodiment C23, mainly the silicone grease and silicone polyether are compounded to prepare a defoaming agent AH-VII. Specifically:

10

AH-VII	
Siloxane defoaming agent (selected from the siloxane defoaming agent A3 in Patent CN101189282)	20
Polysiloxane copolymer (selected from the polymer 1 in Patent CN101189282)	10
Dehydrated sorbitol fatty acid ester	10
Water	60

15

Contrast example 13

20

[0063]

AH-VIII	
Acrylate polymer (selected from Patent US5152925A)	60
PPG1000	30
Hydrophobic precipitation-method white carbon black Sipernat®D13	5
Alkyl modified polysiloxane (same as the embodiment 5)	5

25

30

Contrast example 14

[0064] The copolymer prepared in the embodiment 1 in Patent CN102428142B replaces the acrylate polymer F1 in the embodiment A to prepare a defoaming agent AH-IX.

35

AH-IX	
Acrylate polymer (selected from Patent CN102428142B)	60
PPG1000	30
Hydrophobic precipitation-method white carbon black Sipernat®D10	5
Alkyl modified polysiloxane (same as the embodiment 5)	5

40

Contrast example 15

45

[0065] A defoaming agent AH-X is prepared according to a formula in a table 4 in Patent CN102428142B.

AH-X	
PPG 1000	58.5
Hydrophobic silica Sipernat®D10	3
Acrylate polymer (selected from the embodiment 1 in Patent CN102428142B)	23.5
Polyether-modified polysiloxane silicone surfactant	10
Alkyl-modified siloxane silicone wax	5

50

55

Defoaming and foam inhibiting performance test

EP 3 620 217 A1

Test method

[0066] 600mL of sodium dodecyl benzene sulfonate water solution with the mass percent of 1% is added into a circulation faming instrument with a glass tube having the scale of 0-500mL and the inner diameter of 5cm, the liquid level reaches to the lowest scale "0ml", then the temperature is set as 80 °C, the flow is set as 6L/min, the voltage is set as 220V, then a temperature control switch is switched on to heat the sodium dodecyl benzene sulfonate water solution to set temperature, then a circulating pump is opened to burst and foam, 0.2mL of defoaming agent is added after the foam rises to the 350mL, and the change of the foam height along with time is recorded. If the time that the foam reaches the lowest scale is shorter and the reached scale is lower, the instant defoaming performance of the defoaming agent is better; and if the time that the foam reaches the 350mL position is longer, the foam inhibiting performance of the defoaming agent is better.

Table 1 Result of the defoaming and foam inhibiting performance test

Time/s	Foam height /mL													
	AH1	AH2	AH3	AH4	AH-I	AH-II	AH-III	AH-IV	AH-V	AH-VI	AH-VII	AH-VIII	AH-IX	AH-X
0	350	350	350	350	350	350	350	350	350	350	350	350	350	350
5	200	220	210	200	310	210	320	250	280	270	250	240	250	240
10	180	180	180	190	280	180	280	230	260	250	220	200	200	200
15	170	170	180	160	260	160	250	200	200	230	190	190	180	170
30	160	160	170	160	210	150	200	180	180	200	180	180	180	170
60	150	160	170	160	200	150	180	180	180	210	180	180	170	160
90	150	150	170	150	180	140	170	160	160	250	160	170	160	160
120	140	150	160	140	160	130	170	160	160	280	150	170	160	150
150	140	150	150	140	150	150	190	160	160	310	150	160	150	150
180	130	150	15	150	130	150	190	150	170	350	150	150	150	140
210	130	140	150	160	150	170	210	160	170		150	150	140	140
240	130	140	150	160	160	190	250	170	160		150	150	140	140
270	140	150	160	160	180	210	280	180	160		160	150	140	140
300	140	160	160	180	180	250	300	180	160		170	160	150	150
330	150	160	170	190	200	270	320	180	190		170	170	170	160
360	170	170	180	190	210	300	350	180	200		180	180	180	180
390	190	180	190	200	230	320		200	210		200	190	190	200
420	210	210	210	230	250	350		210	230		230	210	220	220
450	230	240	220	250	280			220	260		260	230	230	230
480	250	260	250	280	310			250	280		280	250	250	250
510	290	290	270	310	330			280	320		310	290	280	280
540	300	310	300	320	350			300	350		350	310	310	310
570	320	330	320	330				350				350	350	350
600	330	350	350	350										

[0067] It can be seen from above data that compared with the polymer defoaming agent AH-I not prepared by modifying through the unsaturated terminated polyether, the defoaming agents AH1-AH4 in the present invention improve the instant defoaming capacity of the defoaming agent; compared with the polymer defoaming agent AH-II not prepared by modifying through the alkene, the defoaming agents AH1-AH4 further improve the foam inhibiting capacity; compared with the polymer defoaming agent AH-III not prepared by modifying through the unsaturated terminated polyether or the alkene, the defoaming agents AH1-AH4 in the present invention greatly improve the instant defoaming capacity and the

foam inhibiting capacity; compared with the polymer defoaming agent AH-IV not prepared by adding the acrylate monomer step by step to form a polymer with one hydrophobic end, the defoaming agents AH1-AH4 further improve the instant defoaming capacity; compared with the polymer AH-V prepared by mixing and dropwise adding instead of dropwise adding the unsaturated terminated polyether and the alkene step by step, the defoaming agents AH1-AH4 only improve the instant defoaming capacity and improve the foam inhibiting capacity; compared with the existing mineral oil defoaming agent AH-VI, the existing organic silicon defoaming agent AH-VII taking the silicone grease as the active substance, the defoaming agents AH1-AH4 are obviously improved in the instant defoaming capacity and foam inhibiting capacity; and compared with the existing acrylate polymer defoaming agent, the defoaming agents AH1-AH4 are obviously improved in the instant defoaming capacity and foam inhibiting capacity by modifying through the unsaturated terminated polyether and the alkene and process changing.

[0068] The present invention belongs to the technical field of fine chemical engineering, and discloses a non-silicon defoaming agent, comprising an acrylate polymer, an organic solvent carrier, hydrophobic particles and defoaming auxiliaries; and the acrylate polymer is prepared from following raw material components: monomer-1, monomer-2, unsaturated terminated polyether, alkene, diluent and initiator. The present invention further discloses a preparing method for the non-silicon defoaming agent. The present invention further discloses the application of the non-silicon defoaming agent to the defoaming and foam inhibiting in systems rich in anionic surfactants. The defoaming agent in the present invention takes the acrylate polymer as the main active substance and has excellent defoaming and foam inhibiting performance. By dropwise adding monomers, the defoaming performance of the acrylate polymer is improved, by using unsaturated terminated polyether to modify, the hydrophilia of the acrylate polymer is improved, the instant defoaming capacity is further improved, and by the alkene with the carbon atoms of 6-22 to modify, the foam inhibiting performance of the defoaming agent is improved.

Claims

1. A non-silicon defoaming agent, **characterized by** comprising an acrylate polymer, an organic solvent carrier, hydrophobic particles and defoaming auxiliaries; the use level of the acrylate polymer is 15-70% of the total mass of the defoaming agent, the use level of the organic solvent carrier is 10-70% of the total mass of the defoaming agent, the use level of the hydrophobic particles is 0.1-15% of the total mass of the defoaming agent, and the use level of the defoaming auxiliaries is 1-25% of the total mass of the defoaming agent; the acrylate polymer is prepared from following raw material components: monomer-1, monomer-2, unsaturated terminated polyether, alkene, diluent and initiator; the total use level of the monomer-1 and monomer-2 is 20-70% of the total mass of the raw material components, the use level of the unsaturated terminated polyether is 1-10% of the total mass of the raw material components, the use level of the alkene is 1-8% of the total mass of the raw material components the use level of the diluent is 20-75% of the total mass of the raw material components, and the use level of the initiator is 0.2-1 % of the total mass of the raw material components.
2. The non-silicon defoaming agent according to claim 1, **characterized in that** the use level of the acrylate polymer is 20-60% of the total mass of the defoaming agent, the use level of the organic solvent carrier is 10-70% of the total mass of the defoaming agent, the use level of the hydrophobic particles is 0.5-10% of the total mass of the defoaming agent, and the use level of the defoaming auxiliaries is 2-20% of the total mass of the defoaming agent.
3. The non-silicon defoaming agent according to claim 1, **characterized in that** the total use level of the monomer-1 and monomer-2 is 20-60% of the total mass of the raw material components, the use level of the unsaturated terminated polyether is 1-8% of the total mass of the raw material components, the use level of the alkene is 1-8% of the total mass of the raw material components the use level of the diluent is 30-70% of the total mass of the raw material components, and the use level of the initiator is 0.4-0.8% of the total mass of the raw material components.
4. The non-silicon defoaming agent according to claim 1, **characterized in that** a preparing method of the acrylate polymer comprises:
 - (1), mixing the monomer-1, monomer-2 and unsaturated terminated polyether which are 70-90% of the total use level of the monomer-1 with the initiator which is 50-70% of the total use level of the initiator to cause the initiator to be fully dissolved and form a mixture a;
 - (2), mixing the alkene with the initiator which is 5-15% of the total use level of the initiator to fully dissolve the initiator and form a mixture b;
 - (3), mixing the rest monomer-1 with the initiator which is 2-15% of the total use level of the initiator to fully dissolve the initiator and form a mixture c;

EP 3 620 217 A1

(4), at 60-100°C, fully dissolving the initiator which is 8-15 of the total use level of the initiator in the diluent, and releasing free radicals to form a mixture d;

(5), at 60-100°C, in order to prevent the generation of excessive free radicals which cause severe polymerization and further cause danger, dropwise adding the mixture a into the mixture d, controlling the dropwise adding time to be 1-5h, and forming a mixture e; during dropwise adding, enabling the temperature to be 60-100°C by circulated water or ice bath;

(6), after completely dropwise adding the mixture a, at 60-100 °C, similarly, in order to prevent the generation of excessive free radicals which cause severe polymerization and further cause danger, dropwise adding the mixture b into the mixture e, controlling the dropwise adding time to be 1-2h, and forming a mixture f; during dropwise adding, enabling the temperature to be 60-100 °C by circulated water or ice bath;

(7), after completely dropwise adding the mixture b, at 60-100°C, dropwise adding the mixture c into the mixture f, controlling the dropwise adding time to be 1-2h, and forming a mixture g; during dropwise adding, enabling the temperature to be 60-100°C by circulated water or ice bath;


(8), after completely dropwise adding the mixture c, at 60-100°C, adding the rest initiator into the mixture g, then regulating the temperature to 80-120°C and performing thermal insulation at such temperature for 1-3h; and

(9), distilling for 0.5-3h at the vacuum degree of -0.09--0.1MPa and the temperature of 90-110°C to remove micro molecular impurities, thus obtaining the acrylate polymer.

5. The non-silicon defoaming agent according to claim 1, **characterized in that** a ratio of the monomer-1 to the monomer-2 is between 1:1-4:1;

the monomer-1 is alkyl acrylate or octadecyl methacrylate;


the monomer-2 is hydroxyalkyl acrylate or hydroxyalkyl methacrylate as shown in following general formulas:



wherein, R is H or methyl; R⁰ is a straight chain or a branched chain alkyl of 1-20 carbon atoms, and any position of which at least contains one hydroxyl.


6. The non-silicon defoaming agent according to claim 5, **characterized in that** the monomer-1 is iso-octyl acrylate or iso-octyl methacrylate; the monomer-2 is hydroxyethyl acrylate or hydroxyethyl methacrylate.

7. The non-silicon defoaming agent according to claim 1, **characterized in that** the unsaturated terminated polyether is as shown in the following general formula:



wherein, R¹ is an alkyl or phenyl with 1-4 carbon atoms or the group as shown in CH₃(CH₂)_xCO-, x is an integer between 8-16; the ratio of m to n is 1:9-3-2; and the molecular weight of the unsaturated terminated polyether is between 400-2500;

the alkene is as shown in the following general formula:



wherein, R² is a straight chain or branched chain alkyl with 4-20 carbon atoms;

the diluent is selected from one or a mixture of at least two of di-iso-decylphthalate, diisooctyl adipate, diisooctyl adipate, dioctyl adipate, 2-ethyl-1-hexyl alcohol, isooctanol, polyethylene glycol with the molecular weight of 300-2000, polypropylene glycol with the molecular weight of 300-2000, and polytetramethylene glycol with the molecular weight of 300-2000;

the initiator is selected from 2,2'-azobis(2-methyl propionitrile), 2,2'-azobis(2,4-dimethyl valeronitrile), 2,2'-azobis(2-methyl butyronitrile) and benzoyl peroxide, or a redox initiator system can be used;

the organic solvent carrier is selected from one or a mixture of at least two of di-iso-decylphthalate, diisooctyl adipate,

diisooctyl adipate, dioctyl adipate, 2-ethyl-1-hexyl alcohol, isooctanol, polytetramethylene glycol with the molecular weight of 300-2000, polybutylene with the molecular weight of 400-2000, polyethylene glycol with the molecular weight of 300-2000 or polyether ester formed by the polyethylene glycol and fatty acid, and polypropylene glycol with the molecular weight of 300-2000 or polyether ester formed by the polyethylene glycol and fatty acid;

the hydrophobic particles are inorganic hydrophobic particles, are selected from one or a mixture of at least two of fatty acid magnesium salt, fatty acid calcium salt, fatty acid aluminum salt, fatty acid zinc salt or hydrophobic precipitation-method white carbon black with the specific area of 20-500m²/g.; and

the defoaming auxiliaries are selected from one of alkoxy polysiloxane, alkyl modified polysiloxane, fluorine modified polysiloxane, sulphur modified polysiloxane, polyether-modified polysiloxane or hydroxyl modified polysiloxane.

8. The non-silicon defoaming agent according to claim 7, **characterized in that** the diluent is polypropylene glycol with the molecular weight of 300-2000;

the initiator is benzoyl peroxide;

the organic solvent carrier is polypropylene glycol with the molecular weight of 300-2000; the hydrophobic particles are hydrophobic precipitation-method white carbon black with the specific area of 20-500m²/g; and

the defoaming auxiliaries are polyether-modified polysiloxane or hydroxyl modified polysiloxane.

9. The preparing method for the non-silicon defoaming agent according to claim 1, **characterized by** comprising:

uniformly mixing the acrylate polymer, the organic solvent carrier, the hydrophobic particles and the defoaming auxiliaries to obtain the defoaming agent.

10. Application of the non-silicon defoaming agent according to claim 1 in systems rich in anionic surfactants, such as the application to the defoaming and foam inhibiting in industries of papermaking, water treatment, textile and the like.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/CN2017/117874

5

A. CLASSIFICATION OF SUBJECT MATTER

B01D 19/04 (2006.01) i; C08F 220/18 (2006.01) i; C08F 283/06 (2006.01) i; C08F 210/14 (2006.01) i
According to International Patent Classification (IPC) or to both national classification and IPC

10

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B01D; B01F; C08F

15

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

CNABS, CNTXT, CNKI, DWPI, SIPOABS: 四新科技, 张振, 刘杨, 曹添, 非硅, 非有机硅, 消泡, 抑泡, 脱气, 丙烯酸酯, 聚酯, 稀, non-silicon, defoamer, antifoamer, foam suppressant, acrylate, polyether, olefin

20

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CN 102428142 A (MARTIN, J. et al.), 25 April 2012 (25.04.2012), claims 1-16 and 35, and description, paragraphs [0014]-[0062]	1-10
A	CN 105744998 A (KEMIRA OYJ), 06 July 2016 (06.07.2016), entire document	1-10
A	US 2017015897 A1 (MEXICANO INST PETROL), 19 January 2017 (19.01.2017), entire document	1-10

30

35

 Further documents are listed in the continuation of Box C.
 See patent family annex.

* Special categories of cited documents:	“T” later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
“A” document defining the general state of the art which is not considered to be of particular relevance	“X” document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
“E” earlier application or patent but published on or after the international filing date	“Y” document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
“L” document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	“&” document member of the same patent family
“O” document referring to an oral disclosure, use, exhibition or other means	
“P” document published prior to the international filing date but later than the priority date claimed	

50

Date of the actual completion of the international search 14 March 2018	Date of mailing of the international search report 23 March 2018
Name and mailing address of the ISA State Intellectual Property Office of the P. R. China No. 6, Xitucheng Road, Jimenqiao Haidian District, Beijing 100088, China Facsimile No. (86-10) 62019451	Authorized officer WAN, Junjie Telephone No. (86-10) 62085023

55

Form PCT/ISA/210 (second sheet) (July 2009)

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.
PCT/CN2017/117874

5
10
15
20
25
30
35
40
45
50
55

Patent Documents referred in the Report	Publication Date	Patent Family	Publication Date
CN 102428142 A	25 April 2012	CN 102428142 B	07 May 2014
		US 8236889 B2	07 August 2012
		WO 2010132262 A2	18 November 2010
		WO 2010132262 A3	07 April 2011
		CA 2758575 C	12 August 2014
		EP 2430095 A2	21 March 2012
		ZA 201107476 B	27 June 2012
		RU 2011142828 A	20 June 2013
		RU 2543481 C2	10 March 2015
		CA 2758575 A1	18 November 2010
		US 2010292380 A1	18 November 2010
		US 2012264863 A1	18 October 2012
		US 8507597 B2	13 August 2013
		ID 201205354 A	27 December 2012
IN 288282 B	13 October 2017		
CN 105744998 A	06 July 2016	RU 2016124127 A	25 December 2017
		EP 3071310 A1	28 September 2016
		US 2016288020 A1	06 October 2016
		CL 2016001174 A1	02 December 2016
		WO 2015071551 A1	21 May 2015
		CA 2928636 A1	21 May 2015
US 2017015897 A1	19 January 2017	BR 112016010445 A2	08 August 2017
		MX 2015009234 A	16 January 2017
		CA 2934708 A1	17 January 2017

Form PCT/ISA/210 (patent family annex) (July 2009)

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- CN 10051850 C **[0004]**
- CN 101991975 B **[0004]**
- CN 101362063 **[0005]**
- CN 102976429 B **[0005]**
- CN 103603215 A **[0006]**
- CN 102002242 B **[0006]**
- CN 101638871 B **[0007]**
- CN 102126763 A **[0007]**
- US 5152925 A **[0008] [0063]**
- CN 102428142 B **[0008] [0064] [0065]**
- CN 101189282 B **[0062]**
- CN 101189282 **[0062]**