



US009780135B2

(12) **United States Patent**  
**Nagata et al.**

(10) **Patent No.:** **US 9,780,135 B2**  
(45) **Date of Patent:** **Oct. 3, 2017**

(54) **IMAGE PICKUP UNIT AND METHOD OF MANUFACTURING THE SAME**

(56) **References Cited**

(71) Applicant: **Sony Corporation**, Tokyo (JP)  
(72) Inventors: **Masaya Nagata**, Kanagawa (JP); **Taizo Takachi**, Kanagawa (JP)  
(73) Assignee: **Sony Corporation**, Tokyo (JP)  
(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 261 days.

U.S. PATENT DOCUMENTS

7,420,754 B2 \* 9/2008 Nagasaka ..... G02B 6/4201 257/433  
2003/0068850 A1 \* 4/2003 Fukuda et al. .... 438/200  
2005/0169620 A1 \* 8/2005 Minamio ..... H01L 27/14618 257/E25.032  
2007/0267712 A1 \* 11/2007 Fujita et al. .... 257/443  
2008/0296573 A1 \* 12/2008 Suehiro et al. .... 257/53  
2009/0294779 A1 \* 12/2009 Ida ..... H01L 27/14618 257/82  
2011/0147782 A1 \* 6/2011 Sano et al. .... 257/98  
2013/0075850 A1 \* 3/2013 Patterson ..... H01L 31/0232 257/432  
2013/0119501 A1 \* 5/2013 Yoshida ..... 257/435  
2014/0145205 A1 \* 5/2014 Kong et al. .... 257/76

(21) Appl. No.: **13/734,166**

(22) Filed: **Jan. 4, 2013**

FOREIGN PATENT DOCUMENTS

(65) **Prior Publication Data**  
US 2013/0181313 A1 Jul. 18, 2013

JP 2009-076629 4/2009

\* cited by examiner

(30) **Foreign Application Priority Data**  
Jan. 12, 2012 (JP) ..... 2012-003873

Primary Examiner — Cuong Q Nguyen

(74) Attorney, Agent, or Firm — Chip Law Group


(51) **Int. Cl.**  
**H01L 27/146** (2006.01)  
**H01L 31/18** (2006.01)  
(52) **U.S. Cl.**  
CPC .. **H01L 27/14634** (2013.01); **H01L 27/14618** (2013.01); **H01L 27/14687** (2013.01); **H01L 31/18** (2013.01); **H01L 27/14625** (2013.01); **H01L 2224/13** (2013.01)

(57) **ABSTRACT**

An image pickup device and a method of the same are described herein. By way of first example, the image pickup device includes a seal member having a first surface, the first surface of the seal member including a concave portion, and an optical device coupled to a second surface of the seal member, the second surface of the seal member being opposite from the first surface of the seal member. By way of a second example, the image pickup device includes a seal member having a first surface, the first surface being a polished surface, and an optical device coupled to a second surface of the seal member, the second surface of the seal member being opposite from the first surface of the seal member.

(58) **Field of Classification Search**  
CPC ..... H01L 27/146; H01L 27/1462; H01L 27/14643  
USPC ..... 257/433, 98, E31.001, E27.13, 99, 435  
See application file for complete search history.

**14 Claims, 24 Drawing Sheets**






FIG. 1

1A




FIG. 2

100

FIG. 3A





FIG. 3B


















FIG. 4





























FIG. 12A




FIG. 12B

100B

FIG. 13A





FIG. 13B



100C

FIG. 14A





FIG. 14B






FIG. 15




FIG. 16




















FIG. 17




















100D

FIG. 25A





FIG. 25B



## IMAGE PICKUP UNIT AND METHOD OF MANUFACTURING THE SAME

### BACKGROUND

This technology relates to an image pickup unit in which an optical sensor such as a charge coupling device (CCD) and a complementary metal-oxide semiconductor (CMOS) image sensor (CIS) is configured as a chip-scale package, and to a method of manufacturing the same.

As a simple method of packaging an optical sensor, a wafer chip scale package (WCSP) structure has been proposed.

It is to be understood that both the foregoing general description and the following detailed description are exemplary, and are intended to provide further explanation of the technology as claimed.

### SUMMARY

An image pickup device and a method of the same are described herein. By way of first example, the image pickup device includes a seal member having a first surface, the first surface of the seal member including a concave portion, and an optical device coupled to a second surface of the seal member, the second surface of the seal member being opposite from the first surface of the seal member.

By way of a second example, the image pickup device includes a seal member having a first surface, the first surface being a polished surface, and an optical device coupled to a second surface of the seal member, the second surface of the seal member being opposite from the first surface of the seal member.

### BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings are included to provide a further understanding of the disclosure, and are incorporated in and constitute a part of this specification. The drawings illustrate embodiments and, together with the specification, serve to explain the principles of the technology.

FIG. 1 is a diagram illustrating a basic structure of a WCSP structure.

FIG. 2 is a diagram illustrating a structure of a WCSP structure without a gap.

FIGS. 3A and 3B are diagrams each illustrating a first configuration example of an image pickup unit according to an embodiment of the disclosure.

FIG. 4 is a diagram illustrating a configuration example of a color filter according to the embodiment.

FIGS. 5A to 5C are first diagrams for explaining a method of manufacturing the image pickup unit of FIG. 3.

FIGS. 6A to 6C are second diagrams for explaining the method of manufacturing the image pickup unit of FIG. 3.

FIGS. 7A to 7C are third diagrams for explaining the method of manufacturing the image pickup unit of FIG. 3.

FIGS. 8A to 8C are fourth diagrams for explaining the method of manufacturing the image pickup unit of FIG. 3.

FIGS. 9A to 9C are fifth diagrams for explaining the method of manufacturing the image pickup unit of FIG. 3.

FIGS. 10A to 10C are sixth diagrams for explaining the method of manufacturing the image pickup unit of FIG. 3.

FIGS. 11A to 11C are seventh diagrams for explaining the method of manufacturing the image pickup unit of FIG. 3.

FIGS. 12A and 12B are diagrams for explaining a manufacturing method in which a glass is processed to allow an outer region of a glass wafer to be higher in height than inner

portion thereof, and a bonding process to a silicon substrate and the like are then performed.

FIGS. 13A and 13B are diagrams each illustrating a second configuration example of the image pickup unit according to the embodiment.

FIGS. 14A and 14B are diagrams each illustrating a third configuration example of the image pickup unit according to the embodiment.

FIG. 15 is a diagram for explaining a first method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIG. 16 is a diagram for explaining a second method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIG. 17 is a diagram for explaining a third method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIGS. 18A to 18C are first diagrams for specifically explaining the second method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIGS. 19A and 19B are second diagrams for specifically explaining the second method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIGS. 20A to 20C are third diagrams for specifically explaining the second method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIGS. 21A to 21C are fourth diagrams for specifically explaining the second method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIGS. 22A to 22C are fifth diagrams for specifically explaining the second method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIGS. 23A to 23C are sixth diagrams for specifically explaining the second method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIGS. 24A to 24C are seventh diagrams for specifically explaining the second method of manufacturing the image pickup unit of FIGS. 14A and 14B.

FIGS. 25A and 25B are diagrams each illustrating a fourth configuration example of the image pickup unit according to the embodiment.

### DETAILED DESCRIPTION

Hereinafter, embodiments of the technology will be described with reference to drawings.

It is desirable to provide an image pickup unit and a method of manufacturing the same which are capable of preventing enlargement of the unit, complication of processes, and increase in cost, and suppressing generation of scratches, cracks, and the like on a seal member, as well as improving the characteristics and the manufacturing yield of the unit.

In Japanese Unexamined Patent Application Publication No. 2009-76629, as shown in the WCSP structure of FIG. 1, a structure including a protection film 10 which has openings is described. The protection film 10 has the openings in a region facing the optical element region (the light receiving portion) of a surface (a front surface) of the seal glass 3, as illustrated by a dashed line in FIG. 1.

The protection film 10 is formed by using, for example, the following conductive materials in consideration of electrostatic chuck and the like in a wafer process. Specifically, the protection film 10 is formed of a high-resistance metal material (such as Ti, TiN, TiW, Ni, Cr, TaN, and CoWP) or a low-resistance metal material (such as Al, Al—Cu, Al—Si—Cu, Cu, Au, and Ag). Alternatively, the protection film 10 is formed of polycrystalline silicon, a polymer compound having conductivity, or a conductive resin material such as

3

a conductive-particle-containing epoxy resin and a conductive-particle-containing polyimide resin.

As described above, the protection film is formed on the outer region of the surface of the seal glass **3** so that a surface **3a** of a light incident region of the seal glass **3** has a concave shape. Therefore, the surface **3a** of the seal glass **3** is prevented from being directly touched in a wafer process. Thus, it may be possible to suppress generation of scratches, cracks, and the like on the seal glass **3**, and to accordingly improve the characteristics and the manufacturing yield of the image pickup unit.

FIG. **2** is a diagram illustrating another structure of the WCSP structure. A WCSP structure **1A** in FIG. **2** is configured by filling the gap **5** with the resin **4** in the WCSP structure **1** of FIG. **1**. Therefore, the WCSP structure **1A** is configured as a WCSP structure without a gap. Hereinafter, such a WCSP structure without a gap is referred to as a cavity less WCSP structure in some cases.

Employing the cavity less WCSP structure without a gap enables significant reduction of thermal stress generated in a gap of the WCSP structure which has the gap. Therefore, occurrence of warpage is allowed to be suppressed. Further, the cavity less WCSP structure is allowed to optically suppress reflection generated on an interface of the gap (having a refractive index of 1) with use of a resin which has a refractive index of 1.5. Therefore, it is expected to increase in an amount of light received by the optical device **2**.

FIGS. **3A** and **3B** are diagrams each illustrating a first configuration example of an image pickup unit according to an embodiment of the disclosure. FIG. **3A** is a plan view illustrating a configuration example in which a resin layer (an intermediate layer) is disposed on a first surface of a substrate, and FIG. **3B** is a simplified side view illustrating an overall configuration of the image pickup unit. In the embodiment, as an example of an optical device (an optical sensor), a CMOS image sensor (CIS) is employed.

An image pickup unit **100** of the embodiment basically has a WCSP structure which is packaged in a size of an optical sensor chip. The image pickup unit **100** may employ a cavity structure in which a gap is formed between an optical element region (a light receiving portion) of an optical device and a surface facing the light receiving portion, of a seal glass, or a cavity less WCSP structure without a gap. In the embodiment, the cavity less WCSP structure is described. In the embodiment, the first surface (a front surface) is a surface formed with the light receiving portion of the optical device as the optical sensor of the image pickup unit, namely, a surface on a side from which image light of a subject enters. A second surface (a back surface) is a surface which does not receive light and is provided with connection electrodes such as solder balls (bumps), an interposer, and the like, namely, a surface opposite to the first surface.

The image pickup unit **100** includes an optical device **110**, a seal member **120**, a resin layer **130** as an intermediate layer, connection pads **140** as electrode pads or external connection terminals, via electrodes **150 (150-1 and 150-2)**, and external connection terminals **160**.

Incidentally, the resin layer **130** and the seal member **120** are each formed of a material which is transparent to light and allows light to pass therethrough. The refractive index of each of these materials is higher than that of the air. For example, the resin layer **130** and the seal member **120** are each formed of a material having a refractive index of about 1.5. In the configuration of FIGS. **3A** and **3B**, an example in which the seal member **120** is formed of a glass is illustrated. In this case, the seal member **120** may be formed as a seal

4

glass or a cover glass. The resin layer **130** has a function as a seal member, in addition to a function as a protection film for the optical element region.

In the optical device **110**, an optical element region **112** which functions as the light receiving portion is formed on a first surface (a front surface) **111a** of a sensor substrate (a silicon substrate) **111**. The external connection terminals **160** such as bumps, which are electrodes connected to the outside, are formed on a second surface (a back surface) **111b**. In the optical device **110**, the connection pads **140** which serve as electrode pads (**140-1 to 140-4**) or external connection terminals are formed on end portions (right and left end portions in FIGS. **3A** and **3B**) on the first surface **111a** of the sensor substrate **111**. In the optical device **110**, an insulating film **113** is formed in a region except for filter portions of the optical element region **112**, on the first surface **111a** of the sensor substrate **111**. In the insulating film **113**, the connection pads **140** are embedded. Parts of the insulating film **113** are opened to form openings **113-1** and **113-2** on the first surface **111a** of the sensor substrate **111**. A non-connection surface of the connection pad **140** is exposed through the openings. In addition, the resin layer **130** is also formed inside the openings of the insulating film **113**, and the connection pads **140** are covered with the resin layer **130**, on the first surface **111a** of the sensor substrate **111**. The connection pads **140** which are formed as the external connection terminals on the first surface **111a** of the sensor substrate **111** of the optical device **110** may be opened as wire bonding pads or may not be opened. Moreover, each of the connection pads **140** may not be a metal layer on an uppermost layer of stacked wirings in the optical device **110**. Note that the opening means a state where the insulating film **113** is partially removed and the pad is accordingly exposed, and where test terminals and the like are directly connectable in manufacturing and the like.

In the optical device **110**, the via electrodes **150 (150-1 and 150-2)** are formed by through silicon vias **114** which pass through the sensor substrate **111** from the first surface **111a** to the second surface **111b**. This enables bonding of a glass in a wafer state without wirings by a wire bonding, in a clean room. Each of the via electrodes **150 (150-1 to 150-4)** is connected to the external connection terminal **160** on the second surface **111b** of the sensor substrate **111**. The external connection terminal **160** is connected to a terminal of an external reference potential (a ground potential) and the like through a wiring **115**.

The optical element region **112** as the light receiving portion is formed on the first surface **111a** of the sensor substrate **111**, and has a light receiving surface (a pixel array portion) **1121** which includes a plurality of pixels (photo-detection devices) arranged in a matrix. In the optical element region **112**, a color filter **1122** is formed on a front surface side of the pixel array portion **1121**. In the color filter **1122**, color filters of red (R), green (G), and blue (B) which are three primary colors, are formed in an array as an on chip color filter (OCCF) with Bayer arrangement, for example, as illustrated in FIG. **4**. However, the arrangement pattern of the color filters is not necessarily limited to Bayer pattern. Incidentally, in the example of FIG. **4**, an infrared cutoff filter (IRCF) **170** is formed to be overlaid on the color filter **1122**.

In the optical element region **112**, a microlens array **1123** intended to collect incident light in each pixel is disposed on a front surface side of the color filter **1122**. In the optical element region **112**, an anti-reflection film and the like are formed on a front surface side of the microlens array **1123**.

5

The seal member (the seal glass) **120** is formed so that an outer region **1212** is formed to be higher in height than an inner region **1211** on the front surface (the surface) **121** on a side from which the image light of a subject enters. The inner region **1211** has an area larger than that of a region facing the optical element region **112** of the optical device **110** by a constant area. In other words, the seal glass **120** is formed to have a concave shape in which the central inner region **1211** is lower in height than the outer region **1212** on the front surface **121**.

Since the seal glass **120** has such a configuration, in a wafer process in manufacturing, only the front surface **1212a** of the outer region **1212** on the front surface **121** of the seal glass **120** is directly touched at the time of being carried or being mounted on a stage or the like of a processing apparatus. Therefore, in the wafer process, a surface **1211a** of the inner region **1211** on the front surface **121** of the seal glass **120** is prevented from being directly touched. As a result, generation of scratches, cracks, and the like is suppressed, and the characteristics and the manufacturing yield of the image pickup unit are improved. As described above, since the seal glass **120** of the embodiment is formed by recessing the glass itself along the inner region **1211** without using a separate member for recessing, the enlargement of the image pickup unit, the complication of processes, and the increase in cost are prevented while generation of scratches, cracks, and the like in the seal member is suppressed. As a result, the seal glass **120** of the embodiment improves the characteristics and the manufacturing yield of the image pickup unit. A specific manufacturing method will be described in detail later.

In addition, since the outer region **1212** has a depth **D** from the front surface **1212a** of the outer region **1212** to the surface **1211a** of the inner region **1211**, the seal glass **120** of the embodiment exerts the following functions and effects. The outer region **1212** is surrounded by the air. Thus, the outer region **1212** functions as a so-called waveguide (an optical waveguide). Accordingly, light traveling toward the optical element region **112**, of light which has entered the front surface **1212a** or the like is guided by the outer region **1212** for a predetermined distance so as to go straight toward a region formed with the connection pad **140** illustrated in FIG. **3B**. Consequently, light which has entered the front surface **1212a** of the outer region **1212** which is higher in height than the surface **1211a** of the inner region **1211** is prevented from becoming stray light to the optical element region **112**. As a result, the outer region **1212** contributes to prevention of lowering in the sensitivity of the optical element region (the light receiving portion) and the manufacturing yield.

The resin layer **130** is formed to fill a gap between the first surface **111a** formed with the optical element region **112** having the above described configuration, of the sensor substrate **111** and the surface **122** facing the first surface **111a**, of the seal member (the seal glass) **120**. In addition, as described above, the resin layer **130** is formed to fill a portion reaching the connection portion of the connection pad **140** in the opening formed in the insulating film **113**. In other words, the image pickup unit **100** of the embodiment is formed to have a so-called cavity less structure. Note that the thickness of the resin layer **130** is set to about 10  $\mu\text{m}$  to about 100  $\mu\text{m}$ , for example. In addition, the thickness of the seal glass **120** is set to about 450  $\mu\text{m}$  to about 800  $\mu\text{m}$ , for example.

6

[Method of Manufacturing Image Pickup Unit of FIGS. **3A** and **3B**]

Next, a method of manufacturing the image pickup unit **100** having the above-described structure will be described. FIG. **5A** to FIG. **11C** are diagrams for explaining the method of manufacturing the image pickup unit according to the embodiment.

(Step ST1)

As illustrated in FIGS. **5A** and **5B**, in a step ST1, a recessed portion DGG having the depth **D** is formed in a region to be the inner region **1211** on the front surface **121A** of a square glass substrate **120A** which has been cleaned and is to be the seal glass **120**. The outer region **1212** is formed in the periphery of the glass substrate **120A** by the inner region **1211**. In this case, for example, as illustrated in FIG. **5C**, the recessed portion DGG is formed for each chip CP on the glass substrate **200** according to a chip map.

(Step ST2)

As illustrated in FIG. **6A**, in a step ST2, a sensor portion as the optical element region **112**, the connection pads **140**, and the like are formed on the first surface **111a** of the silicon substrate (the sensor substrate) **111A**, and then the insulating film **113** is formed. Then, the openings **113-1** and **113-2** each reaching the connection pad **140** are formed in the insulating film **113**. The openings are intended to measure sensor property in advance and select a favorable chip.

(Step ST3)

As illustrated in FIG. **6B**, in a step ST3, on the first surface **111a** side of the silicon substrate **111A**, a film **130A** is formed to cover the optical element region **112** and the insulating film **113**, and to fill the openings **113-1** and **113-2** so as to reach the connection pad **140**. The film **130A** forms the resin layer **130** as the intermediate layer.

(Step ST4)

As illustrated in FIG. **6C**, in a step ST4, the film **130A** is bonded to a surface **122** not formed with the recessed portion DGG, of the glass substrate **120A** illustrated in FIG. **5B**. Specifically, in the step ST4, the glass substrate **120A** formed with the recessed portion DGG is bonded, through the film **130A**, to the optical device **110** including the optical element region **112** which is formed on the silicon substrate **111A**. Next and follow steps are a wiring formation process.

(Step ST5)

As illustrated in FIG. **7A**, in a step ST5, the surface **121A** side formed with the recessed portion DGG of the glass substrate **120A** is mounted on a processing apparatus. Then, the second surface **111b** of the silicon substrate **111A** is abraded by back ground remove (BGR) and chemical mechanical polishing (CMP), to the thickness where the via electrodes are allowed to be formed. For example, the silicon substrate **111A** having the thickness of about 700  $\mu\text{m}$  is abraded to the thickness of about 100  $\mu\text{m}$  to about 50  $\mu\text{m}$ . As described above, in the manufacturing process, only the front surface **1212a** of the outer region **1212** of the front surface **121A** of the glass substrate **120A** is directly touched at the time of being carried or being mounted on a stage of a processing apparatus. Therefore, in a wafer process, the surface **1211a** of the inner region **1211** on the front surface **121** of the seal glass **120** is prevented from being directly touched. As a result, generation of scratches, cracks, and the like is suppressed, and the characteristics and the manufacturing yield of the image pickup unit are improved.

(Step ST6)

As illustrated in FIG. **7B**, in a step ST6, a mask **210** is formed by photolithography and the like in a predetermined position of the second surface **111b** side of the silicon substrate **111A**, except for predetermined positions **211** and **212** in which TSVs are to be formed.

(Step ST7)

As illustrated in FIG. 7C, in a step ST7, TSVs 213 and 214 each reaching the connection pad 140 are formed in the predetermined positions 211 and 212 on the second surface 111b side of the silicon substrate 111A by etching. After that, the mask 210 is removed.

(Step ST8)

As illustrated in FIG. 8A, in a step ST8, for example, a oxidized insulating film 215 is formed to have a thickness of about 10 μm on the entire surface including the inside of the TSVs 213 and 214 of the second surface 111b side of the silicon substrate 111A.

(Step ST9)

As illustrated in FIG. 8B, in a step ST9, etching is performed on the second surface 111b side of the silicon substrate 111A to remove the insulating film 215 formed on the bottom of each of the TSVs 213 and 214. As a result, the surfaces of the connection pads 140-1 and 140-2 in the TSVs 213 and 214 are exposed. The remaining insulating film 215 has a thickness smaller than 10 μm.

(Step ST10)

As illustrated in FIG. 8C, in a step ST10, a seed layer 216 as a conductive layer is formed to have a thickness of about 0.1 μm to about 1 μm on the entire surface including the inside of the TSVs 213 and 214 of the second surface 111b side of the silicon substrate 111A. The seed layer 216 is formed of a stacked film of, for example, titanium (Ti) and copper (Cu).

(Step ST11)

As illustrated in FIG. 9A, in a step ST11, a resist 217 is bonded to the entire surface including above the TSVs 213 and 214 of the second surface 111b of the silicon substrate 111A.

(Step ST12)

As illustrated in FIG. 9B, in a step ST12, the resist 217 is removed from the inside of the TSVs 213 and 214 and the surrounding regions of the TSVs 213 and 214 on the second surface 111b of the silicon substrate 111A.

(Step ST13)

As illustrated in FIG. 9C, in a step ST13, a wiring layer 218 is formed to have a thickness of about 5 μm inside the TSVs 213 and 214 and in the surrounding regions of the TSVs 213 and 214 on the second surface 111b of the silicon substrate 111A. The wiring layer 218 is formed of, for example, Cu. Then, the wiring 115 in FIG. 3B is formed by the wiring layer 218 and the seed layer 216.

(Step ST14)

As illustrated in FIG. 10A, in a step ST14, the resist 217 remaining on the second surface 111b of the silicon substrate 111A is removed.

(Step ST15)

As illustrated in FIG. 10B, in a step ST15, the seed layer 216 is removed, by etching, from a region in which the wiring layer 218 is not formed and the boundary region thereof on the second surface 111b of the silicon substrate 111A.

(Step ST16)

As illustrated in FIG. 10C, in a step ST16, a solder mask 219 is formed on the entire surface including above the TSVs 213 and 214 on the second surface 111b of the silicon substrate 111A.

(Step ST17)

As illustrated in FIG. 11A, in a step ST17, openings 220-1 and 220-2 each reaching the wiring layer 218 are formed in the solder mask 219 in a region which is adjacent to the region inner than the region formed with the TSVs 213 and 214 on the second surface 111b of the silicon substrate 111A.

(Step ST18)

As illustrated in FIG. 11B, in a step ST18, solders 221-1 and 221-2 are printed or solder balls are provided in the openings 220-1 and 220-2 on the second surface 111b of the silicon substrate 111A so as to reach the wiring layer 218 and to be exposed from the openings 220-1 and 220-2.

(Step ST19)

As illustrated in FIG. 11C, in a step ST19, solder balls 222-1 and 222-2 are formed by reflow. The solder balls 222-1 and 222-2 form the external connection terminals 160 in FIG. 3B.

In this way, the manufacturing of the image pickup unit 100 is completed.

According to the embodiment, the seal glass 120 is formed to have a concave shape in which the central inner region 1211 is lower in height than the outer region 1212 on the front surface 121. Since the seal glass 120 has such a configuration, in a wafer process in manufacturing, only the front surface 1212a of the outer region 1212 on the front surface 121 of the seal glass 120 is directly touched at the time of being carried or being mounted on a stage or the like of a processing apparatus. Therefore, in the wafer process, the surface 1211a of the inner region 1211 on the front surface 121 of the seal glass 120 is prevented from being directly touched. As a result, generation of scratches, cracks, and the like is suppressed, and the characteristics and the manufacturing yield of the image pickup unit are improved. As described above, since the seal glass 120 of the embodiment is formed by recessing the glass itself along the inner region 1211 without using a separate member for recessing, the enlargement of the image pickup unit, the complication of processes, and the increase in cost are prevented while generation of scratches, cracks, and the like in the seal member is suppressed. Consequently, according to the embodiment, it may be possible to improve the characteristics and the manufacturing yield of the image pickup unit.

As described above, in the manufacturing process, the recessed portion DGG with the depth D is formed in a region to be the inner region 1211 on the front surface 121A of the glass substrate 120A. Therefore, only the front surface 1212a of the outer region 1212 on the front surface 121A of the glass substrate 120A is directly touched at the time of being carried or being mounted on a stage or the like of a processing apparatus. Accordingly, the surface 1211a of the inner region 1211 on the front surface 121A of the glass substrate 120A is prevented from being directly touched in the wafer process. Thus, generation of scratches, cracks, and the like is suppressed, and the characteristics and the manufacturing yield of the image pickup unit are improved.

Incidentally, in the above-described manufacturing method, the recessed portion DGG is formed for each chip CP on the glass substrate 200 according to a chip map. For example, as illustrated in FIGS. 12A and 12B, in the present technology, a glass may be processed so that an outer region 310 of a glass wafer 300 is higher in height than inner side, and then each of processes such as bonding with the silicon substrate 111 as described above may be performed. Also in the manufacturing method, the surface 1211a of the inner region 1211 on the front surface 121A of the glass substrate 120A is prevented from being directly touched in the wafer process. Therefore, generation of scratches, cracks, and the like is suppressed, and the characteristics and the manufacturing yield of the image pickup unit are improved.

FIGS. 13A and 13B are diagrams each illustrating a second configuration example of the image pickup unit according to the embodiment. FIG. 13A is a plan view illustrating a configuration example in which a resin layer

(an intermediate layer) is provided on the first surface of the substrate, and FIG. 13B is a simplified side view illustrating an overall configuration of the image pickup unit.

An image pickup unit 100B is different from the image pickup unit 100 of FIGS. 3A and 3B in the following points. In the image pickup unit 100B, openings intended to fill a resin layer 130B as an intermediate layer are not formed in an insulating film 113B. Therefore, the image pickup unit 100B does not have a configuration in which the connection pads 140 are connected to the resin layer 130B.

As for a manufacturing method, steps are performed in a similar manner to the steps illustrated in FIG. 5A to FIG. 11C, except that the step of forming the openings in the step ST2 described with reference to FIG. 6A is unnecessary.

Other configurations are similarly to those of the image pickup unit 100 of FIGS. 3A and 3B, and effects similar to those of the image pickup unit 100 of FIGS. 3A and 3B described above are obtainable also in the image pickup unit 100B.

FIGS. 14A and 14B are diagrams each illustrating a third configuration example of the image pickup unit according to the embodiment. FIG. 14A is a plan view illustrating a configuration example in which a resin layer (an intermediate layer) is provided on a first surface of a substrate, and FIG. 14B is a simplified side view illustrating an overall configuration of the image pickup unit.

An image pickup unit 100C is different from the image pickup unit 100 of FIGS. 3A and 3B in the following points. In the image pickup unit 100C, the recessed portion DGG is not formed on a front surface 121C of a seal glass 120C. In other words, in the image pickup unit 100C, the front surface 121C of the seal glass 120C is not processed and remains flat. Therefore, in the manufacturing method, when the glass side is mounted as it is on a stage or the like of a processing apparatus, the surface of the glass substrate is directly touched, thereby causing scratches, cracks, and the like of the glass substrate. Thus, when the image pickup unit 100C with the configuration of FIGS. 14A and 14B is manufactured, instead of formation of a recessed portion on the glass substrate, any of methods illustrated in FIG. 15 to FIG. 17 is employed.

[Method of Manufacturing Image Pickup Unit of FIGS. 14A and 14B]

In the manufacturing method of FIG. 15, as illustrated in (A) of FIG. 15, the glass substrate 120C is bonded, with use of an adhesive, to the optical device 110 including the optical element region 112 formed on the silicon substrate 111A. Next, as illustrated in (B) of FIG. 15, a support substrate 400 as a support functional board is temporarily bonded to the front surface 121C with use of an adhesive 410. Subsequently, as illustrated in (C) of FIG. 15, basically, the processes such as the formation process of the TSVs and the formation process of the solder balls are performed, and then, the temporarily-bonded support substrate 400 is detached as illustrated in (D) of FIG. 15. Note that the support substrate 400 is formed of Si or a glass substrate.

In the manufacturing method of FIG. 16, as illustrated in (A) of FIG. 16, the glass substrate 120C is bonded, with use of an adhesive, to the optical device 110 including the optical element region 112 formed on the silicon substrate 111A. Next, as illustrated in (B) of FIG. 16, a protection film 500 as a support functional board is temporarily bonded to the front surface 121C with use of an adhesive 510. Subsequently, as illustrated in (C) of FIG. 16, basically, the processes such as the formation process of the TSVs and the formation process of the solder balls are performed, and

then, the temporarily-bonded protection film 500 is detached as illustrated in (D) of FIG. 16.

In the manufacturing method of FIG. 17, as illustrated in (A) of FIG. 17, the glass substrate 120C is bonded, with use of an adhesive, to the optical device 110 including the optical element region 112 formed on the silicon substrate 111A. Subsequently, as illustrated in (B) of FIG. 17, basically, the processes such as the formation process of the TSVs and the formation process of the solder balls are performed. After that, as illustrated in (C) of FIG. 17, the front surface 121C of the glass substrate 120C is polished by a polisher 600.

The polishing of the glass may be performed after the support substrate 400 or the protection film 500 is detached in the method of FIG. 15 or FIG. 16.

Although some portions will be described again, the method of manufacturing the image pickup unit 100C of FIGS. 14A and 14B will be specifically described below with reference to FIG. 18A to FIG. 24C by taking the case where the protection film 500 is used, as an example.

FIG. 18A to FIG. 24C are diagrams for specifically explaining a second method of manufacturing the image pickup unit of FIGS. 14A and 14B. Note that, in the following description, like numerals are used to designate substantially like components of FIG. 5A to FIG. 11C and FIG. 16, for the sake of facilitating the understanding. (Step ST21)

As illustrated in FIG. 18A, in a step ST21, the square glass substrate 120C to be the seal glass 120 is prepared, and then the glass substrate 120C is cleaned.

(Step ST22)

As illustrated in FIG. 18B, in a step ST22, the sensor portion which is the optical element region 112, the connection pads 140, and the like are formed on the first surface 111a of the silicon substrate (the sensor substrate) 111A, and the insulating film 113 is then formed. After that, the openings 113-1 and 113-2 each reaching the connection pad 140 are formed in the insulating film 113.

(Step ST23)

As illustrated in FIG. 18C, in a step ST23, the film 130A is formed on the first surface 111a of the silicon substrate 111A to cover the optical element region 112 and the insulating film 113 as well as to fill the openings 113-1 and 113-2 so as to reach the connection pad 140. The film 130A forms the resin layer 130 as the intermediate layer.

(Step ST24)

As illustrated in FIG. 19A, in a step ST24, the film 130A is bonded to the surface 122 which is not to be the front surface of the glass substrate 120C. In other words, in the step ST24, the glass substrate 120C is bonded through the film 130A to the optical device 110 including the optical element region 112 which is formed on the silicon substrate 111A. The step corresponds to a bonding process.

(Step ST25)

As illustrated in FIG. 19B, in a step ST25, the protection film 500 is temporarily bonded, with use of the adhesive 510, to the surface 121C which is a front surface on a light incident side of the glass substrate 120C. Note that, in the description, although the protection film is bonded corresponding to FIG. 16, if the method corresponds to FIG. 15, the support substrate 400 is temporarily bonded with use of the adhesive 410. The step corresponds to the temporal bonding process. The bonding process in the step ST24 and the temporal bonding process in the step ST25 may be performed in any order. Next and follow steps correspond to a wiring formation process.

(Step ST26)

As illustrated in FIG. 20A, in a step ST26, the surface 121A side to which the protection film 500 is bonded, of the glass substrate 120C is mounted on a processing apparatus. Then, the second surface 111b of the silicon substrate 111A is abraded by BGR and CMP, to the thickness where via electrodes are allowed to be formed. For example, the silicon substrate 111A having the thickness of about 700 μm is abraded to the thickness of about 100 μm to about 50 μm. As described above, in the manufacturing process, only the protection film 500 bonded to the front surface 121C of the glass substrate 120C is directly touched at the time of being carried or being mounted on a stage or the like of a processing apparatus. Therefore, in a wafer process, the surface 121C of the glass substrate 120C is prevented from being directly touched. As a result, generation of scratches, cracks, and the like is suppressed, and the characteristics and the manufacturing yield of the image pickup unit are improved.

(Step ST27)

As illustrated in FIG. 20B, in a step ST27, the mask 210 is formed by photolithography and the like in a predetermined position of the second surface 111b of the silicon substrate 111A, except for the predetermined positions 211 and 212 in which the TSVs are to be formed.

(Step ST28)

As illustrated in FIG. 20C, in a step ST28, the TSVs 213 and 214 each reaching the connection pad 140 are formed in the predetermined positions 211 and 212 on the second surface 111b of the silicon substrate 111A by etching. After that, the mask 210 is removed. Note that in the processing of the step ST28, the protection film 500 or the support substrate 400 is detached once in some cases in order to eliminate influence of electrostatic chuck (ESC).

(Step ST29)

As illustrated in FIG. 21A, in a step ST29, for example, the oxidized insulating film 215 is formed to have a thickness of about 10 μm on the entire surface including the inside of the TSVs 213 and 214 of the second surface 111b of the silicon substrate 111A. Note that, also in the process of the step ST29, the protection film 500 or the support substrate 400 is detached once in some cases in consideration of process thermal tolerance.

(Step ST30)

As illustrated in FIG. 21B, in a step ST30, etching is performed on the second surface 111b of the silicon substrate 111A to remove the insulating film 215 formed on the bottom of each of the TSVs 213 and 214. As a result, the surfaces of the connection pads 140-1 and 140-2 in the TSVs 213 and 214 are exposed. The remaining insulating film 215 has a thickness smaller than 10 μm.

(Step ST31)

As illustrated in FIG. 21C, in a step ST31, the seed layer 216 as a conductive layer is formed to have a thickness of about 0.1 μm to about 1 μm on the entire surface including the inside of the TSVs 213 and 214 of the second surface 111b of the silicon substrate 111A. The seed layer 216 is formed of a stacked film of, for example, titanium (Ti) and copper (Cu). Note that, also in the process of the step ST31, the protection film 500 or the support substrate 400 is detached once in some cases in order to eliminate influence of ESC.

(Step ST32)

As illustrated in FIG. 22A, in a step ST32, the resist 217 is bonded to the entire surface including above the TSVs 213 and 214 on the second surface 111b of the silicon substrate 111A. Incidentally, if the protection film 500 or the support

substrate 400 has been detached once in the steps ST28 to ST31, the protection film 500 or the support substrate 400 is bonded again.

(Step ST33)

As illustrated in FIG. 22B, in a step ST33, the resist 217 is removed from the inside of the TSVs 213 and 214 and the surrounding regions of the TSVs 213 and 214 on the second surface 111b of the silicon substrate 111A.

(Step ST34)

As illustrated in FIG. 22C, in a step ST34, the wiring layer 218 is formed to have a thickness of about 5 μm inside the TSVs 213 and 214 and in the surrounding regions of the TSVs 213 and 214 on the second surface 111b of the silicon substrate 111A. The wiring layer 218 is formed of, for example, Cu. Then, the wiring 115 in FIG. 3B is formed by the wiring layer 218 and the seed layer 216.

(Step ST35)

As illustrated in FIG. 23A, in a step ST35, the resist 217 remaining on the second surface 111b of the silicon substrate 111A is removed.

(Step ST36)

As illustrated in FIG. 23B, in a step ST36, the seed layer 216 is removed, by etching, from a region in which the wiring layer 218 is not formed and the boundary region thereof on the second surface 111b of the silicon substrate 111A.

(Step ST37)

As illustrated in FIG. 23C, in a step ST37, the solder mask 219 is formed on the entire surface including above the TSVs 213 and 214 on the second surface 111b of the silicon substrate 111A.

(Step ST38)

As illustrated in FIG. 24A, in a step ST38, the openings 220-1 and 220-2 each reaching the wiring layer 218 are formed in the solder mask 219 in a region which is adjacent a region inner than the region formed with the TSVs 213 and 214 on the second surface 111b of the silicon substrate 111A.

(Step ST39)

As illustrated in FIG. 24B, in a step ST39, the solders 221-1 and 221-2 are printed in the openings 220-1 and 220-2 on the second surface 111b of the silicon substrate 111A so as to reach the wiring layer 218 and to be exposed from the openings 220-1 and 220-2.

(Step ST40)

As illustrated in FIG. 24C, in a step ST40, the solder balls 222-1 and 222-2 are formed by reflow. The solder balls 222-1 and 222-2 form the external connection terminals 160 in FIG. 14B.

After the reflow, a step of polishing the glass substrate 120A may be added. In this case, a protection tape protecting the solder balls is put on the solder balls because the polishing of the glass substrate 120A is performed in a state where the solder balls are located on a downside. The protection tape is detached after the polishing is ended.

In this way, the manufacturing of the image pickup unit 100C is completed.

According to the embodiment, the support substrate 400 or the protection film 500 is temporarily bonded on the front surface 121C of the glass substrate 120C with an adhesive in the manufacturing process, or the front surface 121C is polished after the manufacturing process. Accordingly, in the wafer process in manufacturing, only the support substrate or the protection film bonded to the front surface of the seal glass 120 is directly touched at the time of being carried or being mounted on a stage or the like of a processing apparatus. Therefore, in the wafer process, the front surface 121 of the seal glass 120 is prevented from being directly

touched. As a result, generation of scratches, cracks, and the like is suppressed, and the characteristics and the manufacturing yield of the image pickup unit are improved. As described above, since the seal glass 120 of the embodiment is formed by recessing the glass itself along the inner region 1211 without using a separate member for recessing, the enlargement of the image pickup unit, the complication of processes, and the increase in cost are prevented while generation of scratches, cracks, and the like in the seal member is suppressed. As a result, according to the embodiment, it may be possible to improve the characteristics and the manufacturing yield of the image pickup unit.

FIGS. 25A and 25B are diagrams each illustrating a fourth configuration example of the image pickup unit according to the embodiment. FIG. 25A is a plan view illustrating a configuration example in which a resin layer (an intermediate layer) is provided on a first surface of a substrate, and FIG. 25B is a simplified side view illustrating an overall configuration of the image pickup unit.

An image pickup unit 100D is different from the image pickup unit 100C of FIGS. 14A and 14B in the following points. In the image pickup unit 100D, openings intended to fill a resin layer 130D as an intermediate layer are not formed in an insulating film 113D. Therefore, the image pickup unit 100D does not have a configuration in which the connection pads 140 are connected to the resin layer 130D.

As for a manufacturing method, steps are performed in a similar manner to the steps illustrated in FIG. 18A to FIG. 25C, except that the step of forming the openings in the step ST22 described with reference to FIG. 18B is unnecessary.

Other configurations are similar to those of the image pickup unit 100C of FIGS. 14A and 14B, and effects similar to those of the image pickup unit 100C of FIGS. 14A and 14B described above are obtainable also in the image pickup unit 100D.

Note that the technology may be configured as follows.

An image pickup device comprising: a seal member having a first surface, the first surface of the seal member including a concave portion; and an optical device coupled to a second surface of the seal member, the second surface of the seal member being opposite from the first surface of the seal member.

The concave portion of the seal member may include an outer region and an inner region, the outer region protruding beyond the inner region by a distance (D) in a direction perpendicular to the second surface of the seal member.

The optical device may include an optical element region formed on a first surface of a substrate, the first surface of the substrate facing toward the seal member and the optical element region being configured to perform photoelectric conversion.

The second surface of the seal member may be adhered to the optical device by a resin layer.

The optical device may include a connection pad formed on the first surface of the substrate, and the connection pad may be connected to an external connection terminal formed on a second surface of the substrate through a via electrode, the second surface of the substrate being opposite from the first surface of the substrate.

An insulating layer may be formed on the first surface of the substrate, and a portion of the insulating layer is formed between the connection pad and the resin layer.

The connection pad may be in direct contact with the resin layer.

The outer region may protrude beyond the inner region at a step having a lateral wall, the lateral wall being nearly parallel to the direction perpendicular to the first surface of the seal member.

The concave portion may include an outer region and an inner region on the first surface of the seal member, the outer region protruding beyond the inner region by a distance (D) in a direction perpendicular to the first surface of the seal member, and the inner surface region may align with the optical element region in the direction perpendicular to the first surface of the seal member.

A method for making an image pickup device, the method comprising the steps of: forming a concave portion on a first surface of a seal member; and coupling an optical device to a second surface of the seal member, the second surface of the seal member being opposite from the first surface of the seal member.

In the step of forming the concave portion, an outer region and an inner region may be formed on the first surface of the seal member, the outer surface region being formed to protrude beyond the inner surface region by a distance (D) in a direction perpendicular to the second surface of the seal member.

In the method for making an image pickup device, the optical device may include an optical element region formed on a first surface of a substrate, the optical element region being configured to perform photoelectric conversion and the first surface of the substrate facing toward the seal member.

In the step of coupling the optical device to the second surface of the seal member, the second surface of the seal member may be adhered to the optical device by a resin layer.

In the method for making an image pickup device, the optical device may include a connection pad formed on the first surface of the substrate, and the connection pad may be connected to an external connection terminal formed on a second surface of the substrate through a via electrode, the second surface of the substrate being opposite from the first surface of the substrate.

In the method for making an image pickup device, an insulating layer may be formed on the first surface of the substrate, and a portion of the insulating layer is formed between the connection pad and the resin layer.

In the method for making an image pickup device, the connection pad may be in direct contact with the resin layer.

In the step of forming the concave portion, the outer region may be formed to protrude beyond the inner region at a step having a lateral wall, the lateral wall being nearly parallel to the direction perpendicular to the first surface of the seal member.

In the step of forming the concave portion, the concave portion may be formed to include an outer region and an inner region on the first surface of the seal member, the outer region protruding beyond the inner region by a distance (D) in a direction perpendicular to the first surface of the seal member, and the inner surface region may align with the optical element region in the direction perpendicular to the first surface of the seal member.

A method for making a second image pickup device, the method comprising the steps of: coupling a second surface of a seal member to an optical device; coupling a first surface of the seal member to a protective member, the first surface of the seal member being opposite from the second surface of the seal member; removing the protective member.



15

The method for making the second image pickup device may further comprise the step of performing fabrication processing on the image pickup device, wherein the step of performing processing on the image pickup device is performed after the step of coupling the first surface of the seal member to the protective member.

In the method for making the second image pickup device, the protective member may be a support substrate.

In the second method for making the second image pickup device, the protective member may be a protective film.

The method for making the second image pickup device may further comprise the step of polishing the first surface of the seal member after the step of removing the protective member.

The second image device may comprise: a seal member having a first surface, wherein the first surface is a polished surface; and an optical device coupled to a second surface of the seal member, the second surface of the seal member being opposite from the first surface of the seal member.

Another image pickup unit comprises: an optical device including an optical element region, wirings, and external connection terminals, the optical element region being provided on a first surface of a substrate and functioning as a light receiver, and the wirings and the external connection terminals being provided on a second surface opposite to the first surface of the substrate; and an optically-transparent seal member provided to cover a region including the optical element region of the optical device, thereby to protect the optical element region, wherein the region including the optical element region of the optical device is bonded to a back surface of the seal member, the back surface being opposite to a front surface as a light incident surface of the seal member, and the seal member is provided with an inner region on the front surface, the inner region being defined as a region corresponding to the optical element region of the optical device and being lower in height than an outer region on the front surface.

The optical device may include connection pads provided on the first surface along the optical element region, and via electrodes each passing through the substrate from the second surface to the first surface to be connected to the connection pads and each being connected to the wirings on the second surface.

The another image pickup unit comprises may further comprise an intermediate layer provided between the optical element region on the front surface of the optical device and the back surface of the seal member at least in a region corresponding to the optical element region, the intermediate layer wholly bonding the optical element region of the optical device and the back surface of the seal member.

The optical device may include an insulating film provided on the first surface of the substrate, the insulating film may include openings each reaching the connection pad from the second surface side, and the openings may be filled with the intermediate layer to allow the connection pads to be in contact with the intermediate layer.

Another image pickup unit comprises: an optical device including an optical element region, wirings, and external connection terminals, the optical element region being provided on a first surface of a substrate and functioning as a light receiver, and the wirings and the external connection terminals being provided on a second surface opposite to the first surface of the substrate; an optically-transparent seal member provided to cover a region including the optical element region of the optical device, thereby to protect the optical element region; an intermediate layer provided between the optical element region on a front surface as a

16

light incident surface of the optical device and a back surface of the seal member at least in a region corresponding to the optical element region, the intermediate layer wholly bonding the optical element region of the optical device and the back surface of the seal member, the back surface being opposite to the front surface of the seal member; connection pads provided on the first surface along the optical element region; via electrodes each passing through the substrate from the second surface to the first surface to be connected to the connection pads and each being connected to the wirings on the second surface; and an insulating film provided on the first surface of the substrate, wherein the insulating film includes openings each reaching the connection pad from the second surface side, and the openings is filled with the intermediate layer to allow the connection pads to be in contact with the intermediate layer.

The front surface of the seal member may be polished.

In another method of manufacturing an image pickup unit, the method comprises: forming a recessed portion on a front surface as a light incident surface of an optically-transparent seal member which is provided to protect an optical element region of an optical device, the optical element region being provided on a first surface of a substrate and functioning as a light receiver, the recessed portion being formed in an inner region defined as a region corresponding to the optical element region of the optical device and being lower in height than an outer region on the front surface; bonding a region including the optical element region of the optical device to a back surface of the seal member, the back surface being opposite to the front surface of the seal member; and forming wirings and external connection terminals on a second surface opposite to the first surface of the substrate of the optical device, while supporting the front surface of the seal member.

The another method of manufacturing the image pickup unit may further comprise abrading the second surface of the substrate to a thickness which allows via electrodes to be formed, before formation of the wirings, wherein via electrodes are formed in the formation of the wirings, the via electrodes each passing through the substrate from the second surface to the first surface to be connected to connection pads and each being connected to the wirings on the second surface, the connection pads being provided on the first surface along the optical element region.

The another method of manufacturing the image pickup unit wherein an intermediate layer is formed to fill a gap between the optical element region on the front surface of the optical device and the back surface of the seal member at least in a region corresponding to the optical element region, the intermediate layer allowing the optical element region of the optical device to be bonded to the back surface of the seal member.

The another method of manufacturing the image pickup unit may further comprise: providing an insulating film on the first surface of the substrate of the optical device; and forming openings on the insulating film before the bonding of the optical element region of the optical device and the back surface of the seal member, the openings each reaching the connection pad from the second surface side of the substrate, wherein the intermediate layer is filled in the openings to be in contact with the connection pads in the bonding.

Another method of manufacturing an image pickup unit, the method comprising: (A) bonding a region including an optical element region of an optical device to a back surface of an optically-transparent seal member, the optical element region being provided on a first surface of a substrate and

17

functioning as a light receiver, the seal member provided to cover a region including the optical element region of the optical device, thereby to protect the optical element region, the back surface being opposite to a front surface as a light incident surface of the seal member; (B) temporarily bonding a support functional board as a protection member to the front surface of the seal member; and (C) forming wirings and external connection terminals on a second surface opposite to the first surface of the substrate of the optical device, while supporting the support functional board on the front surface of the seal member, wherein the (A) and the (B) are performed in any order.

Another method of manufacturing an image pickup unit, the method comprising: bonding a side provided with an optical element region of an optical device to a back surface of an optically-transparent seal member, the optical element region being provided on a first surface of a substrate and functioning as a light receiver, the seal member protecting the side provided with the optical element region of the optical device, the back surface being opposite to a front surface on a light incident side of the seal member; and forming wirings and external connection terminals on a second surface opposite to the first surface of the substrate of the optical device, while supporting the front surface of the seal member, wherein the front surface of the seal member is polished after the external connection terminals are formed in formation of the wirings.

The another method of manufacturing an image pickup unit may further comprise abrading the second surface of the substrate to a thickness which allows via electrodes to be formed, before formation of the wirings, wherein via electrodes are formed in the formation of the wirings, the via electrodes each passing through the substrate from the second surface to the first surface to be connected to connection pads and each being connected to the wirings on the second surface, the connection pads being provided on the first surface along the optical element region.

The another method of manufacturing the image pickup unit wherein an intermediate layer is formed to fill a gap between the optical element region on the front surface of the optical device and the back surface of the seal member at least in a region corresponding to the optical element region, the intermediate layer allowing the optical element region of the optical device to be bonded to the back surface of the seal member.

The another method of manufacturing an image pickup unit may further comprise providing an insulating film on the first surface of the substrate of the optical device; and forming openings on the insulating film before the bonding of the optical element region of the optical device and the back surface of the seal member, the openings each reaching the connection pad from the second surface side of the substrate, wherein the intermediate layer is filled in the openings to be in contact with the connection pads in the bonding.

The another method of manufacturing the image pickup unit wherein via electrodes are formed in the formation of the wirings, the via electrodes each passing through the substrate from the second surface to the first surface to be connected to connection pads and being connected to the wirings on the second surface, the connection pads being provided on the first surface along the optical element region, the support functional board temporarily bonded is detached after formation of the via electrodes, and the support functional board is temporarily bonded again before formation of wirings.

18

The another method of manufacturing the image pickup unit wherein in formation of the wirings, the support functional board temporarily bonded is detached after formation of some wirings, and the support functional board is temporarily bonded again before formation of other wirings.

The another method of manufacturing the image pickup unit wherein in formation of the wirings, the front surface of the seal member is polished after the external connection terminals are formed and the support functional board is detached.

The present application contains subject matter related to that disclosed in Japanese Priority Patent Application JP 2012-003873 filed in the Japan Patent Office on Jan. 12, 2012, the entire content of which is hereby incorporated by reference.

It should be understood by those skilled in the art that various modifications, combinations, sub-combinations, and alterations may occur depending on design requirements and other factors insofar as they are within the scope of the appended claims or the equivalents thereof.

What is claimed is:

1. An image pickup device, comprising:
  - an optically-transparent seal member that has a first surface, wherein the first surface of the seal member includes a concave portion that has a first area, wherein the concave portion of the seal member includes an outer region as a light waveguide and an inner region;
  - an optical device coupled to a second surface of the seal member, wherein the second surface of the seal member is opposite from the first surface of the seal member, the optical device includes an optical sensor with a light receiving surface that has a second area; and
  - a resin layer which fills a gap between the light receiving surface and the second surface of the seal member.
2. The image pickup device according to claim 1, wherein the outer region protrudes beyond the inner region by a distance (D) in a direction perpendicular to the second surface of the seal member.
3. The image pickup device according to claim 1, wherein the optical sensor includes an optical element region on a first surface of a substrate, wherein the first surface of the substrate faces toward the seal member and the optical element region is further configured for photoelectric conversion.
4. The image pickup device according to claim 3, wherein the second surface of the seal member is adhered to the optical device by the resin layer.
5. The image pickup device according to claim 4, wherein the optical device includes a connection pad on the first surface of the substrate, and the connection pad is connected to an external connection terminal on a second surface of the substrate through a via-electrode, wherein the second surface of the substrate is opposite from the first surface of the substrate.
6. The image pickup device according to claim 5, wherein an insulating layer is on the first surface of the substrate, and a portion of the insulating layer is between the connection pad and the resin layer.
7. The image pickup device according to claim 5, wherein the connection pad is in direct contact with the resin layer.
8. The image pickup device according to claim 2, wherein the outer region protrudes beyond the inner region at a step that has a lateral wall, wherein the lateral wall is nearly parallel to the direction perpendicular to the first surface of the seal member.

19

9. The image pickup device according to claim 3, wherein the concave portion includes an outer region and an inner region on the first surface of the seal member, the outer region protrudes beyond the inner region by a distance (D) in a direction perpendicular to the first surface of the seal member, and

the inner surface region aligns with the optical element region in the direction perpendicular to the first surface of the seal member.

10. An image pickup device, comprising:

an optically-transparent seal member that has a first surface, wherein the first surface is a polished surface that includes a concave portion,

wherein the concave portion includes an outer region as a light waveguide and an inner region;

an optical device coupled to a second surface of the seal member, the second surface of the seal member is

20

opposite from the first surface of the seal member, wherein the optical device includes an optical sensor with a light receiving surface; and

a resin layer which fills a gap between the light receiving surface and the second surface of the seal member.

11. The image pickup device according to claim 1, wherein the first area is larger than the second area.

12. The image pickup device according to claim 1, wherein the seal member has a thickness in range of 450 μm to 800 μm and a refractive index of about 1.5.

13. The image pickup device according to claim 1, wherein the resin layer has a thickness in range of 10 μm to 100 μm.

14. The image pickup device according to claim 1, wherein the light waveguide is further configured to guide light for a distance, towards a region with a connection pad.

\* \* \* \* \*